

การศึกษาวิธีทางโลหวิทยาแบบผงอัดเพื่อทำเม็ดโลหะทั้งสแตนเลสกับทองแดง



นายวีระชัย บัญชรเทวกุล

004883

วิทยานิพนธ์นี้เป็นส่วนหนึ่งของการศึกษาตามหลักสูตรปริญญาวิศวกรรมศาสตรมหาบัณฑิต

ภาควิชาวิศวกรรมเทคโนโลยี

บัณฑิตวิทยาลัย จุฬาลงกรณ์มหาวิทยาลัย

พ.ศ. ๒๕๒๓

**A STUDY OF THE POWDER METALLURGY METHOD FOR TUNGSTEN-COPPER PELLETS**

**Mr. Weerachai Banchoerdhevakul**

**A Thesis Submitted in Partial Fulfillment of the Requirements**

**for the Degree of Master of Engineering**

**Department of Nuclear Technology**

**Graduate School**

**Chulalongkorn University**

**1980**

Thesis Title     A Study of the Powder Metallurgy Method for Tungsten-  
Copper Pellets

By                     Mr. Weerachai Banchornchevakul

Department        Nuclear Technology

Thesis Advisor    Associate Professor Manas Sterachinda

---

Accepted by the Graduate School, Chulalongkorn University in  
partial fulfillment of the requirements for the Master's degree.

..... *S. Bunnag* ..... Dean of Graduate School  
( Associate Professor Supradit Bunnag , PhD. )

Thesis Committee

..... *S. Sangpetel* ..... Chairman  
( Professor Suwan Sangpetel , M.S.E.E )

..... *M. Mangclaviraj* ..... Member  
( Assistant Professor Virul Mangclaviraj , Dipl. Ing. )

..... *P. Karasuddhi* ..... Member  
( Assistant Professor Pricha Karasuddhi , M. Eng. )

..... *Manas Sterachinda* ..... Member  
( Associate Professor Manas Sterachinda , Maître en Sciences  
Appliquées )

Thesis Title     A Study of the Powder Metallurgy Method for Tungsten-  
Copper Pellets

Name             Mr. Weerachai Banchornchevakul

Thesis Advisor   Associate Professor Manas Sterachinda

Department       Nuclear Technology

Academic Year    1979



## ABSTRACT

Tungsten-Copper pellets were used in the essential steps of preliminary study of Powder Metallurgy method. Nuclear techniques were applied in analysing the compositions as well as the density.

The results showed that solid phase sintering gave a similar microstructure of Copper as in the liquid phase sintering. The only difference was the bonding and coarsening of Tungsten grains. To analyse the constituents, NAA and WDX methods were more suitable than EDX method due to the elimination of resolution problem of the detectors, using gamma transmission method would give better results than the conventional method using weight and volume, especially in the case of porous materials.

หัวข้อวิทยานิพนธ์      การศึกษาวิธีทางโลหวิทยาแบบผงอัดเพื่อทำเม็ดโลหะทั้งสเดน  
 ผสมกับทองแดง  
 ชื่อนิสิต                    นาย วีระชัย นัญชรเทวกุล  
 อาจารย์ที่ปรึกษา        รองศาสตราจารย์ มนัส สติรจินดา  
 ภาควิชา                    นิวเคลียร์เทคโนโลยี  
 ปีการศึกษา                ๒๕๒๒



บทคัดย่อ

จากการศึกษาวิธีทางโลหวิทยาแบบผงอัด ถึงลำดับขั้นตอนต่าง ๆ ที่จำเป็น  
 สำหรับการศึกษาเบื้องต้นโดยใช้ผงอัดของทั้งสเดน และ ทองแดง การนำเทคนิคทาง  
 นิวเคลียร์แบบต่าง ๆ เข้ามาประยุกต์ในการวิเคราะห์หาองค์ประกอบ และ การหา  
 ความหนาแน่นของผงอัดที่เผาประสานแล้ว จากการทดลองพบว่า การเผาประสาน  
 ในสภาพของแข็งจะให้ผลใกล้เคียงกับการเผาประสานในสภาพของเหลว จะแตกต่างกัน  
 เฉพาะเกรนของทั้งสเดนเท่านั้น การวิเคราะห์โดยใช้วิธีนิวตรอนแอกติเวชัน (เอ็น เอ  
 เอ) และ คับบิว ดี เอกซ์ จะเหมาะสม และ ให้ผลดีกว่าการใช้วิธี อี ดี เอกซ์  
 เพราะไม่มีปัญหาเกี่ยวกับความสามารถในการแยกพลังงานของหัววัดรังสี เนื่องจากรังสี  
 เอกซ์เฉพาะตัวของธาตุทั้งสองมีค่าใกล้เคียงกันมาก ทำให้โอกาสที่จะหาปริมาณของ  
 ทองแดงโดยตรงมีน้อยมาก และ การหาความหนาแน่นโดยใช้รังสีแกมมาทะลุผ่านจะให้ผล  
 ดีกว่าการใช้วิธีชั่งน้ำหนัก และ หาปริมาตรมาก โดยเฉพาะในกรณีของวัสดุที่มีความพรุน



Sincere thanks are also expressed to all of my friends and my classmate and other officials that haven't been mentioned here for their generous help. Partial support by the Graduate Research Funds is also sincerely appreciated.

Finally, I wish to express my deep appreciation to my brother, sisters, and my deepest gratitude to my father, mother, for their kindness, love, understanding and encouragement throughout my life.

## CONTENTS

	Page
ABSTRACT (ENGLISH) .....	iv
ABSTRACT (THAI) .....	v
ACKNOWLEDGEMENT .....	vi
LIST OF TABLES .....	ix
LIST OF FIGURES .....	x
CHAPTER	
1. INTRODUCTION .....	1
2. BACKGROUND .....	3
3. THEORY .....	24
4. MATERIALS & METHODS .....	36
5. RESULTS .....	41
6. DISCUSSION AND CONCLUSION .....	58
REFERENCES .....	64
APPENDIX .....	68
BIOGRAPHY .....	70





## LIST OF TABLES

Table	Page
1 Sources of errors in X-ray fluorescence spectrometer .....	32
2. The powder size distribution of Tungsten and Copper .....	41
3. The average density of the green pellets for each method of determination (weight to volume method and gamma transmission method) ....	42
4. Relation between Tungsten-Copper content and the photopeak area of each element using the Detection System I. ....	47
5. Relation between Tungsten-Copper content and the photopeak area of each element using the Detection System II. ....	48

## LIST OF FIGURES

Figure		Page
1	The figure shows the contact angle between liquid and solid phase when a liquid droplet is in contact with a solid surface .....	8
2.	Interaction of photons with atoms .....	17
3.	Pulse-height distribution curves for three kinds of counter .....	22
4.	The figure shows the Covell's method of determining the photopeak area from the interested peak ...	26
5.	The origin of characteristic radiation .....	28
6.	X-rays fluorescence spectrometers (wavelength-dispersive and energy-dispersive systems) .....	30
7.	The optimum length of crystal analyzer .....	31
8.	The system used in density determination by gamma transmission .....	37
9.	Shape of Tungsten and Copper powder before sintering .....	43
10.	The microstructure of the sintered pellets ....	45
11.	Calibration curve shows relation between attenuated gamma rays (relative counting yield per cm) and density of attenuating material .....	49

12.	Spectrum of Tungsten-187 and Copper-64 peaks using Ge(Li) detector as stated in Detection System I. . .	50
13.	Graph shows relation between photopeak-area and Tungsten-Copper content using Detection System II. .	51
14.	Spectrum of Tungsten-187 and Copper-64 peaks using NaI(Tl) 3" X 3" Detector as stated in Detection System II. . . . .	52
15.	Graph shows relation between photopeak area and Tungsten-Copper content using Detection System II. .	53
16.	Spectrum of Tungsten-Copper pellet used in the thesis experiment.  The graph shows relation between X-rays intensities and Diffracting angle (using System V) . . . . .	54
17.	Calibration curve shows relation between photopeak area and %copper in Cast Aluminium Alloys. ....	55
18.	Calibration curve shows relation between photopeak area and %copper in Cast Copper Alloys. ....	55
19.	Calibration curve shows relation between photopeak area and %copper in Cast Aluminium Bronzes. ...	56
20.	Calibration curve shows relation between photopeak area and %copper in nearly pure Copper . . . . .	56
21.	Calibration curve shows relation between photopeak area and %tungsten in Sintered Carbides. ....	57
22.	Calibration curve shows relation between photopeak area and %tungsten in Low Alloys Steels. ....	57