

การเตรียมพลาสติกที่ย่อยสลายได้ทางชีวภาพจากโพลิเอทิลีนความหนาแน่นต่ำ
กับแป้งมันสำปะหลัง



นางสาวปิยะรัตน์ เรียวรักษา

วิทยานิพนธ์นี้เป็นส่วนหนึ่งของการศึกษาตามหลักสูตรปริญญาวิทยาศาสตรมหาบัณฑิต

สาขาวิชาวิทยาศาสตร์สภาวะแวดล้อม

บัณฑิตวิทยาลัย จุฬาลงกรณ์มหาวิทยาลัย

ปีการศึกษา 2540

ISBN 974-639-128-3

ลิขสิทธิ์ของบัณฑิตวิทยาลัย จุฬาลงกรณ์มหาวิทยาลัย

**PREPARATION OF BIODEGRADABLE PLASTIC FROM
LOW DENSITY POLYETHYLENE AND TAPIOCA STARCH**

Miss Piyarat Reawraksa

**A Thesis Submitted in Partial Fulfillment of the Requirements
for the Degree of Master of Science in Environmental Science
Inter-Department of Environmental Science**

Graduate School


Chulalongkorn University

Academic Year 1997


ISBN 974-639-128-3


Thesis Title Preparation of Biodegradable Plastic from Low
 Density Polyethylene and Tapioca Starch
By Miss Piyarat Reawraksa
Inter-department Environmental Science
Thesis Advisor Associate Professor Supawan Tantayanon, Ph.D.

Accepted by the Graduate School, Chulalongkorn University in
Partial Fulfillment of the Requirement for the Master 's Degree .



..... Dean of Graduate School
(Professor Supawat Chutivongse, M.D.)

Thesis Committee


..... Chairman
(Assistant Professor Kumthorn Thirakhupt, Ph.D.)


..... Thesis Advisor
(Associate Professor Supawan Tantayanon, Ph.D.)


..... Member
(Professor Pattarapan Prasassarakich, Ph.D.)


..... Member
(Assistant Professor Wanida Jinsart, Ph.D.)

พิมพ์ต้นฉบับบทความวิทยานิพนธ์ภายในกรอบสี่เหลี่ยมนี้เพียงแผ่นเดียว

ปิยะรัตน์ เรียวรักษา : การเตรียมพลาสติกที่ย่อยสลายได้ทางชีวภาพจากโพลีเอทิลีนความหนาแน่นต่ำกับแป้งมันสำปะหลัง (PREPARATION OF BIODEGRADABLE PLASTIC FROM LOW DENSITY POLYETHYLENE AND TAPIOCA STARCH) อ.ที่ปรึกษา : รศ. ดร. ศุภวรรณ ดันตยานนท์; 57 หน้า. ISBN 974-639-128-3

โพลีเอทิลีนความหนาแน่นต่ำผสมกับแป้งมันสำปะหลังด้วยส่วนผสมต่าง ๆ กัน สมบัติของของผสมเหล่านี้ ได้แก่ ความต้านทานแรงดึงและการยืดตัวเมื่อขาดได้ถูกตรวจสอบเพื่อปรับปรุงสมบัติเชิงกลของของผสม คอมแพคทีบิไลเซอร์หลายตัว ได้แก่ กลีเซอรอลโมโนสเตียเรต, ซิงค์สเตียเรต และ อีโพลีน ได้ถูกเติมลงไป ปริมาณ 1% โดยน้ำหนักของของผสม สมบัติเชิงกลของของผสมแต่ละส่วนผสมได้ถูกเปรียบเทียบกับส่วนผสมเดียวกันที่ไม่มีคอมแพคทีบิไลเซอร์ ผลการทดลองแสดงให้เห็นว่าเมื่อมีกลีเซอรอลโมโนสเตียเรตหรือซิงค์สเตียเรตในของผสมของโพลีเอทิลีนความหนาแน่นต่ำกับแป้งมันสำปะหลัง ทำให้สมบัติเชิงกลมีค่าสูงกว่าเมื่อมีอีโพลีนและสูงกว่าของผสมที่ไม่ได้เติมคอมแพคทีบิไลเซอร์เลย โดยเฉพาะอย่างยิ่งการเติมอีโพลีนกลับทำให้ค่าความต้านทานแรงดึงและค่าการยืดตัวเมื่อขาดลดลง

ในการเปรียบเทียบกับของผสมของโพลีเอทิลีนความหนาแน่นต่ำกับแป้งข้าวโพดที่ผสมกลีเซอรอลโมโนสเตียเรตและซิงค์สเตียเรตในลักษณะเดียวกัน พบว่าของผสมของโพลีเอทิลีนความหนาแน่นต่ำกับแป้งมันสำปะหลังทุกส่วนผสม มีความต้านทานแรงดึงและค่าการยืดตัวเมื่อขาดสูงกว่าของผสมของโพลีเอทิลีนความหนาแน่นต่ำกับแป้งข้าวโพดเมื่อมีกลีเซอรอลโมโนสเตียเรตหรือซิงค์สเตียเรตอยู่ ด้วยเทคนิคสแกนนิ่งอิเล็กตรอนไมโครสโคปปีได้แสดงให้เห็นว่า เม็ดแป้งมันสำปะหลังและแป้งข้าวโพดกระจายตัวอย่างสม่ำเสมออยู่บนโพลิเมอร์เมทริกซ์

ภาควิชา **สาขา**
สาขาวิชา **วิทยาศาสตร์และเทคโนโลยี**
ปีการศึกษา **2540**

ลายมือชื่อนิสิต **ปิยะรัตน์ เรียวรักษา**
ลายมือชื่ออาจารย์ที่ปรึกษา **ศุภวรรณ ดันตยานนท์**
ลายมือชื่ออาจารย์ที่ปรึกษาพร้อม

C726639 : MAJOR INTER-DEPARTMENT OF ENVIRONMENTAL SCIENCE
KEY WORD: BIODEGRADABLE PLASTIC / TAPIOCA STARCH / STARCH-FILLED POLYETHYLENE
PIYARAT REAWRAKSA : PREPARATION OF BIODEGRADABLE PLASTIC FROM LOW
DENSITY POLYETHYLENE AND TAPIOCA STARCH . THESIS ADVISOR : ASSOC. PROF.
SUPAWAN TANTAYANON, Ph.D. 57 pp. ISBN 974-639-128-3.

LDPE/tapioca starch blends at various composition were prepared and their properties, tensile strength and elongation at break, were investigated. In order to improve the mechanical properties of the blends, several compatibilizers i.e. glycerol monostearate, zinc stearate and epolene, were added at 1% by weight of total blend. The measurement of mechanical properties of each blend had been compared with corresponding LDPE/tapioca starch blend without the compatibilizer. The results had shown that the presence of glycerol monostearate or zinc stearate in the blends enhanced the mechanical strength much more than epolene and the one without compatibilizer. Particularly, the addition of epolene even decreased both tensile strength and elongation at break of the blends .

In comparison with LDPE/corn starch blends, LDPE/tapioca starch blends at every composition had higher tensile strength and elongation at break in the presence of either glycerol monostearate or zinc stearate than LDPE/corn starch blends. By using scanning electron microscopic technic, it indicated that starch granules dispersed evenly in polyethylene matrix .

ภาควิชา..... สนิสาท
สาขาวิชา..... วิทยาศาสตร์สุขภาพ: แวดล้อม
ปีการศึกษา..... 2540
ลายมือชื่อนิสิต..... *นิศารัตน์*
ลายมือชื่ออาจารย์ที่ปรึกษา..... *ดร. สนิศานนท์*
ลายมือชื่ออาจารย์ที่ปรึกษาร่วม.....



ACKNOWLEDGEMENT

The author wish to express her deepest gratitude to her advisor, Associate Professor Dr. Supawan Tantayanon, for her kindness, guidance and assistance . Also, she is grateful to Assistant Professor Dr. Kumthorn Thirakhupt and Professor Dr. Pattarapan Prasassarakich and Assistant Professor Dr.Wanida Jinsart for kindly accepting to be her thesis committees .

Sincere acknowledgements are due to Department of Industrial Chemistry and Plastic Technology Center, King Mongkut Bangkok Institute of Technology North for the facility in using of injection molding, tensile testing machine and blow molding. I wish to express gratitude to Graduate School of Chulalongkorn University, Environmental Research Institute and Thai ASAHI company for financial support .

Finally, the author is greatly indepted and deeply grateful to her family for their encouragement and understanding throughout the entire course of study .

CONTENTS

	Page
Thai Abstract.....	iv
English Abstract.....	v
Acknowledgement.....	vi
Contents.....	vii
List of Tables.....	ix
List of Figures.....	x
Chapter	
1. Introduction	
1.1 Problem Statement.....	1
1.2 Various Types of Starch.....	3
2.Theoretical and Literature Review	
2.1 Low Density Polyethylene.....	6
2.2 Constituents of Starch.....	7
2.3 Processing Additive.....	8
2.4 Literature Review.....	9
3. Materials and Experiment	
3.1 Materials.....	12
3.2 Apparatus.....	12
3.3 Sample Preparation.....	13
3.4 Specimens Preparation.....	14
3.5 Measurement.....	16
4. Results and Discussion	
4.1 Straight Blending of LDPE with Tapioca Starch.....	18
4.2 The Failure of Some Compatibilizer.....	20
4.3 Mechanical Properties of LDPE/tapioca starch Blends with Compatibilizers.....	21

	Page
4.4 Reproducibility of Blend.....	28
4.5 Comparison of the Mechanical Properties of LDPE/tapioca starch Blends with LDPE/corn starch Blends.....	29
4.6 Dispersion of Starch Granule and Compatibilizer in the Blends.....	35
4.7 Film Blowing.....	35
5. Conclusion and Suggestions	
5.1 Conclusion.....	39
5.2 Further Suggestions.....	39
Reference.....	41
Appendix.....	44
Biography.....	57

LIST OF TABLES

TABLE	Page
1.1 Amylose and Amylopectin Content and Degree of Polymerization of Various Starch.....	3
1.2 Average Chemical Composition of Starch Granule.....	4
3.1 The Composition of LDPE/tapioca starch Blends.....	14
3.2 The Composition of LDPE/tapioca starch Blends with Compatibilizer.....	15
3.3 The Composition of LDPE/corn starch Blends.....	16
4.1 The Effect of Starch Content on Mechanical Properties of LDPE/tapioca starch Blends.....	19
4.2 Mechanical Properties of LDPE/tapioca starch Blends in the Presence of Epolene.....	21
4.3 Mechanical Properties of LDPE/tapioca starch Blends in the Presence of Zinc stearate.....	24
4.4 Mechanical Properties of LDPE/tapioca starch Blends in the Presence of Glycerol monostearate.....	26
4.5 Mechanical Properties of LDPE/corn starch Blends.....	29

LIST OF FIGURES

Figure	Page
2.1 Both Short and Long Chain in LDPE.....	6
2.2 Linear-chain Structure of Amylose Molecule.....	7
2.3 Structure of Amylopectin Branching Point.....	8
4.1 (a)Tensile Strength and (b) Elongation at Break of LDPE/tapioca starch Blends with and without Epolene.....	23
4.2 (a)Tensile Strength and (b) Elongation at Break of LDPE/tapioca starch Blends with and without Zinc stearate.....	25
4.3 (a)Tensile Strength and (b) Elongation at Break of LDPE/tapioca starch Blends with Glycerol monostearate or Zinc stearate.....	27
4.4 Tensile Strength of LDPE/tapioca starch Blends and LDPE/corn starch Blends with (a) glycerol monostearate and (b) zinc stearate.....	32
4.5 Elongation at Break of LDPE/tapioca starch Blends and LDPE/corn starch Blends with (a) glycerol monostearate and (b) zinc stearate.....	33
4.6 Scanning Electron Microscopy (SEM) of (a) tapioca starch granules and (b)corn starch granules.....	34
4.7 Dispersion of Starch Granules in Polymer Matrix Revealed by SEM.....	36
4.8 Blown Films of (a)LDPE (b) P/T05 (c) P/T05E (d)P/T05G and (e)P/T05Z.....	37
4.9 SEM of Blown Films (a) LDPE/tapioca starch with zinc stearate and (b) LDPE/tapioca starch with glycerol monostearate.....	38