

## รายการอ้างอิง

### ภาษาไทย

- ชัญญ์ ผลประไพ. สภาวะที่เหมาะสมในการเลี้ยงเชื้อเพื่อผลิตโพลีเบต้าไฮดรอกซีบิวทีเรทจาก *Alcaligenes* sp. สายพันธุ์ A-04 ในระดับถังหมัก. วิทยานิพนธ์ปริญญาโทมหาบัณฑิต จุฬาลงกรณ์มหาวิทยาลัย, 2537.
- เสาวรจน์ ช่วยจุลจิตร. Polymer Science I. ภาควิชาวัสดุศาสตร์ คณะวิทยาศาสตร์ จุฬาลงกรณ์มหาวิทยาลัย.
- อรุณ ชาญชัยชาววิวัฒน์. ลักษณะและการสร้างโพลี-เบต้า-ไฮดรอกซีบิวทีเรทโดย *Alcaligenes* sp. A-04. วิทยานิพนธ์ปริญญาโทมหาบัณฑิต จุฬาลงกรณ์มหาวิทยาลัย, 2536.
- อัญชนา สุรติขจร. การสร้างโพลี(3-ไฮดรอกซีบิวทีเรท-โค-3-ไฮดรอกซีวาเลอเรท)โคโพลีเมอร์ โดย *Alcaligenes* sp. สายพันธุ์ A-04. วิทยานิพนธ์ปริญญาโทมหาบัณฑิต จุฬาลงกรณ์มหาวิทยาลัย, 2537.

### ภาษาอังกฤษ

- Adamus, G., Kowalczyk, M., Jedlinski, Z., Ballistreri, A., Scherer, T. and Lenz, R.W. Degradation behavior of poly(methyl methacrylate-g-3-hydroxybutyrate) polymer films. *Polym. Degrad. & Stab.* 50 (1995) : 269-276.
- Akhtar, S., Pouton, C.W., and Notarianni, L.J. Crystallization behaviour and drug release from bacterial polyhydroxyalkanoates. *Polymer.* 33 (1992) : 117-126.
- American Society for Testing and Materials. ASTM standard method D883-91a. Standard terminology relating to plastics. In annual book of ASTM standards. (1992) : 322-335. An american national standard, Philadelphia.
- Bauer, H., and Owen, A.J. Some structural and mechanical properties of bacterially produced poly- $\beta$ -hydroxybutyrate-co- $\beta$ -hydroxyvalerate. *Colloid & Polymer Science.* 266 (1988) : 241-247.

- Bloembergen, S., Holden, D. A., Hamer, G. K., Bluhm, T. L., and Marchessault, R. H. Studies of composition and crystallinity of bacterial poly( $\beta$ -hydroxybutyrate-co- $\beta$ -hydroxyvalerate). *Macromolecules*. 19 (1986) : 2865-2871.
- Bluhm, T.L., Hamer, G.K., Marchessault, R.H. and Veregin, R.P. Isodimorphism in bacterial poly( $\beta$ -hydroxybutyrate-co- $\beta$ -hydroxyvalerate). *Macromol.* 19 (1986) : 2871-2876.
- Brandl, H., Gross, R.A., Lenz, R.W., and Fuller, R.C. Plastic from bacteria and for bacteria: poly( $\beta$ -hydroxyalkanoates) as natural, biocompatible and biodegradable polyesters. *Adv. Biochem. Eng. Biotechnol.* 41 (1990) : 78-79.
- Budwill, K., Fedorax, P.M., and Page, W.J. Methanogenic degradation of poly(3-hydroxyalkanoates). *Appl. Environ. Microbiol.* 58 (1992) : 1398-1401.
- Cacciari, I., Quatrini, P., Zirletta, G., Mincione, E., Vinciguerra, V., Lupattelli, P., and Sermanni, G.G. Isotactic polypropylene biodegradation by a microbial community: physiochemical characterization of metabolites produced. *Appl. Environ. Microbiol.* 59 (1993) : 3695-3700.
- Comeau, Y., Hall, K.J. and Oldham, W.K. Determination of poly  $\beta$ -hydroxybutyrate and poly  $\beta$ -hydroxyvalerate in activated sludge by gas-liquid chromatography. *Appl. Environ. Microbiol.* 54 (1988) : 2325-2327.
- Cox, M.K. The effect of material parameters on the properties and biodegradation of 'BIOPOL'. *Biodegrad. Polym. & Plas.* (1992) Royal Society of Chemistry. UK. : 95-100.
- Csomorova, K., Rychly, J., Bakos, D. and Janigova, I. The effect of inorganic additives on the decomposition of poly(beta-hydroxybutyrate) into volatile products. *Polym. Degrad. & Stab.* 43 (1994) : 441-446.
- De Koning, G.J.M., Scheeren, A.H.C., and Lemstra, P.J. Crystallization phenomena in bacterial poly[(R)-3-hydroxybutyrate]: 3. toughening via texture changes. *Polymer.* 35 (1994) : 4598-4605.
- Doi, Y. *Microbial polyesters.* (1990) VCH Publishers, Inc. New York.
- Doi, Y. Nuclear magnetic resonance studies on poly( $\beta$ -hydroxybutyrate) and copolyester of  $\beta$ -hydroxybutyrate and  $\beta$ -hydroxyvalerate isolated from *Alcaligenes eutrophus* H16. *Macromolecules.* 19 (1986) : 2860-2864.

- Doi, Y., and Fukuda, K. *Biodegradable Plastics and Polymers*. (1994) Elsevier Science B.V. Amsterdam.
- Doi, Y., Kanesawa, Y., and Kunioka, M. Biodegradation of microbial copolyesters: poly(3-hydroxybutyrate-co-3-hydroxyvalerate) and poly(3-hydroxybutyrate-co-4-hydroxybutyrate). *Macromolecules*. 23 (1990) : 26-31.
- Doi, Y., Kanesawa, Y., Koyama, N., Nakamura, S., and Hiramishu, M. Microbial synthesis and properties of biodegradable plastics. pp. 264-270.
- Doi, Y., Kumagai, Y., Tanahashi and Mukai, K. Structural effects on biodegradation of microbial and synthetic poly(hydroxyalkanoates). *Biodegrad. Polym. & Plas.* (1992) Royal Society of Chemistry. UK. : 139-148.
- Doi, Y., Segawa, A., and Kunioka, M. Biodegradable poly(3-hydroxybutyrate-co-4-hydroxybutyrate) produced from  $\gamma$ -butyrolactone and butyric acid by *Alcaligenes eutrophus*. *Polymer Commun.* 30 (1989) : 169-171.
- Doi, Y., Kazuya, K.I., Abe, H., Koyama, N., Ishiwatari, S.I., Takagi, K. and Yoshida, Y. Evaluation of biodegradabilities of biosynthetic and chemosynthetic polyesters in river water. *Polym. Degrad. & Stab.* 51 (1996) : 281-286.
- Evans, J.D., Sikdar, S.K. Biodegradable plastics: an idea whose time has come?. *Chemtech.* 5 (1987) : 38-42.
- Foster, L.J.R. and Tighe, B.J. Enzymatic assay of hydroxybutyric acid monomer formation in poly( $\beta$ -hydroxybutyrate) degradation studies. *Biomaterials*. 16 (1995) : 341-343.
- Gilmore, D.F., Lotti, N., Lenz, R.W., Fuller, R.C. and Scandola, M. Biodegradability of blends of poly(3-hydroxybutyrate-co-3-hydroxyvalerate) with ester-substituted celluloses. *Biodegrad. Polym. & Plas.* (1992) Royal Society of Chemistry. UK. : 251-258.
- Holland, S.J., Jolly, A.W., Vasin, M., and Tighe, B.J. Polymers for Biodegradable medical device II: hydroxybutyrate-hydroxyvalerate copolymer: hydrolytic degradation studies. *Biomaterials*. 8 (1987) : 289-295.
- Holmes, P.A. Application of PHB -a microbially produced Biodegradable thermoplastic. *Phys. Technol.* 16 (1985) : 32-36.

- Hrdlovic, P. Degradable polymers: current state and future potentials. *Int. Polym. Sci. & Tech.* 21 (1994) : T/47-T/56.
- Huffman, G.L. and Keller, D.J. The plastic issue. In : Guillet J. (Ed.) *Polym. Ecolog. Prob.* (1973) p. 155. London, Plehum.
- Ito, H., Marchessault, R.H., and Manley, R.St.J. Uniaxial deformation of poly( $\beta$ -hydroxy butyrate-co-hydroxyvalerate) gel films. *Polymer Commun.* 32 (1991) : 164-167.
- Johnson, K.E., Pometto III, A.L., and Nikolov, Z.L. Degradation of degradable starch-polyethylene plastics in a compost environment. *Appl. Environ. Microbiol.* 59 (1993) : 1155-1161.
- Kanesawa, Y., Tanahashi, N., Doi, Y. and Saito, T. Enzymatic degradation of microbial poly(3-hydroxyalkanoates). *Polym. Degrad. & Stab.* 45 (1994) : 179-185.
- Kazuya, K.I., Doi, Y. and Yao, T. Enzymatic degradation of poly[(R)-3-hydroxybutyrate] by *Comamonas testosteroni* ATSU of soil bacterium. *Polym. Degrad. & Stab.* 45 (1994) : 379-386.
- Kazuya, K.I., Inoue, Y., Yamada, K. and Doi, Y. Kinetics of surface hydrolysis of poly [(R)-3-hydroxybutyrate] film by PHB depolymerase from *Alcaligenes faecalis* T1. *Polym. Degrad. & Stab.* 48 (1995) : 167-174.
- Kelen, T. *Polymer degradation.* (1983) Van Nostrand Reinhold Company. New York.
- Kimura, M., Toyota, K., Iwatsuki, M. and Sawada, H. Effects of soil condition on biodegradation of plastics and responsible microorganisms. *Biodeg. Plast. & Polym.* (1994) : 92-109.
- Kunioka, M., and Doi, Y. Thermal degradation of microbial copolyesters: poly(3-hydroxy butyrate-co-3-hydroxyvalerate) and poly(3-hydroxybutyrate-co-4-hydroxybutyrate). *Macromolecules.* 23 (1990) : 1933-1936.
- Kunioka, M., Tamaki, A., and Doi, Y. Crystalline and thermal properties of bacterial copolyesters: poly(3-hydroxybutyrate-co-3-hydroxyvalerate) and poly(3-hydroxybutyrate-co-4-hydroxybutyrate). *Macromolecules.* 22 (1989) : 694-697.
- Lauzier, C., Rovel, J.F., Debzi, E.M., and Marchesault, R.H. Hydrolytic degradation of isolated poly( $\beta$ -hydroxybutyrate) granules. *Polymer.* 35 (1994) : 4156-4162.

- Leaversuch, R. Industry weights need to make polymers biodegradable. *Mod. Plas.* 64 (1987) : 52-55.
- Lee, S.Y. Bacterial polyhydroxyalkanoates. *Biotech. Bioeng.* 49 (1996) : 1-14.
- Marchessault, R.H., Monasterios, C.J., Jesudason, J.J., Ramsay, B., Saracovan, I., Ramsay, J. and Saito, T. Chemical, enzymatic and microbial degradation of bacterial and synthetic poly- $\beta$ -hydroxyalkanoates. *Polym. Degrad. & Stab.* 45 (1994) : 187-196.
- McCarthy, S.P., Dave, P., Jahedi, T., Eberiel, D. and Gross, R. Enzymatic degradation of blends containing poly(3-hydroxybutyrate-co-3-hydroxyvalerate). *Polym. Degrad. & Stab.* 45 (1994) : 197-203.
- Mergaert, J., Wouters, A., Swings, J. and Kersters, K. Microbial flora involved in the biodegradation of polyhydroxyalkanoates. *Biodegrad. Polym. & Plas.* (1992) Royal Society of Chemistry. UK. : 267-270.
- Mergaert, J., Webb, A., Anderson, C., Wouters, A., and Swings, J. Microbial degradation of poly(3-hydroxybutyrate) and poly(3-hydroxybutyrate-co-3-hydroxyvalerate) in soils. *Appl. Environ. Microbiol.* 59 (1993) : 3233-3238.
- Mitomo, H., Barham, P.J., and Keller, A. Temperature dependence of mechanical properties of poly( $\beta$ -hydroxybutyrate-co- $\beta$ -hydroxyvalerate). *Polymer Commun.* 29 (1988) : 112-115.
- Mitomo, H., Watanabe, Y., Ishigaki, I. and Saito, T. Radiation-induced degradation of poly(3-hydroxybutyrate) and the copolymer poly(3-hydroxybutyrate-co-4-hydroxybutyrate). *Polym. Degrad. & Stab.* 45 (1994) : 11-17.
- Mukai, K., Yamada, K. and Doi, Y. Efficient hydrolysis of polyhydroxyalkanoates by *Pseudomonas stutzeri* YM1414 isolated from lake water. *Polym. Degrad. & Stab.* 43 (1994) : 319-327.
- Nakamura, K., Yoshie, N., Sakurai, M., and Inoue, Y. A structure study of the crystalline state of the bacterial copolyester poly(3-hydroxybutyrate-co-4-hydroxybutyrate). *Polymer.* 35 (1994) : 193-197.
- Narayan, R. Biodegradable plastics. *Biotechnol.* (1993) : 135-150.
- Nicholson, J. *The chemistry of polymers.* (1994) The Royal Society of Chemistry. UK.

- Nishida, H., and Tokiwa, Y. Effects of higher-order structure of poly(3-hydroxybutyrate) on its biodegradation. I. effects of heat treatment on microbial degradation. *J. Appl. Polym. Sci.* 46 (1992) : 1467-1476.
- Nishida, H., and Tokiwa, Y. Effects of higher-order structure of poly(3-hydroxybutyrate) on its biodegradation. II. effects of crystal structure on microbial degradation. *J. Environ. Polym. Degrad.* 1 (1993) : 65-80.
- Ohtake, Y., Kobayashi, T., Itoh, S., Asabe, H., Yabuki, M., Murakami, N. and Ono, K. Development of biodegradable LDPE compound and evaluation of its biodegradability. *Int. Polym. Sci. & Tech.* 22 (1995) : T/49-T/56.
- Organ, S.J. Phase separation in blends of poly(hydroxybutyrate) with poly(hydroxybutyrate-co-hydroxyvalerate): variation with blend components. *Polymer.* 35(1994): 86-92.
- Organ, S.J. Variation in melting point with molecular weight for hydroxybutyrate/hydroxyvalerate copolymers. *Polymer.* 34 (1993) : 2175-2179.
- Pearce, R., and Marchesault, R.H. Multiple melting in blends of isotactic and atactic poly( $\beta$ -hydroxybutyrate). *Polymer.* 35 (1994) : 3990-3997.
- Pearce, R., Brown, G.R., and Marchesault, R.H. Crystallization kinetics in blends of isotactic and atactic poly( $\beta$ -hydroxybutyrate). *Polymer.* 35 (1994) : 3984-3989.
- Raghavan, D. Characterization of biodegradable plastics. *Polym.-Plast. Technol. Eng.* 34 (1995) : 41-63.
- Ramsay, B.A., Langlade, V., Carreau, P.J., and Ramsay, J.A. Biodegradability and mechanical properties of poly ( $\beta$ -hydroxybutyrate-co- $\beta$ -hydroxyvalerate )- starch blends. *Appl. Environ. Microbiol.* 59 (1993) : 1242-1246.
- Satoh, H., Yoshie, N., and Inoue, Y. Hydrolytic degradation of blends of poly(3-hydroxybutyrate) with poly(3-hydroxybutyrate-co-3-hydroxyvalerate). *Polymer.* 35 (1994) : 286-290.
- Scandola, M., Geccouelli and Doi, Y. Viscoelastic relaxation and thermal properties of bacterial poly(3-hydroxybutyrate-co-3-hydroxyvalerate) and poly(3-hydroxybutyrate-co-4-hydroxybutyrate) *Int. J. Biol. Macromol.* 12 (1990) : 112-117.



- Tomasi, G., Scandola, M., Briese, B.H., and Jendrossek, D. Enzymatic degradation of bacterial poly(3-hydroxybutyrate) by a depolymerase from *Pseudomonas lemoignei*. *Macromolecules*. 29 (1996) : 507-513.
- Torres, A., Li, S. M., Roussos, S. and Vert, M. Screening of microorganisms of biodegradation of poly(lactic acid) and lactic acid-containing polymers. *Appl. Environ. Microbiol.* 62 (1996) : 2393-2397.
- Urmeneta, J., Mas-Castella, J., and Guerrero, R. Biodegradation of poly- $\beta$ -hydroxyalkanoates in a lake sediment sample increases bacterial sulphate reduction. *Appl. Environ. Microbiol.* 61 (1995) : 2046-2048.
- Valentin, H., and Dennis, D. Metabolic pathway for poly(3-hydroxybutyrate-co-3-hydroxyvalerate) formation in *Nocardia corallina*: inactivation of *mutB* by chromosomal integration of a kanamycin resistance gene. *Appl. Environ. Microbiol.* 62 (1996) : 372-379.
- Wallen, L.L., and Rohwedder, W.K. Poly- $\beta$ -hydroxyalkanoate from activated sludge. *Environ. Sci. Technol.* 8 (1974) : 576-579.
- Wang, H.T., Palmer, H., Linhardt, R.J., Flanagan, D.R., and Schmitt, E. Degradation of poly(ester) microspheres. *Biomaterials*. 11 (1990) : 679-685.
- Yue, C.L., Gross, R.A. and McCarthy, S.P. Composting studies of Poly( $\beta$ -hydroxybutyrate-co- $\beta$ -hydroxyvalerate). *Polym. Degrad. & Stab.* 51 (1996) : 205-210.

### ภาคผนวก

#### ก) การหาน้ำหนักเซลล์เปียกและน้ำหนักเซลล์แห้งในอาหารสำหรับเตรียมกล้าเชื้อ

เตรียมหัวเชื้อของ *Alcaligenes* sp. A-04 สำหรับเลี้ยงเป็นกล้าเชื้อ ซึ่งมีความเข้มข้นและปริมาณเริ่มต้นจากวิธีดำเนินงานวิจัยข้อ 2) การเตรียมหัวเชื้อสำหรับเลี้ยงเป็นกล้าเชื้อ นำมาเลี้ยงในอาหารเหลวสำหรับเลี้ยงกล้าเชื้อ ทำการเลี้ยงเชื้อเป็นเวลา 24 ชม. นำน้ำหมักมาตรวจปริมาณ 10 20 40 60 และ 80 มล. บั่นแยกเซลล์ที่ 8,000 รอบต่อนาทีเป็นเวลา 10 นาที นำมาละลายในน้ำกลั่นให้มีปริมาตรเป็น 40 มล. และผสมให้เป็นเนื้อเดียวกัน นำแต่ละตัวอย่างมาเจือจางให้ได้ค่า OD<sub>600</sub> กระจายในช่วง 0.1-0.6 บันทึกค่าการเจือจางและค่า OD<sub>600</sub> ปิดตัวอย่าง 15 มล. กรองผ่านเมมเบรนขนาด 0.45 ไมครอน ที่ทราบน้ำหนักแล้ว นำมาชั่งหาน้ำหนักเซลล์เปียก จากนั้นนำไปอบแห้งจนน้ำหนักคงที่เพื่อชั่งหาน้ำหนักเซลล์แห้งต่อไป นำค่าที่ได้มาสร้างกราฟมาตรฐานระหว่าง OD<sub>600</sub> กับน้ำหนักเซลล์เปียกและน้ำหนักเซลล์แห้งเป็นกรัมต่อลิตร (ภาคผนวก ก)






ภาคผนวก ก) กราฟมาตรฐาน ปริมาณน้ำหนักเซลล์เปียก และน้ำหนักเซลล์แห้งของ *Alcaligenes* sp. A-04 ในอาหารสำหรับเตรียมกล้าเชื้อ (น้ำหนักเซลล์เปียกเป็นกรัมต่อลิตรเท่ากับ  $1.148 \times \text{OD } 600$  และน้ำหนักเซลล์แห้งเป็นกรัมต่อลิตรเท่ากับ  $0.353 \times \text{OD } 600$  )

## ข) การหาน้ำหนักเซลล์แห้งในอาหารเลี้ยงเชื้อเพื่อการผลิต PHA

เตรียมหัวเชื้อของ *Alcaligenes* sp. A-04 สำหรับเลี้ยงในอาหารเลี้ยงเชื้อเพื่อการผลิต PHA ซึ่งมีความเข้มข้นและปริมาณเชื้อเริ่มต้น 12 กรัม(น้ำหนักเซลล์เปียก)ต่อลิตร นำมาลงในอาหารเลี้ยงเชื้อเพื่อการผลิต PHA ทำการเลี้ยงเชื้อเป็นเวลา 60 ชม. ตวงน้ำหมักปริมาตร 10 20 40 60 และ 80 มล. บั่นแยกเซลล์ที่ 8,000 รอบต่อนาทีเป็นเวลา 10 นาที นำมาละลายน้ำกลั่นให้มีปริมาตรเป็น 40 มล. และผสมให้เป็นเนื้อเดียวกัน นำแต่ละตัวอย่างมาเจือจางให้ได้ค่า OD<sub>600</sub> อยู่ในช่วง 0.1-0.6 บันทึกค่าการเจือจางและค่า OD<sub>600</sub> เก็บไว้ บีบเปิดสารละลายเซลล์ 20 มล. กรองผ่านเมมเบรนขนาด 0.45 ไมครอนที่ทราบน้ำหนักแห้งแล้ว ล้างเซลล์ด้วยน้ำกลั่น 2 ครั้ง นำไปอบแห้งจนได้น้ำหนักคงที่ คำนวณหาน้ำหนักแห้งของเซลล์จากผลต่างของน้ำหนักเซลล์แห้งและเมมเบรนกับน้ำหนักเมมเบรนเปล่า นำข้อมูลมาสร้างกราฟมาตรฐานระหว่างค่า OD<sub>600</sub> กับน้ำหนักเซลล์แห้งเป็นกรัมต่อลิตร (ภาคผนวก ข)



ภาคผนวก ข) กราฟมาตรฐาน และน้ำหนักเซลล์แห้งของ *Alcaligenes* sp. A-04 ในอาหารเลี้ยงเชื้อเพื่อการผลิต (น้ำหนักเซลล์แห้งเป็นกรัมต่อลิตรเท่ากับ  $1.0625 \times \text{OD } 600$  )

### ค) การคำนวณปริมาณโมโนเมอร์ของ 3HB 3HV และ 4HB

การคำนวณปริมาณโมโนเมอร์ของ 3HB 3HV และ 4HB (กรัมต่อลิตรต่อไลโอไฟไลซ์เซลล์ 20 มก.) ทำการประมวลผลโดยใช้โปรแกรมสำเร็จรูป Star chromatogram Ver.4.0 ซึ่งคำนวณปริมาณโมโนเมอร์เป็นกรัมต่อลิตร (โดยมีสารมาตรฐานภายในเป็นกรดเบนโซอิก 2 มก.ต่อมล.) เปรียบเทียบกับสารมาตรฐานที่ทำการวิเคราะห์ในภาวะเดียวกัน

$$\text{ปริมาณโมโนเมอร์ (กรัมต่อลิตร)} = \frac{\text{ค่าจากการวิเคราะห์ (กรัมต่อลิตร)} \times \text{น้ำหนักเซลล์แห้ง (กรัมต่อลิตร)}}{20 \times 1.10}$$

หมายเหตุ : 1.10 คือ correction factor ระหว่างน้ำหนักเซลล์แห้งโดยการอบต่อน้ำหนักเซลล์แห้งภายใต้สูญญากาศ (dry cell weight = lyophilized cell weight x 1.10)


การคำนวณสัดส่วนองค์ประกอบในพอลิเมอร์ (mole fraction) ทำได้โดย

1. คำนวณหาปริมาณของแต่ละโมโนเมอร์จากสมการที่กล่าวมา
2. คำนวณหาจำนวนโมลของแต่ละโมโนเมอร์โดยการหารด้วยน้ำหนักโมเลกุลของแต่ละโมโนเมอร์ (น้ำหนักโมเลกุลของ 3HB, 4HB และ 3HV = 86, 86 และ 100 ตามลำดับ)
3. คำนวณหาโมลเปอร์เซ็นต์ (โมล %)

$$\text{โมลเปอร์เซ็นต์ ของ 3HB (โมล \%)} = \frac{\text{จำนวนโมลของ 3HB} \times 100}{\text{ผลรวมของจำนวนโมลของโมโนเมอร์ทั้งหมด}}$$

โมโนเมอร์ชนิดอื่นคำนวณในทำนองเดียวกัน

|                                 |         |         |         |        |        |       |       |       |
|---------------------------------|---------|---------|---------|--------|--------|-------|-------|-------|
| สารมาตรฐาน                      | F380    | F288    | F128    | F80    | F40    | F10   | F4    | F1    |
| retention time                  | 11.06   | 11.15   | 11.51   | 11.87  | 12.59  | 14.21 | 15.74 | 18.16 |
| น้ำหนักโมเลกุล<br>(specific MW) | 3840000 | 2890000 | 1090000 | 706000 | 355000 | 96400 | 37900 | 9100  |



ง) กราฟมาตรฐานของสารมาตรฐานพอลิสไตรีน F380-F1 สำหรับการคำนวณหาน้ำหนักโมเลกุลเฉลี่ยของพอลิเมอร์

### ประวัติผู้วิจัย

นางสาว สุกฤตยา วีระนนท์ เกิดเมื่อวันที่ 13 มีนาคม พ.ศ. 2514 ที่จังหวัดอุดรธานี สำเร็จการศึกษาปริญญาตรีวิทยาศาสตร์บัณฑิต ภาควิชาจุลชีววิทยา คณะวิทยาศาสตร์ จุฬาลงกรณ์มหาวิทยาลัย ในปีการศึกษา 2535 และเข้าศึกษาต่อในหลักสูตรวิทยาศาสตรมหาบัณฑิต สาขาจุลชีววิทยาทางอุตสาหกรรม ภาควิชาจุลชีววิทยา ที่จุฬาลงกรณ์มหาวิทยาลัย เมื่อพ.ศ. 2536