

REFERENCES

1. Fread, W. Textbook of Polymer Science. USA: Wiley-Interscience, 1984.
2. Walter Michaeli. Plastic Processing: An Introduction. USA: Hanser Publisher, 1995.
3. Schnabel, W. Polymer Degradation: Principles and Practical Applications. USA: Hamser International, 1981.
4. Mark, Bikales, Overberger, and Menges, Encyclopedia of Polymer Science and Engineering. 2nd ed. Vol.4. New York: John Wiley and Sons, 1983.
5. Grassie, N. and Scott, G. Polymer Degradation and Stabilization. England: Cambridge University Press, 1985.
6. Kelen, T. Polymer Degradation. New York: Van Nostrand Reinhold Company, 1982.
7. Baken, J.A., and Sloan, F.D., Microencapsulation of Drugs. Drug Cosmet Ind., 1972.
8. Baken, J.A. In: The Theory and practice of industrial Pharmacy. Microencapsulation. 3rd ed. Philadelphia: Lea and Febiger, 1986.
9. Taylor, L.J. and Tobias, J.W. Accelerated Photo-Oxidation of Polyethylene II. Further Evaluation of Selected Additives. Journal of Applied Polymer Science 26 (1981) : 2917-2926.
10. Kubota, H., and Takahashi, K. Benzophenone - Sensitized Photodegradation of Polyethylene. Polymer Degradation and Stability 24 (1989) : 201-211.
11. Kaczmarek, H., Kamiska, A., and Sanyal, S. Photoinitiated degradation of polystyrene in the presence of low-molecular organic compounds. European Polymer Journal 36 (2000) : 1167-1173.
12. Weib, G., Knoch, A., Laicher, A., Stanislaus, F., and Daniels, R. Simple Coacervation of Hydroxypropyl Methylcellulose Phthalate (HPMCP) II. Microencapsulation of Ibuprofen. International Journal of Pharmaceutics 124 (1995) : 97-105.
13. Byung Seon Yoon, Moon Ho Shu, Shi Hwa Cheong, Jae Eue Yie, Sung Haw Yoon, and Suck Hyun Lee. Studies on the Degradation Polyethylene: Use of Coated Photodegradants with Biopolymers. Journal of Applied Polymer Science 60 (1996) : 1677-1685.

14. Akin, H., and Hasirci, N. Preparation and Characterization of Crosslinked Gelatin Microspheres. *Journal of Applied Polymer Science* 58 (1995) : 96-100.
15. Ruben, J., and Hernandez. *Plastics Packaging Properties, Processing, Applications and Regulation*. USA: Hanser Publisher, 2000.
16. Daniel, C.A., *Polymer: Structure and Propeties*. USA: Technomic, 1989.
17. Deasy, P.B., *Microencapsulation and Related drug processes*. New York: Marcel Dekker, 1984.
18. Luzzi, L.A., Microencapsulation. *Journal of Pharm Science* 59 (1970) : 1367-1376.
19. Andrade, A.L., Weathering of Polyethylene (LDPE) and Enhanced Photodegradable Polyethylene in the Marine Environment. *Journal of Applied Polymer Science* 39 (1990) : 363-370.
- 20 Raab, M. The Action of Anthraquinone Sensitizers in the Photo-oxidation Degradation of Low Density Polyethylene: Mechanical Evidence of Dark Processes. *Polymer Degradation and Stability* 18 (1987) : 123-134.
21. Bullón, J., Belleville, M. P., and Rios, G. M. Preparation of gelatin formed-in-place membranes: effect of working conditions and substrates. *Journal of Membrane Science* 168 (2000) : 159-165.
22. Carvalho, A., and Grosso, C. R. F. Characterization of gelatin based films modified with transglutaminase, glyoxal and formaldehyde. *Food Hydrocolloids* 18 (2004) : 717-726.
23. Nixon, J.R., and Carless, J.E. The Role of pH in the Coacervation of the System; Gelatin-Water-Ethanol and Gelatin-Water-Sodium Sulphate. *Pharm Pharmacol* 20 (1968) : 215-255.
24. Weib, G., Knoch, A., Laicher, A., Stanislaus, F., and Daniels, R. Simple Coacervation of Hydroxypropyl Methylcellulose Phthalate (HPMCP) I. Temperature and pH dependency of Coacervate Formation. *International Journal of Pharmaceutics* 124 (1995) : 87-96.

25. Halina Kaczmarek, Ma gorzata, and Alina Kami ska, Modification of polystyrene and poly(vinyl chloride) for the purpose of obtaining packaging materials degradable in the natural environment. Polymer Degradation and Stability 83 (2004) : 35-45.
26. Othmer, K., Encyclopedia of Chemical Technology. 3rd ed. Vol. 11. New York: John Wiley and Sons, Inc., 1983.
27. Kondo A., Microencapsulation Utilizing Phase Separation from an Aqueous Solution System. In: Microencapsules Processing and Technology. New York: Marcel Dekker, 1979.



ศูนย์วิทยบรังษยการ
จุฬาลงกรณ์มหาวิทยาลัย



APPENDICES

ศูนย์วิทยทรัพยากร
จุฬาลงกรณ์มหาวิทยาลัย

Appendix A

Table A.1 %Weight loss of LDPE films and LDPE/encapsulated particle films under outdoor test

	Additive	%Additive (%w/w)	Exposure Time (months)			
			1	2	3	4
LDPE	-	-	0.01	0.02	0.03	0.04
LDPE	benzophenone	0.5	0.02	0.03	0.04	0.04
		1	0.01	0.03	0.04	0.03
		3	0.02	0.02	0.04	0.09
		5	0.00	0.03	0.05	0.12
LDPE	gelatin	0.5	0.01	0.02	0.03	0.05
		1	0.01	0.02	0.06	0.04
		3	0.02	0.03	0.07	0.10
		5	0.00	0.04	0.08	0.12
LDPE	EN1	0.5	0.01	0.03	0.02	0.03
		1	0.01	0.05	0.03	0.06
		3	0.00	0.05	0.09	0.16
		5	0.00	0.02	0.08	0.16
LDPE	EN2	0.5	0.00	0.03	0.04	0.06
		1	0.01	0.02	0.06	0.08
		3	0.02	0.02	0.05	0.09
		5	0.01	0.02	0.06	0.12
LDPE	EN3	0.5	0.00	0.03	0.02	0.05
		1	0.00	0.05	0.08	0.09
		3	0.00	0.02	0.10	0.25
		5	0.02	0.02	0.08	0.20
LDPE	EN4	0.5	0.00	0.03	0.04	0.03
		1	0.03	0.02	0.04	0.08
		3	0.01	0.03	0.07	0.10
		5	0.03	0.01	0.04	0.13
LDPE	EN5	0.5	0.00	0.02	0.04	0.02
		1	0.00	0.02	0.06	0.04
		3	0.01	0.03	0.07	0.11
		5	0.03	0.01	0.08	0.13
LDPE	EN6	0.5	0.01	0.02	0.04	0.08
		1	0.01	0.02	0.06	0.04
		3	0.00	0.04	0.03	0.07
		5	0.01	0.04	0.02	0.12

Table A.2 %Weight loss of LDPE films and LDPE/encapsulated particle films under accelerated test

	Additive	%Additive (%w/w)	UVB Exposure Time (hours)			
			20.5	41.0	61.5	82.0
LDPE	-	-	0.01	0.03	0.02	0.01
LDPE	benzophenone	0.5	0.02	0.03	0.04	0.02
		1	0.01	0.03	0.02	0.03
		3	0.02	0.02	0.04	0.01
		5	0.02	0.01	0.01	0.01
LDPE	gelatin	0.5	0.01	0.02	0.03	0.00
		1	0.01	0.02	0.00	0.04
		3	0.02	0.03	0.01	0.02
		5	0.00	0.01	0.02	0.02
LDPE	EN1	0.5	0.01	0.03	0.02	0.03
		1	0.01	0.01	0.03	0.00
		3	0.00	0.01	0.02	0.00
		5	0.02	0.00	0.01	0.00
LDPE	EN2	0.5	0.00	0.00	0.04	0.02
		1	0.01	0.02	0.02	0.03
		3	0.02	0.02	0.03	0.01
		5	0.02	0.01	0.01	0.03
LDPE	EN3	0.5	0.00	0.03	0.02	0.01
		1	0.00	0.03	0.02	0.00
		3	0.00	0.02	0.10	0.01
		5	0.00	0.02	0.00	0.01
LDPE	EN4	0.5	0.00	0.03	0.04	0.03
		1	0.03	0.02	0.04	0.01
		3	0.01	0.03	0.00	0.01
		5	0.01	0.01	0.01	0.02
LDPE	EN5	0.5	0.00	0.02	0.04	0.02
		1	0.00	0.02	0.01	0.04
		3	0.01	0.03	0.02	0.03
		5	0.01	0.00	0.02	0.03
LDPE	EN6	0.5	0.01	0.02	0.04	0.01
		1	0.01	0.02	0.02	0.00
		3	0.00	0.04	0.03	0.01
		5	0.01	0.03	0.01	0.02

Table A.3 %Weight loss of LDPE films and LDPE/encapsulated particle films under accelerated test during 82 -143.5 hours

Additive	%Additive (%w/w)	UVB Exposure Time (hours)			
		82.0	102.5	123.0	143.5
-	-	0.01	0.02	0.03	0.05
benzophenone	5	0.01	0.01	0.02	0.06
gelatin	5	0.02	0.03	0.00	0.04
EN1	5	0.00	0.01	0.02	0.06
EN2	5	0.03	0.00	0.01	0.05
EN3	5	0.01	0.02	0.00	0.06
EN4	5	0.02	0.01	0.03	0.04
EN5	5	0.03	0.00	0.02	0.05
EN6	5	0.02	0.02	0.01	0.04

ศูนย์วิทยทรัพยากร
จุฬาลงกรณ์มหาวิทยาลัย

Appendix B

Table B.1 Carbonyl Index of LDPE films and LDPE/encapsulated films under outdoor test

	Additive	%Additive (%w/w)	Exposure Time (months)				
			0	1	2	3	4
LDPE	-	-	0.072	0.161	0.402	0.606	0.612
LDPE	benzophenone	0.5	0.074	0.285	0.411	0.695	0.627
		1	0.079	0.207	0.599	0.666	0.741
		3	0.045	0.299	0.485	0.796	1.096
		5	0.080	0.312	0.669	0.911	1.399
LDPE	gelatin	0.5	0.079	0.299	0.546	0.622	0.700
		1	0.054	0.323	0.627	0.706	0.693
		3	0.129	0.242	0.467	0.785	0.750
		5	0.137	0.355	0.581	0.785	0.921
LDPE	EN1	0.5	0.028	0.206	0.459	0.706	0.623
		1	0.026	0.316	0.429	0.716	0.722
		3	0.091	0.324	0.593	0.816	0.832
		5	0.024	0.264	0.600	0.826	0.923
LDPE	EN2	0.5	0.152	0.196	0.402	0.597	0.621
		1	0.026	0.349	0.412	0.601	0.612
		3	0.053	0.388	0.501	0.624	0.731
		5	0.068	0.219	0.432	0.693	0.864
LDPE	EN3	0.5	0.023	0.201	0.392	0.622	0.610
		1	0.019	0.158	0.561	0.602	0.635
		3	0.025	0.195	0.422	0.591	0.632
		5	0.031	0.291	0.531	0.623	0.597
LDPE	EN4	0.5	0.058	0.144	0.497	0.665	0.612
		1	0.016	0.196	0.472	0.612	0.621
		3	0.098	0.186	0.632	0.691	0.671
		5	0.097	0.155	0.495	0.764	0.806
LDPE	EN5	0.5	0.172	0.204	0.604	0.590	0.601
		1	0.043	0.149	0.431	0.563	0.619
		3	0.072	0.193	0.413	0.769	0.731
		5	0.093	0.134	0.519	0.749	0.847
LDPE	EN6	0.5	0.041	0.200	0.431	0.559	0.621
		1	0.024	0.150	0.399	0.692	0.612
		3	0.033	0.170	0.597	0.682	0.731
		5	0.032	0.160	0.567	0.612	0.864

Table B.2 Carbonyl Index of LDPE films and LDPE/encapsulated particle films under accelerated test

	Additive	%Additive (%w/w)	UVB Exposure Time (hours)				
			0	20.5	41.0	61.5	82.0
LDPE	-	-	0.072	0.161	0.402	0.606	0.612
LDPE	benzophenone	0.5	0.074	0.285	0.411	0.695	0.627
		1	0.079	0.207	0.599	0.666	0.741
		3	0.045	0.299	0.485	0.796	1.096
		5	0.080	0.312	0.669	0.911	1.399
LDPE	gelatin	0.5	0.079	0.119	0.208	0.267	0.540
		1	0.054	0.068	0.206	0.248	0.597
		3	0.129	0.209	0.153	0.181	0.391
		5	0.137	0.180	0.242	0.322	0.540
LDPE	EN1	0.5	0.028	0.093	0.192	0.365	0.495
		1	0.026	0.086	0.253	0.513	0.586
		3	0.091	0.132	0.240	0.447	0.483
		5	0.024	0.098	0.251	0.344	0.638
LDPE	EN2	0.5	0.023	0.106	0.289	0.330	0.427
		1	0.019	0.104	0.211	0.330	0.398
		3	0.025	0.107	0.227	0.230	0.359
		5	0.031	0.085	0.255	0.290	0.346
LDPE	EN3	0.5	0.023	0.201	0.392	0.622	0.610
		1	0.019	0.158	0.561	0.602	0.635
		3	0.025	0.195	0.422	0.591	0.632
		5	0.031	0.291	0.531	0.623	0.597
LDPE	EN4	0.5	0.021	0.157	0.155	0.330	0.308
		1	0.016	0.120	0.220	0.330	0.316
		3	0.098	0.123	0.301	0.284	0.366
		5	0.097	0.108	0.247	0.335	0.299
LDPE	EN5	0.5	0.065	0.215	0.154	0.271	0.412
		1	0.059	0.146	0.204	0.269	0.401
		3	0.072	0.110	0.167	0.410	0.397
		5	0.081	0.136	0.183	0.326	0.421
LDPE	EN6	0.5	0.041	0.116	0.250	0.305	0.400
		1	0.024	0.229	0.229	0.305	0.470
		3	0.033	0.188	0.188	0.283	0.326
		5	0.032	0.154	0.154	0.185	0.502

Table B.3 Carbonyl Index of LDPE films and LDPE/encapsulated particle films under accelerated test during 82 -143.5 hours

	Additive	%Additive (%w/w)	UVB Exposure Time (hours)			
			82.0	102.5	123.0	143.5
LDPE	-	-	0.38	0.42	0.50	0.60
LDPE	benzophenone	5	0.65	0.80	0.91	1.39
LDPE	gelatin	5	0.50	0.58	0.70	0.80
LDPE	EN1	5	0.64	0.59	0.70	0.81
LDPE	EN2	5	0.36	0.46	0.51	0.60
LDPE	EN3	5	0.35	0.43	0.40	0.50
LDPE	EN4	5	0.30	0.38	0.49	0.56
LDPE	EN5	5	0.42	0.45	0.43	0.58
LDPE	EN6	5	0.50	0.40	0.49	0.58

ศูนย์วิทยทรัพยากร
จุฬาลงกรณ์มหาวิทยาลัย

Appendix C

Table C.1 Tensile strength of LDPE films and LDPE/encapsulated particle films under outdoor test

	Additive	%Additive (%w/w)	Exposure Time (months)				
			0	1	2	3	4
LDPE	-	-	7.217	6.512	6.574	6.674	5.620
LDPE	benzophenone	0.5	6.473	7.275	7.054	6.960	5.928
		1	7.479	7.110	7.125	6.461	4.976
		3	6.667	6.810	6.689	5.723	3.954
		5	6.134	6.741	6.169	5.215	3.021
LDPE	gelatin	0.5	6.401	7.301	6.443	6.539	5.900
		1	6.600	6.681	7.485	5.877	4.900
		3	5.491	5.914	6.128	6.036	4.587
		5	5.464	5.794	6.051	5.046	3.954
LDPE	EN1	0.5	5.992	4.527	5.385	5.322	5.012
		1	5.817	6.049	5.712	4.279	4.592
		3	5.898	5.896	4.785	4.300	3.278
		5	4.505	5.372	4.310	3.210	2.518
LDPE	EN2	0.5	6.235	5.311	5.709	5.394	4.900
		1	5.924	5.472	5.642	4.900	4.657
		3	5.002	4.935	4.980	4.830	4.068
		5	4.047	4.672	4.520	4.629	3.210
LDPE	EN3	0.5	6.657	5.355	5.500	5.210	5.120
		1	4.916	5.271	5.174	4.597	3.957
		3	4.842	4.915	4.279	4.579	3.759
		5	4.986	3.827	5.178	4.546	3.021
LDPE	EN4	0.5	5.598	6.849	6.038	4.816	5.120
		1	5.364	6.487	5.353	5.911	5.090
		3	5.161	6.057	5.505	4.838	4.269
		5	4.804	5.342	4.235	4.560	3.876
LDPE	EN5	0.5	6.293	5.211	5.609	5.424	4.700
		1	5.916	5.452	5.562	4.800	4.567
		3	5.112	4.895	4.900	4.850	4.075
		5	4.066	4.762	4.490	4.599	3.120
LDPE	EN6	0.5	5.304	5.691	5.429	4.172	5.310
		1	4.053	4.675	4.205	4.096	3.870
		3	5.389	5.542	6.427	4.336	3.640
		5	4.147	4.213	4.556	3.945	2.900

Table C.2 Elongation at break of LDPE films and LDPE/encapsulated particle films under outdoor test

	Additive	%Additive (%w/w)	Exposure Time (months)				
			0	1	2	3	4
LDPE	-	-	25.709	20.467	12.742	10.077	8.336
LDPE	benzophenone	0.5	21.044	27.655	15.189	7.365	7.458
		1	24.444	15.389	10.065	6.958	3.536
		3	19.763	17.082	8.544	5.796	2.196
		5	18.263	15.090	8.169	5.293	1.563
LDPE	gelatin	0.5	22.656	19.044	7.871	6.275	4.563
		1	26.357	16.025	8.849	5.036	3.981
		3	14.731	9.184	5.783	5.012	3.210
		5	19.566	10.543	6.478	3.861	2.950
LDPE	EN1	0.5	22.079	4.240	2.734	4.814	4.006
		1	15.081	7.209	3.718	4.598	3.197
		3	10.445	6.169	2.866	3.095	2.685
		5	11.741	6.144	3.298	2.119	1.998
LDPE	EN2	0.5	12.219	9.591	6.906	4.780	4.520
		1	13.966	9.046	4.551	3.590	3.410
		3	9.604	5.995	3.860	3.184	2.547
		5	7.082	6.621	3.368	3.460	2.692
LDPE	EN3	0.5	22.472	7.726	4.958	3.589	4.687
		1	9.890	7.766	4.033	2.998	3.659
		3	13.504	6.768	3.386	3.065	2.996
		5	13.180	3.962	3.460	2.963	1.998
LDPE	EN4	0.5	13.873	10.104	5.242	4.163	4.724
		1	12.800	10.550	3.991	5.816	3.559
		3	10.341	4.420	3.527	5.447	4.231
		5	10.075	4.509	2.738	4.009	2.553
LDPE	EN5	0.5	12.329	9.951	6.836	4.694	4.420
		1	13.698	9.156	4.624	3.698	3.529
		3	9.634	5.695	3.800	3.344	2.547
		5	7.192	6.581	3.468	3.590	2.782
LDPE	EN6	0.5	11.060	7.244	4.535	2.217	3.091
		1	7.231	6.357	3.066	3.960	3.659
		3	11.064	8.175	5.926	3.016	3.264
		5	7.249	4.296	3.175	3.009	2.654

Table C.3 Tensile strength of LDPE films and LDPE/encapsulated particle films under accelerated test

	Additive	%Additive (%w/w)	UVB Exposure Time (hours)				
			0	20.5	41.0	61.5	82.0
LDPE	-	-	7.217	7.032	6.992	6.832	6.768
LDPE	benzophenone	5	6.134	5.671	6.413	5.619	6.122
LDPE	gelatin	5	5.464	5.885	5.099	5.455	4.597
LDPE	EN1	5	4.505	4.224	4.271	3.606	3.450
LDPE	EN2	5	4.047	4.265	3.998	3.881	2.676
LDPE	EN3	5	4.986	4.003	3.584	3.945	3.894
LDPE	EN4	5	4.037	4.365	3.918	3.221	2.666
LDPE	EN5	5	4.930	4.225	3.538	3.601	2.616

Table C.4 Elongation at break of LDPE films and LDPE/encapsulated particle films under accelerated test

	Additive	%Additive (%w/w)	UVB Exposure Time (hours)				
			-	20.500	41.000	61.500	82.000
LDPE	-	-	25.709	23.057	21.032	20.037	19.384
LDPE	benzophenone	5	18.263	22.081	17.496	9.837	10.536
LDPE	gelatin	5	19.566	17.588	10.944	8.030	5.947
LDPE	EN1	5	11.741	9.879	6.680	3.775	2.423
LDPE	EN2	5	7.082	6.217	6.004	4.981	2.169
LDPE	EN3	5	13.180	10.317	5.959	6.656	5.889
LDPE	EN4	5	8.084	7.240	6.114	4.921	2.209
LDPE	EN5	5	7.082	6.227	5.964	4.901	2.619
LDPE	EN6	5	7.091	6.617	6.034	4.989	2.199

Appendix D




Figure D.1 FTIR spectra of LDPE containing (a) 1% gelatin and (b) 5% gelatin films




Figure D.2 FTIR spectra of LDPE containing (a) 1%benzophenone and (b) 5% benzophenone

Appendix E

Table 3.4 The formulation of LDPE films and LDPE/additives films

VITA

Miss Naritsara Sriklueab was born on May 14, 1980 in Bangkok, Thailand. She received her Bachelor Degree of Science in Chemistry, Mahidol University in 2001. She continued her Master Degree study in the program of Applied Polymer Science and Textile Technology, Department of Materials Science, Faculty of Science, Chulalongkorn University, and completed program in April, 2005.

ศูนย์วิทยบรังษยการ
จุฬาลงกรณ์มหาวิทยาลัย