

การสังเคราะห์ผลและข้อมูลทางประวัติศาสตร์ สำหรับ
พลาสติกสลายตัวทางชีวภาพ



นาย เรืองเดช คงศรี

วิทยานิพนธ์นี้เป็นส่วนหนึ่งของการศึกษาตามหลักสูตรปริญญาวิทยาศาสตร์มหาบัณฑิต

สาขาวิชา ปีตรเคมี

บัณฑิตวิทยาลัย จุฬาลงกรณ์มหาวิทยาลัย

พ.ศ. 2536

ISBN 974-583-514-5

ลิขสิทธิ์ของบัณฑิตวิทยาลัย จุฬาลงกรณ์มหาวิทยาลัย

SYNTHESIS OF POLY(ϵ -CAPROLACTONE) AND METHYLACRYLATE GRAFTED STARCH
FOR BIODEGRADABLE PLASTICS



Mr. Ruangdaj Tongsri

A Thesis Submitted in Partial Fulfillment of the Requirements

for the Degree of Master of Science

Program of Petrochemistry

Graduate School

Chulalongkorn University

1993

ISBN 974-583-514-5

Thesis Title Synthesis of Poly(ϵ -caprolactone) and Methylacrylate
 Grafted Starch for Biodegradable Plastics
By Mr. Ruangdaj Tongsri
Department Petro-Polymer Interprogram
Thesis Advisor Associate Professor Supawan Tantayanon, Ph.D.

Accepted by the Graduate School, Chulalongkorn University in
Partial Fulfillment of the requirements for the Master's Degree

Thavorn Vajarabha Dean of Graduate School
(Professor Thavorn Vajarabhaya, Ph.D.)

Thesis Committee

Pirawan Bhunthumnavin Chairman
(Associate Professor Pirawan Bhunthumnavin, Ph.D.)

Sup. Tantay Thesis Advisor
(Associate Professor Supawan Tantayanon, Ph.D.)

Somchai Pengprecha Member
(Assistant Professor Somchai Pengprecha, Ph.D.)

Chintana Saiwan Member
(Chintana Saiwan, Ph.D.)

พิมพ์ต้นฉบับปกด้วยอักษรยานินพนธ์ภาษาในกรอบสีเขียวนี้เพียงแผ่นเดียว

เรื่อง เดช คงศรี : การสังเคราะห์โพลีเอทีโอลอนคา โปรแลคตอน และแบงกราฟต์ด้วย เมทริลอะคริเลต ส้ำรับพลาลิติกลายตัวทางชีวภาพ (SYNTHESIS OF POLY (ϵ -CAPROLACTONE) AND METHYLACRYLATE GRAFTED STARCH FOR BIODEGRADABLE PLASTICS) อ.กีรติกา : รศ.ดร.คุณธรรม ตันထยานนท์, 119 หน้า. ISBN 974-583-514-5

ได้สังเคราะห์โพลีเมอร์ลายตัวทางชีวภาพล่วงชนิดศืด โพลีเอทีโอลอนคา โปรแลคตอน และแบงกราฟต์ด้วยเมทริลอะคริเลต ส้ำรับปฏิกิริยา โพลีเมอร์ไช่ยนของเอทีโอลอนคา โปรแลคตอน ได้ทำ การศึกษาที่อุณหภูมิ 85 องศาเซลเซียล ในระบบสั่นสะเทือนลายภายในตับบรรยายการค่าในต่อเนื่องโดยมีไตร เอทิลอะซูมีนียมเป็นตัวเริ่มปฏิกิริยา ได้ศึกษาโดยการเปลี่ยนแปลงอัตราล่วงความเข้มข้นของโนโนนเมอร์ต่อ ตัวเริ่มปฏิกิริยา พบว่าร้อยละผลิตภัณฑ์ของโพลีเมอร์ที่ได้มีค่าสูงถึง 98.76 ส้ำรับปฏิกิริยากราฟต์โคโพลี- เมอร์ไช่ยนของ เมทริลอะคริเลตบนแบงมันสีปะหังนั้น ใช้ไอโอนชีริคประจุบวก 4 เป็นตัวเริ่มปฏิกิริยา ส้ำรับปฏิกิริยาผู้ได้ศึกษาผลของตัวแปรต่างๆ คือต่อกราฟติงยีลด์และกราฟติง เอฟฟิเชียนซ์ พบร้า เมื่อให้ ปริมาณของของผลลัพธ์ 140 มิลลิลิตร ซึ่งประกอบด้วยปริมาณของแบงมันสีปะหัง 3.5000 กรัม ความเข้มข้นของ เมทริลอะคริเลต 0.7939 โมลาร์ ปริมาณของกรดไนตริก 0.5×10^{-3} โมล และ ปริมาณของไตร เอทิลอะซูมีน 0.3500 กรัม ซึ่งมีช่วงเวลาส้ำรับเติมตัวเริ่มปฏิกิริยา 15 นาที ทำ ปฏิกิริยาที่อุณหภูมิ 45 องศาเซลเซียล เมื่อนำเอ้า โพลีเอทีโอลอนคา โปรแลคตอน แบงกราฟต์ด้วยเมทริล อะคริเลตและโพลีเมอร์ผลลัมของโพลีเมอร์ทั้งสองชนิด โดยนำแต่ละชนิดผลลัมกับโพลีไวนิลคลอไรด์ และโพลี ไวนิลอะซีเตต ตามลำดับ และนำไปทำเป็นแผ่นฟิล์ม นำเอาแผ่นฟิล์มไปทดสอบการย่อยล่อลายด้วยเขื้อราก 5 ชนิด คือ Penicillium funiculosum, Aspergillus flavus, Aspergillus niger, Gliocladium virens, and Chaetomium globosum เป็นเวลา 50 วัน พบร้า โพลีเอทีโอลอนคา- โปรแลคตอน และแบงกราฟต์ด้วยเมทริลอะคริเลตถูกย่อยได้ดี แต่ต่อกว่า โพลีเมอร์ผลลัมของโพลีเอทีโอลอนคา โปรแลคตอน เมทริลอะคริเลตถูกย่อยได้ดี และต่อกว่า โพลีเมอร์ผลลัมของโพลีเอทีโอลอนคา โปรแลคตอน

ภาควิชา สำหรับสาขาวิชาปัตตานี- โพลีเมอร์
สาขาวิชา ปัตตานี
ปีการศึกษา 2536

ลายมือชื่อนักศึกษา
ลายมือชื่ออาจารย์ที่ปรึกษา
ลายมือชื่ออาจารย์ที่ปรึกษาร่วม

#: MAJOR PETROCHEMISTRY
KEY WORD: BIODEGRADABLE PLASTICS / POLY (ϵ -CAPROLACTONE) / METHYLACRYLATE
GRAFTED STARCH.

RUANGDAJ TONGSRI : SYNTHESIS OF POLY (ϵ -CAPROLACTONE) AND
METHYLACRYLATE GRAFTED STARCH FOR BIODEGRADABLE PLASTICS.

THESIS ADVISOR : ASSOCIATE PROFESSOR SUPAWAN TANTAYANON, Ph.D.
119 pp. ISBN 974-583-514-5

Two different biodegradable polymers, poly (ϵ -caprolactone) (PCL) and methylacrylate grafted starch (Starch-g-PMA), were synthesized. The polymerization of ϵ -caprolactone was carried out at 85°C, in the solution system, under nitrogen atmosphere, using triethylaluminum as the initiator. The concentration ratio of monomer and initiator was varied. The percentage yield of PCL was obtained as high as 98.76. The graft copolymerization of methylacrylate onto cassava starch was initiated by Ce(IV) ion. Several factors were examined in order to optimise the grafting yield and grafting efficiency. It was found that the highest grafting yield and grafting efficiency was achieved when the reaction mixture was composed of 3.5000 g of cassava starch, 0.7939 M methylacrylate, nitric acid 0.5×10^3 mole and 0.3500 g of triethylaluminum in 140 ml with 15 min addition time of the initiator at 45°C. The synthesized polymers, PCL, Starch-g-PMA, and their polymer blends with poly (vinyl chloride) and poly (vinyl acetate) were casted into films. The films were exposed to five fungi, Penicillium funiculosum, Aspergillus flavus, Aspergillus niger, Gliocladium virens, and Chaetomium globosum for 50 days. The results on biodegradability were quite promising. PCL and Starch-g-PMA were more easily biodegradable and the polymer blends of Starch-g-PMA seem to be degraded better than that of PCL.

ภาควิชา สาขาวิชาปัตalogue 2000
สาขาวิชา ปัตalogue 2000
ปีการศึกษา 2536

ลายมือชื่อนิสิต
ลายมือชื่ออาจารย์ที่ปรึกษา Suwan Tantayano.
ลายมือชื่ออาจารย์ที่ปรึกษาร่วม -



ACKNOWLEDGEMENT

The author would like to express his appreciation and gratitude to Asso. Prof. Dr. Supawan Tantayanon, his advisor, for her valuable guidance, supervision, discussion and financial support.

He would like to express his gratitude to Asso. Prof. Kanika Chantarasaard and Ms. Siriporn Klaothodsaporn at Department of Microbiology for their helpfulness on biodegradation study. This sincere gratitude is also extended to his ex-coadvisor, Dr.Prapaipit Chamsuksai, at Department of Chemistry for her supervision.

His sincere thanks are due to all his friends for their helpfulness and encouragement. Finally, he would like to thank his parents for their patience, support and encouragement over the many years he spent on study.

CONTENTS

	page
ABSTRACT (IN THAI).....	iv
ABSTRACT (IN ENGLISH).....	v
ACKNOWLEDGEMENT.....	vi
LIST OF TABLES.....	xi
LIST OF FIGURES.....	xiii
LIST OF SCHEMES.....	xiv
CHAPTER I : INTRODUCTION.....	1
1.1 Plastic degradations.....	2
1.2 Study on polymer biodegradation.....	8
1.3 Applications of biodegradable plastics.....	12
1.4 The objectives of this research.....	13
CHAPTER II : THEORY.....	14
2.1 Ring-opening polymerization.....	14
2.2 Graft copolymerization.....	21
CHAPTER III : EXPERIMENTS AND RESULTS.....	32
3.1 Chemicals and apparatus.....	32
3.2 Procedure.....	35

CONTENTS (Continued)

	Page
3.2.1 Synthesis of ϵ - caprolactone)	
3.2.1.1 Synthesis of ethyl	
magnesium bromide.....	35
3.2.1.2 Synthesis of triethyl	
aluminum.....	36
3.2.1.3 Polymerization of	
ϵ - caprolactone.....	37
3.2.2 Synthesis of methylacrylate	
grafted starch.....	40
3.2.2.1 Effect of variation of	
reaction volume.....	40
3.2.2.2 Effect of time-interval for	
the addition of initiator.....	46
3.2.2.3 Effect of variation of	
initiator.....	48
3.2.2.4 Effect of variation of	
monomer.....	51
3.2.2.5 Effect of amount of	
nitric acid.....	54

CONTENTS (Continued)

	Page
3.2.2.6 Effect of variation of temperature.....	59
3.2.2.7 Comparative study of graft copolymerization of methylacrylate onto different starches.....	59
3.3 Characterization of the synthesized polymers.....	60
3.4 Preparation of cast films as sample specimens.....	66
3.5 Preliminary biodegradation study of polymer films.....	68
CHAPTER IV : DISCUSSIONS.....	77
4.1 Synthesis of poly (ϵ -caprolactone).....	77
4.2 Graft copolymerization of methylacrylate onto starch.....	79
4.2.1 Effect of variation of the reaction volumes.....	79

CONTENTS (Continued)

	Page
4.2.2 The time-intervals of the addition of the initiator	82
4.2.3 Effect of variation of initiator.....	84
4.2.4 Effect of variation of monomer.....	87
4.2.5 Effect of the amount of nitric acid....	89
4.2.6 Effect of variation of reaction temperature.....	92
4.2.7 Graft copolymerization of methylacrylate onto different starches.....	94
4.3 Preliminary biodegradation study of polymer films.....	95
CHAPTER V : CONCLUSIONS.....	97
REFERENCES.....	99
APPENDIX.....	109
VITA.....	119

LIST OF TABLES

	page
1 Applications of biodegradable plastics.....	12
2.1 The temperature ranges for starch gelatinization.....	25
3.1 Conditions for synthesis of poly (ϵ -caprolactone).....	38
3.2 Results of ϵ -caprolactone polymerizations.....	39
3.3 Effect of reaction volume.....	43
3.4 Grafting parameters of polymers in Table 3.3.....	45
3.5 Effect of time-intervals for the addition of initiator.	47
3.6 Grafting parameters of polymers in Table 3.5.....	48
3.7 Effect of variation of initiator.....	49
3.8 Grafting parameters of polymers in Table 3.7.....	50
3.9 Effect of variation of monomer.....	52
3.10 Grafting parameters of polymers in Table 3.9.....	53
3.11 Effect of amount of nitric acid.....	55
3.12 Grafting parameters of polymers in Table 3.11.....	56
3.13 Effect of variation of temperature.....	57
3.14 Grafting parameters of polymers in Table 3.13.....	58
3.15 Grafting parameters of polymethylacrylate graft onto different starches.....	59
3.16 Preparation of polymer films.....	67
3.17 The observed growth of <u>Penicillium funiculosum</u> on specimens.....	70

LIST OF TABLES(Continued)

	page
3.18 The observed growth of <u>Aspergillus flavus</u> on specimens.....	71
3.19 The observed growth of <u>Aspergillus niger</u> on specimens.	72
3.20 The observed growth of <u>Gliocladium virens</u>	73
3.21 The observed growth of <u>Chaetomium globosum</u>	74
3.22 Percentage molecular weight loss.....	75

LIST OF FIGURES

	page
3.1 Apparatus for preparing the Grignard reagent.....	36
3.2 A 'dry bag'.....	37
3.3 IR spectrum of poly (ϵ -caprolactone) ; KBr pellet.....	61
3.4 IR spectra of starch.....	62
3.5 $^1\text{H-NMR}$ spectrum of poly (ϵ -caprolactone).....	64
3.6 $^{13}\text{C-NMR}$ spectrum of poly (ϵ -caprolactone).....	64
3.7 A simple mold for casting polymers into films.....	66
4.1 Plot of grafting parameters against the reaction volumes.....	80
4.2 Effect of time-interval on grafting parameters.....	83
4.3 Effect of initiator amount on grafting parameters.....	85
4.4 Grafting parameters as functions of monomer concentrations.....	88
4.5 Effect of amount of nitric acid on grafting parameters.	90
4.6 Effect of temperature on grafting parameters.....	93

LIST OF SCHEMES

	page
2.1 The representation of graft copolymer ; (A) is the repeating unit of the main chain, (B) is of the side chain and (x) is the branch point.....	21
2.2 The structures of amylose and amylopectin.....	23
4.1 The procedure for synthesis of poly (ϵ -caprolactone)..	77