



## REFERENCES

Alford, C.E. Stable aluminum hydroxide suspension U.S.  
Patent No 2,999,790, New York : Sterling Drug.,  
1959

Armstrong, N.A. and Clarke, C.D. Adsorption sites of kaolin.  
J.Pharm. Sci. 65 (March 1976) : 373-375

Clarke, C.D. and Armstrong, N.A. Influence of pH on the  
adsorption of benzoic acid by kaolin. Pharm. J.  
209(1972) : 44-45.

Feldkamp, J.R., Shah, D.N., Meyer, S.L., White J.L., and  
Hem, S.L. Effect of adsorbed carbonate on  
surface charge characteristics and  
physical properties of aluminum hydroxide  
gel. J. Pharm. Sci. 70(June 1981) : 638-640.

\_\_\_\_\_, White, J.L., and Hem, S.L. Effect of  
Surface charge and particle size on gel structure  
of aluminum hydroxycarbonate gel. J. Pharm. Sci.  
71(January 1982) : 43-46.

Florence, A.T. and Attwood, D. Interfacial phenomena.  
Physicochemical principles of pharmacy. pp. 435-  
441 London : The Macmillian Press Ltd., 1981

Greene, L.C., Moorestown, N.J., Misher, A., and Smith, W.E. Concentration antacid compositions and method of producing antacid activity.  
U.S. Patent No 3,591,680, Philadelphia : SKF Lab., 1969

Hem, S.L., Russo, E.J., Bahal, S.M., and Levi, R.S. Effect of pH of precipitation on antacid properties of hydrous aluminum oxide.  
J. Pharm. Sci. 59(March 1970) : 317-321

\_\_\_\_\_, Russo, E.J., Harwood, R.J., Tejani, B.H., Bahal, S.M., and Levi, R.S. Kinetics of hydrous aluminum oxide conversion in mixtures of amorphous alumina gels of various acid reactivities.  
J. Pharm. Sci. 59 (March 1970) : 376-379

\_\_\_\_\_, White, J.L., Buchler, J.D., Luber, J.R., Grim, W.M., and Lipka, E.A. Evaluation of antacid suspensions containing aluminum hydroxide and magnesium hydroxide. Am. J. Hosp. Pharm. 39 (November 1982) : 1925-1930

Joint Committee on Powder Diffraction Standards (JCPDS). Selected Powder Diffraction data for minerals. 1<sup>st</sup> ed., Philadelphia : Publication DBM-1-23, 1974

Kerkhof, N.J., Vanderlaan, R.K., White, J.L., and Hem, S.L. pH-stat titration of aluminum hydroxide gel.

J. Pharm. Sci. 66(November 1977) : 1528-1533

\_\_\_\_\_, White, J.L., and Hem, S.L. Role of carbonate in acid neutralization of aluminum hydroxide gel.

J. Pharm. Sci. 66(November 1977) 1533-1535

Liu, J-C, Feldkamp, J.R., White, J.L., and Hem, S.L. Adsorption of phosphate by aluminum hydroxycarbonate. J.Pharm. Sci. 73(October 1984) : 1355-1358

\_\_\_\_\_, Feldkamp, J.R., White, J.L., Hem, S.L., Otsuka, N., Conroy, D.F., Pendharkar, C.M., Feld, K.M., Harwood, R.J., and Grim, W.M. Particle morphology of amorphous aluminum hydroxycarbonate and its effect on tablet production. Drug. Dev. Ind. Pharm. 13 (December 1987) : 2087-2110

Martin, A., Swarbrick, J., and Cammarata, A. Ionic equilibria. In Physical pharmacy, 3<sup>rd</sup> ed., pp. 192, Philadelphia : Lea & febiger, 1983

McCarthy, T.J. Formulated factor affecting the activity of preservatives. In J.J.Kabara (ed.), Cosmetic and Drug Preservation Principle and Practice. volume 1,pp 359-388 New York : Marcel Dekker, Inc., 1984

McEvoy, G.K. Antacids and adsorbents. American Hospital Formulary Service (AHFS) Drug Information TM 88. pp. 1606-1611. U.S.A : American Society of Hospital Pharmacists, Inc., 1988

Morefield, E.M., Feldkamps, J.R., Peck, G.E., White, J.L., and Hem, S.L. Int. J. Pharm. 34(1987) : 263-265

\_\_\_\_\_, Konechnik, T.J., Peck, G.E., Feldkamp, J.R., White, J.L., and Hem, S.L. Effect of shear on the apparent viscosity of amorphous carbonate ion containing aluminum hydroxide suspension. J. Pharm. Sci. 75(march 1986) : 297-300

\_\_\_\_\_, Peck, G.E., Hem, S.L., Feldkamp, J.R., and White, J.L. Adsorption of hypochlorite by aluminum hydroxide. J.Pharm.Sci., 74(September 1985) : 1019-1020

Nail, S.L., White, J.L., and Hem, S.L. Comparison of IR spectroscopic analysis and X-ray diffraction of aluminum hydroxide gel. J. Pharm. Sci. 64(July 1975) : 1166-1169

\_\_\_\_\_. IR studies of development of order in aluminum hydroxide gels. J.Pharm. Sci. 65(February 1976a) : 231-234

- \_\_\_\_\_. structure of aluminum hydroxide gel I :  
Initial precipitate. J. Pharm. Sci. 65 (August 1976b) : 1188-1191
- \_\_\_\_\_. Structure of aluminum hydroxide gel II : Aging mechanism. J. Pharm. Sci. 65 (August 1976c) : 1192-1195
- \_\_\_\_\_. Structure of aluminum hydroxide gel III : Mechanism of stabilization by sorbitol. J. Pharm. Sci. 65 (August 1976d) : 1195-1198
- \_\_\_\_\_. Kinetics of acid neutralization by aluminum hydroxide gel. J. Pharm. Sci. 65 (August 1976e) : 1255-1258
- \_\_\_\_\_. Differential thermal analysis of aluminum hydroxide gel. J. Pharm. Sci. 65 (September 1976f) : 1391-1393
- Nairn, J.G. Gels. In A.R. Gennaro (ed.), Remington Pharmaceutical Science. 18<sup>th</sup> ed. pp. 1539-1540. Pennsylvania : Mack Publication Company, 1990
- Nakamori, R., Tanaka, F., Nojiri, T., Yoshino, H., and Okumura, M. Phenol formation from alkyl parabens by bacteria. J. Pharm. Sci. 64 (June 1975) : 1071-1073

Parab, P.V., Nayak, M.P., and Ritschel, W.A. Influence of hydroxypropyl methylcellulose and of manufacturing technique on In-Vitro performance of selected antacids. Drug. Dev. Ind. Pharm. 11 (January 1985) : 169-185

Reynolds, J.E.M. Aluminum hydroxide gel. Martindale The Extrapharmacopoeia. 29<sup>th</sup> ed. pp. 1075-1077. London : The pharmaceutical Press, 1989

Rinse, J. and Dontje, A.J. Polymeric aluminum oxide hydroxides. U.S. Patent No 3,056,725, Los Angeles: Delaware, 1962

Rubino, A.M., Providence, N., and Margres, J.T. Resuspendable dried antacid. U.S. Patent No 4,112,072, Phoenix : Armour Pharmaceutical Company, 1973

Schmidt, P.C. and Benke, K. Untersuchungen zur adsorption und stabilitat von konservieerungsstoffen in antacidasuspensionen 1. Mitteilung : Bestimmung und Beeinflussung der adsorption. Pharm. Acta. Helv. 63(1988 a) : 117-127

\_\_\_\_\_. Untersuchungen zur adsorption und stabilitat von konservierungsstoffen in antacidasuspensionen 2. Mitteilung : Reaktionskinetische Stabilitatsuntersuchungen. Pharm. Acta. Helv. 63(1988b) : 188-196

Scholtz, E.C., Feldkamp, J.R., White, J.L., and Hem, S.L.  
Desorption of carbonate from aluminum hydroxycarbonate gel by nitrogen purging. J. Pharm. Sci. 73(February 1984a) : 209-212

\_\_\_\_\_. Properties of carbonate-containing aluminum hydroxide produced by precipitation at constant pH. J. Pharm. Sci. 73(July 1984b) : 967-973

\_\_\_\_\_. Exchange of sodium by magnesium in aluminum hydroxycarbonate gel. J. Pharm. Sci. 73(July 1984c) : 1007-1009

\_\_\_\_\_. Point of Zero Charge of amorphous aluminum hydroxide as function of adsorbed carbonate. J. Pharm. Sci. 74(April 1985) : 478-481

Scholzt, E.C., Zapata, M.I., Hem, S.L., Feldkamp, J.R., and White, J.L. Physicochemical interpretation of pH-stat titration of amorphous aluminum hydroxycarbonate. J. Pharm. Sci. 72 (August 1983) : 973-975

Schott, H. Relationship between Zero Point of Charge and solubility product for hydroxides of polyvalent cations. J. Pharm. Sci. 66 (November 1977) : 1548-1550

Sepelyak, R.J., Feldkamp, J.R., Moody, T.E., White, J.L., and Hem, S.L. Adsorption of pepsin by aluminum hydroxide I : Adsorption mechanism. J. Pharm. Sci. 73 (November 1984a) : 1514-1517

\_\_\_\_\_. Adsorption of pepsin by aluminum hydroxide II : Pepsin inactivation. J. Pharm. Sci. 73 (November 1984b) : 1517-1522

Serna, C.J., Lyons, J.C., White, J.L., and Hem, S.L. Stabilization of aluminum hydroxide gel by specifically adsorbed carbonate. J. Pharm. Sci. 72(July 1983) : 769-771

\_\_\_\_\_. White, J.L., and Hem, S.L. Structure survey of carbonate-containing antacids, J. Pharm. Sci. 67 (March 1978a) : 324-327

\_\_\_\_\_. Nature of amorphous aluminum hydroxycarbonate. J. Pharm. Sci. 67 (August 1978b) : 1144-1147

\_\_\_\_\_. Factor affecting homogeneous precipitation of aluminum hydroxide gel. J. Pharm. Sci. 67(August 1978c) : 1179-1181

Shah, D.N., Feldkamp, J.R., White, J.L., and Hem, S.L. Effect of the pH-Zero Point of Charge relationship on the interaction of ionic compounds and polyols with aluminum hydroxide gel. J. Pharm. Sci. 71 (February 1982) : 266-268

\_\_\_\_\_. White, J.L., and Hem, S.L. Mechanism of interaction between polyols and aluminum hydroxide gel. J. Pharm. Sci. 70 (October 1981) : 1101-1104

Swinyard, E.A. Gastrointestinal drugs. In A.R. Gennaro (ed.), Remington Pharmaceutical Science. 18<sup>th</sup> ed, pp. 774-775. Pennsylvania : Mack Publication Company, 1990

Szymanski, H.A. and Erickson, R.E. Infrared Band Handbook. volume 1., pp.371. New York : IFI/Plenum Data Corporation., 1970

The United States Pharmacopeial Convention, Inc. The United States Pharmacopeia(USP). 22<sup>nd</sup> rev., pp. 52, 1624-1625. U.S.A. : 1990

Vanderlaan, R.K., White, J.L., and Hem, S.L. Effect of interaction of aluminum hydroxycarbonate gel and magnesium hydroxide gel on acid neutralization. J. Pharm. Sci. 68(December 1979) : 1498-1501

\_\_\_\_\_. Formation of hydrotalcite in mixtures of aluminum hydroxycarbonate and magnesium hydroxide gels. J. Pharm. Sci. 71(July 1982) : 780-786


Wang, M.K., White, J.L., and Hem, S.L. Effect of polybasic acids on structure of aluminum hydroxycarbonate gel. J. Pharm. Sci. 69(June 1980) : 668-671

White, J.L. and Hem, S.L. Role of carbonate in aluminum hydroxide gel established by Raman and IR analyses. J. Pharm. Sci. 64 (March 1975) : 468-469

Wou, L.L-S. and Mulley, B.A. Microstructure of aluminum hydroxide and the formation of aluminum dye Lakes. J. Pharm. Sci. 72(February 1984) : 1738-1744

Zapata, M.I., Feldkamp, J.R., Peck, G.E., White, J.L., and Hem, S.L. Mechanism of freeze-thaw instability of aluminum hydroxycarbonate and magnesium hydroxide gel. J. Pharm. Sci. 73 (January 1984) : 3-8

ศูนย์วิทยบริการ  
จุฬาลงกรณ์มหาวิทยาลัย



**APPENDIX**

ศูนย์วิทยบริพยากร  
จุฬาลงกรณ์มหาวิทยาลัย

Table 29

The Point of Zero Charge of Gel 1 during aging at ambient temperature

Vol.KOH pH at various ionic strength				Vol.HCl pH at various ionic strength				initial
(ml)	0.0	0.1	0.2	(ml)	0.0	0.1	0.2	
0.0	7.99	7.80	7.74	0.0	7.99	7.80	7.74	
0.2	8.03	7.83	7.76	1.0	7.57	7.42	7.40	
0.4	8.06	7.86	7.79	2.0	7.18	7.11	7.08	
0.6	8.10	7.90	7.82	3.0	6.86	6.78	6.76	
0.8	8.14	7.94	7.86	4.0	6.60	6.54	6.53	
1.0	8.19	7.98	7.90	4.2	6.54	6.52	6.51	
1.2	8.22	8.02	7.94	4.4	6.46	6.48	6.49	
1.4	8.26	8.06	7.98	4.6	6.43	6.45	6.48	
1.6	8.31	8.11	8.03	4.8	6.39	6.42	6.46	
1.8	8.36	8.16	8.08	5.0	6.32	6.40	6.43	
2.0	8.41	8.22	8.14					

Vol.KOH pH at various ionic strength				Vol.HCl pH at various ionic strength				after storage for 3 months
(ml)	0.0	0.1	0.2	(ml)	0.0	0.1	0.2	
0.0	8.03	7.95	7.66	0.0	8.03	7.95	7.66	
1.0	8.20	8.02	7.70	3.0	6.82	6.80	6.72	
2.0	8.41	8.20	7.86	3.2	6.76	6.75	6.68	
3.0	8.61	8.38	8.01	3.4	6.72	6.69	6.64	
4.0	8.75	8.50	8.11	3.6	6.66	6.64	6.62	
				3.8	6.62	6.61	6.61	
				4.0	6.58	6.59	6.59	
				4.2	6.53	6.55	6.58	
				4.4	6.50	6.51	6.54	
				4.6	6.46	6.48	6.51	
				4.8	6.40	6.43	6.47	
				5.0	6.36	6.40	6.46	

Vol.KOH pH at various ionic strength				Vol.HCl pH at various ionic strength				after storage for 6 months
(ml)	0.0	0.1	0.2	(ml)	0.0	0.1	0.2	
0.0	7.95	7.64	7.53	0.0	7.95	7.64	7.53	
1.0	8.17	7.84	7.71	3.0	6.97	6.89	6.85	
2.0	8.37	8.02	7.87	3.2	6.93	6.86	6.83	
3.0	8.58	8.21	8.04	3.4	6.87	6.83	6.80	
4.0	8.72	8.33	8.15	3.6	6.83	6.79	6.76	
				3.8	6.78	6.75	6.73	
				4.0	6.73	6.73	6.71	
				4.2	6.67	6.68	6.69	
				4.4	6.63	6.65	6.66	
				5.0	6.50	6.53	6.60	
				6.0	6.32	6.37	6.46	

Table 30

The Point of Zero Charge of Gel 2 during aging at ambient temperature

Vol.KOH pH at various ionic strength				Vol.HCl pH at various ionic strength				initial
(ml)	0.0	0.1	0.2	(ml)	0.0	0.1	0.2	
0.0	7.20	7.04	6.96	0.0	7.20	7.04	6.96	
0.2	7.23	7.09	6.99	0.2	7.06	7.00	6.94	
0.4	7.28	7.16	7.05	0.4	7.00	6.95	6.91	
1.0	7.54	7.30	7.08	0.6	6.93	6.90	6.89	
2.0	7.80	7.75	7.50	0.8	6.87	6.88	6.88	
				1.0	6.83	6.85	6.86	
				1.2	6.77	6.80	6.82	
				1.4	6.72	6.75	6.78	
				1.6	6.65	6.69	6.74	
				1.8	6.60	6.65	6.71	
				2.0	6.54	6.60	6.68	
				3.0	6.28	6.37	6.49	

Vol.KOH pH at various ionic strength				Vol.HCl pH at various ionic strength				after storage for 3 months
(ml)	0.0	0.1	0.2	(ml)	0.0	0.1	0.2	
0.0	7.18	7.09	7.07	0.0	7.18	7.09	7.07	
0.8	7.35	7.16	7.13	0.4	7.09	7.03	7.02	
1.0	7.44	7.24	7.21	0.6	7.06	7.01	6.99	
1.2	7.50	7.28	7.26	0.8	7.01	6.98	6.95	
1.6	7.66	7.37	7.34	1.0	6.97	6.95	6.93	
1.8	7.73	7.42	7.39	1.2	6.93	6.91	6.90	
2.0	7.80	7.46	7.42	1.4	6.87	6.87	6.87	
				1.6	6.80	6.84	6.84	
				1.8	6.72	6.80	6.83	
				2.0	6.67	6.75	6.80	
				2.2	6.61	6.70	6.75	

Vol.KOH pH at various ionic strength				Vol.HCl pH at various ionic strength				after storage for 6 months
(ml)	0.0	0.1	0.2	(ml)	0.0	0.1	0.2	
0.0	7.18	7.15	7.13	0.0	7.18	7.15	7.13	
1.0	7.48	7.38	7.32	0.4	7.09	7.05	7.04	
2.0	7.85	7.73	7.64	0.6	7.00	6.97	6.96	
3.0	8.25	8.08	7.97	0.8	6.94	6.93	6.93	
4.0	8.67	8.45	8.32	1.0	6.89	6.90	6.91	
				1.2	6.84	6.87	6.89	
				1.4	6.80	6.86	6.88	
				2.0	6.70	6.78	6.81	
				3.0	6.51	6.63	6.69	
				4.0	6.23	6.37	6.43	

Table 31

The Point of Zero Charge of Gel 3 during aging at ambient temperature

Vol.KOH pH at various ionic strength				Vol.HCl pH at ionic strength				
(ml)	0.0	0.1	0.2	(ml)	0.0	0.1	0.2	
0.0	6.75	6.83	6.84	0.0	6.75	6.83	6.84	initial
0.2	6.88	6.89	6.90	0.2	6.64	6.78	6.79	
0.4	6.95	6.95	6.94	0.4	6.52	6.74	6.75	
0.6	7.02	7.01	6.99	0.6	6.44	6.70	6.72	
0.8	7.09	7.06	7.02	0.8	6.36	6.66	6.68	
1.0	7.17	7.11	7.07	1.0	6.29	6.63	6.65	
1.2	7.24	7.14	7.10	1.2	6.22	6.58	6.62	
1.4	7.32	7.18	7.14	1.4	6.12	6.41	6.47	
2.0	7.39	7.24	7.19	2.0	5.82	6.30	6.35	

Vol.KOH pH at various ionic strength				Vol.HCl pH at various ionic strength				
(ml)	0.0	0.1	0.2	(ml)	0.0	0.1	0.2	
0.0	6.70	6.80	6.85	0.0	6.70	6.80	6.85	after storage for 3 months
0.2	6.77	6.85	6.89	0.2	6.64	6.74	6.79	
0.4	6.85	6.91	6.94	0.4	6.59	6.70	6.76	
0.6	6.97	7.01	7.03	0.6	6.53	6.64	6.71	
0.8	7.09	7.12	7.14	0.8	6.48	6.60	6.68	
1.0	7.18	7.20	7.21	1.0	6.40	6.54	6.63	
1.2	7.28	7.29	7.29					
1.4	7.33	7.32	7.31					
1.6	7.36	7.34	7.32					
1.8	7.41	7.37	7.34					
2.0	7.44	7.39	7.35					

Vol.KOH pH at various ionic strength				Vol.HCl pH at various ionic strength				
(ml)	0.0	0.1	0.2	(ml)	0.0	0.1	0.2	
0.0	6.69	6.92	7.03	0.0	6.69	6.92	7.03	after storage for 6 months
0.4	6.81	6.99	7.09	0.2	6.60	6.83	6.95	
1.0	7.01	7.14	7.22	0.4	6.52	6.76	6.89	
1.4	7.18	7.23	7.28	0.6	6.43	6.68	6.83	
1.8	7.30	7.32	7.34	0.8	6.33	6.60	6.76	
2.0	7.36	7.38	7.39	1.0	6.22	6.50	6.68	
2.2	7.44	7.43	7.43					
2.4	7.49	7.47	7.46					
2.6	7.56	7.52	7.50					
2.8	7.62	7.56	7.53					
3.0	7.68	7.62	7.58					

Table 32

The Point of Zero Charge of Gel 4 during aging at ambient temperature

Vol.KOH pH at various ionic strength				Vol.HCl pH at various ionic strength				
(ml)	0.0	0.1	0.2	(ml)	0.0	0.1	0.2	
0.0	6.71	6.86	6.90	0.0	6.71	6.86	6.90	initial
0.2	6.84	6.92	6.95	0.2	6.60	6.82	6.85	
0.4	6.94	6.97	6.99	0.4	6.47	6.77	6.82	
0.6	7.03	7.02	7.01	0.6	6.38	6.69	6.74	
0.8	7.11	7.05	7.03	0.8	6.30	6.63	6.68	
1.0	7.19	7.12	7.10	1.0	6.18	6.53	6.60	
1.2	7.27	7.16	7.13					
1.4	7.38	7.26	7.18					
1.6	7.44	7.30	7.24					
1.8	7.51	7.36	7.29					
2.0	7.60	7.43	7.34					

Vol.KOH pH at various ionic strength				Vol.HCl pH at various ionic strength				
(ml)	0.0	0.1	0.2	(ml)	0.0	0.1	0.2	
0.0	6.70	6.96	6.99	0.0	6.70	6.96	6.99	after storage for 3 months
0.2	6.78	7.03	7.06	0.2	6.64	6.92	6.96	
0.4	6.82	7.06	7.09	0.4	6.57	6.87	6.92	
0.6	6.99	7.13	7.16	0.6	6.48	6.80	6.86	
0.8	7.11	7.20	7.23	0.8	6.40	6.72	6.79	
1.0	7.22	7.29	7.31	1.0	6.28	6.61	6.69	
1.2	7.33	7.36	7.37					
1.4	7.40	7.40	7.39					
1.6	7.50	7.48	7.47					
1.8	7.63	7.60	7.58					
2.0	7.74	7.69	7.66					

Vol.KOH pH at various ionic strength				Vol.HCl pH at various ionic strength				
(ml)	0.0	0.1	0.2	(ml)	0.0	0.1	0.2	
0.0	6.64	6.87	6.99	0.0	6.64	6.87	6.99	after storage for 6 months
0.4	6.82	7.01	7.12	0.2	6.57	6.81	6.95	
0.6	6.99	7.12	7.19	0.4	6.49	6.74	6.89	
0.8	7.12	7.20	7.25	0.6	6.40	6.65	6.83	
1.0	7.25	7.30	7.32	0.8	6.32	6.57	6.76	
1.2	7.42	7.41	7.40	1.0	6.22	6.48	6.58	
1.4	7.52	7.47	7.45					
1.6	7.67	7.55	7.53					
1.8	7.76	7.64	7.58					
2.0	7.84	7.72	7.64					

Table 33

The Point of Zero Charge of Gel 5 during aging at ambient temperature

Vol.KOH pH at various ionic strength (ml)			Vol.HCl pH at various ionic strength (ml)					
0.0	0.1	0.2	0.0	0.1	0.2			
0.0	8.08	7.76	7.70	0.0	8.08	7.76	7.70	initial
1.0	8.21	8.00	7.76	3.0	6.85	6.79	6.76	
2.0	8.43	8.21	7.93	4.0	6.55	6.53	6.50	
3.0	8.65	8.42	8.17	4.2	6.48	6.44	6.40	
4.0	8.81	8.55	8.24	4.4	6.41	6.37	6.34	
5.0	8.95	8.65	8.32	4.6	6.35	6.32	6.31	
6.0	9.07	8.76	8.41	4.8	6.30	6.30	6.30	
				5.0	6.25	6.27	6.28	
				5.2	6.19	6.22	6.25	
				5.4	6.13	6.18	6.22	
				6.0	6.05	6.13	6.19	

Vol.KOH pH at various ionic strength (ml)			Vol.HCl pH at various ionic strength (ml)					
0.0	0.1	0.2	0.0	0.1	0.2			
0.0	7.84	7.66	7.57	0.0	7.84	7.66	7.57	after storage for 3 months
1.0	8.25	8.05	7.95	2.0	7.00	7.89	6.85	
2.0	8.66	8.45	8.34	2.2	6.94	6.84	6.81	
3.0	8.80	8.57	8.43	2.4	6.86	6.80	6.77	
4.0	8.87	8.63	8.47	2.6	6.81	6.76	6.73	
				2.8	6.74	6.70	6.68	
				3.0	6.68	6.65	6.64	
				3.2	6.62	6.60	6.59	
				3.4	6.56	6.56	6.55	
				3.6	6.52	6.53	6.54	
				3.8	6.46	6.48	6.49	
				4.0	6.41	6.45	6.47	

Vol.KOH pH at various ionic strength (ml)			Vol.HCl pH at various ionic strength (ml)					
0.0	0.1	0.2	0.0	0.1	0.2			
0.0	7.72	7.65	7.63	0.0	7.72	7.65	7.63	after storage for 6 months
1.0	8.25	8.21	8.12	1.0	7.34	7.27	7.25	
2.0	8.70	8.66	8.57	1.6	7.10	7.04	7.03	
3.0	8.78	8.73	8.63	1.8	7.05	7.01	7.00	
4.0	8.85	8.77	8.66	2.0	7.01	6.99	6.98	
5.0	8.93	8.83	8.70	2.2	6.95	6.96	6.96	
				2.4	6.84	6.88	6.90	
				2.6	6.79	6.84	6.87	
				2.8	6.76	6.81	6.84	
				3.0	6.74	6.79	6.82	
				4.0	6.60	6.68	6.74	

Table 34

The Point of Zero Charge of Gel 6 during aging at ambient temperature

Vol.KOH pH at various ionic strength				Vol.HCl pH at various ionic strength				initial
(ml)	0.0	0.1	0.2	(ml)	0.0	0.1	0.2	
0.0	7.19	7.21	7.24	0.0	7.19	7.21	7.24	
0.2	7.28	7.27	7.26	0.4	7.00	7.06	7.08	
0.4	7.35	7.33	7.31	0.8	6.79	6.90	6.96	
0.6	7.45	7.43	7.42	1.2	6.68	6.80	6.88	
0.8	7.53	7.50	7.47	2.0	6.26	6.47	6.56	
1.0	7.60	7.55	7.52	4.0	5.80	6.03	6.17	
2.0	7.93	7.82	7.77	6.0	5.63	5.87	6.00	
3.0	8.25	8.14	8.00					
4.0	8.48	8.33	8.19					

Vol.KOH pH at various ionic strength				Vol.HCl pH at various ionic strength				after storage for 3 months
(ml)	0.0	0.1	0.2	(ml)	0.0	0.1	0.2	
0.0	7.21	7.27	7.29	0.0	7.21	7.27	7.29	
0.4	7.35	7.41	7.43	0.4	7.05	7.13	7.17	
0.6	7.40	7.47	7.49	1.0	6.95	7.05	7.12	
1.6	7.65	7.68	7.70	2.0	6.87	6.97	7.05	
1.8	7.71	7.71	7.72	3.0	6.78	6.90	6.99	
2.0	7.77	7.75	7.74					
2.2	7.84	7.80	7.78					
2.6	8.00	7.95	7.91					
3.6	8.41	8.34	8.18					
4.6	8.62	8.52	8.35					
5.6	8.81	8.69	8.49					

Vol.KOH pH at various ionic strength				Vol.HCl pH at various ionic strength				after storage for 6 months
(ml)	0.0	0.1	0.2	(ml)	0.0	0.1	0.2	
0.0	7.01	7.13	7.21	0.0	7.01	7.13	7.21	
1.0	7.46	7.49	7.52	0.2	6.97	7.09	7.18	
1.2	7.54	7.58	7.60	0.4	6.90	7.04	7.14	
1.4	7.64	7.65	7.66	0.8	6.79	6.96	7.07	
1.6	7.71	7.71	7.72	1.0	6.70	6.90	7.02	
1.8	7.80	7.78	7.77					
2.0	7.87	7.84	7.80					
2.2	7.94	7.89	7.84					
2.4	8.00	7.94	7.88					
2.6	8.07	7.98	7.91					
2.8	8.15	8.03	7.94					
3.0	8.19	8.07	7.97					

Table 35

The Point of Zero Charge of Gel 7 during aging at ambient temperature

Vol.KOH pH at various ionic strength				Vol.HCl pH at various ionic strength				
(ml)	0.0	0.1	0.2	(ml)	0.0	0.1	0.2	
0.0	7.18	7.30	7.37	0.0	7.18	7.30	7.37	initial
1.0	7.60	7.63	7.66	0.4	7.12	7.28	7.35	
1.2	7.65	7.67	7.69	0.8	6.94	7.16	7.24	
1.4	7.70	7.71	7.73	1.0	6.88	7.10	7.19	
1.6	7.76	7.77	7.77	1.4	6.73	6.98	7.10	
1.8	7.80	7.80	7.79	2.0	6.57	6.86	7.01	
2.0	7.85	7.84	7.83					
2.2	7.89	7.88	7.86					
2.4	7.96	7.94	7.91					
2.6	8.01	7.97	7.93					
2.8	8.05	8.01	7.96					
3.0	8.14	8.09	8.03					

Vol.KOH pH at various ionic strength				Vol.HCl pH at various ionic strength				
(ml)	0.0	0.1	0.2	(ml)	0.0	0.1	0.2	
0.0	7.19	7.36	7.39	0.0	7.19	7.36	7.39	after storage for 3 months-
1.0	7.48	7.57	7.60	0.2	7.16	7.34	7.37	
2.0	7.72	7.74	7.76	0.4	7.14	7.31	7.35	
2.2	7.75	7.78	7.79	0.6	7.11	7.29	7.33	
2.4	7.81	7.81	7.81	0.8	7.08	7.26	7.31	
2.6	7.85	7.84	7.83	1.0	7.04	7.24	7.29	
2.8	7.89	7.88	7.87	2.0	6.32	6.54	6.62	
3.0	7.93	7.91	7.90					
4.0	8.14	8.08	8.06					
5.0	8.38	8.25	8.22					

Vol.KOH pH at various ionic strength				Vol.HCl pH at various ionic strength				
(ml)	0.0	0.1	0.2	(ml)	0.0	0.1	0.2	
0.0	7.18	7.34	7.41	0.0	7.18	7.34	7.41	
1.0	7.57	7.65	7.71	1.0	7.10	7.28	7.38	
1.2	7.66	7.72	7.78	2.0	7.00	7.20	7.32	
1.4	7.80	7.82	7.86	3.0	6.88	7.10	7.23	
1.6	7.87	7.89	7.92	4.0	6.76	7.00	7.15	
1.8	7.92	7.93	7.96	5.0	6.58	6.87	7.05	
2.0	8.00	8.00	7.99					
2.2	8.05	8.04	8.03					
2.4	8.12	8.09	8.07					
3.0	8.31	8.26	8.20					
4.0	8.64	8.54	8.47					
5.0	8.92	8.79	8.71					

after storage for 6 months



## VITAE

Mr. Nimit Worakul was born on April 11, 1965, in Songkhla, Thailand. He graduated with a Bachelor of Science in Pharmacy in 1988 from the Faculty of Pharmacy, Prince of Songkhla University, Songkhla, Thailand.

ศูนย์วิทยบริการ  
อุปกรณ์รวมมหาวิทยาลัย