

REFERENCES

- Ahlberg, K. M., Assavanop, P., Tay, W. M. 1995. A comparison of the apical dye penetration patterns shown by methylene blue and india ink in root-filled teeth. Int Endod J 28(1): 30-4.
- Aktener, B. O., Cengiz, T., Piskin, B. 1989. The penetration of smear material into dentinal tubules during instrumentation with surface-active reagents: a scanning electron microscopic study. J Endod 15(12): 588-90.
- Barthel, C. R., Moshonov, J., Shuping, G., Orstavik, D. 1999. Bacterial leakage versus dye leakage in obturated root canals. Int Endod J 32(5): 370-5.
- Basrani, B. R., Manek, S., Sodhi, R. N., Fillery, E., Manzur, A. 2007. Interaction between sodium hypochlorite and chlorhexidine gluconate. J Endod 33(8): 966-9.
- Biggs, S. G., Knowles, K. I., Ibarrola, J. L., Pashley, D. H. 2006. An in vitro assessment of the sealing ability of resilon/epiphany using fluid filtration. J Endod 32(8): 759-61.
- Bodrumlu, E., Tunga, U. 2006. Apical leakage of Resilon obturation material. J Contemp Dent Pract 7(4): 45-52.
- Bui, T. B., Baumgartner, J. C., Mitchell, J. C. 2008. Evaluation of the Interaction between Sodium Hypochlorite and Chlorhexidine Gluconate and its Effect on Root Dentin. J Endod 34(2): 181-5.
- Camps, J., Pashley, D. 2003. Reliability of the dye penetration studies. J Endod 29(9): 592-4.

- Carratu, P., Amato, M., Riccitiello, F., Rengo, S. 2002. Evaluation of leakage of bacteria and endotoxins in teeth treated endodontically by two different techniques. J Endod 28(4): 272-5.
- Chailertvanitkul, P., Saunders, W. P., Saunders, E. M., MacKenzie, D. 1997. An evaluation of microbial coronal leakage in the restored pulp chamber of root-canal treated multirooted teeth. Int Endod J 30(5): 318-22.
- Cobankara, F. K., Adanir, N., Belli, S., Pashley, D. H, 2002. A quantitative evaluation of apical leakage of four root-canal sealers. Int Endod J 35(12): 979-84.
- De Oliveira, D. P., Barbizam, J. V., Trope, M., Teixeira, F. B. 2006. Comparison between gutta-percha and resilon removal using two different techniques in endodontic retreatment. J Endod 32(5): 362-4.
- Derkson, G. D., Pashley, D. H., Derkson, M. E. 1986. Microleakage measurement of selected restorative materials: a new in vitro method. J Prosthet Dent 56(4): 435-40.
- Ezzie, E., Fleury, A., Solomon, E., Spears, R., He, J. 2006. Efficacy of retreatment techniques for a resin-based root canal obturation material. J Endod 32(4): 341-4.
- Fardal, O., Turnbull, R. S. 1986. A review of the literature on use of chlorhexidine in dentistry. J Am Dent Assoc 112(6): 863-9.
- Ferguson, D. B., Marley, J. T., Hartwell, G. R. 2003. The effect of chlorhexidine gluconate as an endodontic irrigant on the apical seal: long-term results. J Endod 29(2): 91-4.

- Fogel, H. M., Marshall, F. J., Pashley, D. H. 1988. Effects of distance from the pulp and thickness on the hydraulic conductance of human radicular dentin. J Dent Res 67(11): 1381-5.
- Gesi, A., Raffaelli, O., Goracci, C., Pashley, D. H., Tay, F. R., Ferrari, M. 2005 Interfacial strength of Resilon and gutta-percha to intraradicular dentin. J Endod 31(11): 809-13.
- Gettleman, B. H., Messer, H. H., ElDeeb, M. E. 1991. Adhesion of sealer cements to dentin with and without the smear layer. J Endod 17(1): 15-20.
- Goldman, M., Goldman, L. B., Cavaleri, R., Bogis, J., Lin, P. S. 1982. The efficacy of several endodontic irrigating solutions: a scanning electron microscopic study: Part 2. J Endod 8(11): 487-92.
- Goldman, M., Simmonds, S., Rush, R. 1989. The usefulness of dye-penetration studies reexamined. Oral Surg Oral Med Oral Pathol 67(3): 327-32.
- Grossman, L. 1981. Endodontic practice Philadelphia, Lea&Febigure.
- Hiraishi, N., Papacchini, F., Loushine, R. J. et al. 2005. Shear bond strength of Resilon to a methacrylate-based root canal sealer. Int Endod J 38(10): 753-63.
- Ishley, D. J., ElDeeb, M. E. 1983. An in vitro assessment of the quality of apical seal of thermomechanically obturated canals with and without sealer. J Endod 9(6): 242-5.
- Katz, A., Rosenwasser, R., Tamse, A. 1998. Root positioning and leakage to dye in extracted teeth using reduced pressure. Int Endod J 31(1): 63-6.

- Kersten, H. W., Moorer, W. R. 1989. Particles and molecules in endodontic leakage. Int Endod J 22(3): 118-24.
- Key, J. E., Rahemtulla, F. G., Eleazer, P. D. 2006. Cytotoxicity of a new root canal filling material on human gingival fibroblasts. J Endod 32(8): 756-8.
- Kidd, E. A. 1976. Microleakage: a review. J Dent 4(5): 199-206.
- Kontakiotis, E. G., Georgopoulou, M. K., Morfis, A. S. 2001. Dye penetration in dry and water-filled gaps along root fillings. Int Endod J 34(2): 133-6.
- Kuruville, J. R., Kamath, M. P. 1998. Antimicrobial activity of 2.5% sodium hypochlorite and 0.2% chlorhexidine gluconate separately and combined, as endodontic irrigants. J Endod 24(7): 472-6.
- Lester, K. S., Boyde, A. 1977. Scanning electron microscopy of instrumented, irrigated and filled root canals. Br Dent J 143(11): 359-67.
- Loe, H. 1973. Does chlorhexidine have a place in the prophylaxis of dental diseases? J Periodontal Res 12 (Suppl): 93-9.
- Lucena-Martin, C., Ferrer-Luque, C. M., Gonzalez-Rodriguez, M. P., Robles-Gijon, V., Navajas-Rodriguez de Mondelo, J. M. 2002. A comparative study of apical leakage of Endomethasone, Top Seal, and Roeko Seal sealer cements. J Endod 28(6): 423-6.
- Mader, C. L., Baumgartner, J. C., Peters, D. D. 1984. Scanning electron microscopic investigation of the smeared layer on root canal walls. J Endod 10(10): 477-83.

- Mareending, M., Paque, F., Fischer, J., Zehnder, M. 2007. Impact of irrigant sequence on mechanical properties of human root dentin. J Endod 33(11): 1325-8.
- Marley, J. T., Ferguson, D. B., Hartwell, G. R. 2001. Effects of chlorhexidine gluconate as an endodontic irrigant on the apical seal: short-term results. J Endod 27(12): 775-8.
- Masters, J., Higa, R., Torabinejad, M. 1995. Effects of vacuuming on dye penetration patterns in root canals and glass tubes. J Endod 21(6): 332-4.
- Matloff, I. R., Jensen, J. R., Singer, L., Tabibi, A. 1982. A comparison of methods used in root canal sealability studies. Oral Surg Oral Med Oral Pathol 53(2): 203-8.
- McComb, D., Smith, D. C. 1975. A preliminary scanning electron microscopic study of root canals after endodontic procedures. J Endod 1(7): 238-42.
- Merdad, K., Pascon, A. E., Kulkarni, G., Santerre, P., Friedman, S. 2007. Short-term cytotoxicity assessment of components of the epiPhany resin-percha obturating system by indirect and direct contact millipore filter assays. J Endod 33(1): 24-7.
- Miner, M. R., Berzins, D. W., Bahcall, J. K. 2006. A comparison of thermal properties between gutta-percha and a synthetic polymer based root canal filling material (Resilon). J Endod 32(7): 683-6.
- Nielsen, B. A., Beeler, W. J., Vy, C., Baumgartner, J. C. 2006. Setting times of Resilon and other sealers in aerobic and anaerobic environments. J Endod 32(2): 130-2.

- Okino, L. A., Siqueira, E. L., Santos, M., Bombana, A. C., Figueiredo, J. A. 2004. Dissolution of pulp tissue by aqueous solution of chlorhexidine digluconate and chlorhexidine digluconate gel. Int Endod J 37(1): 38-41.
- Oksan, T., Aktener, B. O., Sen, B. H., Tezel, H. 1993. The penetration of root canal sealers into dentinal tubules. A scanning electron microscopic study. Int Endod J 26(5): 301-5.
- Oliver, C. M., Abbott, P. V. 1991. Entrapped air and its effects on dye penetration of voids. Endod Dent Traumatol 7(3): 135-8.
- Onay, E. O., Ungor, M., Orucoglu, H. 2006. An in vitro evaluation of the apical sealing ability of a new resin-based root canal obturation system. J Endod 32(10): 976-8.
- Oncag, O., Hosgor, M., Hilmioglu, S., Zekioglu, O., Eronat, C., Burhanoglu, D. 2003. Comparison of antibacterial and toxic effects of various root canal irrigants. Int Endod J 36(6): 423-32.
- Orucoglu, H., Sengun, A., Yilmaz, N. 2005. Apical leakage of resin based root canal sealers with a new computerized fluid filtration meter. J Endod 31(12): 886-90.
- Pitout, E., Oberholzer, T. G., Blignaut, E., Molepo, J. 2006. Coronal leakage of teeth root-filled with gutta-percha or Resilon root canal filling material. J Endod 32(9): 879-81.
- Pommel, L., Camps, J. 2001a. Effects of pressure and measurement time on the fluid filtration method in endodontics. J Endod 27(4): 256-8.
- Pommel, L., Jacquot, B., Camps, J. 2001b. Lack of correlation among three methods for evaluation of apical leakage. J Endod 27(5): 347-50.

- Ray, H. A., Trope, M. 1995. Periapical status of endodontically treated teeth in relation to the technical quality of the root filling and the coronal restoration. Int Endod J 28(1): 12-8.
- Robertson, D., Leeb, I. J., McKee, M., Brewer, E. 1980. A clearing technique for the study of root canal systems. J Endod 6(1): 421-4.
- Roda, R. S., Gutmann, J. L. 1995. Reliability of reduced air pressure methods used to assess the apical seal. Int Endod J 28(3): 154-62.
- Sagsen, B., Er, O., Kahraman, Y., Akdogan, G. 2007. Resistance to fracture of roots filled with three different techniques. Int Endod J 40(1): 31-5.
- Sagsen, B., Er, O., Kahraman, Y., Orucoglu, H. 2006. Evaluation of microleakage of roots filled with different techniques with a computerized fluid filtration technique. J Endod 32(12): 1168-70.
- Schafer, E., Olthoff, G. 2002. Effect of three different sealers on the sealing ability of both thermafil obturators and cold laterally compacted Gutta-Percha. J Endod 28(9): 638-42.
- Schafer, E., Zandbiglari, T., Schafer, J. 2007. Influence of resin-based adhesive root canal fillings on the resistance to fracture of endodontically treated roots: an in vitro preliminary study. Oral Surg Oral Med Oral Pathol Oral Radiol Endod 103(2): 274-9.
- Shemesh, H., Wu, M. K., Wesselink, P. R. 2006. Leakage along apical root fillings with and without smear layer using two different leakage models: a two-month longitudinal ex vivo study. Int Endod J 39(12): 968-76.

- Shipper, G., Ørstavik, D., Teixeira, F. B., Trope, M. 2004. An evaluation of microbial leakage in roots filled with a thermoplastic synthetic polymer-based root canal filling material (Resilon). J Endod 30(5): 342-7.
- Shipper, G., Teixeira, F. B., Arnold, R. R., Trope, M. 2005. Periapical inflammation after coronal microbial inoculation of dog roots filled with gutta-percha or resilon. J Endod 31(2): 91-6.
- Sly, M. M., Moore, B. K., Platt, J. A., Brown, C. E. 2007. Push-out bond strength of a new endodontic obturation system (Resilon/Epiphany). J Endod 33(2): 160-2.
- Spångberg, L. S., Acierno, T. G., Yongbum, Cha. B. 1989. Influence of entrapped air on the accuracy of leakage studies using dye penetration methods. J Endod 15(11): 548-51.
- Spradling, P. M., Senia, E. S. 1982. The relative sealing ability of paste-type filling materials. J Endod 8(12): 543-9.
- Stratton, R. K., Apicella, M. J., Mines, P. 2006. A fluid filtration comparison of gutta-percha versus Resilon, a new soft resin endodontic obturation system. J Endod 32(7): 642-5.
- Sundqvist, G., Figdor, D., Persson, S., Sjögren, U. 1998. Microbiologic analysis of teeth with failed endodontic treatment and the outcome of conservative re-treatment. Oral Surg Oral Med Oral Pathol Oral Radiol Endod 85(1): 86-93.
- Susini, G., About, I., Tran-Hung, L., Camps, J. 2006. Cytotoxicity of Epiphany and Resilon with a root model. Int Endod J 39(12): 940-4.

- Swanson, K., Madison, S. 1987. An evaluation of coronal microleakage in endodontically treated teeth. Part I. Time periods. J Endod 13(2): 56-9.
- Tagger, M., Tamse, A., Katz, A., Tagger, E. 1983. An improved method of three-dimensional study of apical leakage. Quintessence Int Dent Dig 14(10): 981-98.
- Tay, F. R., Hiraishi, N., Pashley, D. H. et al. 2006. Bondability of Resilon to a methacrylate-based root canal sealer. J Endod 32(2): 133-7.
- Tay, F. R., Loushine, R. J., Weller, R. N. et al. 2005a. Ultrastructural evaluation of the apical seal in roots filled with a polycaprolactone-based root canal filling material. J Endod 31(7): 514-9.
- Tay, F. R., Pashley, D. H., Williams, M. C. et al. 2005b. Susceptibility of a polycaprolactone-based root canal filling material to degradation. I. Alkaline hydrolysis. J Endod 31(8): 593-8.
- Tay, F. R., Pashley, D. H., Yiu, C. K. et al. 2005c. Susceptibility of a polycaprolactone-based root canal filling material to degradation. II. Gravimetric evaluation of enzymatic hydrolysis. J Endod 31(10): 737-41.
- Teixeira, C. S., Felipe, M. C., Felipe, W. T. 2005. The effect of application time of EDTA and NaOCl on intracanal smear layer removal: an SEM analysis. Int Endod J 38(5): 285-90.
- Teixeira, F. B., Teixeira, E. C., Thompson, J., Leinfelder, K. F., Trope, M. 2004a. Dentinal bonding reaches the root canal system. J Esthet Restor Dent 16(6): 348-54

- Teixeira, F. B., Teixeira, E. C., Thompson, J. Y., Trope, M. 2004b. Fracture resistance of roots endodontically treated with a new resin filling material. J Am Dent Assoc 135(5):646-52.
- Timpawat, S., Amornchat, C., Trisuwan, W. R. 2001. Bacterial coronal leakage after obturation with three root canal sealers. J Endod 27(1): 36-9.
- Torabinejad, M., Ung, B., Kettering, J. D. 1990. In vitro bacterial penetration of coronally unsealed endodontically treated teeth. J Endod 16(12): 566-9.
- Trope, M. 2006. Resilon will biodegrade from lipases released by bacteria or by bacterial or salivary enzymes. J Endod 32(2): 85; reply-6.
- Tunga, U., Bodrumlu, E. 2006. Assessment of the sealing ability of a new root canal obturation material. J Endod 32(9): 876-8.
- Ungor, M., Onay, E. O., Orucoglu, H. 2006. Push-out bond strengths: the Epiphany-Resilon endodontic obturation system compared with different pairings of Epiphany, Resilon, AH Plus and gutta-percha. Int Endod J 39(8): 643-7.
- Versiani, M. A., Carvalho-Junior, J. R., Padilha, M. I., Lacey, S., Pascon, E. A., Sousa-Neto, M. D. 2006. A comparative study of physicochemical properties of AH Plus and Epiphany root canal sealants. Int Endod J 39(6): 464-71.
- Vianna, M. E., Gomes, B. P., Berber, V. B., Zaia, A. A., Ferraz, C. C., de Souza-Filho, F. J. 2004. In vitro evaluation of the antimicrobial activity of chlorhexidine and sodium hypochlorite. Oral Surg Oral Med Oral Pathol Oral Radiol Endod 97(2): 79-84.

- Vivacqua-Gomes, N., Ferraz, C. C., Gomes, B. P., Zaia, A. A., Teixeira, F. B., Souza-Filho, F. J. 2002. Influence of irrigants on the coronal microleakage of laterally condensed gutta-percha root fillings. Int Endod J 35(9): 791-5.
- Walton, L., Torabinejad, M. 2002. clinical implication of the smear layer in endodontic. Oral Surg Oral Med Oral Pathol Oral Radiol Endod 94(4): 658-66.
- Wang, C. S., Debelian, G. J., Teixeira, F. B. 2006 Effect of intracanal medicament on the sealing ability of root canals filled with Resilon. J Endod 32(6):532-6.
- White, R. R., Goldman, M., Lin, P. S. 1984. The influence of the smeared layer upon dentinal tubule penetration by plastic filling materials. J Endod 10(12): 558-62.
- White, R. R., Goldman, M., Lin, P. S. 1987. The influence of the smeared layer upon dentinal tubule penetration by endodontic filling materials. Part II. J Endod 13(8): 369-74.
- Williams, C., Loushine, R. J., Weller, R. N., Pashley, D. H., Tay, F. R. 2006. A comparison of cohesive strength and stiffness of Resilon and gutta-percha. J Endod 32(6): 553-5.
- Williamson, A. E., Dawson, D. V., Drake, D. R., Walton, R. E., Rivera, E. M. 2005. Effect of root canal filling/sealer systems on apical endotoxin penetration: a coronal leakage evaluation. J Endod 31(8): 599-604.
- Wimonchit, S., Timpawat, S., Vongsavan, N. 2002. A comparison of techniques for assessment of coronal dye leakage. J Endod 28(1):1-4.

- Wu, M. K., De Gee, A. J., Wesselink, P. R. 1994. Fluid transport and dye penetration along root canal fillings. Int Endod J 27(5): 233-8.
- Wu, M. K., De Gee, A. J., Wesselink, P. R., Moorer, W. R. 1993a. Fluid transport and bacterial penetration along root canal fillings. Int Endod J 26(1): 203-8.
- Wu, M. K., Wesselink, P. R. 1993b. Endodontic leakage studies reconsidered. Part I. Methodology, application and relevance. Int Endod J 26(1): 37-43.
- Xu, Q., Fan, M. W., Fan, B., Cheung, G. S., Hu, H. L. 2005. A new quantitative method using glucose for analysis of endodontic leakage. Oral Surg Oral Med Oral Pathol Oral Radiol Endod 99(1): 107-11.
- Youngson, C. C., Jones, J. C., Fox, K., Smith, I. S., Wood, D. J., Gale, M. 1999. A fluid filtration and clearing technique to assess microleakage associated with three dentine bonding systems. J Dent 27(3): 223-33.
- Zehnder, M. 2006. Root canal irrigants. J Endod 32(5): 389-98.

APPENDICES

Concentrations of glucose were calculated by using standard curve between absorbance value and glucose concentration and presented in mmol L^{-1} at each time interval following root canal obturation.

$$Y = 0.054936 + 0.2424X \quad (R^2 = 0.9984)$$




Figure 20 Standard curves between glucose concentration (mM) and absorbance (500 nm)

Limitation

The lowest glucose level for which the current procedure is believed to be accurate is 0.04 mmol L^{-1} which derive from an absorbance value of 0.05. Therefore the absorbance value < 0.05 was calculated 0 mM glucose concentration.

Table 6 The leakage amount of glucose concentration in group 1.

Sample No (G1)	Day1		Day7		Week 1	Day14		Week 2	Day21		Week 3	Day28		Week 4
	OD	Glu.(mM)	OD	Glu.(mM)	Glu.(mM)	OD	Glu.(mM)	Glu.(mM)	OD	Glu.(mM)	Glu.(mM)	OD	Glu.(mM)	Glu.(mM)
1	0.032	0	2.225	8.95240924	8.952409	5.96	24.360825	15.40842	7	28.6512541	4.290429	8.36	34.261815	5.6105611
2	0.039	0	1.06	4.14630363	4.146304	2.74	11.076997	6.930693	4.28	17.430132	6.3531353	5.86	23.948284	6.5181518
3	0.001	0	0.072	0.07039604	0.070396	0.254	0.8212211	0.750825	0.537	1.98871287	1.1674917	1.045	4.0844224	2.0957096
4	0.126	0.2931683	0.231	0.72633663	0.433168	0.405	1.4441584	0.717822	0.592	2.21561056	0.7714521	0.863	3.3335974	1.1179868
5	0.153	0.4045545	2.325	9.3649505	8.960396	6.88	28.156205	18.79125	10.58	43.420231	15.264026	15.04	61.819571	18.39934
6	0	0	0.01	0	0	0.032	0	0	0.035	0	0	0.046	0	0
7	0.42	1.5060396	0.821	3.16033003	1.65429	0.968	3.7667657	0.606436	0.86	3.32122112	-0.445545	0.84	3.2387129	-0.082508
8	0.054	0	0.153	0.40455446	0.404554	0.209	0.6355776	0.231023	0.226	0.70570957	0.070132	0.25	0.8047195	0.0990099
9	0.003	0	0.004	0	0	0.028	0	0	0.082	0.11165017	0.1116502	0.162	0.4416832	0.330033
10	0.005	0	0.009	0	0	0.021	0	0	0.027	0	0	0.033	0	0
11	0.007	0	7.72	31.6215512	31.62155	5.46	22.298119	-9.323432	9.7	39.789868	17.491749	12.34	50.680957	10.891089
12	0.005	0	0.036	0	0	0.175	0.4953135	0.495314	0.404	1.440033	0.9447195	0.5	1.8360726	0.3960396
13	0.007	0	0	0	0	0.002	0	0	0.009	0	0	0.015	0	0
14	0.008	0	0	0	0	0.002	0	0	0.003	0	0	0.004	0	0
15	0.006	0	0	0	0	0.009	0	0	0.031	0	0	0.057	0.0085149	0.0085149
16	0.009	0	0	0	0	0.001	0	0	0.001	0	0	0.002	0	0
17	0.008	0	0	0	0	0.021	0	0	0.051	0	0	0.079	0.0992739	0.0992739
18	0.002	0	0.45	1.62980198	1.629802	1.24	4.8888779	3.259076	2.14	8.60174917	3.7128713	2.96	11.984587	3.3828383
19	0.009	0	0.078	0.09514851	0.095149	0.372	1.3080198	1.212871	1.989	7.97881188	6.6707921	4.48	18.255215	10.276403
20	0.007	0	0	0	0	0.002	0	0	0.008	0	0	0.008	0	0

Table 7 The leakage amount of glucose concentration in group 2.

Sample No (G2)	Day1		Day7		Week 1	Day14		Week 2	Day21		Week 3	Day28		Week 4
	OD	Glu.(mM)	OD	Glu.(mM)	Glu.(mM)	OD	Glu.(mM)	Glu.(mM)	OD	Glu.(mM)	Glu.(mM)	OD	Glu.(mM)	Glu.(mM)
1	0.917	3.556370	1.075	4.208185	0.651815	1.18	4.6413531	0.433168	1.12	4.3938284	-0.247525	1.04	4.06379538	-0.330033
2	0.02	0	0.082	0.111650	0.111650	0.242	0.7717162	0.660066	0.375	1.320396	0.5486799	0.573	2.13722772	0.816832
3	0.052	0	0.058	0.012640	0.012640	0.059	0.0167657	0.004125	0.058	0.0126403	-0.004125	0.066	0.04564356	0.033003
4	0	0	0.033	0	0	0.065	0.0415182	0.041518	0.092	0.1529043	0.1113861	0.123	0.28079208	0.127888
5	0.018	0	0.03	0	0	0.035	0	0	0.045	0	0	0.047	0	0
6	0.058	0.01264	0.153	0.404554	0.391914	0.384	1.3575248	0.952970	0.531	1.9639604	0.6064356	0.676	2.56214521	0.598185
7	0.014	0	0.054	0	0	0.138	0.3426733	0.342673	0.224	0.6974587	0.3547855	0.391	1.38640264	0.688944
8	0.007	0	0.061	0.025017	0.025017	0.261	0.850099	0.825083	0.473	1.7246865	0.8745875	0.743	2.83854785	1.113861
9	0.739	2.822046	0.88	3.403729	0.581683	1.1	4.3113201	0.907591	1.16	4.5588449	0.2475248	1.52	6.0439934	1.485149
10	0.004	0	0.004	0	0	0.008	0	0	0.008	0	0	0.008	0	0
11	0.097	0.173531	1.08	4.228812	4.055281	4.18	17.017591	12.788779	6.92	28.321221	11.30363	10	41.0274917	12.70627
12	0.006	0	0.04	0	0	0.085	0.1240264	0.124026	0.129	0.3055446	0.1815182	0.171	0.47881188	0.173267
13	0.009	0	0	0	0	0.004	0	0	0.004	0	0	0	0	0
14	0.007	0	0.01	0	0	0.041	0	0	0.065	0.0415182	0.0415182	0.086	0.12815182	0.086634
15	0.007	0	0.002	0	0	0.051	0	0	0.096	0.1694059	0.1694059	0.12	0.26841584	0.09901
16	0.008	0	0	0	0	0.003	0	0	0.003	0	0	0.001	0	0
17	0.007	0	0	0	0	0.004	0	0	0.001	0	0	0	0	0
18	0.007	0	0	0	0	0.003	0	0	0	0	0	0	0	0
19	0.007	0	0	0	0	0.001	0	0	0.002	0	0	0	0	0
20	0.009	0	0	0	0	0.021	0	0	0.048	0	0	0.078	0.09514851	0.095149

Table 8 The leakage amount of glucose concentration in group 3.

Sample No (G3)	Day1		Day7		Week 1	Day14		Week 2	Day21		Week 3	Day28		Week 4
	OD	Glu.(mM)	OD	Glu.(mM)	Glu.(mM)	OD	Glu.(mM)	Glu.(mM)	OD	Glu.(mM)	Glu.(mM)	OD	Glu.(mM)	Glu.(mM)
1	0.391	1.38640264	2.985	12.0877228	10.70132	9	36.9020792	24.81436	10.76	44.1628053	7.260726	13.3	54.6413531	10.47855
2	1.215	4.78574257	2.375	9.57122112	4.785479	2.94	11.9020792	2.330858	3.18	12.8921782	0.990099	3.62	14.7073597	1.815182
3	2.226	8.95653465	3.59	14.5835974	5.627063	7.08	28.9812871	14.39769	8.88	36.4070297	7.425743	10.3	42.2651155	5.858086
4	0.032	0	0.039	0	0	0.05	0	0	0.051	0	0	0.053	0	0
5	0.032	0	0.207	0.62732673	0.627327	3.12	12.6446535	12.01733	5.92	24.1958086	11.55116	9.3	38.139703	13.94389
6	0.025	0	0.162	0.44168317	0.441683	0.305	1.03161716	0.589934	0.396	1.4070297	0.375413	0.567	2.11247525	0.705446
7	0.013	0	0.217	0.66858086	0.668581	0.592	2.21561056	1.54703	0.887	3.43260726	1.216997	1.2	4.72386139	1.291254
8	0.021	0	0.602	2.25686469	2.256865	2.28	9.17930693	6.922442	3.74	15.2024092	6.023102	6.02	24.6083498	9.405941
9	0.001	0	0.001	0	0	0.002	0	0	0.009	0	0	0.011	0	0
10	0.001	0	0.138	0.34267327	0.342673	0.293	0.98211221	0.639439	0.501	1.84019802	0.858086	0.808	3.10669967	1.266502
11	0.007	0	0.044	0	0	0.622	2.33937294	2.339373	1.28	5.05389439	2.714521	1.26	4.97138614	-0.08251
12	0.006	0	0.043	0	0	0.294	0.98623762	0.986238	0.433	1.55966997	0.573432	0.534	1.97633663	0.416667
13	0.007	0	0.021	0	0	0.1	0.18590759	0.185908	0.232	0.73046205	0.544554	0.421	1.51016502	0.779703
14	0.003	0	0	0	0	0.001	0	0	0.002	0	0	0.002	0	0
15	0.009	0	0	0	0	0.003	0	0	0.005	0	0	0.005	0	0
16	0.009	0	0.001	0	0	0.152	0.40042904	0.400429	0.68	2.57864686	2.178218	1.28	5.05389439	2.475248
17	0.008	0	0	0	0	0.006	0	0	0.01	0	0	0.008	0	0
18	0.006	0	0	0	0	0.002	0	0	0	0	0	0	0	0
19	0.009	0	0	0	0	0.002	0	0	0	0	0	0	0	0
20	0.001	0	0	0	0	0.026	0	0	0.057	0.00851485	0.008515	0.094	0.16115512	0.15264

Table 9 The leakage amount of glucose concentration in Negative control group.

Sample No (G-neg.)	Day1		Day7		Day14		Day21		Day28	
	OD	Glu.(mM)	OD	Glu.(mM)	OD	Glu.(mM)	OD	Glu.(mM)	OD	Glu.(mM)
1	0.001	0	0	0	0.003	0	0	0	0	0
2	0.002	0	0	0	0.003	0	0	0	0	0
3	0.003	0	0	0	0.003	0	0	0	0	0
4	0.004	0	0	0	0.004	0	0	0	0	0
5	0.002	0	0	0	0.004	0	0	0	0	0

Table 10 The leakage amount of glucose concentration in Positive control group.

Sample No (G-positive)	Day1		Day7		Day14		Day21		Day28	
	OD	Glu.(mM)	OD	Glu.(mM)	OD	Glu.(mM)	OD	Glu.(mM)	OD	Glu.(mM)
1	0.147	0.379802	12.78	52.49614	90.4	372.71066	93.2	384.2618	96	395.813
2	0.108	0.218911	11.04	45.31792	50.6	208.51924	52.4	215.945	53.8	221.7206
3	15.34	63.05719	13.68	56.20901	108.2	446.143	114	470.0704	119.8	493.9978
4	3.48	14.1298	10.62	43.58525	24	98.783267	27.4	112.8097	29.8	122.7107
5	0.033	-0.0905	10.98	45.0704	36.5	150.35092	39.8	163.9648	39.8	163.9648

STATISTICS ANALYSIS

Table 11 Statistical analysis using SPSS of glucose leakage concentration

			Statistics					
Group			D1	D7	D14	D21	D28	
Positive control	N	Valid	5	5	5	5	5	
		Missing	0	0	0	0	0	
	Mean		15.557142	48.535743	255.30142	269.41033	279.64135	
	Median		.37980198	45.317921	208.51924	215.94498	221.72056	
	Std. Deviation		27.230176	5.5098587	148.24519	151.62157	158.75111	
	Range		63.057195	12.623762	347.35974	357.26073	371.28713	
	Minimum		.000000	43.585248	98.783267	112.80967	122.71066	
	Maximum		63.057195	56.209010	446.14300	470.07040	493.99779	
	Percentiles	25		.10945545	44.327822	124.56710	138.38723	143.33772
		50		.37980198	45.317921	208.51924	215.94498	221.72056
		75		38.593498	54.352574	409.42683	427.16611	444.90538
Negative control	N	Valid	5	5	5	5	5	
		Missing	0	0	0	0	0	
	Mean		.00000000	.00000000	.00000000	.00000000	.00000000	
	Median		.00000000	.00000000	.00000000	.00000000	.00000000	
	Std. Deviation		.00000000	.00000000	.00000000	.00000000	.00000000	
	Range		.000000	.000000	.000000	.000000	.000000	
	Minimum		.000000	.000000	.000000	.000000	.000000	
	Maximum		.000000	.000000	.000000	.000000	.000000	
	Percentiles	25		.00000000	.00000000	.00000000	.00000000	.00000000
		50		.00000000	.00000000	.00000000	.00000000	.00000000
		75		.00000000	.00000000	.00000000	.00000000	.00000000

Table 12 Statistical analysis using SPSS of glucose leakage concentration
(Test distribution of data)

One-Sample Kolmogorov-Smirnov Test			D1	D7	D14	D21	D28
Group1	N		20	20	20	20	20
	Normal Parameter ^{a,b}	Mean	.11018812	3.0085891	4.9626040	7.7827492	10.739871
		Std. Deviation	.34602547	7.3171726	9.0518643	13.653533	18.281578
	Most Extreme Differences	Absolute	.475	.340	.351	.328	.342
		Positive	.475	.325	.351	.328	.342
		Negative	-.375	-.340	-.292	-.284	-.278
	Kolmogorov-Smirnov Z		2.124	1.523	1.571	1.467	1.530
Asymp. Sig. (2-tailed)		.000	.019	.014	.027	.019	
Group2	N		20	20	20	20	20
	Normal Parameter ^{a,b}	Mean	.32822935	.61972935	1.4737294	2.1831205	3.0678284
		Std. Deviation	.98641546	1.4450035	3.9040220	6.3081775	9.0889970
	Most Extreme Differences	Absolute	.475	.437	.363	.365	.368
		Positive	.475	.437	.363	.364	.360
		Negative	-.370	-.334	-.353	-.365	-.368
	Kolmogorov-Smirnov Z		2.126	1.956	1.625	1.631	1.645
Asymp. Sig. (2-tailed)		.000	.001	.010	.010	.009	
Group3	N		20	20	20	20	20
	Normal Parameter ^{a,b}	Mean	.75643399	2.0289835	5.3875347	7.4735627	9.8988927
		Std. Deviation	2.2195437	4.4385490	10.312364	12.965150	16.514217
	Most Extreme Differences	Absolute	.483	.420	.366	.324	.365
		Positive	.483	.420	.366	.324	.365
		Negative	-.367	-.324	-.301	-.282	-.274
	Kolmogorov-Smirnov Z		2.162	1.880	1.638	1.449	1.634
Asymp. Sig. (2-tailed)		.000	.002	.009	.030	.010	

a. Test distribution is Normal.

b. Calculated from data.

Group 1 = final flushed with sterile water

Group 2 = final flushed with 2% CHX

Group 3 = final flushed with 2.5% NaOCl followed by 2% CHX

D1 = Day 1

D7 = Day 7

D14 = Day 14

D21 = Day 21

D28 = Day 28

Table 13 Statistical analysis using SPSS of glucose leakage concentration
(NPar Tests; Kruskal-Wallis Test)

Descriptives

Statistics

Group			D1	D7	D14	D21	D28	
Group1	N	Valid	20	20	20	20	20	
		Missing	0	0	0	0	0	
	Mean		.11018812	3.0085891	4.9626040	7.7827492	10.739871	
	Median		.00000000	.03519802	.56544554	1.0728713	1.3203960	
	Std. Deviation		.34602547	7.3171726	9.0518643	13.653533	18.281578	
	Range		1.506040	31.621551	28.156205	43.420231	61.819571	
	Minimum		.000000	.000000	.000000	.000000	.000000	
	Maximum		1.506040	31.621551	28.156205	43.420231	61.819571	
	Percentiles	25		.00000000	.00000000	.00000000	.00000000	.00000000
		50		.00000000	.03519802	.56544554	1.0728713	1.3203960
75			.00000000	2.7776980	4.6083498	8.4460149	16.687558	
Group2	N	Valid	20	20	20	20	20	
		Missing	0	0	0	0	0	
	Mean		.32822935	.61972935	1.4737294	2.1831205	3.0678284	
	Median		.00000000	.00000000	.00838284	.09721122	.19828383	
	Std. Deviation		.98641546	1.4450035	3.9040220	6.3081775	9.0889970	
	Range		3.556370	4.228812	17.017591	28.321221	41.027492	
	Minimum		.000000	.000000	.000000	.000000	.000000	
	Maximum		3.556370	4.228812	17.017591	28.321221	41.027492	
	Percentiles	25		.00000000	.00000000	.00000000	.00000000	.00000000
		50		.00000000	.00000000	.00838284	.09721122	.19828383
75			.00000000	.08999175	.83050330	1.6236139	2.4559158	
Group3	N	Valid	20	20	20	20	20	
		Missing	0	0	0	0	0	
	Mean		.75643399	2.0289835	5.3875347	7.4735627	9.8988927	
	Median		.00000000	.00000000	.69127063	1.4833498	2.0444059	
	Std. Deviation		2.2195437	4.4385490	10.312364	12.965150	16.514217	
	Range		8.956535	14.583597	36.902079	44.162805	54.641353	
	Minimum		.000000	.000000	.000000	.000000	.000000	
	Maximum		8.956535	14.583597	36.902079	44.162805	54.641353	
	Percentiles	25		.00000000	.00000000	.00000000	.00000000	.00000000
		50		.00000000	.00000000	.69127063	1.4833498	2.0444059
75			.00000000	.65826733	7.4693234	10.932607	12.293993	

The glucose leakage concentration obtained at each of the time intervals were compared between groups using the Kruskal-Wallis test.

NPar Tests
Kruskal-Wallis Test

Ranks

	Group	N	Mean Rank
D1	Group1	20	29.83
	Group2	20	31.30
	Group3	20	30.38
	Total	60	
D7	Group1	20	33.40
	Group2	20	27.35
	Group3	20	30.75
	Total	60	
D14	Group1	20	31.90
	Group2	20	26.40
	Group3	20	33.20
	Total	60	
D21	Group1	20	32.15
	Group2	20	26.25
	Group3	20	33.10
	Total	60	
D28	Group1	20	32.65
	Group2	20	26.08
	Group3	20	32.78
	Total	60	

Test Statistics^{a,b}

	D1	D7	D14	D21	D28
Chi-Square	.173	1.505	1.880	1.914	2.000
df	2	2	2	2	2
Asymp. Sig.	.917	.471	.391	.384	.368

a. Kruskal Wallis Test

b. Grouping Variable: Group

Table 14 Statistical analysis using SPSS of glucose leakage concentration
(NPar Tests; Friedman Test)

Comparison within the same specimen at each of time intervals was using Friedman test.

Group 1

Descriptive Statistics

	N	Mean	Std. Deviation	Minimum	Maximum	Percentiles		
						25th	50th (Median)	75th
G1-D1	20	.1101881	.346025465	.000000	1.506040	.0000000	.00000000	.0000000
G1-D7	20	3.008589	7.317172557	.000000	31.62155	.0000000	.03519802	2.777698
G1-D14	20	4.962604	9.051864340	.000000	28.15620	.0000000	.56544554	4.608350
G1-D21	20	7.782749	13.653533109	.000000	43.42023	.0000000	1.07287129	8.446015
G1-D28	20	10.73987	18.281578187	.000000	61.81957	.0000000	1.32039604	16.68756

Friedman Test

Ranks

	Mean Rank
G1-D1	1.83
G1-D7	2.38
G1-D14	2.95
G1-D21	3.55
G1-D28	4.30

Test Statistics^a

N	20
Chi-Square	47.263
df	4
Asymp. Sig.	.000

a. Friedman Test

Group 2

Descriptive Statistics

	N	Mean	Std. Deviation	Minimum	Maximum	Percentiles		
						25th	50th (Median)	75th
G2-D1	20	.3282293	.986415463	.000000	3.556370	.0000000	.00000000	.0000000
G2-D7	20	.6197294	1.445003532	.000000	4.228812	.0000000	.00000000	.0899918
G2-D14	20	1.473729	3.904022016	.000000	17.01759	.0000000	.00838284	.8305033
G2-D21	20	2.183120	6.308177477	.000000	28.32122	.0000000	.09721122	1.623614
G2-D28	20	3.067828	9.088996983	.000000	41.02749	.0000000	.19828383	2.455916

Friedman Test

Ranks

	Mean Rank
G2-D1	1.95
G2-D7	2.35
G2-D14	3.03
G2-D21	3.53
G2-D28	4.15

Test Statistics^a

N	20
Chi-Square	41.824
df	4
Asymp. Sig.	.000

a. Friedman Test

Group 3

Descriptive Statistics

	N	Mean	Std. Deviation	Minimum	Maximum	Percentiles		
						25th	50th (Median)	75th
G3-D1	20	.7564340	2.219543689	.000000	8.956535	.0000000	.00000000	.0000000
G3-D7	20	2.028983	4.438549035	.000000	14.58360	.0000000	.00000000	.6582673
G3-D14	20	5.387535	10.312364146	.000000	36.90208	.0000000	.69127063	7.469323
G3-D21	20	7.473563	12.965150434	.000000	44.16281	.0000000	1.48334984	10.93261
G3-D28	20	9.898893	16.514217435	.000000	54.64135	.0000000	2.04440594	12.29399

Friedman Test

Ranks

	Mean Rank
G3-D1	1.85
G3-D7	2.25
G3-D14	2.95
G3-D21	3.70
G3-D28	4.25

Test Statistics^a

N	20
Chi-Square	50.032
df	4
Asymp. Sig.	.000

a. Friedman Test

Table 15 Statistical analysis using SPSS of the rate of glucose leakage concentration
(Test distribution of data)

One-Sample Kolmogorov-Smirnov Test

group	TIME		glucose(mM)	
group1	D1-D7	N	20	
		Normal	Mean	2.89840099
		Parameters(a,b)	Std. Deviation	7.310023159
		Most Extreme	Absolute	.368
		Differences	Positive	.368
			Negative	-.346
		Kolmogorov-Smirnov Z		1.644
		Asymp. Sig. (2-tailed)		.009
		D7-D14	N	20
			Normal	Mean
	Parameters(a,b)		Std. Deviation	5.907025420
	Most Extreme		Absolute	.350
	Differences		Positive	.350
		Negative	-.320	
	Kolmogorov-Smirnov Z		1.565	
Asymp. Sig. (2-tailed)		.015		
D14-D21	D14-D21	N	20	
		Normal	Mean	2.82014521
		Parameters(a,b)	Std. Deviation	5.129937748
		Most Extreme	Absolute	.326
		Differences	Positive	.326
			Negative	-.262
		Kolmogorov-Smirnov Z		1.459
		Asymp. Sig. (2-tailed)		.028
D21-D28	D21-D28	N	20	
		Normal	Mean	2.95712211
		Parameters(a,b)	Std. Deviation	5.022093573
		Most Extreme	Absolute	.295
		Differences	Positive	.295
			Negative	-.273
		Kolmogorov-Smirnov Z		1.319
		Asymp. Sig. (2-tailed)		.062
group2	D1-D7	N	20	

		Normal	Mean	.29150000
		Parameters(a,b)	Std. Deviation	.908321900
		Most Extreme	Absolute	.378
		Differences	Positive	.378
			Negative	-.374
		Kolmogorov-Smirnov Z		1.693
		Asymp. Sig. (2-tailed)		.006
	D7-D14	N		20
		Normal	Mean	.85399995
		Parameters(a,b)	Std. Deviation	2.829702001
		Most Extreme	Absolute	.436
		Differences	Positive	.436
			Negative	-.381
		Kolmogorov-Smirnov Z		1.950
		Asymp. Sig. (2-tailed)		.001
	D14-D21	N		20
		Normal	Mean	.70939109
		Parameters(a,b)	Std. Deviation	2.507517818
		Most Extreme	Absolute	.424
		Differences	Positive	.424
			Negative	-.351
		Kolmogorov-Smirnov Z		1.895
		Asymp. Sig. (2-tailed)		.002
	D21-D28	N		20
		Normal	Mean	.88470792
		Parameters(a,b)	Std. Deviation	2.818397610
		Most Extreme	Absolute	.368
		Differences	Positive	.368
			Negative	-.333
		Kolmogorov-Smirnov Z		1.644
		Asymp. Sig. (2-tailed)		.009
group3	D1-D7	N		20
		Normal	Mean	1.27254950
		Parameters(a,b)	Std. Deviation	2.742854196
		Most Extreme	Absolute	.387
		Differences	Positive	.387
			Negative	-.321
		Kolmogorov-Smirnov Z		1.731
		Asymp. Sig. (2-tailed)		.005
	D7-D14	N		20
		Normal	Mean	3.35855116

	Parameters(a,b)	Std. Deviation	6.509135796
	Most Extreme	Absolute	.362
	Differences	Positive	.362
		Negative	-.303
	Kolmogorov-Smirnov Z		1.620
	Asymp. Sig. (2-tailed)		.011
D14-D21	N		20
	Normal	Mean	2.08602805
	Parameters(a,b)	Std. Deviation	3.297637115
	Most Extreme	Absolute	.304
	Differences	Positive	.304
		Negative	-.264
	Kolmogorov-Smirnov Z		1.359
	Asymp. Sig. (2-tailed)		.050
D21-D28	N		20
	Normal	Mean	2.42533003
	Parameters(a,b)	Std. Deviation	4.125523470
	Most Extreme	Absolute	.309
	Differences	Positive	.309
		Negative	-.272
	Kolmogorov-Smirnov Z		1.381
	Asymp. Sig. (2-tailed)		.044

Table 16 Statistical analysis using SPSS of the rate of glucose leakage concentration (NPar Tests; Kruskal-Wallis Test)

Descriptives

Statistics

		glucose(mM)		
group1	D1-D7	N	Valid	20
			Missing	0
		Mean	2.89840099	
		Median	.03519802	
		Std. Deviation	7.310023159	
		Range	31.621551	
		Minimum	.000000	
		Maximum	31.621551	
	D7-D14	N	Valid	20

			Missing	0
		Mean		1.95401485
		Median		.11551155
		Std. Deviation		5.907025420
		Range		28.114686
		Minimum		-9.323432
		Maximum		18.791254
	D14-D21	N	Valid	20
			Missing	0
		Mean		2.82014521
		Median		.09089109
		Std. Deviation		5.129937748
		Range		17.937294
		Minimum		-.445545
		Maximum		17.491749
		D21-D28	N	Valid
	Missing			0
	Mean		2.95712211	
	Median		.21465347	
	Std. Deviation		5.022093573	
	Range		18.481848	
	Minimum		-.082508	
	Maximum		18.399340	
group2	D1-D7		N	Valid
		Missing		0
		Mean		.29150000
		Median		.00000000
		Std. Deviation		.908321900
		Range		4.055281
		Minimum		.000000
		Maximum		4.055281
		D7-D14	N	Valid
	Missing			0
	Mean		.85399995	
	Median		.00206250	
	Std. Deviation		2.829702001	
	Range		12.788779	
	Minimum		.000000	
	Maximum		12.788779	
	D14-D21		N	Valid

			Missing	0
		Mean		.70939109
		Median		.02075908
		Std. Deviation		2.507517818
		Range		11.551155
		Minimum		-.247525
		Maximum		11.303630
	D21-D28	N	Valid	20
			Missing	0
		Mean		.88470792
		Median		.09089109
		Std. Deviation		2.818397610
		Range		13.036304
		Minimum		-.330033
		Maximum		12.706271
group3	D1-D7	N	Valid	20
			Missing	0
		Mean		1.27254950
		Median		.00000000
		Std. Deviation		2.742854196
		Range		10.701320
		Minimum		.000000
		Maximum		10.701320
	D7-D14	N	Valid	20
			Missing	0
		Mean		3.35855116
		Median		.49518152
		Std. Deviation		6.509135796
		Range		24.814356
		Minimum		.000000
		Maximum		24.814356
	D14-D21	N	Valid	20
			Missing	0
		Mean		2.08602805
		Median		.55899340
		Std. Deviation		3.297637115
		Range		11.551155
		Minimum		.000000
		Maximum		11.551155
D21-D28	N	Valid	20	

		Missing	0
		Mean	2.42533003
		Median	.56105611
		Std. Deviation	4.125523470
		Range	14.026403
		Minimum	-.082508
		Maximum	13.943894

NPar Tests

Kruskal-Wallis Test

Ranks

group	TIME	N	Mean Rank
group1	glucose(mM) D1-D7	20	38.90
	D7-D14	20	38.50
	D14-D21	20	41.10
	D21-D28	20	43.50
	Total	80	
group2	glucose(mM) D1-D7	20	35.03
	D7-D14	20	42.65
	D14-D21	20	39.60
	D21-D28	20	44.73
	Total	80	
group3	glucose(mM) D1-D7	20	33.45
	D7-D14	20	43.15
	D14-D21	20	43.43
	D21-D28	20	41.98
	Total	80	

Test Statistics^{a,b}

group	glucose(mM)	
group1	Chi-Square	.634
	df	3
	Asymp. Sig.	.889
group2	Chi-Square	2.209
	df	3
	Asymp. Sig.	.530
group3	Chi-Square	2.706
	df	3
	Asymp. Sig.	.439

a. Kruskal Wallis Test

b. Grouping Variable: TIME

NPar Tests

Kruskal-Wallis Test

Ranks

TIME	group	N	Mean Rank
D1-D7	glucose(mM) group1	20	33.70
	group2	20	26.80
	group3	20	31.00
	Total	60	
D7-D14	glucose(mM) group1	20	30.05
	group2	20	27.10
	group3	20	34.35
	Total	60	
D14-D21	glucose(mM) group1	20	31.95
	group2	20	24.75
	group3	20	34.80
	Total	60	
D21-D28	glucose(mM) group1	20	32.60
	group2	20	26.40
	group3	20	32.50
	Total	60	

Test Statistics^{a,b}

TIME	glucose(mM)	
D1-D7	Chi-Square	1.978
	df	2
	Asymp. Sig.	.372
D7-D14	Chi-Square	1.918
	df	2
	Asymp. Sig.	.383
D14-D21	Chi-Square	3.728
	df	2
	Asymp. Sig.	.155
D21-D28	Chi-Square	1.717
	df	2
	Asymp. Sig.	.424

a. Kruskal Wallis Test

b. Grouping Variable: group

BIOGRAPHY

Miss Chureerat Kanchanakaew was born on 5th of April 1977 in Songkhla. She graduated with D.D.S. (Doctor of Dental Surgery) from the Faculty of Dentistry, Prince of Songkla University in 2001, and became a dentist in Sawi Hospital, Chumporn, in 2001-2003, then working in Hadyai Hospital, Songkla, in 2004. She studied in a Master degree program in Endodontology at Graduate School, Chulalongkorn University in 2006.