

**NO_x REMOVAL BY SELECTIVE - REDUCTION
WITH PROPENE**



Ms. Rattida Sujintamane

A Thesis Submitted in Partial Fulfilment of the Requirements
for the Degree of Master of Science
The Petroleum and Petrochemical College, Chulalongkorn University
in Academic Partnership with
The University of Michigan, The University of Oklahoma,
and Case Western Reserve University

2002

ISBN 974-03-1561-5

Thesis Title : NO_x Removal by Storage - Reduction with Propene
By : Ms. Rattida Sujintamanee
Program : Petrochemical Technology
Thesis Advisors : Prof. Somchai Osuwan
Prof. Erdogan Gulari

Accepted by the Petroleum and Petrochemical College, Chulalongkorn University, in partial fulfilment of the requirements for the Degree of Master of Science.

K. Bunyakiat

..... College Director
(Assoc. Prof. Kunchana Bunyakiat)

Thesis Committee:

A. Osuwan

.....
(Prof. Somchai Osuwan)

Erdogan Gulari

.....
(Prof. Erdogan Gulari)

Thirasak Rirksomboon

.....
(Asst. Prof. Thirasak Rirksomboon)

Sirirat Jitkarnka

.....
(Dr. Sirirat Jitkarnka)

ABSTRACT

4371019063 : PETROCHEMICAL TECHNOLOGY PROGRAM

Rattida Sujintamane: NO_x Removal by Storage-Reduction with Propene. Thesis Advisors: Prof. Erdogan Gulari and Prof. Somchai Osuwan, 36 pp. ISBN 974-03-1561-5

Keywords : NO_x storage-reduction/ Gold catalyst/ Gold/ Barium catalyst/ Impregnation/ Sol-gel

NO_x, which consist of NO and NO₂, are air pollutants. They affect the environment and human health. The major source of NO_x is fossil fuel combustion in power plants and engines. In this work, the catalytic reduction of NO_x with propene in the presence of oxygen was carried out over Au/Al₂O₃ and Au/Ba/Al₂O₃ catalysts prepared by impregnation and sol-gel methods. Au and Ba loadings were varied in the range 0.5-1% and 5-15%, respectively. The catalysts were characterized by BET, XRD, and AAS. It was found that 0.7% Au impregnated on an Al₂O₃ sol-gel support and 0.7% Au impregnated on a 5% Ba/Al₂O₃ sol-gel support showed the best activity at 475 and 500 °C, respectively. The percentage of Au loading had no significant effect on catalytic activity while the percentage of Ba loading showed a significant effect. The catalytic activity decreased with increasing percentage of Ba loading. The sequence of Au and Ba impregnation was also investigated. The results showed that it had only a slight effect on catalytic activity. The presence of water vapor had no effect on the activity of both Au/Al₂O₃ and Au/Ba/Al₂O₃ catalysts.

บทคัดย่อ

รัศมิดา สุจินตะมณี : การกำจัดก๊าซไนโตรเจนออกไซด์โดยวิธีสโตเรจ-รีดักชันด้วยก๊าซโพรพีน (NO_x Removal by Storage-Reduction with propene) อ. ที่ปรึกษา : ศ.ดร. เอโดแกน กุลารี่ และ ศ.ดร. สมชาย โอสุวรรณ 36 หน้า ISBN 974-03-1561-5

ก๊าซไนโตรเจนออกไซด์ซึ่งประกอบด้วย ก๊าซไนตริกออกไซด์ และก๊าซไนโตรเจนไดออกไซด์เป็นก๊าซมลพิษที่ส่งผลกระทบต่อสิ่งแวดล้อมและมนุษย์ แหล่งกำเนิดหลักของก๊าซไนโตรเจนออกไซด์ คือ การเผาไหม้เชื้อเพลิงในโรงไฟฟ้าและในเครื่องยนต์ งานวิจัยนี้ได้ศึกษาปฏิกิริยารีดักชันของก๊าซไนโตรเจนออกไซด์ด้วยก๊าซโพรพีนในบรรยากาศของออกซิเจนโดยอาศัยตัวเร่งปฏิกิริยาทองและแบเรียมบนตัวรองรับอลูมินาที่เตรียมโดยวิธีอิมเพกเนชัน และ โซลเจล โลหะทองและแบเรียมได้ถูกศึกษาในช่วงค่าหน้าพื้นที่ร้อยละ 0.5-1 และ 5-15 ตามลำดับ คุณสมบัติของตัวเร่งปฏิกิริยาที่เตรียมได้นั้น ถูกวิเคราะห์โดยวิธี บรูเนอร์-เอมเมต-เทลเลอร์ (BET) , เอกซ์เรย์ ดิฟแฟรกชัน (XRD) และ อะตอมมิก แอบซอร์พชัน สเปกโตรสโคปี (AAS) จากการศึกษพบว่าตัวเร่งปฏิกิริยาทอง ร้อยละ 0.7 ที่ถูกอิมเพกเนตบนตัวรองรับโซลเจลอลูมินา และ ตัวเร่งปฏิกิริยาทอง ร้อยละ 0.7 ที่ถูกอิมเพกเนตบนตัวรองรับโซลเจลแบเรียมอลูมินาซึ่งมีแบเรียมร้อยละ 5 บรรจุอยู่ มีความว่องไวดีที่สุดในอุณหภูมิ 475 และ 500 องศาเซลเซียส ตามลำดับ น้ำหนักร้อยละต่างๆของทองไม่มีผลกระทบต่อเด่นชัดนักต่อความว่องไวของตัวเร่งปฏิกิริยา ในขณะที่น้ำหนักร้อยละต่างๆ ของแบเรียมมีผลกระทบอย่างเด่นชัด กล่าวคือ ความว่องไวของตัวเร่งปฏิกิริยาจะลดลงเมื่อน้ำหนักร้อยละของแบเรียมเพิ่มขึ้น นอกจากนี้ยังพบว่าลำดับของการอิมเพกเนชันของโลหะทองและแบเรียมมีผลกระทบเล็กน้อยต่อความว่องไวของตัวเร่งปฏิกิริยา และยังพบอีกว่า ในบรรยากาศที่มีไอน้ำปนอยู่นั้น ไม่ส่งผลกระทบต่อความว่องไวของตัวเร่งปฏิกิริยาทองบนตัวรองรับอลูมินา และทองบนตัวรองรับแบเรียมอลูมินา

ACKNOWLEDGEMENTS

I would like to express my deepest sincere gratitude to these individuals who are always my inspiration to complete this work.

To my advisors, Prof. Somchai Osuwan and Prof. Erdogan Gulari for their helpful advises, supports and kindness.

To Ms. Jiraporn Leerat, Ms. Apanee Luengnarruemitchai, Ms. Siriporn Jongpatiwut, Mr. Siriphong Roatluechai and all of Ph.D. students at The Petroleum and Petrochemical College for the valuable suggestion and guidance.

To Asst. Prof. Thirasak Risksomboon and Dr. Sirirat Jitkarnka for serving as my committee.

To The Petroleum and Petrochemical College faculty and staffs for their valuable help.

Finally my deepest thanks to my family and my friends for their love, encouragement, and for being a constant source of inspiration.

TABLE OF CONTENTS

	PAGE
Title Page	i
Abstract (in English)	iii
Abstract (in Thai)	iv
Acknowledgements	v
Table of Contents	vi
List of Tables	ix
List of Figures	x
CHAPTER	
I INTRODUCTION	1
1.1 Introduction	1
1.2 Research Objectives	3
II LITERATURE SURVEY	4
2.1 NO _x Storage and Reduction (NSR)	4
2.2 Properties of Gold	7
2.3 Heterogeneous Catalysis of Gold	7
2.4 Nitric Oxide Reduction (Selective Catalytic Reduction, SCR) with Hydrocarbons over Gold Catalysts	9
2.5 Catalyst Preparation	9
2.5.1 Sol-Gel Method	9
2.5.2 Incipient Wetness Impregnation Method	11
III EXPERIMENTAL	12
3.1 Materials	12
3.1.1 Catalyst Preparation Materials	12
3.1.2 Reactant Gases	12

3.2	Catalyst Preparation	13
3.2.1	Sol-Gel Method	13
3.2.1.1	Barium Supported on Alumina	13
3.2.1.2	Gold supported on Alumina	13
3.2.2	Impregnation	13
3.2.2.1	Gold Impregnated on Alumina and Barium/Alumina Sol-Gel Support	13
3.2.2.2	Barium Impregnated on Gold/Alumina Sol-Gel Support	14
3.3	Catalyst Characterization	14
3.3.1	Surface Area Measurement	14
3.3.2	X-Ray Diffraction (XRD)	14
3.3.3	Atomic Absorption Spectroscopy (AAS)	15
3.4	Apparatus	16
3.4.1	Gas Blending System	16
3.4.2	Catalytic Reactor	16
3.4.3	Analytical Instruments	16
3.5	Catalytic Activity Measurements	18
3.5.1	NO _x Storage-Reduction (NSR)	18
3.5.2	Selective Catalytic Reduction (SCR)	18
3.5.3	Study Effect of Pretreatment Gas	19
IV	RESULTS AND DISCUSSION	20
4.1	Catalyst Characterization	20
4.2	Catalytic Activity Testing	26
4.2.1	NO _x Storage-Reduction	26
4.2.2	Selective Catalytic Reduction	26
4.2.2.1	Effect of Preparation Method	26
4.2.2.1	Effect of % Metal Loading	27
4.2.2.3	Effect of Impregnation Sequence	30
4.2.2.4	Effect of Water Vapor	30

CHAPTER		PAGE
	4.2.2.5 Effect of Pretreatment Gas	32
V	CONCLUSIONS AND RECOMMENDATIONS	33
	REFERENCES	34
	CIRRICULUM VITAE	36

LIST OF TABLES

TABLE	PAGE
4.1 BET surface area results	21
4.2 % Gold loading from AAS	22

LIST OF FIGURES

FIGURE	PAGE
2.1 NO _x storage period of NSR catalyst	5
2.2 NO _x reduction period of NSR catalyst	5
3.1 Schematic flow diagram of experimental equipment	17
4.1 XRD pattern for 0.7%Au/Al ₂ O ₃ catalysts with different preparation methods	23
4.2 XRD pattern for Al ₂ O ₃ (sol-gel) and 0.5-1.0%Au (imp) on Al ₂ O ₃ (sol-gel) catalysts	24
4.3 XRD pattern for 0.7%Au (imp) on 5-15%Ba/Al ₂ O ₃ (sol-gel) catalysts	24
4.4 XRD pattern for 10%Ba/Al ₂ O ₃ (sol-gel) and 0.5-1.0%Au (imp) on 10%Ba/Al ₂ O ₃ catalysts	25
4.5 XRD pattern for 0.7%Au/10%Ba/Al ₂ O ₃ catalysts with different impregnation sequences	25
4.6 NO _x conversion over Au/Al ₂ O ₃ catalysts with different preparation methods	27
4.7 NO _x conversion over Au/Al ₂ O ₃ catalysts with different percentage of gold loadings	28
4.8 NO _x conversion over Au/Ba/Al ₂ O ₃ catalysts with different percentage of barium loadings	28
4.9 NO _x conversion over Au/Ba/Al ₂ O ₃ catalysts with different percentage of gold loadings	29
4.10 NO _x conversion over Au/Ba/Al ₂ O ₃ catalysts with different impregnation sequences	30
4.11 Effect of water vapor on the activity of 0.7%Au (imp) on Al ₂ O ₃ (sol-gel) catalyst	31
4.12 Effect of water vapor on the activity of 0.7%Au (imp) on 10%Ba/Al ₂ O ₃ (sol-gel) catalyst	31

FIGURE	PAGE
4.13 Effect of pretreatment gas on the activity of 0.7%Au (imp) on Al ₂ O ₃ (sol-gel) catalyst in the presence of water	32