

รายการอ้างอิง

ภาษาไทย

ชนัญ พลประไพพ. สภาวะที่เหมาะสมในการเลี้ยงเชื้อเพื่อผลิตโพลี-เบต้า-ไฮดรอกซีบิวทิเรกจาก *Alcaligenes sp.* สายพันธุ์ A-04 ในระดับถังหมัก. วิทยานิพนธ์ปริญญามหาบัณฑิต จุฬาลงกรณ์มหาวิทยาลัย, 2537.

อรุณ ชาญชัยเชาว์วิวัฒน์. ลักษณะและการสร้าง โพลี-เบต้า-ไฮดรอกซีบิวทิเรก โดย *Alcaligenes sp.* A-04. วิทยานิพนธ์ปริญญามหาบัณฑิต จุฬาลงกรณ์มหาวิทยาลัย, 2536.

อรุษา สรราเรี. ปฏิบัติการโพลีเมอร์ ภาควิชาวัสดุศาสตร์ คณะวิทยาศาสตร์ จุฬาลงกรณ์มหาวิทยาลัย, 2530.

ภาษาอังกฤษ

Akiyama, M., Taima, Y., and Doi, Y. Production of poly-(3-hydroxyalkanoates) by a bacterium of the genus *Alcaligenes* utilizing long chain fatty acids. Appl.Microbiol.Biotechnol. 37(1992):698-701

Ballard, D.G.H., Holmes, P.A., and Senior, P.J. Formation of polymers of β -hydroxybutyric acid in bacterial cell and a comparison of the morphology of growth with the formation of polyethylene in the solid state. In M. Fontanille and A. Guyot (ed.) Recent advances in mechanistic and synthetic aspects of polymerization. 215 (1987) : 239-314.

Berger, E., Ramsay, B.A., Ramsay, J.A., and Chavarie, C. PHB recovery by hypochlorite digestion of non PHB biomass. Biotechnol.Tech. 3(1989) : 227-232.

Berrins, L.M."Injection molding of thermoplastics" in Plastics Engineering Hand Book of Society of the Plastics Industry, ed. Berrins, M.L. (New York: Van Nostrand Reinhol, 1991), p. 153-154.

- Bloembergen, S., Holden, D.A., Hamer, G.K., Bluhm, T.L., and Marchessault, R.H. Study of composition and crystallinity of bacterial poly(β -hydroxybutyrate-co- β -hydroxyvalerate). Macromolecule. 19 (1986) : 2865-2871.
- Bluhm, T. L., G. K. Hamer, R. H. Marchersault, C. A. Fyfe, and R. P. Veregin. Isodimorphism in bacterial poly(β -hydroxybutyrate-co- β -hydroxyvalerate). Macromolecules, 19 (1986): 2871-2876.
- Bourgne, D., Ouellette, B., Andra, G and Grolean, D. Production of poly- β -hydroxybutylrate from methanol characterzation of a new isolate of *Methylobacterium extorquens*. Appl. Microbiol. Biotechnol. (1992) : 7-12
- Brandl, H., Gross, R.A., Lenz, R.W. and Fuller, R.C. Plastic from bacteria : Poly(β -hydroxyalkanoates) as natural, biocompatible and biodegradable polymers. Adv.Biochem.Eng. 41(1990) : 78-79.
- Braunegg, G., B. Sonnleitner, and R. M. Lafferty. A rapid gas chromatographic method for the determinetion of poly 3-hydroxybutyric acid in microbial biomass. Eur. J. Appl. Microbiol. 6(1978): 29-37.
- Byrom, D. Polymer synthetsis by microorganisms:technology and economic Tibtech. 5(1987) : 246-250.
- Chowbury, A. Bacterial and exoenzymes capable of degrading poly- β -hydroxybutyric acid. Arch. Mikrobiol. 47 (1963) : 167-200.
- Comeau, Y., Hall, K.J., and Oldham, W.K. Determination of poly- β -hydroxybutyrate and poly- β -hydroxyvalerate in activated sludge by gas-liquid chromatography. Appl. Environ. Microbiol. 54 (1988) : 2325-2327.
- Dawes, E.A., and Senior, P.J. The role and regulation of energy reserve polymers in microorganism. Adv.Microb.Physiol. 10(1973):135-266.

- De Smet, M.J., G. Eggink, B. Witholt, J. Kingma, and H. Wynberg. Characterization of intracellular inclusions formed by *Pseudomonas oleovorans* during growth on octane. J. Bacteriol. 154 (1983) : 870-878.
- Doi, Y. Biosynthesis and characterization of poly (3-hydroxybutyrate-co-4-hydroxybutyrate) in *Alcaligenes eutrophus*. Int.J. Biol. Macromol. 12 (1990) : 106-111.
- _____. Nuclear Magnatic Resonance studies on poly (β -hydroxybutyrate) and copolyester of β -hydroxybutyrate and β -hydroxyvalerate isolated from *Alcaligenes eutrophus* H16. Macromolecules 19(1986) : 2860-2864.
- _____. Production of copolymers of 3-hydroxybutyrate and 3-hydroxyvalerate by *Alcaligenes eutrophus* from butyric and pentaonic acids. Appl. Microbiol. Biotechnol. 28 (1988) : 330-334.
- _____. Kanesawa, Y., and Kunioka, M. Biodegradation of microbial copolymers: poly (3-hydroxybutyrate-co-3-hydroxy valerate) and poly (3-hydroxybutyrate-co-4-hydroxybutyrate). Macromolecules, 23(1990) : 26-31
- _____. Kunioka, M., Nakamura, Y., and Soga, K. Biosynthesis of copolymers in *alcaligenes eutrophus* H16 from ^{13}C -labeled acetate and propionate. Macromolecules 20 (1987) : 2988 : 2991.
- _____. Kunioka, M., Nakamura, Y. and Soga, K. Nuclear Magnatic Resonance studies on Unusual Bacterial copolyester of 3-hydroxybutyrate and 4-hydroxybutyrate. Macromolecules . (1988) : 2722-2727.
- _____. Segawa, A., Kawagnchi, Y., and Kunioka, M. Cyclic nature of poly (3-hydroxyalkanoate) metabolism in *Alcaligenes eutrophus*. FEMS Miicrobiol. Letts. 67 (1990) : 165-170.

- _____. Segawa, A., Kunioka, M. Biodegradable poly (3-hydroxybutyrate -co-4-hydroxybutyrate) produced from gramma-butyrolactone and butyric by *Alcaligenes eutrophus*. Polym. Commun. 30 (1989) : 169-171.
- _____. Tamaki, A., Kunioka, M., and Soga, K. Biosynthesis of an unusual copolyester (10 mol%3-hydroxybutyrate and 90 mol% 3-hydroxyvalerate units) in *Alcaligenes eutrophus* from pentaonic acid. J. Chem. Soc. Chem. Commun. 1987 (1987) : 1635-1636.
- Dunlop, W. F., and A. W. Robards. Ultrastructural study of poly- β -hydroxybutyrate granules from *Bacillus cesens*. J. Bacteriol. 114 (1973) : 1271-1280.
- Evan, D.J. and Sikda, K.S. Biodegradable plastic . Chemtech. 5 (1990) : 38-42.
- Findley, R.H., and White, D.C. Polymeric batahydroxyalkanoates from environmental samples and *Bacillus megaterium*. Appl. Environ. Microbiol. 51 (1983) : 71-78.
- Gillmeyer, F. W. "Structures and properties" in Text Book of Polymer Science, ed. Billmeyer, F. W. (Wiley-Interscience, 1984) p. 261-377.
- Groom, C.A., Luong, J.H.T., and Mulchandani, A. On-line culture fluorescence measurement during the batchcultivation of poly- β -hydroxybutyrate producing *Alcaligenes eutrophus*. J. Biotechnol. 8 (1988) : 271-278.
- Gross, R. A., H. Brandl, H. W. Ulmer, M. A. Posada, R. C. Fuller, and R. W. Len3. The biosynthesis and characterization of new poly (β -hydroxyalkanoates). Polym. Prep. 30 (1989) : 492-493.
- Haywood, G.W., A.J. Anderson, and E.A. Dawes. A survey of the accumulation of novel polyhydroxyalkanoates by bacterial. Biotechnol. Lett. 11 (1989) : 471-476.

Heinzle, E., and Lafferty, R. M. A kinetic model for growth and synthesis of poly- β -hydroxybutyric acid (PHB) in *Alcaligenes eutrophus* H16. European J. Appl. Microbiol. Biotechnol. 11 (1980) : 8-16.

Holland, S.J., Jolly, A.M., Yasin, M., and Tighe, B.J. Polymers for biodegradable medical device. II. HYdroxybutyrate-hydroxyvalerate copolymers: hydrolytic degradation studies. Biometerial 8 (1987) : 289-295.

Holmes, P.A. Application of PHB-a microbially produced biodegradable thermoplastic . Phys. Technol. 16(1985): 32-36.

Huffman, G.L., and Keller, D.J. The plastic issue. In : Guillet J. (Ed. Polymers and Ecological Problems P. 155. London: Plemun, 1973.

Kamiya, N., Yamamoto, Y., Inove, Y., Chujo, R. Microstructure of bacterially synthesized poly (3-hydroxybutyrate-co-3-hydroxyvalerate). Macromolecules. 22 (1989) : 1676-1682.

Kempers, A.J. Determination of sub-microquantities of ammonium and nitrates in soils with phenol, sodium nitroprusside and hypochlorite. Geoderma 12(1974) : 201-206.

Kunioka, M., Nakamura, Y., and Doi, Y. New bacterial copolymers produced in *Alcaligenes eutrophus* from organic acids. Polym. Cpmun. 29 (1988) : 174-176.

_____. Kawaguchi, Y., and Doi, Y. Production of biodegradable copolymers of 3-hydroxybutyrate and 4-hydroxybutyrate by *Alcaligenes eutrophus*. Appl. Microbiol. Biotechnol. 30 (1989) : 569-573.

Lageveen, R. G., G. W. Huisman, H. Preusting, P. Ketelaar. G. Eggink, and B. Witholt. Formation of polyesters by *Pseudomonas oleoverans*; Effect of substrates on formation and composition of poly-(R)-3-hydroxyalkanoates and poly (r)-3-hydroxyalkanoates. Appl. Environ. Microbiol. 54 (1988) : 2924-2932.

Law, J.H., and Slepecky, R.A. Assay of poly- β -hydroxybutyric acid. J. Bacteriol. 82 (1961) : 33-36.

Leaversuch, R. Industry weights need to make polymers biodegradable. Mod. Plast. 64 (1987) : 52-55.

Lemoigne, M. Products of dehydration and of polymerization of β -hydroxybutyric acid. Bull. Soc. Chem. Biol. 8(1926) : 770-782.

Lundgren, D. G., R. M. Pfister, and J. M. Mertrick. Structure of poly (β -hydroxybutyric acid) granules. J. Gen. Microbiol. 34 (1 964) : 441-446.

Lusty, C.J., and Doudoroff, M. Poly- β -hydroxybutyrate depolymerase of *Pseudomonas lemoigneii*. Proc. Natl. Acad. Sci. USA 56 (1966) : 960-965.

Mergaert, J., Webb, A., Anderson, C., Wouters, A., and Swings, J. Microbial degradation of poly(3-hydroxybutyrate) and poly(3-hydroxybutyrate-co-3-hydroxyvalerate) in soils. Appl. Environ. Microbiol. 59 (1993) : 3233-3238.

Mitomo, H., P.J. Barhanr , and A. Keller. Crystallization and morphology of poly (β - hydroxy butyrate) and its copolymer Polym.J. 19 (1987) : 1241-1253.

Mulchandani, A., Luong, J.H.T, and Groom. C. Substrate inhibition kinetic for microbial growth and synthesis of poly- β -hydroxybutyric acid by *Alcaligenes eutrophus* ATCC 17697. Appl. Microbiol. Biotechnol. 30 (1989): 11-17.

- Nagayama, K., Saito, T., Fukui, T., Shirakura, Y., and Tomita, K. Purification and Properties of extra cellular poly(3-hydroxybutyrate) depolymerase from *Pseudomonas lemoignei*. Biochem. Biophys. Acta. 827 (1985) : 63-72.
- Oeding, V., and Schlegel, H. G. β -ketothiolase from *Hydrogenomonas eutropha* H16 and its significance in the regulation of poly- β -hydroxybutyrate metabolism. Biol. J. 134 (1973) : 239-248.
- Odham, G., Tunlid, A., Westerdahl, G., and Marden, P. Combined determination of poly- β -hydroxyalkanoic and cellular fatty acids in starved marinebacteria and serwage by gas chromatography with flame ionization or mass spectrometry detection. Appl. Environ. Microbiol. 52 (1986) : 905-910.
- Page, W.J. Production of poly- β -hydroxybutyrate by *Azotobacter vinelandii* UWD in media containing sugars and complex nitrogen sources. Appl. Microbiol. Biotechnol. 38(1992) : 117-121.
- Pruter A. T. Mar. Poll. Bull. 18(1987) : 305.
- Ramsay, B.A., Lomaliza, K., Chavarie, C. Dube, B., batrill, P., and Ramsay, J.A. Production of (Poly- β -hydroxybutyric-co- β -hydroxyvaleric) acids. Appl. Environ. Microbiol. 56 (1990): 2093-2098.
- _____. Ramsay, J. A., and Cooper, D. G. Production of poly- β -hydroxyalkanoic acid by *Pseudomonas cepaccia*. Appl. Environ. Microbiol. 55 (1989) : 584-589.
- _____. Znog, G., and Cooper, D. Use of a nylon manufacturing waste as an industial fermentation substrate. Appl. Environ. Microbiol. (1986) : 152-156.
- Repaske, B. Quantitativer requirement for exponential growth of *Alcaligenes eutrophus*. Appl. Environ. Microbiol. 32(1976) : 585-591.

Scandola , M., M. Pizzoli, G. Cecconelli., A.Cesara, S. paoletti, and L. Navarini. Viscoelasticity and thermal Properties of bacterial poly (D-(--)- β -hydroxy butyrate) Int. J. Biol. Macromol. 10(1988):373-377

Senior, P.J., and Dawes, E.A. The regulation of poly- β -hydroxybutyrate metabolism in *Azotobacter beijerinckii*. Biochem. J. 134 (1973) : 225-238.

Sonnleitner, B., Heinze, E., Braunegg, G., and Lafferty R.M. Formal kinetics of poly- β -hydroxybutyric acid (PHB) production in *Alcaligenes eutrophus* H16 and *Mycoplana rubra* R14 with respect to the dissolved oxygen tension in ammonium-limited batch cultures. Eur. J. Appl. Microbiol. 7(1979) : 1-10.

Steinbuchel, A., Debzi, E., Marchessault, R. H., and Timm, A. Systhesis and production of poly (3-hydroxyvaleric acid) homopolyester by *Chrombacterium violaceum*. Appl. Microbiol. Biotechnol. 39 (1993) : 443-449.

_____. and Pieper, U. Production of a copolyester of 3 -hydroxybutyric acid and 3-hydroxyvaleric acid from single unrelated carbon sources by a mutant of *Alcaligenes eutrophus*. Appl. Microbiol. Biotechnol. 37 (1992) : 1-6.

_____. and Schlegel, H. G. Excretion of pyruvate by mutants of *Alcaligenes eutrophus*, which are impaired in the accumulation of poly(β -hydroxybutyric acid) (PHB) under conditions permitting synthesis of PHB. Appl. Microbiol. Biotechnol. 31 (1989) : 168-175.


Suzuki, T. Kinetic and effect of nitrogen source feeding production of poly- β -hydroxybutyric acid by fed-batch culture. Appl. Microbiol. Biotechnol. 24(1986a) : 366-369.

- Yamane, T., and Shimizu, S. Kinetics and effect of nitrogen source feeding on production of poly- β -hydroxybutyric acid by fed-batch culture. Appl. Microbiol. Biotechnol. 24 (1986) : 366-369.
- Taidi, B., Anderson, A.J., Dawes, E.A., and Byrom, D. Effect of carbon source and concentration on the molecular mass of poly(β -hydroxybutyrate) produced by *Methylobacterium extorquens* and *Alcaligenes eutrophus*. Appl. Microbiol. Biotechnol. 40(1994) : 786-790.
- Tanio, T., Fukui, T., Saito, T., Tomita, K., Kaiho, T. and Masamune, S. An extracellular poly(3-hydroxybutyrate) depolymerase from *Alcaligenes faecalis*. Eur. J. Biochem. 124 (1982) : 71-77.
- Tortoara, G. J., Funke, B. R., and Case, C. L. Lipid metabolism. In Microbiology and Introduction 3rd edition, pp. 132-134. The Benjamin/Cumming Publishing Comp Tnc. 1989.
- Wallen, L.L., and Rohwedder, W.R. Poly- β -hydroxyalkanoate from activated sludge. Environ. Sci. Technol. 8(1974) : 576-579.
- Ward, A.C., Rowley, B.I. and Dawes, E.A. Effect of oxygen and nitrogen limitation on poly- β -hydroxybutyrate biosynthesis in ammonium grown *Azotobacter beijerinckii*. J. Gen. Microbiol. 102(1977) : 61-68.
- Wilber R.J. Oceanus . 30 (3) (1987) : 61
- Williams , D.R., Anderson , A.J. , Dawes , E.A. , and Ewing . D.F. Production of a co-polyester of 3 - hydroxy butyrate acid and 3 - hydroxy valeric acid from succinic acid by *Rhodococcus ruber* : biosynthetic consideration. Appl. Microbiol. Biotechnol. 40 (1994) : 717-723.
- Williamson, D.H., and Wilkinson, J.F. The isolation and estimation of the poly- β -hydroxybutyrate inclusions of *Bacillus sp.* J. Gen. Microbiol. 19 (1958) : 198-209.


ภาคผนวก

ภาคผนวกที่ 1 การหาตัวน้ำหนักเซลล์เบียก และน้ำหนักเซลล์แห้งในอาหารสำหรับเตรียมกล้าเชื้อ
(2.3.2 สูตรที่ 1)

เตรียมหัวเชื้อของ *Alcaligenes sp.* A-04 ซึ่งมีความเข้มข้นเริ่มต้นและปริมาณจาก 2.4.3 นำมาเลี้ยงในอาหารสำหรับเตรียมกล้าเชื้อ 2.3.2 สูตรที่ 1 ซึ่งเป็นสูตรที่ได้ทำการคัดเลือกแล้วว่าเหมาะสมสำหรับการเติบโต เพื่อให้มีปริมาณเซลล์มากและได้เซลล์ที่มีประสิทธิภาพเมื่อถ่ายในขั้นตอนการผลิต เลี้ยงเชื้อเป็นเวลา 16 ชั่วโมง นำน้ำมันกษาวดงปริมาตร 10 20 40 60 และ 80 มล. ปั๊นแยกเซลล์ที่ 5,000 รอบต่อนาที เวลา 10 นาที นำมาลละเอียดในน้ำกลั่นให้เป็น 40 มล. และผสมให้เป็นเนื้อเดียวกัน นำแท่นลตัวอย่างมาเจือจางให้ได้ค่า $0D_{660}$ กรวยรายในช่วง 0.1-0.6 บันทึกค่าการเจือจาง และค่า $0D_{660}$ ปีเปตตัวอย่าง 15 มล. กรองผ่านแมมเบรนขนาด 0.45 ไมครอนที่กรานน้ำหนักเบียกและน้ำหนักแห้งแล้ว นำมาซึ่งหนาน้ำหนักเซลล์เบียกจากนั้นเอาไปอบแห้งจนน้ำหนักคงที่เพื่อหนาน้ำหนักเซลล์แห้งต่อไป นำค่าที่ได้มาสร้างกราฟมาตรฐานระหว่าง $0D_{660}$ กับน้ำหนักเซลล์เบียก (ภาคผนวกที่ 1ก) และ $0D_{660}$ กับน้ำหนักเซลล์แห้ง (ภาคผนวก 1ข)




ภาคผนวกที่ 1 ก กราฟมาตรฐานสำหรับปริมาณน้ำหนักเชลล์เบียกของ *Alcaligenes* sp.
 A-04 (น้ำหนักเชลล์เบียก (กรัมต่อลิตร)) = $2.65625 \times OD_{660}$




ภาคผนวกที่ 1 กราฟมาตรฐานสำหรับวิเคราะห์น้ำหนักเซลล์แห้งของ *Alcaligenes sp.*
A-04 (น้ำหนักเซลล์แห้ง (กรัมต่อลิตร) = $0.5769 \times OD_{660}$)

ภาคผนวกที่ 2 การหาตัวน้ำหนักเซลล์แห้งในอาหารเลี้ยงเชื้อเพื่อการผลิต (2.3.3) และกราฟ
มาตรฐานรายห้วงน้ำหนักแห้ง OD_{660}

เลี้ยงเชื้อ *Alcaligenes sp.* A-04 ในอาหารสูตรที่ 2.3.3 เป็นเวลา 60 ชม. ตวงน้ำหนักปริมาตร 10 20 40 60 80 และ 100 มล. ปั๊นแยกเซลล์ที่ 5,000 รอบ เวลา 10 นาที นำมาลซลายน้ำกลั่นให้เป็น 40 มล. และผสมถ้าเป็นเนื้อเดียวกัน นำแต่ละตัว อย่างมาเจือจางให้ได้ค่า OD_{660} อยู่ในช่วง 0.1-0.5 บันทึกค่าการเจือจางและค่า OD_{660} เก็บไว้ บันทึกน้ำหนักแห้งของเมมเบรน ปีเปตแอลช้อย่าง 20 มล. กรองผ่านเมมเบรนขนาด 0.45 ไมครอน สาวเซลล์ด้วยน้ำกลั่นนำไปอบแห้งจนน้ำหนักคงที่ บันทึกผลต่างของน้ำหนักเซลล์แห้ง และ เมมเบรนแห้ง กับ น้ำหนักเมมเบรนแห้ง นำข้อมูลมาสร้างกราฟ มาตรฐานรายห้วง OD_{660} กับ น้ำหนักเซลล์แห้ง (ภาคผนวก 2ก)



ภาคผนวกที่ 2ก กราฟมาตรฐานสำหรับหาปริมาณ - น้ำหนักเชลล์แห้ง ของ *Alcaligenes* sp . A-04 ในอาหารสำหรับการผลิตโคลิเมอร์ (สูตรที่ 2)
 (น้ำหนักเชลล์แห้ง = $0.4356 \times OD$)



ภาคผนวกที่ 3 กราฟมาตรฐานสำหรับวิเคราะห์ปริมาณการตรวจว่าเลอเริก

START 21.07.10.42.

STOP TM 10

BOOK 2

(1)

METHOD 41
STOP

Valeric acid

4.98

C-R1A
SMPL # 00
FILE # 2
REPT # 2185
METHOD 41

#	NAME	TIME	CONC	MK	AREA
0		4.98	99.9999	V	52360
	TOTAL		99.9999		52360

START 21.07.12.30.

(2)

STOP

1.88

C-R1A
SMPL # 00
FILE # 2
REPT # 2191
METHOD 41

#	NAME	TIME	CONC	MK	AREA
0		1.13	4.7678		5823
0		1.33	4.5893	V	5605
0		1.63	14.1071	V	17232
0		1.88	28.6581	V	35006
0		2.5	7.1869	V	8778
0		3.01	5.1454	V	6285
0		3.39	2.4399	V	2980
0		4.96	33.1052		40438
	TOTAL		100		122151

ภาคผนวกที่ 3 ก โครงการโปรแกรมของกรค瓦เลอเริกมารฐาน (1) และ โครงการโปรแกรมของกรคва
เลอเริก ที่เหลือในน้ำหมัก (2)


ภาคผนวกที่ 4 การเตรียมรีเอเจนต์ใช้ในการวิเคราะห์ปริมาณแอมโมเนียมชัลเฟต์
โพแทสเซียมคลอไรด์เข้มข้น 2 มิลลาร์ ได้จากโพแทสเซียมคลอไรด์ 150 กรัม
ในน้ำปลอดปะจุ 800 มล. แล้วปรับปริมาตรให้เป็น 100 มล.

ฟีโนลในไตรพัลซายด์รีเอเจนต์ ได้จากละลายนีโนล 7 กรัม และ
โซเดียมพัลซายด์ 34 มก. ในน้ำปลอดปะจุ 80 มล. เจือจางให้ได้ 100 มล. เก็บในขวดสีชา
ที่อุณหภูมิ 4°C


บัฟเฟอร์ไอโอลคลอไรด์รีเอเจนต์ ได้จากละลายนีโตรออกไซด์ 1.480
กรัม ในน้ำปลอดปะจุ 70 มล. เติมโซเดียมไอโตรเจนฟลอสเฟต์ 4.98 กรัม และเติม
โซเดียมไอโอลคลอไรด์ (เข้มข้น 5-5.25% โดยปริมาตร) 20 มล. ปรับค่า PH ให้อยู่ในช่วง
 $11.4-12.2$ ด้วยโซเดียมไอโตรออกไซด์ และ ปรับปริมาตรสุดท้ายเป็น 100 มล.

สารละลายนีโนล EDTA ได้จากสารละลายนีโนล EDTA จำนวน 6 กรัม ในน้ำปลอดปะจุ 8
0 มล. ปรับ PH ให้ได้ 7.0 และปรับปริมาตรเป็น 100 มล.


สารละลายนามารฐาน แอมโมเนียมชัลเฟต์ ซึ่ง แอมโมเนียมชัลเฟต์ที่แห้ง 0.4717
กรัม ละลายในน้ำกลั่นปลอดปะจุปรับปริมาตรเป็น 1 ลิตร เก็บไว้ที่อุณหภูมิ 4°C ก่อน
ใช้นำมาเจือจางโดยปีเปต 4 มล. และเจือจางด้วยน้ำกลั่นปลอดปะจุ ปรับปริมาตรเป็น 200 มล.
($\text{NH}_4^+ - \text{N}$) เท่ากัน 2 ไมโครกรัม/มล.




ภาคผนวกที่ 4ก กราฟมาตรฐานสำหรับวิเคราะห์ปริมาณในไนโตรเจนแอมโมเนียม ($\text{NH}_4^+ - \text{N}$)
 $(\text{ปริมาณ} (\text{NH}_4^+ - \text{N}) = \frac{1}{0.026} \times \text{OD}_{636})$



ภาคผนวกที่ ๕ก กราฟมาตรฐานสำหรับวิเคราะห์ปริมาณ HHB
(ความชันเท่ากับ 7539)




ภาคผนวกที่ 5ข กราฟมาตรฐานสำหรับวิเคราะห์ปริมาณ 3HV
(ความชันเท่ากับ 8979)




อัตราส่วนในพื้นที่ใต้กราฟ (กรดเบนโซอิก/4HB)


ภาคผนวกที่ ๕ค กราฟมาตรฐานสำหรับวิเคราะห์ปริมาณ 4HB
(ความซัมเม่กัน ๙๘๘๓)



ภาคพนวกที่ ๖ โครงมาติกรรม ของสารมาตรฐาน P (3HB-24%3HV)



ภาคผนวกที่ ๖ โปรแกรม ของสารมาตรฐานเกลือโซเดียมของ 3HB



ภาคผนวกที่ ๖ โปรแกรมติดограм ของสารมาตรฐานเกลือโซเดียมของ 4HB

ภาคผนวกที่ 7 การคำนวณค่า intrinsic viscosity $[\eta]$ (ปฏิบัติการโพลีเมอร์ และ Billmeyer, 1984)

การคำนวณค่า intrinsic viscosity $[\eta]$

1 หาค่า specific viscosity (η_{sp}) โดย

$$\eta_{sp} = (t - t_0) t_0$$

โดยที่ t = เวลาที่สารละลายของโพลีเมอร์ไหลจากจุดหนึ่งไปสิ้นอีกจุดหนึ่งใน capillary tube ของ viscometer

t_0 = เวลาที่ตัวทึบทำละลายไหลจากจุดหนึ่งไปสิ้นอีกจุดหนึ่งใน capillary tube ของ viscometer


2 หาค่า reduced viscosity (η_{red}) โดย

$$\eta_{red} = \eta_{sp}/c$$

c = ความเข้มข้นของสารละลาย มีหน่วยเป็น กรัม/100 มล.

3 หาค่า $[\eta]$ โดยสร้างกราฟระหว่าง η_{red} กับ c ที่ความเข้มข้นต่างๆ แล้ว extrapolate ไปที่ความเข้มข้นเท่ากับศูนย์ซึ่งเป็นค่า $[\eta]$ กล่าวคือ $[\eta]$ เป็นค่า reduce viscosity ที่ความเข้มข้นเท่ากับศูนย์นั้นเอง ($[\eta] = (\eta_{sp}/c)_{c=0}$)

ภาคผนวกที่ 8 ลักษณะของ specimen สำหรับการวิเคราะห์สมบัติเชิงกลของแผ่นฟิล์ม
(ASTM D882-91)



รูปที่ 48 specimen สำหรับการวิเคราะห์สมบัติเชิงกล

ประวัติผู้เขียน

นางสาว อัญชนา ศุรติขาว เกิดวันที่ 1 กันยายน พ.ศ. 2511 ที่จังหวัดกรุงเทพ
มหานคร สำเร็จการศึกษาปริญญาวิทยาศาสตรบัณฑิต สาขาวุฒิชีววิทยา คณะวิทยาศาสตร์
จุฬาลงกรณ์มหาวิทยาลัย ในปีการศึกษา 2532 และเข้าศึกษาต่อในหลักสูตรวิทยาศาสตร์
มหาบัณฑิต สาขาวุฒิชีววิทยาอุตสาหกรรม จุฬาลงกรณ์มหาวิทยาลัย เมื่อ พ.ศ. 2534