



## REFERENCES


1. Lieberman, H.A., and Lachman, L., Pharmaceutical Dosage Forms (Tablets), Vol 2, 247 (1981).
2. Carstensen, J.T., Kothari, R., and Chowhan, Z.T., Drug Dev. and Ind. Pharm., 6 (6), 569(1980)
3. Flasch, H., Asmussen, G., and Heinz, H., Drug Res., 28(1), 2(1978)
4. Sprengler, H., and Shenker, E., Pharm. Acta. Helv., 12, 337(1937)
5. Sprengler, H., and Jud, J., ibid, 18, 565(1943)
6. Feinstein, W., and Bartilucci, A.J., J.Pharm. Sci., 55, 332 (1966)
7. Fakouki, T.A., et al., J. Pharm. Sci., 52, 700 (1963)
8. Finholt, P. "Influence of Formulation on Dissolution Rates in Dissolution Technology, ed. by Leeson, L.J., and Carstensen, J.T., Washington D.C. : I.P.T. Academy of Pharmaceutical Science, 106 (1974)
9. American Pharmaceutical Association., The United States Pharmacopeia, 19<sup>th</sup> rev., Easton, Pa : Mack Publishing Co. (1975).
10. American Pharmaceutical Association., The National Formulary, 14<sup>th</sup> ed., Easton, Pa : Mack Publishing Co. (1975)
11. Higuchi, W.I., J. Pharm. Sci., 54, 170 (1965)
12. Mc Ginity, et al., Pharmaceutical Dosage Forms (Tablets), Vol 2, ed. by Lieberman, H.A., and Lachman, L., Marcel Dekken, INC., N.Y., 310(1981)

13. Wuster, D.E., and Taylor, P.W., J.Pharm. Sci., 54, 170 (1965)
14. Carstensen, J.T., Pharmaceutics of Solids and Solid Dosage Forms, Wiley, N.Y. (1977)
15. Higuchi, T., J.Pharm. Sci., 52, 1145 (1963)
16. Chiou, W.L., and Megelman, S., J.Pharm. Sci., 58, 1505 (1969)
17. Mayersohn, M., and Gibaldi, M., J.Pharm. Sci., 55, 1323 (1966)
18. Summer, M.P., and Enverver, R.P., J.Pharm. Sci., 66, 825 (1977)
19. Goldberg, A.H., Gibaldi, M., and Kanig, J.L., J.Pharm. Sci., 54, 1145 (1965)
20. Goldberg, A.H., Gibaldi, M., and Kanig, J.L., J.Pharm. Sci., 55, 482 (1966)
21. Goldberg, A.H., et al., J.Pharm. Sci., 55, 487 (1966)
22. Chiou, W.L., and Niazi, S., J.Pharm. Sci., 65, 1212 (1976)
23. Stoll, R.G., et al., J.Pharm. Sci., 58, 1457 (1969)
24. Aguiar, A.J., et al., J. Pharm. Sci., 56, 847 (1967)
25. Halebian, J.K., J.Pharm. Sci., 64, 1269 (1975)
26. Shefter, E., and Higuchi, T., J.Pharm. Sci., 52, 781 (1963)
27. Higuchi, T., and Lach, J.L., J. Am. Pharm. Assoc. Sci., 43, 524 (1954)
28. Higuchi, W.I., et al., J.Pharm. Sci., 54, 1405 (1965)
29. Zoglio, M.A., et al., J. Pharm. Sci., 58, 222 (1969)
30. Higuchi, T., and Ikeda, M., J.Pharm. Sci., 63, 809 (1974)
31. Yang, K.Y., et al., J. Pharm. Sci., 68, 560 (1979)

32. Monkhouse, D.C., and Lach, J.L., J. Pharm. Sci., 61, 1430 (1972)
33. Mc. Ginity, J.W., and Harris, M.R., J. Pharm. Sci., 6, 35 (1980)
34. Nogami, et al., "Pharmaceutical Dosage Forms", Ed. by Lieberman, H.A., and Lachman, L., Vol 2, Marcel Dekken, Inc., 366 (1981)
35. Parrotte, E.L., and Sharma, V.K., J. Pharm. Sci., 56, 1341 (1967)
36. Singh, P., et al., J. Pharm. Sci., 57, 959 (1968)
37. Finholt, P., and Solvang, S., J. Pharm. Sci., 57, 1322 (1968)
38. Mendell, E.J., Pharm. Acta. Helv., 49, 248 (1974)
39. Rubinstein, M.H., and Price, E.J. J. Pharm. Pharmac., 29, Suppl. 5 P (1977)
40. Kalidindi, S.R., and Shangraw, R.F., Drug Dev. and Ind. Pharm., 8 (2), Part I. "Direct Compression", 215 (1982)
41. Kalidindi, S.R., and Shangraw, R.F., Drug Dev. and Ind. Pharm., 8 (5), Part II "Wet Granulation", 631 (1982)
42. Shangraw, R.F., et al., Pharmaceutical Technology, 4 (10), 48(1980)
43. Gorman, E.A., et al., J. Pharm. Sci., 8, 397 (1982)
44. Ac-Di-Sol<sup>R</sup> "Modified Cellulose Gum", Technical Information Bulletin, SD-1, FMC Corp., Philadelphia (1979)
45. Ac-Di-Sol<sup>R</sup> "Modified Cellulose Gum", Technical Information Bulletin, SD-2, FMC Corp., Philadelphia (1979)
46. Walkling, W.D., et al., Drug Dev. and Ind. Pharm., 5, 17(1979)
47. Monkhouse, D.C., and Lach, J.L., J. Pharm. Sci., 61, 1430 (1972)
48. Monkhouse, D.C., and Lach, J.L., J. Pharm. Sci., 61, 1435 (1972)
49. Chiou, W.L., and Riegelman, S., J. Pharm. Sci., 60, 1376 (1971)

50. Sekiguchi, K., and Obi, N., Chem. Pharm. Bull., 9, 866 (1961)
51. Wade, A., and Reynolds, J.E.F., Martindale, The Extra Pharmacopoeia, 27<sup>th</sup> ed., the Council of the Pharmaceutical Society of Great Britain, London, 426 (1977)
52. Mc. Ginity, J.W., and Harris, M.R., Drug Dev. and Ind. Pharm., 6, 49 (1980)
53. Aballah, H.Y., et al., Drug Dev. and Ind. Pharm., 9, 795 (1983)
54. Narurkar, A.N., and Jarowski, C.I., Drug Dev. and Ind. Pharm., 9 (6) 996 (1983)
55. British Pharmacopoeia Comission, "British Pharmacopoeia" Vol 1, 205 (1980)
56. WHO "Specifications for the Quality Control of Pharmaceutical Preparation of the International pharmacopoeia", 2<sup>nd</sup> ed., 239 (1967)
57. Society of Japanese pharmacopoeia, "The Pharmacopoeia of Japan", 10<sup>th</sup> ed., Yakuji Nippo, Ltd., 527 (1982)
58. American Pharmaceutical Association., "The United States Pharmacopoeia", 19<sup>th</sup> rev., Easton. Pa., : Mack Publishing Co., 214 (1975)
59. American Pharmaceutical Association, "The United States Pharmacopoeia", 18<sup>th</sup> rev., Easton. Pa., Mack Publishing Co., 934 (1970)
60. Ullah, I., and Cadwallader, D., J.Pharm. Sci., 60, 1499 (1971)
61. American Pharmaceutical Association, "The United States Pharmacopoeia", 19<sup>th</sup> rev., Easton. Pa., : Mack Publishing Co., 617 (1975)

62. American Pharmaceutical Association, "The United States Pharmacopeia", 21<sup>st</sup> rev., Easton. Pa., : Mack Publishing Co., 473 (1985)
63. American Pharmaceutical Association, "The United States Pharmacopeia", 21<sup>st</sup> rev. Easton Pa., : Mack Publishing Co., 871 (1985)
64. American Pharmaceutical Association, "The United States Pharmacopeia" 21<sup>st</sup> rev. Easton. Pa., : Mack Publishing Co., 453 (1985)
65. Rudnic, E.M., et al., Drug Dev. and Ind. Pharm., 7 (3), 349, 358 (1981)
66. Lieberman, H.A. and Lachman, L., "Pharmaceutical Dosage Forms (Tablets)", Vol 1, 87 (1981)
67. Kalidindi, S.R., and Shangraw, R.F., Drug Dev. and Ind. Pharm., 8 (5), 648 (1982)
68. Shangraw, R., et al. Pharmaceutical Technology, 4 (10), 50 (1980)



## APPENDIX

# ศูนย์วิทยทรัพยากร อุปางกรณ์มหาวิทยาลัย

Table 26 Effect of Disintegrants on Disintegration Time of Griseofulvin Tablets

| Formula Number | Disintegration Time, min $\pm$ S.D.       |  |   |
|----------------|---|--|---|
|                | Wet granulation<br>Tablet Hardness 5-7 kp | Wet granulation<br>Tablet Hardness 9-11 kp | Dry granulation<br>Tablet Hardness 5-7 kp |
| 1              | > 60                                      | > 60                                       | > 60                                      |
| 2              | 15.08 $\pm$ 0.3705                        | 17.51 $\pm$ 0.1942                         | 0.14 $\pm$ 0.0279                         |
| 3              | 5.12 $\pm$ 0.1173                         | 14.38 $\pm$ 0.1048                         | 0.12 $\pm$ 0.0289                         |
| 4              | 0.43 $\pm$ 0.0409                         | 2.27 $\pm$ 0.0937                          | 0.11 $\pm$ 0.0240                         |
| 5              | 0.36 $\pm$ 0.0376                         | 2.28 $\pm$ 0.4050                          | 0.10 $\pm$ 0.0126                         |
| 6              | 0.32 $\pm$ 0.0279                         | 2.20 $\pm$ 0.0836                          | 0.10 $\pm$ 0.0126                         |
| 7              | 0.21 $\pm$ 0.0376                         | 2.06 $\pm$ 0.1076                          | 0.10 $\pm$ 0.0154                         |
| 22             | > 60                                      | > 60                                       | > 60                                      |
| 23             | 5.37 $\pm$ 0.0691                         | 14.56 $\pm$ 0.1972                         | 0.31 $\pm$ 0.0296                         |
| 24             | 5.56 $\pm$ 0.1569                         | 15.44 $\pm$ 0.0861                         | 0.41 $\pm$ 0.0286                         |

Table 27 Effect of Disintegrants on Disintegration Time of Prednisolone Tablets

| Formula<br>Number | Disintegration Time, min. $\pm$ S.D.      |   |   |
|-------------------|---|---|---|
|                   | Wet granulation<br>Tablet Hardness 1-2 Kp | Wet granulation<br>Tablet Hardness 3-5 Kp | Dry granulation<br>Tablet Hardness 1-2 Kp |
|                   |   |   |   |
| 8                 | 30.33 $\pm$ 0.2984                        | 41.66 $\pm$ 0.5164                        | 1.17 $\pm$ 0.0236                         |
| 9                 | 0.21 $\pm$ 0.0240                         | 1.27 $\pm$ 0.0783                         | 0.15 $\pm$ 0.0412                         |
| 10                | 0.08 $\pm$ 0.0275                         | 0.30 $\pm$ 0.0562                         | 0.10 $\pm$ 0.0154                         |
| 11                | 0.07 $\pm$ 0.0184                         | 0.27 $\pm$ 0.0238                         | 0.09 $\pm$ 0.0346                         |
| 12                | 0.07 $\pm$ 0.0178                         | 0.25 $\pm$ 0.0343                         | 0.08 $\pm$ 0.0167                         |
| 13                | 0.06 $\pm$ 0.0118                         | 0.20 $\pm$ 0.0256                         | 0.08 $\pm$ 0.0126                         |
| 14                | 0.05 $\pm$ 0.0109                         | 0.18 $\pm$ 0.0352                         | 0.08 $\pm$ 0.0200                         |
| 25                | 14.45 $\pm$ 0.1300                        | 44.66 $\pm$ 0.5164                        | 10.50 $\pm$ 0.8366                        |
| 26                | 0.58 $\pm$ 0.0387                         | 2.15 $\pm$ 0.1830                         | 0.13 $\pm$ 0.0346                         |
| 27                | 1.00 $\pm$ 0.0707                         | 2.35 $\pm$ 0.0591                         | 0.15 $\pm$ 0.0155                         |

Table 28 Effect of Disintegrants on Disintegration Time of Furosemide Tablets

| Formula<br>Number | Disintegration Time, min $\pm$ S.D.                   |  |   |
|-------------------|---|--|---|
|                   | Wet granulation<br>Tablet Hardness 4-6 K <sub>p</sub> | Wet granulation<br>Tablet Hardness 8-11 K <sub>p</sub> | Dry granulation<br>Tablet Hardness 4-6 K <sub>p</sub> |
| 15                | > 60  | > 60   | 2.14 $\pm$ 0.0813                                     |
| 16                | 0.40 $\pm$ 0.0340                                     | 8.54 $\pm$ 0.5657                                      | 0.10 $\pm$ 0.0126                                     |
| 17                | 0.36 $\pm$ 0.0240                                     | 2.27 $\pm$ 0.1038                                      | 0.05 $\pm$ 0.0077                                     |
| 18.               | 0.20 $\pm$ 0.0240                                     | 1.31 $\pm$ 0.0376                                      | 0.04 $\pm$ 0.0063                                     |
| 19                | 0.20 $\pm$ 0.0340                                     | 1.26 $\pm$ 0.0878                                      | 0.04 $\pm$ 0.0077                                     |
| 20                | 0.19 $\pm$ 0.0240                                     | 1.19 $\pm$ 0.0734                                      | 0.04 $\pm$ 0.0063                                     |
| 21                | 0.15 $\pm$ 0.0236                                     | 1.12 $\pm$ 0.0440                                      | 0.03 $\pm$ 0.0109                                     |
| 28                | > 60  | > 60   | 25.05 $\pm$ 0.5039                                    |
| 29                | 0.39 $\pm$ 0.0334                                     | 7.46 $\pm$ 0.1540                                      | 0.22 $\pm$ 0.0394                                     |
| 30                | 0.40 $\pm$ 0.0387                                     | 10.33 $\pm$ 0.5164                                     | 0.24 $\pm$ 0.0272                                     |

Table 29 Effect of Disintegrants on Dissolution Time (t 85 %) of Griseofulvin Tablets

| Formula<br>Number | Dissolution Time (t 85 %), min $\pm$ S.D. |  |   |
|-------------------|---|--|---|
|                   | Wet granulation<br>Tablet Hardness 5-7 Kp | Wet granulation<br>Tablet Hardness 9-11 Kp | Dry granulation<br>Tablet Hardness 5-7 Kp |
|                   |   |  |   |
| 1                 | > 60                                      | > 60                                       | > 60                                      |
| 2                 | 24.45 $\pm$ 1.4849                        | 40.45 $\pm$ 2.8284                         | > 60                                      |
| 3                 | 22.25 $\pm$ 1.4142                        | 27.15 $\pm$ 1.6263                         | 51.25 $\pm$ 2.4748                        |
| 4                 | 22.10 $\pm$ 1.7776                        | 25.25 $\pm$ 1.4142                         | 43.15 $\pm$ 1.4142                        |
| 5                 | 17.45 $\pm$ 1.4142                        | 24.20 $\pm$ 2.5455                         | 25.00 $\pm$ 0.7778                        |
| 6                 | 15.05 $\pm$ 1.4849                        | 22.45 $\pm$ 5.6556                         | 22.25 $\pm$ 1.4142                        |
| 7                 | 14.10 $\pm$ 1.2727                        | 21.25 $\pm$ 4.5961                         | 19.20 $\pm$ 1.1313                        |
| 22                | 53.25 $\pm$ 3.8890                        | > 60                                       | > 60                                      |
| 23                | 47.25 $\pm$ 2.8284                        | 56.25 $\pm$ 1.7677                         | > 60                                      |
| 24                | 53.25 $\pm$ 3.8890                        | > 60                                       | > 60                                      |

Table 30 Effect of Disintegrants on Dissolution Time (t 70 %) of Prednisolone Tablets

| Formula Number | Dissolution Time (t 70%), min $\pm$ S.D.  |   |   |
|----------------|---|---|---|
|                | Wet granulation<br>Tablet Hardness 1-2 Kp | Wet granulation<br>Tablet Hardness 3-5 Kp | Dry granulation<br>Tablet Hardness 1-2 Kp |
| 8              | 38.25 $\pm$ 2.4748                        | > 60                                      | > 60                                      |
| 9              | 30.25 $\pm$ 2.8284                        | 40.25 $\pm$ 2.8284                        | > 60                                      |
| 10             | 12.25 $\pm$ 1.0606                        | 20.10 $\pm$ 2.6870                        | 59.25 $\pm$ 1.4142                        |
| 11             | 8.10 $\pm$ 1.2727                         | 10.25 $\pm$ 1.0606                        | 52.35 $\pm$ 2.7577                        |
| 12             | 4.10 $\pm$ 1.5556                         | 8.25 $\pm$ 1.4142                         | 45.75 $\pm$ 1.4142                        |
| 13             | 3.45 $\pm$ 1.2727                         | 6.45 $\pm$ 1.6263                         | 15.75 $\pm$ 1.1313                        |
| 14             | 3.10 $\pm$ 0.8485                         | 4.10 $\pm$ 1.2727                         | 10.75 $\pm$ 2.6162                        |
| 25             | 33.25 $\pm$ 3.8890                        | 45.25 $\pm$ 5.3033                        | > 60                                      |
| 26             | 15.20 $\pm$ 0.8485                        | 22.05 $\pm$ 2.8284                        | > 60                                      |
| 27             | 20.10 $\pm$ 1.2727                        | 30.10 $\pm$ 2.6870                        | > 60                                      |

Table 31 Effect of Disintegrants on Dissolution Time ( $t_{65\%}$ ) of Furosemide Tablets

| Formula Number | Dissolution Time ( $t_{65\%}$ ), min $\pm$ S.D. |  |   |
|----------------|---|--|---|
|                | Wet granulation<br>Tablet Hardness 4-6 Kp       | Wet granulation<br>Tablet Hardness 8-11 Kp | Dry granulation<br>Tablet Hardness 4-6 Kp |
| 15             | $20.10 \pm 2.6870$                              | $> 60$                                     | $> 60$                                    |
| 16             | $9.20 \pm 1.1313$                               | $18.10 \pm 1.5556$                         | $> 60$                                    |
| 17             | $8.45 \pm 1.5556$                               | $16.45 \pm 2.8284$                         | $43.20 \pm 3.9597$                        |
| 18             | $7.10 \pm 1.5556$                               | $14.20 \pm 3.1112$                         | $36.45 \pm 3.0405$                        |
| 19             | $6.75 \pm 1.4142$                               | $11.10 \pm 2.8284$                         | $32.45 \pm 2.8284$                        |
| 20             | $5.85 \pm 1.2020$                               | $8.35 \pm 1.4142$                          | $30.45 \pm 1.4142$                        |
| 21             | $4.10 \pm 1.2727$                               | $7.45 \pm 1.4142$                          | $27.05 \pm 1.4849$                        |
| 28             | $17.45 \pm 2.1000$                              | $> 60$                                     | $> 60$                                    |
| 29             | $9.45 \pm 1.4142$                               | $22.25 \pm 1.7677$                         | $45.25 \pm 1.7677$                        |
| 30             | $11.10 \pm 1.2727$                              | $24.25 \pm 2.4748$                         | $47.45 \pm 4.2426$                        |

Table 32 Effect of The Methods to Incorporate Disintegrant into Granules on The Weight Variation of Griseofulvin Tablets (Formula No. 3), Prednisolone Tablets (Formula No.10), and Furosemide Tablets (Formula No.17)

| Formula Number | Wet granulation<br>Intragranular |        | Wet granulation<br>Extragranular |        | Wet granulation<br>50:50 Intra:Extra |        |
|----------------|----------------------------------|--------|----------------------------------|--------|--------------------------------------|--------|
|                | Av. weight (gm $\pm$ S.D.)       | % C.V. | Av. weight (gm $\pm$ S.D.)       | % C.V. | Av. weight (gm $\pm$ S.D.)           | % C.V. |
| 3              | 0.3123 $\pm$ 0.0003              | 0.09   | 0.3124 $\pm$ 0.0003              | 0.10   | 0.3157 $\pm$ 0.0017                  | 0.53   |
| 10             | 0.1324 $\pm$ 0.0010              | 0.79   | 0.1324 $\pm$ 0.0011              | 0.89   | 0.1339 $\pm$ 0.0009                  | 0.66   |
| 17             | 0.1482 $\pm$ 0.0013              | 0.87   | 0.1494 $\pm$ 0.0012              | 0.84   | 0.1463 $\pm$ 0.0009                  | 0.64   |

Table 33 Effect of The Methods to Incorporate Disintegrant into Granules on The Thickness of Griseofulvin Tablets (Formula No.3), Prednisolone Tablets (Formula No.10), and Furosemide Tablets (Formula No 17)

| Formula Number | Wet granulation<br>Intragranular  |                                   | Wet granulation<br>Extragranular  |                                   | Wet granulation<br>50:50 Intra:Extra |                                   |
|----------------|-----------------------------------|-----------------------------------|-----------------------------------|-----------------------------------|--------------------------------------|-----------------------------------|
|                | Average Thickness (mm $\pm$ S.D.)    | Average Thickness (mm $\pm$ S.D.) |
| 3              | 5.03 $\pm$ 0.0418                 |                                   | 5.02 $\pm$ 0.0204                 |                                   | 5.27 $\pm$ 0.0141                    |                                   |
| 10             | 3.93 $\pm$ 0.0556                 |                                   | 3.95 $\pm$ 0.0500                 |                                   | 4.24 $\pm$ 0.0574                    |                                   |
| 17             | 4.06 $\pm$ 0.0529                 |                                   | 4.06 $\pm$ 0.0768                 |                                   | 4.09 $\pm$ 0.0100                    |                                   |

Table 34 Effect of The Methods of Incorporating Disintegrant into Granules on The Hardness of Griseofulvin Tablets (Formula No.3), Prednisolone Tablets (Formula No. 10) and Furosemide Tablets (Formula No. 17)

| Formula Number | Wet granulation Intragranular |        | Wet granulation Extragranular |        | Wet granulation 50:50 Intra: Extra |        |
|----------------|-------------------------------|--------|-------------------------------|--------|------------------------------------|--------|
|                | Hardness ( $K_p \pm S.D.$ )   | % C.V. | Hardness ( $K_p \pm S.D.$ )   | % C.V. | Hardness ( $K_p \pm S.D.$ )        | % C.V. |
| 3              | $4.96 \pm 0.2716$             | 5.47   | $5.06 \pm 0.5779$             | 9.53   | $6.72 \pm 0.3155$                  | 4.69   |
| 10             | $2.54 \pm 0.1404$             | 5.52   | $2.53 \pm 0.2023$             | 7.99   | $1.86 \pm 0.1646$                  | 8.85   |
| 17             | $5.17 \pm 0.1810$             | 3.16   | $5.61 \pm 0.2632$             | 4.69   | $5.37 \pm 0.3529$                  | 6.57   |

Table 35 Effect of The Methods of Incorporating Disintegrant into Granules on The Friability of Griseofulvin Tablets (Formula No.3), Prednisolone tablets (Formula No. 10) and , Furosemide Tablets (Formula No.17)

| Formula Number | Wet granulation Intragranular |              | Wet granulation Extragranular |              | Wet granulation 50:50 Intra:Extra |              |
|----------------|-------------------------------|--------------|-------------------------------|--------------|-----------------------------------|--------------|
|                | Friability %                  | Friability % | Friability %                  | Friability % | Friability %                      | Friability % |
| 3              | 0.33                          |              | 0.38                          |              | 0.36                              |              |
| 10             | 0.56                          |              | 0.60                          |              | 0.56                              |              |
| 17             | 0.18                          |              | 0.20                          |              | 0.20                              |              |

Table 36 Effect of The Methods of Incorporating Disintegrant into Granules on Disintegration Time of Griseofulvin Tablets (Formula No.3), Prednisolone Tablets (Formula No.10), and Furosemide Tablets (Formula No. 17)

| Formula<br>Number | Disintegration Time, min. $\pm$ S.D. |                                  |                                      |
|-------------------|--------------------------------------|----------------------------------|--------------------------------------|
|                   | Wet granulation<br>Intragranular     | Wet granulation<br>Extragranular | Wet granulation<br>50:50 Intra:Extra |
| 3                 | 4.46 $\pm$ 0.1569                    | 4.04 $\pm$ 0.1772                | 5.12 $\pm$ 0.1173                    |
| 10                | 0.06 $\pm$ 0.0118                    | 0.05 $\pm$ 0.0190                | 0.08 $\pm$ 0.0257                    |
| 17                | 0.31 $\pm$ 0.0471                    | 0.32 $\pm$ 0.0527                | 0.36 $\pm$ 0.0240                    |

Table 37 Effect of The Methods of Incorporating Disintegrant into Granules on Dissolution Time of Griseofulvin Tablets (Formula No. 3), Prednisolone Tablets (Formula No.10) ,and Furosemide Tablets (Formula No.17)

| Formula<br>Number | Dissolution Time, min. $\pm$ S.D. |                                  |                                      |
|-------------------|-----------------------------------|----------------------------------|--------------------------------------|
|                   | Wet granulation<br>Intragranular  | Wet granulation<br>Extragranular | Wet granulation<br>50:50 Intra:Extra |
| 3 (t 85 %)        | 30.25 $\pm$ 2.8284                | 28.10 $\pm$ 1.2727               | 25.25 $\pm$ 1.4142                   |
| 10 (t 70 %)       | 7.20 $\pm$ 1.1313                 | 4.10 $\pm$ 2.8284                | 12.25 $\pm$ 1.0606                   |
| 17 (t 65 %)       | 14.10 $\pm$ 2.6870                | 12.20 $\pm$ 2.8284               | 8.45 $\pm$ 1.5556                    |

## VITA

Flight Lieutenant Thavisak Teruya was born on November 15, 1952. He got his degree in Bachelor of Pharmacy in 1976 from Faculty of Pharmacy, Chiangmai University. During 1976-1979, he was an instructor in the Department of Manufacturing Pharmacy, Faculty of Pharmacy, Chiangmai University. Since 1979, he has worked in Division of Pharmaceutical Analysis and Research, Department of Medical Supplies, Directorate of Medical Services, Royal Thai Air Force.



ศูนย์วิทยทรัพยากร  
จุฬาลงกรณ์มหาวิทยาลัย