

REFERENCES

- A.A.Davydov., M.L. Shepotko., and A.A. Budneva., "Basic Sites on the Oxide Surfaces: Their Effect on the Catalytic Methane Coupling", *Catalysis Today*. **24**(1995):225.
- A. Matsumoto., T. Kitajima., and K. Tsutsumi., "Adsorption Characteristics and Polymerization of Pyrrole on Y-zeolites", *Langmuir*. **15**(1999):7626.
- A. Zecchina., C. Lamberti., and S. Bordiga., "Surface acidity and basicity: General concepts", *Catalysis Today*. **41**(1998):169.
- C. Binet., A. Jadi., J. Lamotte., and J. C. Lavelley., "Use of Pyrrole as an IR Spectroscopic Molecular Probe in a Surface Basicity Study of Metal Oxides", *J. Chem. Soc., Faraday Trans.* **92**(1996):123.
- C. Yang., J. Wang., and Q. Xu., "Aluminated Zeolites β and their Properties II. Basicities of Aluminated Zeolites β : An FTIR Study of Chemisorbed Pyrrole", *Microporous Material*. **11**(1997):261.
- D. Murphy., P. Massiani., R. Frank., and D. Barthomeuf., "Basic Sites Heterogeneity and Location in Alkali Cation Exchanged EMT Zeolite. An IR Study Using Adsorbed Pyrrole", *J. Phys chem*. **100**(1996):6731.
- J. C. Lavelley., "Infrared Spectrometric Studies of the Surface Basicity of Metal Oxides and Zeolites Using Adsorbed Probe Molecules", *Catalysis Today*. **27** (1996):377.
- J. Xie., M. Huang., and S. Kaliaguine., "Base and acid sites in alkaline earth cation-exchanged X zeolites", *Catalysis letters*. **29**(1994):281.
- L.M. Kustov., "New Trends in IR-Spectroscopic Characterization of Acid and Basic Sites in Zeolites and Oxide Catalysts", *Topics in Catalysis*. **4**(1997):131.
- M. Huang., and S. Kaliaguine., "Zeolite Basicity Characterized by Pyrrole Chemisorption: An Infrared Study", *J. Chem. Soc., Faraday Trans.* **88** (1992):751.
- P. Kaßner., and M. Baerns., "Comparative Characterization of Basicity and Acidity of Metal Oxide Catalysts for the Oxidative Coupling of Methane by Different Methods", *Applied Catalysis A: General*. **139**(1996):107.

P.O. Scokart., and P.G.Rouxhet., "Characterization of the Basicity of Oxides through the Infrared Study of Pyrrole Adsorption", *J.C.S. Faraday Trans.* **76** (1980):1476.

S. Scire., C. Crisafulli., R. Maggiore., S. Minico., and S. Galvagno., "Effect of the Acid-Base Properties of Pd-Ca/Al₂O₃ Catalysts on the Selective Hydrogenation of Phenol to Cyclohexanone: FT-IR and TPD Characterization", *Applied Surface Science.* **136**(1998):311.

APPENDIX

APPENDIX

GAS CHROMATOGRAPH

A1 Operating condition

Flame ionization detector gas chromatograph model 9A and Thermal conductivity detector gas chromatograph model 8A were used to analyze the amount of pyrrole and carbondioxide adsorption, respectively.

The operating conditions for gas chromatograph are described below:

GC model	Shimadzu GC-9A	Shimadzu GC-8A
Detector	FID	TCD
Nitrogen flow rate	30 ml/min	-
Helium flow rate	-	30 ml/min
Column temperature	70°C	70°C
Injection temperature	140°C	90°C
Detector temperature	140°C	90°C

A2 Calibration curve

The calibration curves of pyrrole and carbondioxide are presented in the following figures.




Figure A1 The calibration curve of pyrrole




Figure A2 The calibration curve of carbondioxide

VITA

Miss Jeeraporn Jantharasorn was born in Chonburi on April 10, 1975. She received the Bachelor degree of Science from the Department of Chemistry, Faculty of Science, King Monkut's Institute of Technology Ladkrabang in 1997.

