

**FACTORS AFFECTING TRANSESTERIFICATION OF PALM OIL INTO  
BIODIESEL IN THE PRESENCE OF NaOH AND ZrO<sub>2</sub>**



Rujirat Longloilert

A Thesis Submitted in Partial Fulfilment of the Requirements  
for the Degree of Master of Science  
The Petroleum and Petrochemical College, Chulalongkorn University  
in Academic Partnership with  
The University of Michigan, The University of Oklahoma,  
and Case Western Reserve University

2008

512030

**Thesis Title:** Factors Affecting Transesterification of Palm Oil into Biodiesel in the Presence of NaOH and ZrO<sub>2</sub>  
**By:** Ms. Rujirat Longloilert  
**Program:** Polymer Science  
**Thesis Advisors:** Assoc. Prof. Sujitra Wongkasemjit  
Asst. Prof. Apanee Leungnaruemitchai  
Assoc. Prof. Somchai Pengprecha

---

Accepted by the Petroleum and Petrochemical College, Chulalongkorn University, in partial fulfilment of the requirements for the Degree of Master of Science.

**Thesis Committee:**

..... *Nantaya Yanumet* ..... College Director  
(Assoq. Prof. Nantaya Yanumet)

..... *Sujitra Wongkasemjit* .....  
(Assoc. Prof. Sujitra Wongkasemjit)

..... *Apanee Leungnaruemitchai* .....  
(Asst. Prof. Apanee Leungnaruemitchai)

..... *Somchai Pengprecha* .....  
(Assoc. Prof. Somchai Pengprecha)

..... *Anuvat Sirivat* .....  
(Assoc. Prof. Anuvat Sirivat)

..... *B. Kimm* .....  
(Assist. Prof. Bussarin Ksapabutr)

## ABSTRACT

4972027063: Polymer Science Program

Rujirat Longloilert: Factors Affecting Transesterification of Palm Oil into Biodiesel in the Presence of NaOH and ZrO<sub>2</sub>.

Thesis Advisors: Assoc. Prof. Sujitra Wongkasemjit, Asst. Prof.

Apanee Leungnaruemitchai, and Assoc. Prof. Somchai Pengprecha

38 pp.

Keywords: Biodiesel/ Transesterification/ Heterogeneous catalyst/ Zirconia/ NaOH

In this study, a basic heterogeneous catalyst, NaOH/ZrO<sub>2</sub>, was used for the transesterification of palm oil into biodiesel. To determine the optimum condition for producing biodiesel, many parameters were investigated, including %NaOH loaded on zirconia support, amount of catalyst, reaction time, methanol to oil ratio, reaction temperature, and calcination temperature of the catalyst. The results showed that 91% of %conversion can be obtained by the transesterification of palm oil using 1% NaOH in methanol loaded on zirconia as heterogeneous catalyst. The optimal conditions were to use 1:15 molar ratio of oil to methanol with the addition of 3% catalyst, and heating for 90 min at 70°C. The fatty acid methyl ester product was analyzed its content using gas chromatography, as followed EN 14103, and found around 92%. The biodiesel obtained was investigated its properties, and found 0.23% linolenic acid methyl ester; 4.54 cSt of kinematic viscosity; 182±2°C flash point, and 40858±199.50 kJ/kg heating value. Furthermore, the preliminary study of re-used catalyst indicated that the used NaOH/ZrO<sub>2</sub> catalyst could not be directly reused for transesterification reaction without further treatment. However, it could be easily regenerated and resulted in the same activity as the fresh catalyst.

## บทคัดย่อ

นางสาวรุจิรัตน์ ล่องลอยเลิศ : ปัจจัยที่มีผลต่อการเกิดปฏิกิริยาทรานเอสเทอร์ริฟิเคชันของน้ำมันปาล์มไปเป็นไบโอดีเซล ที่มีโซเดียมไฮดรอกไซด์และเซอร์โคเนีย (Factors Affecting Transesterification of Palm Oil into Biodiesel in the Presence of NaOH and ZrO<sub>2</sub>) อ. ที่ปรึกษา: รศ.ดร.สุจิตรา วงศ์เกษมจิตต์, ผศ.ดร.อาภาณี เหลืองนฤมิตชัย และ รศ.ดร.สมใจ เฟื่องปรีชา 38 หน้า

ในงานวิจัยนี้ได้นำ NaOH/ZrO<sub>2</sub> ซึ่งเป็นตัวเร่งปฏิกิริยาวิวิธพันธุ์ชนิดเบสมาใช้ในการเร่งปฏิกิริยาทรานเอสเทอร์ริฟิเคชันของน้ำมันปาล์มเพื่อเปลี่ยนให้เป็นไบโอดีเซล ในการหาสภาวะที่เหมาะสมสำหรับการผลิตไบโอดีเซล ตัวแปรที่ถูกนำมาศึกษาได้แก่ ปริมาณโซเดียมไฮดรอกไซด์ที่เติมลงไปบนตัวรองรับเซอร์โคเนีย, ปริมาณตัวเร่งปฏิกิริยาที่ใช้, เวลาที่ใช้ในการทำปฏิกิริยา, อัตราส่วนระหว่างเมทานอลและน้ำมัน, อุณหภูมิที่ใช้ในการเกิดปฏิกิริยา และ อุณหภูมิที่ใช้ในการเผาตัวเร่งปฏิกิริยา จากผลการทดลองพบว่าเมื่อใช้โซเดียมไฮดรอกไซด์ 1% ในเมทานอล เติมลงไปในตัวรองรับเซอร์โคเนีย ในสภาวะที่มีอัตราส่วนระหว่างน้ำมันและเมทานอลเท่ากับ 1:15, ปริมาณตัวเร่ง 0.75 กรัม ณ อุณหภูมิ 70 องศาเซลเซียส เป็นเวลานาน 90 นาที ให้ผลของการเปลี่ยนน้ำมันปาล์มไปเป็นไบโอดีเซลร้อยละ 91 ปริมาณเอสเทอร์ของน้ำมันปาล์มซึ่งตรวจวัดได้จากเทคนิคแก๊สโครมาโตกราฟี ตามมาตรฐาน EN 14103 มีค่าประมาณ 92% เมื่อนำไบโอดีเซลที่สังเคราะห์ได้ไปทดสอบคุณสมบัติบางประการพบว่า มีกรดไลโนเลนิกเมทิลเอสเทอร์ 0.23%, ค่าความหนืด 4.54 cSt, จุดวาบไฟ 182±2°C และค่าพลังงานความร้อนเท่ากับ 40858±199.50 kJ/kg นอกจากนี้งานวิจัยนี้ยังได้ศึกษาการนำ NaOH/ZrO<sub>2</sub> ที่ใช้แล้วกลับมาใช้ใหม่ ซึ่งพบว่า NaOH/ZrO<sub>2</sub> ที่ใช้แล้วโดยไม่ได้ผ่านกระบวนการใดๆ ไม่สามารถใช้เร่งปฏิกิริยาทรานเอสเทอร์ริฟิเคชันได้ อย่างไรก็ตาม เมื่อนำ NaOH/ZrO<sub>2</sub> ที่ใช้แล้วมาผ่านการบำบัดสามารถนำกลับมาใช้เร่งปฏิกิริยาดังกล่าวได้ผลเป็นอย่างดี

## ACKNOWLEDGEMENTS

I am grateful for the partial scholarship and partial funding of the thesis work provided by the Postgraduate Education and Research Programs in Petroleum and Petrochemical Technology (PPT Consortium); the Ratchadapisek Sompote Fund, Chulalongkorn University, the Petroleum and Petrochemical College; and the National Excellence Center for Petrochemicals and Advanced Materials, Thailand.

I wish to express special thanks to my advisor and co advisors, Assoc Prof. Sujitra Wongkasemjit, Asst. Prof. Apanee Leungnaruemitchai and Assoc. Prof. Somchai Pengprecha. Furthermore, I would like to thank you all of the members in my research group for their kindness, cheerfulness, suggestions, encouragement and friendly assistance. I had the most enjoyable time working with all of them. Finally, I am deeply indebted to my parents for their true love, support and understanding through my whole life.

## TABLE OF CONTENTS

	<b>PAGE</b>
Title Page	i
Abstract (in English)	iii
Abstract (in Thai)	iv
Acknowledgements	v
Table of Contents	vi
List of Tables	viii
List of Figures	ix
 <b>CHAPTER</b>	
<b>I INTRODUCTION</b>	<b>1</b>
 <b>II LITERATURE REVIEW</b>	 <b>3</b>
 <b>III EXPERIMENTAL</b>	 <b>11</b>
3.1 Materials	11
3.2 Instruments	
3.3 Methodology	11
3.3.1 Preparation of NaOH/ZrO <sub>2</sub> catalyst	11
3.3.2 Catalyst characterization	12
3.3.3 Transesterification of palm oil using heterogeneous catalyst	12
3.3.3 Biodiesel analysis	15
 <b>IV RESULTS AND DISCUSSION</b>	 <b>17</b>
4.1 Catalyst characterization	17
4.2 Transesterification of palm oil	20
4.2.1 Effect of NaOH concentration	20
4.2.2 Effect of catalyst amount	21

4.2.3	Effect of reaction time	22
4.2.4	Effect of molar ratio of methanol to oil	23
4.2.5	Effect of reaction temperature	24
4.2.6	Effect of calcination temperature	25
4.2.7	Reused catalyst	26
4.3	Properties of biodiesel	27
<b>V</b>	<b>CONCLUSIONS AND RECOMENDATIONS</b>	<b>28</b>
	<b>REFERENCES</b>	<b>29</b>
	<b>APPENDICES</b>	<b>32</b>
<b>Appendix A</b>	GC Chromatograms of samples	32
<b>Appendix B</b>	SEM-EDS of pure zirconia and 1%NaOH/ZrO <sub>2</sub>	36
<b>Appendix C</b>	Kinematic Viscosity of biodiesel	36
<b>Appendix D</b>	<sup>1</sup> H-NMR spectrum of sample at optimum condition	37
	<b>CURRICULUM VITAE</b>	<b>38</b>

**LIST OF TABLES**

<b>TABLE</b>		<b>PAGE</b>
2.1	Iodine values and main compositions of fatty acids in vegetable oils	4
2.2	Properties and heating values of vegetable oils	5
4.1	The surface area and the pore volume of pure zirconia and 1% NaOH (of methanol content) loaded on zirconia	20
4.2	Some standard specifications of biodiesel from the Ministry of Energy	27



## LIST OF FIGURES

FIGURE		PAGE
3.1	Experimental set up for the transesterification reaction	13
4.1	XRD patterns of zirconia calcined at 500°C for (a) pure zirconia, (b) 1% NaOH in methanol/zirconia, (c) used 1% NaOH in methanol/zirconia without calcination and (d) used 1% NaOH in methanol/ zirconia with calcination	18
4.2	XRD patterns of 1%NaOH in methanol supported on zirconia after calcining for 5 hour at various calcination temperatures for (a) 100°C, (b) 300°C, (c) 500°C, (d) 700°C and (e) 900°C	18
4.3	SEM micrograph of unloaded ZrO <sub>2</sub> calcined at 500°C	19
4.4	SEM micrographs of 1% NaOH in methanol/ZrO <sub>2</sub> calcined at 500°C with magnifications of (a) x350 and (b) x10000	19
4.5	Effect of NaOH concentration loaded on zirconia support on biodiesel yield using 5% catalyst/oil ratio, 18:1 methanol/oil molar ratio, 120 min reaction time and 70°C temperature	21
4.6	Effect of the amount of 1%NaOH in methanol loaded on zirconia support on biodiesel yield using 18:1 methanol/oil molar ratio, 120 min reaction time and 70°C temperature	22
4.7	Effect of reaction time on biodiesel yield using 3% of 1% NaOH in methanol/ZrO <sub>2</sub> to oil mass ratio, 18:1 methanol/oil molar ratio, and 70°C temperature	23

<b>FIGURE</b>		<b>PAGE</b>
4.8	Effect of methanol to oil ratio on biodiesel yield using 3% of 1% NaOH in methanol/ZrO <sub>2</sub> to oil mass ratio, 90 min reaction time and 70°C temperature	24
4.9	Effect of temperature on biodiesel yield using 3% of 1% NaOH in methanol/ZrO <sub>2</sub> of methanol content to oil mass ratio, 90 min reaction time, 15:1 methanol/oil molar ratio	25
4.10	Effect of calcination temperature on biodiesel yield using 3% of 1% NaOH in methanol/ZrO <sub>2</sub> to oil mass ratio, 90 min reaction time, 70°C temperature, 15:1 methanol/oil molar ratio	26