CATALYST DEVELOPMENT FOR POLYETHYLENE SYNTHESIS: EFFECT OF CHLORINATED COMPOUNDS ON ZIEGLER CATALYST.

Mr. Niwat Athiwattananont

A Thesis Submitted in Partial Fulfillment of the Requirements
for the Degree of Master of Science

The Petroleum and Petrochemical College, Chulalongkorn University
in Academic Partnership with

The University of Michigan, The University of Oklahoma
and Case Western Reserve University

1998

ISBN 974-638-468-6

Thesis Title : Catalyst Development for Polyethylene Synthesis:

Effect of Chlorinated Compounds on Ziegler Catalyst.

By : Mr. Niwat Athiwattananont

Program: Petrochemical Technology

Thesis Advisors : Assoc. Prof. Richard Mallinson

Prof. Somchai Osuwan

Dr. Rathanawan Magaraphan

Dr. Suracha Udomsak

Accepted by the Petroleum and Petrochemical College, Chulalongkorn University, in partial fulfillment of the requirements for the Degree of Master of Science.

...... Director of the College

(Prof. Somchai Osuwan)

Thesis Committee

(Assoc. Prof. Richard Mallinson)

(Prof. Somchai Osuwan)

R Magaryohan

(Dr. Rathanawan Magaraphan)

(Dr. Suracha Udomsak)

ABSTRACT

##961012 : PETROCHEMICAL TECHNOLOGY PROGRAM

KEY WORDS: Ziegler-Natta / Polymerization / Ethylene / Catalyst / Chlorinated compound.

Niwat Athiwattananont: Catalyst Development for Polyethylene Synthesis: Effect of Chlorinated Compounds on Ziegler Catalyst. Thesis Advisors: Assoc. Prof. Richard Mallinson, Prof. Somchai Osuwan, Dr. Rathanawan Magaraphan, and Dr. Suracha Udomsak 60 pp., ISBN 974-638-468-6

The effects of chlorinated compounds on the activity and productivity of ethylene polymerization, with a MgCl₂-supported TiCl₄ catalyst activated by Al(C₂H₅)₃, have been investigated. Three types of chlorinated compound; chloroform (CHCl₃), 1,1,1-trichloroethane (CH₃CCl₃) and benzylchloride (C₆H₅CH₂Cl), were used as activators.

The intensity of the activating effect depends on type and amount of activator added. Addition of CHCl₃ or CH₃CCl₃ at an optimum ratio of activator per titanium leads to activity and productivity improvement. In contrast, addition of C₆H₅CH₂Cl shows slight decreases in activity.

Results suggest that the main role of halogenated molecules may be accounted for by their oxidizing character. It would allow re-oxidation of Ti(II) deactivated species into potentially active Ti(III) species. As a result, the activity of this catalytic system decays more slowly than without the addition of activator.

บทคัดย่อ

นิวัฒน์ อธิวัฒนานนท์ : การพัฒนาดัวเร่งปฏิกิริยาสำหรับการสังเคราะห์โพลิเอทที่ถิ่น: ศึกษาผลของสารประกอบคลอไรค์ค่อตัวเร่งปฏิกิริยาซิกเลอร์ (Catalyst Development for Polyethylene Synthesis : Effect of Chlorinated Compounds on Ziegler Catalyst) อ.ที่ปรึกษา : รศ. คร. ริชาร์ค มอลลินสัน (Assoc. Prof. Richard Mallinson) ศ. คร. สมชาย โอสุวรรณ คร. รัตนวรรณ มกรพันธุ์ และ คร. สุรชา อุคมศักดิ์ 60 หน้า ISBN 974-638-468-6

การวิจัยนี้ได้ศึกษาผลของสารประกอบคลอไรค์ต่อความว่องไวของปฏิกิริยา และผลิตผล ของการโพลิเมอไรซ์โพลิเอททีลืน ที่ใช้ตัวเร่งปฏิกิริยา TiCl4 ซับพอร์ทบน MgCl2 ซึ่งถูกทำให้ ว่องไวโคย Al(C₂H₅)₃ โดยใช้สารประกอบคลอไรค์ 3 ชนิคคือ คลอโรฟอร์ม (CHCl₃), 1,1,1-ไตรคลอโรอีเซน (CH₃CCl₃) และเบนซิลคลอไรค์ (C₆H₅CH₂Cl) เป็นสารกระคุ้น (activator)

ผลของการกระตุ้นจะมากหรือน้อยขึ้นอยู่กับชนิด และปริมาณของสารกระตุ้นที่เติมลงไป การเติม CHCl3 หรือ CH3CCl3 ที่อัตราส่วนระหว่างสารกระตุ้นกับตัวเร่งปฏิกิริยาในอัตราที่ พอเหมาะจะทำให้สามารถเพิ่มความว่องไวของปฏิกิริยา และเพิ่มผลิตผลได้ แต่ในทางกลับกัน การ เติม C6H5CH2Cl จะลดความว่องไวของปฏิกิริยาลง

จากผลการทคลองสรุปได้ว่าสาเหตุหลักเกิดจากกุณสมบัติการเป็นตัวออกซิไดซ์ (oxidizing character) ของสารประกอบคลอไรด์ที่ทำให้เกิดออกซิเดชันของ Ti(II) ซึ่งไม่ ว่องไว ไปเป็น Ti(III) ซึ่งว่องไว จากผลดังกล่าวความว่องไวของตัวเร่งปฏิกิริยาในระบบนี้จะลด ลงช้ากว่าในระบบที่ไม่เติมสารประกอบคลอไรด์

ACKNOWLEDGMENTS

It is a pleasure to acknowledge my sincere gratitude to my advisor, Associate Professor Richard Mallinson of the University of Oklahoma for his advice and constructive discussions.

Appreciation is also extended to my co-advisors, Professor Somchai Osuwan and Dr. Rathanawan Magaraphan of The Petroleum and Petrochemical College, Chulalongkorn University, for their kind assistance and cooperation.

I would like to thank Thai Polyethylene company for supporting me in providing all of raw materials and apparatus. I appreciate my colleagues at TPE, Mr. Cholanat Yanaranop who encouraged me to study Zigler-Natta catalyst and Dr. Suracha Udomsak for his help and many discussions about Ziegler-Natta catalysts.

Finally, I am deeply grateful to both family and friends for their moral support.

TABLE OF CONTENTS

			PA	GE
	Titl	e Page		i
	Abs	stract		iii
	Ack	nowled	gments	v
	List	es	viii	
	List of Figures			ix
CHAPTER				
I	INT	rodu	CTION	1
II	LITERATURE REVIEW			
	2.1	Backgr	round	3
	2.2	Titani	um-Aluminum Alkyl Catalyst	5
	2.3	Effect	of Cocatalyst	9
	2.4	Effect	of Temperature	12
	2.5	Mecha	anisms of Polymerization	14
	2.6	Activa	ation of Dead Centers by Chlorinated Compounds	18
III	EX	PERIM	ENTAL SECTION	
	3.1	Scope	of Research Work	19
	3.2	Exper	imental Plans	
		3.2.1	Fixed or controlled parameters	19
		3.2.2	Variable parameters	19
	3.3	Mater	ials	20

CHAPTER			PAGE
	3.4	Catalyst Preparation	21
	3.5	Catalyst Characterization	22
	3.6	Reactor System	22
	3.7	Polymerization Procedure	23
	3.8	Polymer Characterization	24
IV	RES	SULTS AND DISCUSSION	
	4.1	Kinetic Rate Time Profiles	25
	4.2	Effect of Chloroform (CHCl ₃)	29
	4.3	Effect of Trichloroethane (CH ₃ CCl ₃)	35
	4.4	Effect of Benzylchloride (C ₆ H ₅ CH ₂ Cl)	39
	4.5	Effect of Activator Additionime	43
	4.6	Effect of Type of Activator	46
	4.7	Polymer Characterization	46
v	COI	NCLUSIONS AND RECOMMENDATIONS	
	5.1	Conclusions	50
	5.2	Recommendations for Future Work	51
	REF	FERENCES	52
	APP	PENDIX	58
	CUI	RRICULUM VITAE	60

LIST OF TABLES

ΓABLE		PAGE
2.1	Early discoveries of low pressure linear polyethylene	6
2.2	Early supported catalysts	6
2.3	Magnesium hydroxychloride supported catalysts	8
2.4	Magnesium alkoxide based catalysts	8
2.5	Magnesium chloride based catalysts	8

LIST OF FIGURES

FIGURE		PAGE
2.1	The innovations in polyolefin technology	4
2.2	Effect of Al/Ti ratio on polymerization rate	10
2.3	Dependence of polymerization rate on Al/Ti ratio	11
2.4	Effect of temperature on polymerization rate	13
2.5	Titanium atom having an octahedral configuration	16
2.6	Proposed mechanism by Cossee	16
2.7	Molecular orbital overlap in the Cossee mechanism	17
2.8	Propose mechanism by Rodriguez and Van Looy	17
3.1	The schematic diagram of polymerization reactor system	23
4.1	Kinetic rate time profile	26
4.2	Effect of chloroform concentration on kinetic rate	
	time profile	30
4.3	Effect of chloroform concentration on average	
	polymerization rate	31
4.4	Effect of chloroform concentration on productivity	32
4.5	Effect of chloroform concentration on deactivation time	
	and initial rate of polymerization	34
4.6	Effect of trichloethane concentration on kinetic rate	
	time profile	36
4.7	Effect of trichloethane concentration on productivity	37
4.8	Effect of trichloethane concentration on deactivation time	
	and initial rate of polymerization	38
4.9	Effect of benzylchloride concentration on kinetic rate	
	time profile	40

49

FIGURE		PAGE
4.10	Effect of benzylchloride concentration on productivity	40
4.11	Effect of benzylchloride concentration on deactivation time	e
	and initial rate of polymerization	42
4.12	Effect of time activitor addition on kinetic rate time	
	profile	44
4.13	Effect of time of activitor addition on productivity	45
4.14	Effect of type of activator at optimum ratio on kinetic rate	
	time profile	47
4.15	Effect of type of activator on productivity	48
4 16	Effect of chloroform concentration on molecular weight	

distribution of polyethylene