

REFERENCES

- Alami, E., Almgren, M., and Brown, W. Interaction of hydrophobically end-capped poly(ethylene oxide) with nonionic surfactants in aqueous solution. Fluorescence and light scattering studies. Macromolecules 29 (1996): 5026-5035.
- Ananthapadmanabhan, K.P. In Interactions of surfactant with polymers and proteins; Goddard, E.D., and Ananthapadmanabhan, K.P., eds. Boca Raton: CRC Press, 1994.
- Brackman, J.C., and Engberts, J.B.F.N. Influence of polymers on the micellization of cetyltrimethylammonium salts. Langmuir 7 (1991): 2097-2102.
- Brackman, J.C., and Engberts, J.B.F.N. Effect of surfactant charge on polymer-micelle interaction: n-Dodecyldimethylamine. Langmuir 8 (1992): 434-422.
- Brackman, J.C., van Os, N.M., and Engberts, J.B.F.N. Polymer-nonionic micelle complexation. Formation of poly(propylene oxide)-complexed n-octyl thioglucoside micelles. Langmuir 4 (1988): 1266-1269.
- Brown, W., Fudin, J., and Miguel, M.G. Poly(ethylene oxide)-sodium dodecyl sulfate interactions studied using static and dynamic light scattering. Macromolecules 25 (1992): 7192-7198.
- Cabane, B. Structure of some polymer-detergent aggregates in water. J. Phys. Chem. 81 (1977): 1639-1645.

- Feitosa, E., Brown, W., and Hansson, P. Interactions between the non-ionic surfactant C₁₂E₅ and poly(ethylene oxide) studied using dynamic light scattering and fluorescence quenching. Macromolecules 29 (1996): 2169-2178.
- Fundin, J., and Brown, W. Polymer/surfactant interaction. Sodium poly (styrene sulfonate) and CTAB complex formation. Light scattering measurements in dilute aqueous solution. Macromolecules 27 (1994): 5024-5031.
- Goddard, E.D., and Anathapadmanabhan, K.P., eds. Interactions of surfactants with polymers and protein. Boca Raton, F.L.: CRC Press, 1993.
- Guido, S. Phase behavior of aqueous solutions of hydroxypropylcellulose. Macromolecules 28 (1995): 4530-4539.
- Guo, X.H. , et al. Small-angle neutron scattering study of the structure of the protein/detergent complexes. Biopolymer 29 (1990): 335.
- Hayakana, K., Kwak, J.C.T. Interactions between polymers and cationic surfactants. In Cationic surfactants: Physical chemistry; Rubingh, D.N., and Holland, P.M., eds. New York: Marcel Dekker, 1991.
- Holmberg, C., et al. Hydrodynamic and thermodynamic aspects of the SDS-EHEC-water system. J. Phys. Chem. 91 (1987): 871-876.
- Karlstrom, G. , Carlsson, A., and Lindman, B. Phase diagrams of nonionic polymer-water systems. Experimental and theoretical studies of the effect of surfactants and other cosolutes. J. Phys. Chem. 94 (1990): 5005-5015.
- Li, F., et al. Studies on cetyltrimethylammonium bromide (CTAB) micellar solution and CTAB reversed microemulsion by ESR and ²H NMR. Colloids Surfaces A: Physicochem. Eng. Aspects 127 (1997): 89-96.

- Lindman, B., and Thalberg, K. In Interaction of surfactants with polymers and proteins; Goddard, E.D., and Ananthapadmanabhan, K.P., eds. Boca Raton, F.L.: CRC Press, 1993.
- Moroi, Y.. et al. J. Colloid Interface Sci. 86 (1982): 282.
- Nagarajan, R. Thermodynamic of nonionic polymer-micelle association. Colloids and surfaces 13 (1985): 1-17.
- Nilsson, S. Interactions between water-soluble cellulose derivatives and surfactants. 1. The HPMC/SDS/water system. Macromolecules 28 (1995): 7837-7844.
- Porter, M.R. Handbook of surfactants. 2nd ed. London: Chapman & Hall, 1994.
- Rao, U.R.K., et al. Micellar chain model for the origin of the viscoelasticity in dilute surfactant solution. J. Phys. Chem. 91 (1987) : 3286-3291.
- Reekmans, S., et al. Micellar properties of aqueous solutions of hexadecyltrimethylammonium salts in the presence of nonionic polymer. Macromolecules 26 (1993): 687-694.
- Rosen, M.L. Surfactants and interfacial phenomena. 2nd ed. New York: John Wiley & Sons, 1989.
- Ruckenstein, E., Huber, G., and Hoffmann, H. Surfactant aggregation in the presence of polymers. Langmuir 3 (1987): 382-387.
- Saito, S. and Tsuchiya, T. Characteristics of n-octyl β-D-thioglucopyranoside, a new non-ionic detergent useful for membrane biochemistry. Biochem. J. 222 (1984): 829-832.
- Saito, S., and Tsuchiya, T. Synthesis of alkyl β-D-thioglucopyranoside, a series of new nonionic detergents. Chem. Pharm. Bull. 33 (1985): 503-508.
- Saito, S. Polymer-surfactant interactions. In nonionic surfactants:

- Schick, M.J., ed. New York: Marcel Dekker, 1987.
- Shiraha, K., Tsujii, K., and Takagi, T. Free boundary electrophoresis of sodium dodecylsulfate-protein polypeptide complexes with special reference to SDS-polyacrylamide gel electrophoresis. *J. Biochem.* 75 (1974): 309.
- Tamer, R.E., et al. Conformational change of protein-sodium dodecylsulfate complexes in solution: a study of dynamic light scattering. *J. Chem. Phys.* 76 (1982): 3866.
- Werbowyj, R.S. and Gray, D.G. Optical properties of (hydroxypropyl)cellulose liquid crystals. *Macromolecules* 17 (1984): 1512-1520.
- Winnik, F.M., et al. Interaction of hydroxypropylcellulose with aqueous surfactants: Fluorescence probe studies and look at pyrene-labeled polymer. *J. Phys. Chem.* 91 (1987): 594-597.
- Winnik, F.M. Interaction of fluorescent dye labeled (hydroxypropyl)cellulose with nonionic surfactant. *Langmuir* 6 (1990): 522-524.
- Winnik, F.M., and Regismond, S.T.A. Fluorescence methods in the study of the interactions of surfactants with polymers. *Colloids Surfaces A: Physicochem. Eng. Aspects* 118 (1996): 1-39.
- Wirick, M.G., Waldman, M.H. Some solution properties of fractionated water-soluble hydroxypropylcelulose. *J. Appl. Polym. Sci.* 14 (1970): 579-597.
- Witte, F.M., and Engberts, J.B.F.N. Micelle-polymer complexes: aggregation numbers, micellar rate effects and factors determining the complexation process. *Colloids Surf.* 36 (1989): 417.
- Young, R.J., and Lovell, P.A., eds. Introduction to polymers. 2nd ed. London: Chapman & Hall, 1991.

APPENDIX

A. Viscosity Measurements

The HPC/Water System

Table A1 Reduced viscosity, η_{sp}/c , as a function of total HPC concentration at 30 °C for the HPC/water system (Figure 3.1)

[HPC] (g/l)	η_{sp}/c (l/g)				Average	SD
	1	2	3	4		
0.5	0.1369	0.1370	0.1372	0.1391	0.1376	1.0408e-3
1.0	0.1365	0.1367	0.1311	0.1309	0.1338	3.2352e-3
1.5	0.1321	0.1317	0.1310	0.1300	0.1312	9.2014e-4
2.0	0.1364	0.1364	0.1376	0.1378	0.1371	7.5498e-4
2.5	0.1386	0.1391	0.1410	0.1409	0.1399	1.2302e-3
3.0	0.1406	0.1409	0.1423	0.1419	0.1414	8.0571e-4

Table A2 Inherent viscosity, $(\ln \eta_r)/c$, as a function of total HPC concentration at 30 °C for the HPC/water system (Figure 3.1)

[HPC] (g/l)	$(\ln \eta_r)/c$ (l/g)				Average	SD
	1	2	3	4		
0.5	0.1323	0.1325	0.1327	0.1347	0.1331	1.1121e-3
1.0	0.1280	0.1281	0.1232	0.1230	0.1256	2.8593e-3
1.5	0.1205	0.1202	0.1196	0.1188	0.1198	7.5000e-4
2.0	0.1206	0.1206	0.1216	0.1217	0.1211	6.0759e-4
2.5	0.1190	0.1194	0.1208	0.1207	0.1200	9.1059e-4
3.0	0.1173	0.1175	0.1185	0.1182	0.1178	6.4291e-4

Table A3 Relative viscosity, η_r , as a function of total HPC concentration at 30 °C for the HPC/water system (Figure 3.2)

[HPC] (g/l)	η_r		Average	SD
	1	2		
1.0	1.1360	1.1369	1.1365	6.3640e-4
2.0	1.2731	1.2726	1.2729	3.5355e-4
3.0	1.4242	1.4242	1.4242	0.0000
4.0	1.5886	1.5879	1.5883	4.9497e-7
5.0	1.7890	1.7894	1.7892	2.8284e-4
6.0	1.9814	1.9820	1.9817	4.2426e-4
7.0	2.1930	2.1933	2.1932	2.1213e-4
8.0	2.4216	2.4205	2.4211	7.7782e-4
9.0	2.6979	2.6981	2.6980	1.4142e-4
10.0	2.9656	2.9662	2.9662	8.4853e-4

The OTG/Water System

Table A4 Viscosity as a function of OTG solution at 30 °C for the OTG/water system (Figure 3.6)

[OTG] (mM)	Viscosity (cP)		Average	SD
	1	2		
0.060	0.8061	0.8058	0.8060	2.1213e-4
0.084	0.8060	0.8054	0.8057	4.2426e-4
0.204	0.8076	0.8082	0.8079	4.2426e-4
0.420	0.8113	0.8117	0.8115	2.8284e-4
1.020	0.7985	0.7991	0.7988	4.2426e-4
2.040	0.7964	0.7964	0.7964	0.0000
5.040	0.7985	0.7985	0.7985	0.0000
8.040	0.7995	0.8003	0.7999	5.6569e-4
10.20	0.8016	0.8012	0.8014	2.8284e-4
12.00	0.8041	0.8034	0.8038	4.9497e-4
16.20	0.8155	0.8144	0.8150	7.7782e-4
20.04	0.8322	0.8310	0.8316	8.4853e-4
30.00	0.8681	0.8687	0.8684	4.2426e-4

The CTAB/Water System

Table A5 Viscosity as a function of CTAB concentration at 30 °C for the CTAB/water system (Figure 3.9)

[CTAB] (mM)	Viscosity (cP)		Average	SD
	1	2		
0.80	0.8146	0.8152	0.8149	4.2426e-4
0.85	0.8160	0.8164	0.8162	2.8284e-4
0.90	0.8163	0.8161	0.8162	1.4142e-4
1.00	0.8163	0.8161	0.8162	1.4142e-4
1.50	0.8179	0.8178	0.8179	7.0711e-5
2.00	0.8202	0.8208	0.8205	4.2426e-4
2.50	0.8254	0.8258	0.8256	2.8284e-4
3.00	0.8262	0.8261	0.8262	7.0711e-5
3.50	0.8294	0.8288	0.8291	4.2426e-4
4.00	0.8334	0.8329	0.8332	3.5355e-4
5.00	0.8369	0.8366	0.8367	2.1213e-4
6.00	0.8423	0.8417	0.8420	4.2426e-4
7.00	0.8505	0.8500	0.8502	2.8284e-4
8.00	0.8512	0.8512	0.8512	0.0000
9.00	0.8550	0.8552	0.8551	1.4142e-4
10.00	0.8618	0.8613	0.8616	3.5355e-4

The HPC/OTG/Water System

Table A6 Specific viscosity, η_{sp} , as a function of total OTG concentration at 30 °C for the HPC/OTG/water system at the fixed HPC concentration of 5 g/l (Figure 3.11)

[OTG] (mM)	η_{sp}		Average	SD
	1	2		
0.00	0.7817	0.7822	0.7820	3.5355e-4
0.06	0.7721	0.7725	0.7723	2.8284e-4
0.08	0.7707	0.7724	0.7716	1.2021e-3
0.20	0.7654	0.7645	0.7649	6.3640e-4
0.42	0.7624	0.7601	0.7613	1.6263e-3
1.02	0.7602	0.7625	0.7613	1.6263e-3
2.04	0.7652	0.7644	0.7648	5.6569e-4
5.04	0.7709	0.7727	0.7718	1.2728e-3
8.04	0.7769	0.7782	0.7776	9.1924e-4
9.00	0.7671	0.7632	0.7652	2.7577e-3
10.20	0.7811	0.7819	0.7815	5.6569e-4
12.00	0.7914	0.7934	0.7924	1.4142e-3
16.20	0.8376	0.8387	0.8382	7.7782e-4
20.04	0.8666	0.8681	0.8674	1.0607e-3
27.00	0.8993	0.8996	0.8995	2.1213e-4
45.00	1.1110	1.1134	1.1122	1.6971e-3
63.00	1.3915	1.3938	1.3927	1.6263e-3

Table A7 Viscosity as a function of total OTG concentration at 30 °C for the HPC/OTG/water system at fixed HPC concentration of 5 g/l (Figure 3.12)

[OTG] (mM)	Viscosity (cP)		Average	SD
	1	2		
0.00	1.4508	1.4513	1.4511	3.5355e-4
0.06	1.4430	1.4434	1.4432	2.8284e-4
0.08	1.4419	1.4433	1.4426	9.8995e-4
0.20	1.4383	1.4369	1.4376	9.8995e-4
0.42	1.4351	1.4345	1.4318	4.2426e-4
1.02	1.4334	1.4353	1.4344	1.3435e-3
2.04	1.4374	1.4368	1.4371	4.2426e-4
5.04	1.4421	1.4436	1.4426	1.0607e-3
8.04	1.4469	1.4480	1.4475	7.7782e-4
9.00	1.4610	1.4578	1.4594	2.2627e-3
10.20	1.4504	1.4511	1.4508	4.9497e-4
12.00	1.4588	1.4604	1.4596	1.1311e-3
16.20	1.4964	1.4972	1.4968	5.6569e-4
20.04	1.5200	1.5212	1.5206	8.4853e-4
27.00	1.5706	1.5704	1.5705	1.4142e-3
45.00	1.7454	1.7473	1.7464	1.3435e-3
63.00	1.9773	1.9792	1.9783	1.3435e-3

The HPC/CTAB/Water System

Table A8 Specific viscosity, η_{sp} , as a function of total CTAB concentration at 30 °C for the HPC/CTAB/water system at the fixed HPC concentration of 1 g/l (Figure 3.20)

[CTAB] (mM)	[CTAB]/HPC]	η_{sp}		Average	SD
		1	2		
0.05	0.01822	0.0868	0.0871	0.0870	2.1213e-4
0.10	0.03645	0.0902	0.0899	0.0900	2.1213e-4
0.50	0.18223	0.0946	0.0942	0.0900	2.1213e-4
0.70	0.25512	0.0914	0.0916	0.0915	1.4141e-4
0.85	0.30979	0.0961	0.0962	0.0962	7.0711e-5
0.90	0.32801	0.0924	0.0917	0.0920	4.9497e-4
1.00	0.36446	0.0920	0.0917	0.0918	2.1213e-4
1.50	0.54669	0.0818	0.0813	0.0816	3.5355e-4
2.00	0.72892	0.0882	0.0886	0.0884	2.8284e-4
2.50	0.91115	0.0910	0.0923	0.0916	9.1924e-4
3.00	1.09338	0.1043	0.1046	0.1044	2.1213e-4
3.50	1.27561	0.1049	0.1064	0.1056	1.0607e-3
4.00	1.45784	0.1125	0.1097	0.1111	1.9799e-3
5.00	1.82230	0.1287	0.1261	0.1274	1.8385e-3
6.00	2.18676	0.1269	0.1282	0.1276	9.1924e-4
7.00	2.55080	0.1266	0.1274	0.1270	5.6568e-4
8.00	2.91568	0.1250	0.1227	0.1238	1.6263e-3
9.00	3.28014	0.1294	0.1294	0.1294	0.0000e0
10.00	3.64460	0.1357	0.1367	0.1362	7.0711e-4

Table A9 Specific viscosity, η_{sp} , as a function of total CTAB concentration at 30 °C for the HPC/CTAB/water system at the fixed HPC concentration of 2 g/l (Figure 3.20)

[CTAB] (mM)	[CTAB]/HPC]	η_{sp}		Average	SD
		1	2		
0.05	9.1115e-3	0.2420	0.2405	0.2412	1.0607e-3
0.10	0.01822	0.2423	0.2420	0.2422	2.1213e-4
0.50	0.09112	0.2456	0.2462	0.2459	4.2626e-4
0.70	0.12756	0.2728	0.2735	0.2732	4.9497e-4
0.80	0.14578	0.2844	0.2835	0.2840	6.3640e-4
0.85	0.15490	0.2927	0.2918	0.2922	6.3640e-4
0.90	0.16401	0.2975	0.2957	0.2966	1.2728e-4
1.00	0.18223	0.3071	0.3060	0.3066	7.7782e-4
1.50	0.27334	0.3124	0.3112	0.3118	8.4853e-4
2.00	0.36446	0.2875	0.2863	0.2869	8.4853e-4
2.50	0.45558	0.2618	0.2608	0.2613	7.0711e-4
3.00	0.54669	0.2502	0.2487	0.2494	1.0607e-3
3.50	0.63780	0.2401	0.2411	0.2406	7.0711e-4
4.00	0.72892	0.2388	0.2372	0.2380	1.1314e-3
5.00	0.91115	0.2468	0.2463	0.2466	3.5355e-4
6.00	1.09338	0.2463	0.2450	0.2456	9.1924e-4
7.00	1.27540	0.2566	0.2552	0.2559	9.8995e-4
8.00	1.45784	0.2718	0.2719	0.2718	7.0711e-5
9.00	1.64007	0.2902	0.2885	0.2894	1.2021e-3
10.00	1.82230	0.2793	0.2796	0.2794	2.1213e-4

Table A10 Specific viscosity, η_{sp} , as a function of total CTAB concentration at 30 °C for the HPC/CTAB/water system at the fixed HPC concentration of 3 g/l (Figure 3.20)

[CTAB] (mM)	[CTAB]/HPC]	η_{sp}		Average	SD
		1	2		
0.05	6.07433e-3	0.4255	0.4280	0.4268	1.7678e-3
0.10	0.01215	0.4185	0.4196	0.4190	7.7782e-4
0.50	0.06074	0.4404	0.4406	0.4405	1.4142e-4
0.70	0.08504	0.4860	0.4860	0.4860	0.0000e0
0.80	0.09719	0.5162	0.5153	0.5158	6.3640e-4
0.85	0.10326	0.5438	0.5435	0.5436	2.1213e-4
0.90	0.10934	0.5556	0.5548	0.5552	5.6568e-4
1.00	0.12149	0.5693	0.5695	0.5694	1.4442e-4
1.50	0.18223	0.5704	0.5692	0.5698	8.4853e-4
2.00	0.24297	0.5520	0.5507	0.5514	9.1924e-4
2.50	0.30372	0.5924	0.5924	0.5924	0.0000e0
3.00	0.36446	0.5530	0.5528	0.5529	1.4142e-4
3.50	0.42520	0.5290	0.5268	0.5279	1.5556e-3
4.00	0.48595	0.4909	0.4894	0.4902	1.0607e-3
5.00	0.60753	0.4457	0.4453	0.4455	2.8284e-4
6.00	0.72892	0.4262	0.4260	0.4261	1.4142e-4
7.00	0.85027	0.4063	0.4080	0.4072	1.2021e-3
8.00	0.97189	0.4147	0.4154	0.4151	4.9497e-4

Table A11 Specific viscosity, η_{sp} , as a function of total CTAB concentration at 30 °C for the HPC/CTAB/water system at the fixed HPC concentration of 4 g/l (Figure 3.20)

[CTAB] (mM)	[CTAB]/HPC]	η_{sp}		Average	SD
		1	2		
0.05	4.55558e-3	0.5715	0.5732	0.5724	1.2021e-3
0.10	9.11150e-3	0.5763	0.5756	0.5759	4.2426e-4
0.70	0.06378	0.6514	0.6524	0.6519	7.0711e-4
0.80	0.07289	0.6981	0.6971	0.6976	7.0711e-4
0.85	0.07745	0.7099	0.7103	0.7101	2.8284e-4
0.90	0.08200	0.7443	0.7432	0.7438	7.7782e-4
1.00	0.09112	0.7801	0.7798	0.7800	2.1213e-4
1.50	0.13667	0.9407	0.9418	0.9412	7.7782e-4
2.00	0.18223	1.0205	1.0203	1.0204	1.4142e-4
2.50	0.22779	1.0230	1.0235	1.0232	3.5355e-4
3.00	0.27334	0.9645	0.9643	0.9644	1.4142e-4
3.50	0.31890	0.9274	0.9582	0.9278	5.6568e-4
4.00	0.36446	0.8730	0.8707	0.8718	1.6263e-3
5.00	0.45558	0.8087	0.8093	0.8090	4.2426e-4
6.00	0.54669	0.6876	0.6867	0.6872	6.3640e-4
7.00	0.63770	0.6399	0.6396	0.6398	2.1213e-4
8.00	0.72892	0.6013	0.6002	0.6008	7.7782e-4
9.00	0.82004	0.5610	0.5603	0.5606	4.9497e-4
10.00	0.91115	0.5341	0.5350	0.5346	6.3640e-4

Table A12 Specific viscosity, η_{sp} , as a function of total CTAB concentration at 30 °C for the HPC/CTAB/water system at the fixed HPC concentration of 5 g/l (Figure 3.20)

[CTAB] (mM)	[CTAB]/HPC]	η_{sp}		Average	SD
		1	2		
0.05	3.6446e-3	0.7405	0.7430	0.7418	1.7678e-3
0.10	7.2892e-3	0.7511	0.7509	0.7510	1.4142e-4
0.50	0.03645	0.7845	0.7812	0.7828	2.3334e-3
0.70	0.05102	0.8692	0.8695	0.8694	2.1213e-4
0.80	0.05831	0.9324	0.9334	0.9329	7.0711e-4
0.85	0.03195	0.9440	0.9433	0.9436	4.9497e-4
0.90	0.06560	1.0376	1.0392	1.0384	1.1314e-3
1.00	0.07289	1.0266	1.0236	1.0251	2.1213e-3
1.50	0.10934	1.2919	1.2909	1.2914	7.0711e-4
2.00	0.14578	1.4381	1.4377	1.4379	2.8284e-4
2.50	0.18223	1.5108	1.5093	1.5100	1.0607e-3
3.00	0.21868	1.4962	1.4984	1.4973	1.5556e-3
3.50	0.25512	1.4674	1.4706	1.4690	2.2627e-3
4.00	0.29157	1.3976	1.3973	1.3974	1.9092e-3
5.00	0.36446	1.2893	1.2920	1.2906	1.9092e-3
6.00	0.43735	1.1367	1.1368	1.1367	7.0711e-3
7.00	0.51016	1.0821	1.0812	1.0816	6.3640e-4
8.00	0.58314	0.9516	0.9521	0.9518	3.5355e-4
9.00	0.65603	0.8559	0.8540	0.8550	1.3435e-3

Table A13 Viscosity as a function of total CTAB concentration at 30 °C for the HPC/CTAB/water system at the fixed HPC concentration of 1 g/l

[CTAB] (mM)	[CTAB]/HPC]	Viscosity (cP)		Average	SD
		1	2		
0.05	0.01822	0.9145	0.9148	0.9146	2.1213e-4
0.10	0.03645	0.9173	0.9171	0.9172	1.4142e-4
0.50	0.18223	0.9210	0.9207	0.9208	2.1213e-4
0.70	0.25512	0.9184	0.9185	0.9184	7.0711e-5
0.85	0.30979	0.9223	0.9224	0.9224	7.0711e-5
0.90	0.32801	0.9194	0.9193	0.9194	7.0711e-5
1.00	0.36446	0.9188	0.9187	0.9188	7.0711e-5
1.50	0.54669	0.9102	0.9098	0.9100	2.8284e-4
2.00	0.72892	0.9157	0.9161	0.9159	2.8284e-4
2.50	0.91115	0.9210	0.9191	0.9200	1.3435e-3
3.00	1.09338	0.9293	0.9295	0.9294	7.0711e-5
3.50	1.27561	0.9296	0.9310	0.9303	9.8995e-4
4.00	1.45784	0.9361	0.9338	0.9349	1.6263e-3
5.00	1.82230	0.9498	0.9476	0.9487	1.5556e-3
6.00	2.18676	0.9483	0.9493	0.9488	9.8826e-4
7.00	2.55080	0.9480	0.9487	0.9484	4.9497e-4
8.00	2.91568	0.9467	0.9447	0.9457	1.4142e-4
9.00	3.28014	0.9504	0.9503	0.9504	7.0711e-5
10.00	3.64460	0.9557	0.9565	0.9561	5.6568e-4

Table A14 Viscosity as a function of total CTAB concentration at 30 °C for the HPC/CTAB/water system at the fixed HPC concentration of 2 g/l

[CTAB] (mM)	[CTAB]/HPC]	Viscosity (cP)		Average	SD
		1	2		
0.05	9.1115e-3	1.0318	1.0306	1.0312	8.4853e-4
0.10	0.01822	1.0321	1.0318	1.0320	2.1213e-4
0.50	0.09112	1.0348	1.0353	1.0350	3.5355e-4
0.70	0.12756	1.0574	1.0580	1.0577	4.2426e-4
0.80	0.14578	1.0670	1.0662	1.0666	5.6568e-4
0.85	0.15490	1.0740	1.0732	1.0736	5.6568e-4
0.90	0.16401	1.0779	1.0764	1.0772	1.0607e-3
1.00	0.18223	1.0859	1.0849	1.0854	7.0711e-4
1.50	0.27334	1.0903	1.0893	1.0898	7.0711e-4
2.00	0.36446	1.0696	1.0686	1.0691	7.0711e-4
2.50	0.45558	1.0482	1.0474	1.0478	5.6568e-4
3.00	0.54669	1.0386	1.0374	1.0380	8.4583e-4
3.50	0.63780	1.0302	1.0311	1.0306	6.3640e-4
4.00	0.72892	1.0292	1.0278	1.0280	9.8995e-4
5.00	0.91115	1.0358	1.0354	1.0356	2.8284e-4
6.00	1.09338	1.0354	1.0343	1.0348	7.7782e-4
7.00	1.27540	1.0439	1.0428	1.0434	7.7782e-4
8.00	1.45784	1.0565	1.0567	1.0566	1.4142e-4
9.00	1.64007	1.0718	1.0742	1.0730	1.6970e-3
10.00	1.82230	1.0628	1.0630	1.0629	1.4142e-4

Table A15 Viscosity as a function of total CTAB concentration at 30 °C for the HPC/CTAB/water system at the fixed HPC concentration of 3 g/l

[CTAB] (mM)	[CTAB]/HPC]	Viscosity (cP)		Average	SD
		1	2		
0.05	6.07433e-3	1.1576	1.1596	1.1586	1.4142e-3
0.10	0.01215	1.1519	1.1528	1.1523	6.3640e-4
0.50	0.06074	1.1697	1.1698	1.1698	7.0711e-5
0.70	0.08504	1.2067	1.2067	1.2067	0.0000e0
0.80	0.09719	1.2312	1.2305	1.2309	4.9497e-4
0.85	0.10326	1.2536	1.2534	1.2535	1.4142e-4
0.90	0.10934	1.2632	1.2626	1.2629	4.2426e-4
1.00	0.12149	1.2744	1.2745	1.2744	7.0711e-5
1.50	0.18223	1.2752	1.2742	1.2747	7.0711e-4
2.00	0.24297	1.2602	1.2592	1.2597	7.0711e-4
2.50	0.30372	1.2931	1.2931	1.2931	0.0000e0
3.00	0.36446	1.2610	1.2612	1.2611	1.4142e-4
3.50	0.42520	1.2416	1.2399	1.2408	1.2021e-3
4.00	0.48595	1.2107	1.2014	1.2111	4.9497e-4
5.00	0.60753	1.1739	1.1736	1.1737	2.1213e-4
6.00	0.72892	1.1581	1.1580	1.1580	7.0711e-5
7.00	0.85027	1.1420	1.1434	1.1427	9.8995e-4
8.00	0.97189	1.1488	1.1494	1.1491	4.2426e-4

Table A16 Viscosity as a function of total CTAB concentration at 30 °C for the HPC/CTAB/water system at the fixed HPC concentration of 4 g/l

[CTAB] (mM)	[CTAB]/HPC]	Viscosity (cP)		Average	SD
		1	2		
0.05	4.55558e-3	1.2915	1.2929	1.2922	9.8995e-4
0.10	9.11150e-3	1.2954	1.2949	1.2952	3.5355e-4
0.70	0.06378	1.3572	1.3580	1.3576	5.6568e-4
0.80	0.07289	1.3955	1.3947	1.3951	5.6568e-4
0.85	0.07745	1.4052	1.4056	1.4054	2.8284e-4
0.90	0.08200	1.4335	1.4326	1.4330	6.3640e-4
1.00	0.09112	1.4629	1.4627	1.4628	1.4142e-4
1.50	0.13667	1.5949	1.5958	1.5954	6.3640e-4
2.00	0.18223	1.6605	1.6604	1.6604	7.0711e-5
2.50	0.22779	1.6625	1.6630	1.6628	3.5355e-4
3.00	0.27334	1.6145	1.6143	1.6144	1.4142e-4
3.50	0.31890	1.5840	1.5846	1.5843	4.2426e-4
4.00	0.36446	1.5393	1.5374	1.5384	1.3435e-3
5.00	0.45558	1.4864	1.4870	1.4867	4.2426e-4
6.00	0.54669	1.3869	1.3862	1.3866	4.9497e-4
7.00	0.63770	1.3477	1.3475	1.3476	1.4142e-4
8.00	0.72892	1.3160	1.3151	1.3156	6.3640e-4
9.00	0.82004	1.2828	1.2823	1.2826	3.5355e-4
10.00	0.91115	1.2607	1.2615	1.2611	5.6568e-4

Table A17 Viscosity as a function of total CTAB concentration at 30 °C for the HPC/CTAB/water system at the fixed HPC concentration of 5 g/l

[CTAB] (mM)	[CTAB]/HPC]	Viscosity (cP)		Average	SD
		1	2		
0.05	3.6446e-3	1.4430	1.4450	1.4440	1.4142e-3
0.10	7.2892e-3	1.4518	1.4516	1.4517	1.4142e-4
0.50	0.03645	1.4768	1.4794	1.4781	1.8385e-3
0.70	0.05102	1.5497	1.5499	1.5198	1.4142e-4
0.80	0.05831	1.6021	1.6029	1.6025	5.6568e-4
0.85	0.03195	1.6117	1.6111	1.6114	4.2426e-4
0.90	0.06560	1.6893	1.6906	1.6900	9.1924e-4
1.00	0.07289	1.6801	1.6777	1.6789	1.6970e-3
1.50	0.10934	1.9001	1.8993	1.8997	5.6568e-4
2.00	0.14578	2.0214	2.0210	2.0212	2.8284e-4
2.50	0.18223	2.0815	2.0803	2.0809	8.4853e-4
3.00	0.21868	2.0695	2.0713	2.0704	1.2728e-3
3.50	0.25512	2.0456	2.0483	2.0470	1.9092e-3
4.00	0.29157	1.9877	1.9875	1.9876	1.4142e-4
5.00	0.36446	1.8979	1.9002	1.8990	1.6263e-3
6.00	0.43735	1.7714	1.7715	1.7714	7.0711e-5
7.00	0.51016	1.7262	1.7255	1.7258	4.9497e-4
8.00	0.58314	1.6180	1.6184	1.6182	2.8284e-4
9.00	0.65603	1.5386	1.5371	1.5378	1.0607e-3

Table A18 Interaction viscosity, η_I , and the ratio of $\eta_I/\eta_{I, \text{max}}$ as a function of total CTAB concentration for the HPC/CTAB/water system at the fixed HPC concentration of 2 g/l (Figure 3.22)

[CTAB] (mM)	η_I		Average	SD	$\eta_I/\eta_{I, \text{max.}}$		Average	SD
	1	2			1	2		
0.05	-0.0007	-0.0019	0.0013	8.4853e-4	-0.0131	-0.0363	-0.0247	0.0164
0.10	-0.0004	-0.0007	-0.0005	2.1213e-4	-0.0075	-0.0134	-0.0104	4.1494e-3
0.50	0.0023	0.0028	0.0026	3.5355e-4	0.0431	0.0534	0.0483	7.3284e-3
0.70	0.0249	0.0255	0.0252	4.2426e-4	0.4663	0.4866	0.4765	0.0144
0.80	0.0345	0.0337	0.0341	5.6569e-4	0.6461	0.6431	0.6446	2.0772e-3
0.85	0.0415	0.0407	0.0411	5.6569e-4	0.7772	0.7767	0.7769	3.0830e-4
0.90	0.0454	0.0439	0.0447	1.0607e-3	0.8502	0.8378	0.8440	8.7688e-3
1.00	0.0534	0.0524	0.0529	7.0711e-4	1.0000	1.0000	1.0000	0.0000
1.50	0.0578	0.0568	0.0573	7.0711e-4	1.0824	1.0840	1.0832	1.1119e-3
2.00	0.0371	0.0361	0.0366	7.0711e-4	0.6948	0.6889	0.6918	4.1191e-3
2.50	0.0157	0.0149	0.0153	5.6569e-4	0.2941	0.2844	0.2892	6.8281e-3
3.00	0.0061	0.0049	0.0055	8.4853e-4	0.1142	0.0935	0.1039	0.0147
3.50	-0.0023	-0.0014	-0.0018	6.3640e-4	-0.0431	-0.0267	-0.0349	0.0116
4.00	-0.0033	-0.0047	-0.0040	9.8995e-4	-0.0618	-0.0897	-0.0757	0.0197
5.00	0.0033	0.0029	0.0031	2.8284e-4	0.0618	0.0553	0.0586	4.5638e-3
6.00	0.0029	0.0018	0.0024	7.7782e-4	0.0543	0.0344	0.0443	0.0141
7.00	0.0114	0.0103	0.0109	7.7782e-4	0.2135	0.1966	0.2050	0.0120
8.00	0.0240	0.0242	0.0241	1.4142e-4	0.4494	0.4618	0.4556	8.7638e-3
9.00	0.0393	0.0417	0.0405	1.6971e-3	0.7360	0.7958	0.7659	0.0423
10.00	0.0303	0.0305	0.0304	1.4142e-4	0.5674	0.5802	0.5747	0.0104

Table A19 Interaction viscosity, η_I , and the ratio of $\eta_I/\eta_{I, \text{max.}}$ as a function of total CTAB concentration for the HPC/CTAB/water system at the fixed HPC concentration of 3 g/l (Figure 3.22)

[CTAB] (mM)	η_I		Average	SD	$\eta_I/\eta_{I, \text{max.}}$		Average	SD
	1	2			1	2		
0.05	0.0062	0.0082	0.0072	1.4142e-3	0.0501	0.0668	0.0584	0.0118
0.10	0.0005	0.0014	0.0010	6.3640e-4	0.0040	0.0114	0.0077	5.2056e-3
0.50	0.0183	0.0184	0.0184	7.0711e-5	0.1478	0.1498	0.1488	1.4270e-3
0.70	0.0553	0.0553	0.0553	0.0000	0.4467	0.4503	0.4485	2.5721e-3
0.80	0.0798	0.0791	0.0795	4.9497e-4	0.6446	0.6441	0.6444	3.1907e-4
0.85	0.1022	0.1020	0.1021	1.4142e-4	0.8255	0.8306	0.8281	3.6019e-3
0.90	0.1118	0.1112	0.1115	4.2426e-4	0.9031	0.9055	0.9043	1.7451e-3
1.00	0.1230	0.1231	0.1230	7.0711e-5	0.9935	1.0024	0.9980	6.2968e-3
1.50	0.1238	0.1228	0.1233	7.0711e-4	1.0000	1.0000	1.0000	0.0000
2.00	0.1088	0.1078	0.1083	7.0711e-4	0.8788	0.8778	0.8783	6.9768e-4
2.50	0.1417	0.1417	0.1417	0.0000	1.1446	1.1539	1.1492	6.5908e-3
3.00	0.1098	0.1096	0.1097	1.4142e-4	0.8869	0.8925	0.8897	3.9554e-3
3.50	0.0902	0.0885	0.0894	1.2021e-3	0.7286	0.7207	0.7246	1.7451e-3
4.00	0.0593	0.0600	0.0597	4.9497e-4	0.4790	0.4886	0.4838	6.7889e-3
5.00	0.0225	0.0222	0.0224	2.1213e-4	0.1817	0.1808	0.1813	6.8094e-4
6.00	0.0067	0.0066	0.0066	7.0711e-5	0.0541	0.0537	0.0539	2.6419e-4
7.00	-0.0094	-0.0083	-0.0088	7.7782e-4	-0.0759	-0.0676	-0.0718	5.8968e-3
8.00	-0.0026	-0.0020	0.0023	4.2426e-4	-0.0210	-0.0163	-0.0186	3.3340e-3

Table A20 Interaction viscosity, η_I , and the ratio of $\eta_I/\eta_{I, \text{max.}}$ as a function of total CTAB concentration for the HPC/CTAB/water system at the fixed HPC concentration of 4 g/l (Figure 3.22)

[CTAB] (mM)	η_I		Average	SD	$\eta_I/\eta_{I, \text{max.}}$		Average	SD
	1	2			1	2		
0.05	0.0019	0.0033	0.0026	9.8995e-4	0.0051	0.0089	0.0070	2.6707e-3
0.10	0.0058	0.0053	0.0056	3.5355e-4	0.01563	0.0143	0.0150	9.5051e-4
0.70	0.0676	0.0684	0.0680	5.6569e-4	0.1822	0.1845	0.1834	1.5603e-3
0.80	0.1059	0.1051	0.1055	5.6569e-4	0.2855	0.2834	0.2845	1.4711e-3
0.85	0.1156	0.1160	0.1158	2.8284e-4	0.3117	0.3128	0.3123	8.2223e-4
0.90	0.1439	0.1430	0.1435	6.3640e-4	0.3880	0.3856	0.3868	1.6423e-3
1.00	0.1733	0.1731	0.1732	1.4142e-4	0.4672	0.4668	0.4670	2.9229e-4
1.50	0.3053	0.3062	0.3058	6.3640e-4	0.8231	0.8258	0.8245	1.8732e-3
2.00	0.3709	0.3708	0.3709	7.0711e-5	1.0000	1.0000	1.0000	0.0000
2.50	0.3729	0.3734	0.3732	3.5355e-4	1.0054	1.0070	1.0062	1.1452e-3
3.00	0.3249	0.3247	0.3248	1.4142e-4	0.8760	0.8757	0.8758	2.1435e-4
3.50	0.2944	0.2950	0.2947	4.2426e-4	0.7937	0.7956	0.7947	1.2956e-3
4.00	0.2497	0.2478	0.2488	1.3435e-3	0.6732	0.6683	0.6708	3.4949e-3
5.00	0.1968	0.1974	0.1971	4.2426e-4	0.5306	0.5324	0.5315	1.2454e-3
6.00	0.0973	0.0966	0.0970	4.9497e-4	0.2623	0.2605	0.2614	1.2849e-3
7.00	0.0581	0.0579	0.0580	1.4142e-4	0.1566	0.1561	0.1564	3.5152e-4
8.00	0.0264	0.0255	0.0260	6.3640e-4	0.0712	0.0688	0.0700	1.7027e-3
9.00	-0.0068	-0.0073	-0.0070	3.5355e-4	-0.0183	-0.0197	-0.0190	9.5698e-4
10.00	-0.0289	-0.0281	-0.0285	5.6569e-4	-0.0779	-0.0758	-0.0769	1.5107e-3

Table A21 Interaction viscosity, η_I , and the ratio of $\eta_I/\eta_{I, \text{max.}}$ as a function of total CTAB concentration for the HPC/CTAB/water system at the fixed HPC concentration of 5 g/l (Figure 3.22)

[CTAB] (mM)	η_I		Average	SD	$\eta_I/\eta_{I, \text{max.}}$		Average	SD
	1	2			1	2		
0.05	-0.0085	-0.0065	-0.0075	1.4142e-3	-0.0138	-0.0105	-0.0121	2.3100e-3
0.10	0.0003	0.0001	0.0002	1.4142e-4	0.0005	0.0002	0.0003	2.2917e-4
0.50	0.0279	0.0253	0.0268	1.8385e-3	0.0451	0.0408	0.0430	3.0590e-3
0.70	0.0982	0.0984	0.0983	1.4142e-4	0.1589	0.1588	0.1588	9.8136e-5
0.80	0.1506	0.1514	0.1510	5.6569e-4	0.2437	0.2443	0.2440	4.1226e-4
0.85	0.1602	0.1596	0.1599	4.2426e-4	0.2592	0.2575	0.2584	1.2168e-3
0.90	0.2378	0.2391	0.2385	9.1924e-4	0.3848	0.3858	0.3853	6.9294e-4
1.00	0.2286	0.2262	0.2274	1.6971e-3	0.3699	0.3650	0.3674	3.4977e-3
1.50	0.4486	0.4478	0.4482	5.6569e-4	0.7259	0.7225	0.7242	2.4033e-3
2.00	0.5699	0.5695	0.5697	2.8284e-4	0.9222	0.9188	0.9205	2.3501e-3
2.50	0.6300	0.6288	0.6294	8.4853e-4	1.0194	1.0140	1.0170	3.4625e-3
3.00	0.6180	0.6198	0.6189	1.2728e-3	1.0000	1.0000	1.0000	0.0000
3.50	0.5941	0.5968	0.5955	1.9092e-3	0.9613	0.9629	0.9621	1.1062e-3
4.00	0.5362	0.5360	0.5961	1.4142e-4	0.8676	0.8648	0.8662	2.0099e-3
5.00	0.4464	0.4487	0.4476	1.6263e-3	0.7223	0.7239	0.7231	1.1406e-3
6.00	0.3199	0.3200	0.3200	7.0711e-5	0.5176	0.5163	0.5170	9.4891e-4
7.00	0.2747	0.2740	0.2744	4.9497e-4	0.4445	0.4421	0.4433	1.7114e-3
8.00	0.1665	0.1669	0.1667	2.8284e-4	0.2694	0.2693	0.2693	9.6918e-5
9.00	0.0871	0.0856	0.0864	1.0607e-3	0.1409	0.1381	0.1395	2.0007e-3

Table A22 Specific viscosity, η_{sp} , as a function of total CTAB concentration at 30 °C at the fixed HPC concentration of 4 g/l and at the fixed NaCl concentration of 5 mM (Figure 3.19)

[CTAB] (mM)	[CTAB]/HPC]	η_{sp}		Average	SD
		1	2		
0.05	4.55558e-3	0.5535	0.5529	0.5532	4.2426e-4
0.10	9.11150e-3	0.5560	0.5571	0.5566	7.7782e-4
0.50	0.04556	0.6242	0.6232	0.6237	7.0711e-4
0.70	0.06378	0.6387	0.6392	0.6390	3.5355e-4
0.80	0.07289	0.6667	0.6677	0.6672	7.0711e-4
0.85	0.07745	0.6625	0.6619	0.6622	4.2426e-4
0.90	0.08200	0.6942	0.6952	0.6947	7.0711e-4
1.00	0.09112	0.6886	0.6883	0.6885	2.1213e-4
1.50	0.13667	0.7446	0.7442	0.7444	2.8284e-4
2.00	0.18223	0.7785	0.7795	0.7790	7.0711e-4
2.50	0.22779	0.7731	0.7740	0.7736	6.3640e-4
3.00	0.27334	0.7592	0.7589	0.7591	2.1213e-4
3.50	0.31890	0.7468	0.7469	0.7469	7.0711e-5
4.00	0.36446	0.6821	0.6808	0.6814	9.1924e-4
5.00	0.45558	0.6115	0.6126	0.6120	7.7782e-4
6.00	0.54669	0.5486	0.5481	0.5481	3.5355e-4
7.00	0.63770	0.5062	0.5072	0.5072	7.0711e-4
8.00	0.72892	0.4757	0.4765	0.4765	5.6569e-4
9.00	0.82004	0.4224	0.4200	0.4200	1.6971e-3
10.00	0.91115	0.3923	0.3907	0.3907	1.1314e-3

Table A23 Specific viscosity, η_{sp} , as a function of total CTAB concentration at 30 °C at the fixed HPC concentration of 4 g/l and at the fixed NaCl concentration of 20 mM (Figure 3.19)

[CTAB] (mM)	[CTAB]/HPC]	η_{sp}		Average	SD
		1	2		
0.05	4.55558e-3	0.5987	0.5976	0.5982	7.7782e-4
0.10	9.11150e-3	0.5987	0.5976	0.5982	7.7782e-4
0.50	0.04556	0.6090	0.6095	0.6093	3.5355e-4
0.70	0.06378	0.5856	0.5864	0.5860	5.6569e-4
0.80	0.07289	0.5882	0.5878	0.5880	2.8284e-4
0.85	0.07745	0.6060	0.6046	0.6053	9.8995e-4
0.90	0.08200	0.6174	0.6185	0.6180	7.7782e-4
1.00	0.09112	0.6188	0.6175	0.6182	9.1924e-4
1.50	0.13667	0.5621	0.5630	0.5626	6.3640e-4
2.00	0.18223	0.6007	0.6015	0.6011	5.6569e-4
2.50	0.22779	0.5970	0.5961	0.5965	6.3640e-4
3.00	0.27334	0.5951	0.5970	0.5961	1.3435e-3
3.50	0.31890	0.6198	0.6191	0.6194	4.9497e-4
4.00	0.36446	0.6411	0.6426	0.6418	1.0607e-3
5.00	0.45558	0.6038	0.6025	0.6032	9.1924e-4
6.00	0.54669	0.5435	0.5424	0.5430	7.7782e-4
7.00	0.63770	0.5344	0.5358	0.5351	9.8995e-4
8.00	0.72892	0.4456	0.4436	0.4446	1.4142e-3
9.00	0.82004	0.4050	0.4071	0.4061	1.4849e-3
10.00	0.91115	0.3871	0.3867	0.3869	2.8284e-4

B. Dynamic Light Scattering Measurements

The HPC/Water System

Table B1 Data for the HPC concentration of 1 g/l at various angles

Measurement 1:

Angle (degree)	Sample (μs)	Mean (nm)	Width	Z _{Ave} (nm)	Poly- dispersity	In Range	Merit	D _{app} (cm ² /s)
60	3.20	36.7	55.6	28.3	0.537	98.6	44.0	15.2e-8
	3.20	38.1	58.0	29.3	0.545	96.7	43.7	14.6e-8
	3.20	37.4	56.9	28.7	0.546	94.9	43.3	14.9e-8
	Average	37.4	56.8	28.8	0.543	96.7	43.7	14.9e-8
	SD	0.0000	0.7000	1.2014	0.5033	4.9329e-3	1.8502	0.3512
	75	2.00	35.2	52.2	27.5	0.509	95.3	44.3
Average	2.00	35.5	53.2	27.5	0.523	94.9	45.1	15.7e-8
	2.00	35.1	52.4	27.4	0.512	94.8	44.7	15.9e-8
	Average	2.00	35.3	52.6	27.5	0.515	95.0	44.7
	SD	0.0000	0.2082	0.5292	0.0577	7.3711e-3	0.2646	0.4000
	90	1.30	33.1	48.2	26.2	0.483	95.0	45.7
	Average	1.30	32.6	46.8	25.9	0.467	96.6	45.5
Average	1.30	33.0	47.8	26.2	0.478	96.5	45.7	16.9e-8
	1.30	32.9	47.6	26.1	0.476	96.0	45.6	16.9e-8
	SD	0.0000	0.2646	0.7211	0.1732	8.1854e-3	0.8963	0.1155
	105	1.00	31.3	43.2	25.5	0.424	96.7	43.6
	Average	1.00	31.3	44.5	25.1	0.458	96.7	43.1
	SD	0.0000	0.0000	0.6506	0.2000	0.0470	0.1155	0.2887

Measurement 2:

Angle (degree)	Sample (μs)	Mean (nm)	Width	Z _{Ave} (nm)	Poly- dispersity	In Range	Merit	D _{app} (cm ² /s)
60	2.80	34.2	50.3	26.3	0.496	95.7	37.8	16.3e-8
	2.80	33.5	48.5	26.6	0.477	93.3	39.1	16.6e-8
	2.80	34.9	51.9	27.2	0.513	94.2	40.8	16.0e-8
	Average	34.2	50.2	26.7	0.495	94.4	39.2	16.3e-7
	SD	0.0000	0.7000	1.7010	0.4583	0.0180	1.2124	1.5044
	75	1.80	31.9	45.1	25.7	0.448	95.8	43.1
Average	1.80	31.6	45.1	25.3	0.459	95.8	43.8	17.6e-8
	1.80	31.0	42.7	25.3	0.419	94.8	43.1	17.9e-8
	Average	31.5	44.3	25.4	0.442	95.5	43.3	17.6e-8
	SD	0.0000	0.4583	1.3856	0.2309	0.2070	0.5774	0.4041
	90	1.40	31.0	43.6	22.3	0.443	95.1	42.2
	Average	1.40	31.5	45.4	25.0	0.471	92.8	42.4
Average	1.40	31.4	44.6	25.2	0.452	95.2	42.4	17.7e-8
	1.40	31.3	44.5	24.2	0.455	94.4	42.3	17.8e-7
	SD	0.0000	0.2646	0.9018	1.6197	0.0143	1.3577	0.1155
	105	1.00	30.1	42.1	24.3	0.439	92.7	41.4
	Average	1.00	30.3	42.1	24.6	0.429	94.5	40.8
	SD	0.0000	0.2000	0.5196	0.1528	9.0185e-3	1.2877	0.4163




Figure B1 Plot of the apparent diffusion coefficient as a function of the scattering vector at 30 °C for the HPC/water system at the fixed HPC concentration of 1 g/l (a) measurement 1; (b) measurement 2.

Table B2 Data for the HPC concentration of 2 g/l at various angles

Measurement 1:

Angle (degree)	Sample (μs)	Mean (nm)	Width	Z_Ave (nm)	Poly- dispersity	In Range	Merit	D _{app} (cm ² /s)
60	2.80	30.7	43.6	24.6	0.455	97.9	49.5	18.1e-8
	2.80	30.9	44.0	24.8	0.455	97.6	48.8	18.0e-8
	2.80	30.8	43.5	24.7	0.449	97.5	48.1	18.1e-8
	Average	2.80	30.8	43.7	24.7	0.453	97.7	48.8
	SD	0.0000	0.1000	0.2646	0.1000	3.4641e-3	0.2082	0.7000
	75	1.70	29.5	41.4	23.8	0.439	98.3	46.0
Average	1.70	29.3	41.0	23.8	0.434	97.7	45.3	19.0e-8
	1.70	29.4	40.5	24.0	0.419	96.7	45.0	18.9e-8
	SD	0.0000	0.1000	0.4509	0.1155	0.0104	0.8083	0.5139
	90	1.20	28.2	38.9	23.3	0.412	98.1	44.4
	1.20	28.2	39.1	22.9	0.426	98.6	44.5	19.7e-8
	Average	1.20	28.8	39.5	23.5	0.416	98.8	46.9
105	1.20	28.5	39.2	23.2	0.418	98.5	45.3	19.6e-8
	SD	0.0000	0.4243	0.3055	0.3055	7.2111e-3	0.3606	1.4154
	0.90	27.5	36.4	22.8	0.383	97.6	44.6	20.3e-8
	0.90	27.5	25.9	23.2	0.395	97.9	44.5	20.2e-8
	0.90	27.3	36.1	22.7	0.377	98.1	44.6	20.4e-8
	Average	0.90	27.4	32.8	22.9	0.3850	97.9	44.5
SD	0.0000	0.1155	5.9775	0.2646	9.1652e-3	0.2517	0.0577	1.0000e-7

Measurement 2:




Figure B2 Plot of the apparent diffusion coefficient as a function of the scattering vector at 30 °C for the HPC/water system at the fixed HPC concentration of 2 g/l (a) measurement 1; (b) measurement 2.

Table B3 Data for the HPC concentration of 3 g/l at various angles**Measurement 1:**

Angle (degree)	Sample (μs)	Mean (nm)	Width	Z_Ave (nm)	Poly- dispersity	In Range	Merit	D _{app} (cm ² /s)
60	2.70	30.6	43.9	24.4	0.467	99.2	44.7	16.2e-8
	2.70	30.3	43.0	24.3	0.453	98.8	44.8	18.4e-8
	2.70	30.6	43.9	24.5	0.464	99.4	44.8	18.2e-8
	Average	2.70	30.5	43.6	0.461	99.1	44.8	17.6e-7
	SD	0.0000	0.1732	0.5196	0.1000	7.3711e-3	0.3055	0.0577
	75	1.70	29.2	41.5	23.4	0.453	99.8	45.1
Average	1.70	29.0	40.6	23.5	0.437	99.4	45.2	19.2e-8
	1.70	29.1	40.6	23.5	0.436	99.0	44.9	19.2e-8
	Average	1.70	29.1	40.9	23.5	0.442	99.4	45.1
	SD	0.0000	0.1000	0.5196	0.0577	9.5394e-3	0.4000	0.1528
	90	1.20	28.0	38.0	23.0	0.403	98.6	44.9
	Average	1.20	28.1	38.2	23.0	0.407	98.7	45.2
Average	1.20	28.2	38.4	23.1	0.409	98.4	45.5	19.8e-8
	SD	0.0000	0.1000	0.2000	0.0577	3.0551e-3	0.1523	0.3000
	105	0.90	27.3	37.0	22.5	0.402	98.7	45.4
	Average	0.90	27.6	37.6	22.7	0.408	98.8	45.5
	SD	0.0000	0.1000	0.276	0.0577	3.0551e-3	0.1523	0.3000
	105	0.90	27.6	37.8	22.6	0.413	98.8	46.0
Average	0.90	27.5	37.5	22.6	0.408	98.8	45.6	20.2e-8
	SD	0.0000	0.1732	0.4163	0.1000	5.5076e-3	0.5077	0.3215

Measurement 2:

Angle (degree)	Sample (μs)	Mean (nm)	Width	Z_Ave (nm)	Poly- dispersity	In Range	Merit	D _{app} (cm ² /s)
60	2.70	30.7	44.1	24.5	0.465	97.0	48.8	18.1e-8
	2.70	30.3	43.2	24.2	0.460	97.6	48.5	18.4e-8
	2.70	30.7	44.2	24.5	0.468	99.5	48.5	18.1e-8
	Average	2.70	30.6	43.8	0.464	98.0	48.6	18.2e-7
	SD	0.0000	0.2309	0.5508	0.1732	4.0415e-3	1.3051	0.1732
	75	1.70	29.5	41.5	23.8	0.443	99.1	47.3
Average	1.70	29.7	41.9	24.0	0.445	97.9	47.3	18.7e-8
	1.70	29.4	41.2	23.7	0.440	98.3	47.7	19.0e-8
	Average	1.70	29.5	41.5	0.443	98.6	47.4	1.8867e-7
	SD	0.0000	0.1528	0.3512	0.1528	2.5166e-3	0.6429	0.2309
	90	1.20	28.5	39.6	24.1	0.430	98.5	46.3
	Average	1.20	28.9	40.1	23.5	0.427	97.3	46.3
Average	1.20	28.7	40.3	23.2	0.440	98.9	46.0	19.4e-8
	SD	0.0000	0.2000	0.3606	0.4583	6.8069e-3	0.8327	0.1732
	105	0.90	28.0	38.2	23.0	0.409	99.2	49.8
	Average	0.90	28.0	37.9	24.2	0.401	98.8	50.0
	SD	0.0000	0.4041	1.3077	0.6658	0.0223	0.2646	0.2000
	105	0.90	28.7	40.3	23.1	0.443	99.3	50.2
Average	0.90	28.2	38.8	23.4	0.418	99.1	50.0	19.7e-7
	SD	0.0000	0.4041	1.3077	0.6658	0.0223	0.2646	0.2000




Figure B3 Plot of the apparent diffusion coefficient as a function of the scattering vector at 30 °C for the HPC/water system at the fixed HPC concentration of 3 g/l (a) measurement 1; (b) measurement 2.

Table B4 Data for the HPC concentration of 4 g/l at various angles

Measurement 1:

Angle (degree)	Sample (μs)	Mean (nm)	Width	Z _{Ave} (nm)	Poly- dispersity	In Range	Merit	D _{app} (cm ² /s)
60	2.60	32.8	48.5	25.7	0.504	94.5	53.3	17.0e-8
	2.60	33.0	48.4	25.9	0.494	95.2	53.5	16.9e-8
	2.60	32.6	47.8	25.6	0.495	98.6	53.9	17.1e-8
	Average	2.60	32.8	48.2	25.7	0.498	96.1	53.6
	SD	0.0000	0.2000	0.3786	0.1528	5.5076e-3	2.1932	0.3055
	75	1.70	31.3	45.1	24.9	0.472	96.7	53.9
Average	1.70	31.0	44.8	24.6	0.474	96.8	53.5	17.8e-8
	1.70	31.7	46.1	25.1	0.482	97.1	53.5	18.0e-8
	SD	0.0000	0.3512	0.6807	0.2517	5.2915e-3	0.2080	0.2309
	90	1.50	29.6	42.2	23.7	0.460	98.4	52.3
	1.50	29.5	41.2	23.9	0.434	99.2	52.1	18.9e-8
	Average	1.50	29.5	44.4	23.9	0.439	97.7	52.2
105	1.50	29.5	42.6	23.8	0.4443	98.4	52.2	18.9e-7
	SD	0.0000	0.0577	1.6371	0.1155	0.0138	0.7506	0.1000
	1.00	28.9	40.6	23.3	0.442	99.1	52.7	19.3e-8
	1.00	28.9	40.2	23.5	0.429	98.1	52.0	19.2e-8
	Average	1.00	28.6	39.7	23.2	0.428	99.8	51.8
	SD	0.0000	0.1732	0.4509	0.1528	7.8102e-3	0.8544	0.4726

Measurement 2:

Angle (degree)	Sample (μs)	Mean (nm)	Width	Z _{Ave} (nm)	Poly- dispersity	In Range	Merit	D _{app} (cm ² /s)	
Average	60	2.80	31.8	46.6	25.0	0.493	99.1	45.8	17.5e-8
		2.80	31.6	45.7	25.1	0.476	97.7	45.1	17.6e-8
		2.80	31.9	46.5	25.2	0.484	98.8	44.6	17.4e-8
		2.80	31.8	46.3	25.1	0.484	98.5	45.2	17.5e-8
	SD	0.0000	0.1528	0.4933	0.1000	8.5049e-3	0.7371	0.6028	1.0000e-9
	75	1.70	30.6	44.2	24.4	0.473	99.4	45.9	18.2e-8
Average		1.70	30.9	44.7	24.5	0.477	97.9	45.8	18.0e-8
		1.70	30.0	42.3	24.2	0.446	98.6	45.4	18.6e-8
		1.70	30.5	43.7	24.4	0.466	98.6	45.7	18.3e-7
	SD	0.0000	0.4583	1.2662	0.1528	0.0169	0.7506	0.2646	3.0551e-9
	90	1.20	29.4	41.2	23.8	0.438	97.9	45.2	18.9e-8
		1.20	29.7	42.1	23.3	0.451	98.4	45.5	18.8e-8
Average		1.20	29.5	41.7	23.7	0.448	99.2	45.1	18.9e-8
		1.20	29.5	41.7	23.6	0.446	98.5	45.3	18.9e-7
	SD	0.0000	0.1528	0.4509	0.2646	6.8069e-3	0.6557	0.2082	5.7735e-10
	105	1.00	28.7	40.1	23.2	0.434	98.7	45.3	19.4e-8
		1.00	28.6	39.5	23.3	0.423	99.0	45.2	19.5e-8
		1.00	28.8	40.2	23.4	0.432	98.4	45.9	19.3e-8
Average	1.00	28.8	39.9	23.3	0.430	98.7	45.5	19.4e-8	
	SD	0.0000	0.0707	0.3786	0.1000	5.8595e-3	0.3000	0.3786	1.0000e-9




Figure B4 Plot of the apparent diffusion coefficient as a function of the scattering vector at 30 °C for the HPC/water system at the fixed HPC concentration of 4 g/l (a) measurement; (b) measurement 2.

Table B5 Data for the HPC concentration of 5 g/l at various angles

Measurement 1:

Angle (degree)	Sample (μs)	Mean (nm)	Width	Z_Ave (nm)	Poly-dispersity	In Range	Merit	D _{app} (cm ² /s)
60	2.60	30.6	44.5	24.3	0.480	97.2	52.2	18.2e-8
	2.60	30.4	44.2	23.1	0.480	98.3	52.1	18.3e-8
	2.60	30.3	44.0	24.0	0.481	98.6	51.7	18.4e-8
	Average	30.4	44.2	23.8	0.480	98.0	52.0	18.3e-8
	SD	0.0000	0.1528	0.2517	0.6245	5.7735e-3	0.7371	0.2646
	75	1.60	29.6	52.4	23.6	0.464	97.9	52.0
Average	1.60	29.6	42.6	23.5	0.471	98.8	52.3	18.8e-8
	1.60	30.0	43.4	23.8	0.476	96.4	51.1	18.6e-8
	Average	29.7	46.1	23.6	0.468	97.7	51.8	18.7e-8
	SD	0.0000	0.2309	5.4418	0.1528	4.9497e-3	1.2124	0.6245
	90	1.20	28.4	39.6	23.0	0.433	99.3	52.0
	1.20	28.3	39.9	22.8	0.445	98.4	52.3	19.7e-8
Average	1.20	28.4	39.4	23.1	0.428	99.1	51.9	19.6e-8
	Average	28.4	39.6	23.0	0.435	98.9	52.1	19.6e-8
	SD	0.0000	0.0577	0.2517	0.1528	8.7369e-3	0.4726	0.2082
	105	0.90	28.0	38.7	22.8	0.423	99.4	52.6
	0.90	27.6	38.4	22.4	0.430	98.7	52.4	20.1e-8
	Average	27.6	38.1	22.5	0.421	98.9	52.5	20.1e-8
SD	0.90	27.7	38.4	22.6	0.425	99.0	52.5	20.0e-8
	0.0000	0.2309	0.3000	0.2082	4.7258e-3	0.3606	0.1000	1.1155e-9

Measurement 2:

Angle (degree)	Sample (μs)	Mean (nm)	Width	Z_Ave (nm)	Poly-dispersity	In Range	Merit	D _{app} (cm ² /s)
60	3.40	31.9	46.9	25.0	0.498	96.0	51.5	17.5e-8
	3.40	33.3	47.9	22.1	0.508	98.2	51.5	17.2e-8
	3.40	32.2	47.7	25.1	0.507	97.5	51.5	17.3e-8
	Average	32.5	47.5	24.1	0.504	97.2	51.5	17.3e-8
	SD	0.0000	0.7371	0.5292	1.7039	5.5076e-3	1.1240	0.0000
	75	1.70	31.7	46.9	24.8	0.506	96.5	53.0
Average	1.70	31.4	46.6	22.7	0.510	98.4	53.0	17.7e-8
	1.70	31.7	47.2	24.7	0.514	96.1	53.2	17.6e-8
	Average	31.6	24.1	24.1	0.510	97.0	53.1	17.7e-8
	SD	0.0000	0.1732	1.1846	1.1846	4.0000e-3	1.2288	0.1155
	90	1.20	30.0	43.5	23.6	0.485	96.9	51.8
	1.20	30.3	44.8	23.8	0.501	98.3	51.9	18.4e-8
Average	1.20	30.3	44.8	23.8	0.501	98.3	51.9	18.4e-8
	1.20	30.2	44.4	23.7	0.496	97.8	51.9	18.5e-8
	SD	0.0000	0.1732	0.7506	0.1155	9.2376e-3	0.8083	0.0577
	105	1.00	29.7	43.1	23.5	0.402	97.8	52.9
	1.00	29.4	42.1	23.5	0.465	97.8	53.1	18.9e-8
	Average	29.2	42.3	23.1	0.478	97.4	53.0	19.1e-8
SD	1.00	29.4	42.5	23.4	0.448	97.7	53.0	18.9e-7
	0.0000	0.2517	0.5292	0.2309	0.0406	0.2369	0.1000	2.0000e-9




Figure B5 Plot of the apparent diffusion coefficient as a function of the scattering vector at 30 °C for the HPC/water system at the fixed HPC concentration of 5 g/l (a) measurement 1; (b) measurement 2.

Table B6 The center of mass diffusion coefficient (D_c) as a function of HPC concentration at 30 °C for the HPC/water system.

[HPC] (g/l)	D_c (cm ² /s)		Average	SD
	1	2		
1.0	1.2965e-7	1.5235e-7	1.4100e-7	1.6055e-8
2.0	1.6731e-7	1.6322e-7	1.6527e-7	2.8921e-9
3.0	1.7115e-7	1.7280e-7	1.7197e-7	1.1628e-9
4.0	1.5469e-7	1.6338e-7	1.5903e-7	6.1448e-9
5.0	1.7068e-7	1.6170e-7	1.6619e-7	6.3503e-9




Figure B6 Plot of the polydispersity as a function of HPC concentration at 30 °C for the HPC/water system at the fixed angle of 90 °.

The HPC/OTG/Water System

Table B7 Data for the HPC/OTG/water system at the fixed HPC concentration of 5 g/l and at the fixed OTG concentration of 1.02 mM.

Angle (degree)	Sample (μs)	Mean (nm)	Width	Z _{Ave} (nm)	Poly- dispersity	In Range	Merit	D _{app} (cm ² /s)
Average	3.10	34.9	52.8	26.9	0.535	98.6	42.8	15.9e-8
	3.10	35.6	53.9	27.4	0.537	98.8	46.0	15.6e-8
	3.10	35.7	54.2	27.4	0.543	98.9	46.9	15.6e-8
	3.10	35.4	53.6	27.2	0.538	98.8	45.2	15.7e-8
	SD	0.0000	0.4359	0.7371	0.2887	4.1633e-3	0.1528	2.1548
	75	2.00	34.7	52.4	26.7	0.537	98.9	48.3
Average	2.00	35.1	54.0	26.8	0.560	98.9	48.7	15.8e-8
	2.00	34.8	52.8	26.7	0.544	99.3	48.3	16.0e-8
	2.00	34.9	53.1	26.7	0.547	99.0	48.4	15.9e-8
	SD	0.0000	0.2082	0.8327	0.0577	0.0118	0.2309	0.2309
	90	1.40	32.6	49.0	25.2	0.529	99.0	48.1
	1.40	33.0	49.4	25.6	0.521	98.7	48.3	16.8e-8
Average	1.40	34.0	51.4	26.2	0.536	97.8	48.7	16.3e-8
	1.40	33.2	49.9	25.7	0.529	98.5	48.4	16.7e-8
	SD	0.0000	0.7211	1.2858	0.5033	7.5056e-3	0.6245	0.3055
	105	1.00	32.3	46.8	24.9	0.537	98.7	45.2
	1.00	32.0	47.6	24.9	0.515	98.8	45.5	17.4e-8
	1.00	32.5	47.5	25.6	0.489	98.8	45.4	17.1e-8
Average	1.00	32.3	47.3	25.1	0.514	98.8	45.4	17.2e-8
	SD	0.0000	0.2517	0.4359	0.4041	0.0240	0.0577	0.1528




Figure B7 Plot of the apparent diffusion coefficient as a function of scattering vector at 30 °C for the fixed HPC concentration of 5 g/l and the fixed OTG concentration of 1.02 mM.

Table B8 Data for the HPC/OTG/water system at the fixed HPC concentration of 5 g/l and at the fixed OTG concentration of 3.00 mM.

Angle (degree)	Sample (μs)	Mean (nm)	Width	Z _{Ave} (nm)	Poly- dispersity	In Range	Merit	D _{app} (cm ² /s)
60	3.30	37.0	57.4	27.9	0.579	98.0	47.4	15.0e-8
	3.30	37.0	57.4	27.9	0.577	99.1	47.0	15.0e-8
	3.30	36.4	55.8	27.8	0.558	99.0	47.2	15.2e-8
	Average	3.30	36.8	56.9	0.571	98.7	47.2	15.1e-8
75	SD	0.0000	0.3434	0.9238	0.0577	0.0116	0.2000	1.1547e-9
	2.00	35.1	53.6	26.9	0.552	99.8	46.1	15.8e-8
	2.00	35.2	53.8	27.0	0.550	98.5	46.8	15.8e-8
	Average	2.00	35.4	54.5	0.563	99.0	46.9	15.7e-8
90	SD	0.0000	0.1528	0.4726	0.0577	7.0000e-3	0.6557	0.4359
	1.40	33.5	51.0	25.7	0.546	99.2	49.7	16.6e-8
	1.40	33.8	51.4	26.0	0.545	98.6	49.8	16.4e-8
	Average	1.40	34.0	51.9	0.552	98.4	49.7	16.3e-8
105	SD	0.0000	0.2517	0.4509	0.1732	3.7859e-3	0.4163	0.0577
	1.00	32.7	48.2	25.3	0.530	99.1	49.6	17.0e-8
	1.00	32.5	48.9	25.1	0.528	99.2	49.7	17.1e-8
	Average	1.00	32.1	48.2	0.525	99.0	50.2	17.3e-8
120	SD	0.0000	0.3055	0.4041	0.2000	2.5166e-3	0.1000	0.3215
								1.5275e-9




Figure B8 Plot of the apparent diffusion coefficient as a function of scattering vector at 30 °C for the fixed HPC concentration of 5 g/l and the fixed OTG concentration of 3.00 mM.

Table B9 Data for the HPC/OTG/water system at the fixed HPC concentration of 5 g/l and at the fixed OTG concentration of 5.04 mM.

Angle (degree)	Sample (μs)	Mean (nm)	Width	Z _{Ave} (nm)	Poly- dispersity	In Range	Merit	D _{app} (cm ² /s)
60	3.00	37.4	58.3	28.2	0.582	99.3	49.9	14.8e-8
	3.00	37.6	58.9	28.3	0.591	98.5	48.6	14.8e-8
	3.00	36.4	56.6	27.5	0.579	97.5	47.5	15.2e-8
	Average	3.00	37.1	57.9	28.0	0.584	98.4	48.7
SD	0.0000	0.6429	1.1930	0.4359	6.2450e-3	0.9018	1.2014	2.3094e-9
75	2.10	35.8	55.0	27.3	0.561	97.8	47.6	15.5e-8
	2.10	36.3	56.1	27.5	0.570	97.8	50.2	15.3e-8
	2.10	35.4	54.4	26.9	0.562	96.8	48.0	15.7e-8
	Average	2.10	35.8	55.2	27.2	0.564	97.5	48.6
SD	0.0000	0.4509	0.8622	0.3055	4.9329e-3	0.5774	1.4000	2.0000e-9
90	1.40	34.5	52.4	26.5	0.543	99.0	47.8	16.1e-8
	1.40	34.1	51.8	26.2	0.544	99.3	48.1	16.3e-8
	1.40	34.2	52.1	26.2	0.549	98.2	47.8	16.2e-8
	Average	1.40	34.3	52.1	26.3	0.545	98.8	47.9
SD	0.0000	0.2082	0.3000	0.1732	3.2146e-3	0.5686	0.1732	1.0000e-9
105	1.10	32.9	49.2	25.5	0.521	98.5	50.3	16.9
	1.10	33.4	50.5	25.7	0.538	99.1	50.4	16.6
	1.10	33.2	50.2	25.6	0.537	98.9	50.2	16.7
	Average	1.10	33.2	50.0	25.6	0.5320	98.8	50.3
SD	0.0000	0.2517	0.6807	0.1000	9.5394e-3	0.3055	0.1000	0.1528




Figure B9 Plot of the apparent diffusion coefficient as a function of scattering vector at 30 °C for the fixed HPC concentration of 5 g/l and the fixed OTG concentration of 5.04 mM.

Table B10 Data for the HPC/OTG/water system at the fixed HPC concentration of 5 g/l and at the fixed OTG concentration of 7.00 mM.

Angle (degree)	Sample (μs)	Mean (nm)	Width	Z _{Ave} (nm)	Poly- dispersity	In Range	Merit	D _{app} (cm ² /s)
60	3.40	38.7	60.4	29.2	0.585	96.8	47.1	14.3e-8
	3.40	38.0	59.0	28.7	0.577	96.8	46.5	14.6e-8
	3.40	38.4	60.1	28.8	0.590	98.8	47.4	14.5e-8
	Average	3.40	38.4	59.8	0.584	97.5	47.0	14.5e-8
SD	0.0000	0.3512	0.7371	0.2646	6.5574e-3	1.1547	0.4583	15.3e-9
75	2.10	37.0	56.8	28.2	0.561	96.7	50.3	15.0e-8
	2.10	37.5	58.8	28.1	0.594	97.4	51.0	14.8e-8
	2.10	37.0	57.8	27.8	0.589	97.0	49.8	15.0e-8
	Average	2.10	37.2	57.8	0.581	97.0	50.4	14.9e-8
SD	0.0000	0.2887	1.0000	0.2082	0.0178	0.3512	0.6028	1.1547e-9
90	1.50	35.5	54.1	27.3	0.546	98.6	45.9	15.6e-8
	1.50	35.3	53.9	27.0	0.552	98.0	45.5	15.7e-8
	1.50	35.9	55.7	27.2	0.573	98.6	45.9	15.4e-8
	Average	1.50	35.6	54.6	0.557	98.4	45.8	15.6e-8
SD	0.0000	0.3055	0.9866	0.1528	0.0142	0.3464	0.2309	1.5275e-9
105	1.10	35.0	54.4	26.5	0.578	98.9	45.9	15.9e-8
	1.10	35.0	53.7	26.8	0.556	98.4	46.3	15.8e-8
	1.10	34.8	53.8	26.4	0.571	97.3	46.3	16.0e-8
	Average	1.10	34.9	54.0	0.568	98.2	46.2	15.9e-8
SD	0.0000	0.1155	0.3786	0.2082	0.0112	0.8185	0.2309	1.0000e-9




Figure B10 Plot of the apparent diffusion coefficient as a function of scattering vector at 30 °C for the fixed HPC concentration of 5 g/l and the fixed OTG concentration of 7.00 mM.

Table B11. Data for the HPC/OTG/water system at the fixed HPC concentration of 5 g/l and at the fixed OTG concentration of 9.00 mM.

Angle (degree)	Sample (μ s)	Mean (nm)	Width	Z _{Ave} (nm)	Poly- dispersity	In Range	Merit	D _{app} (cm ² /s)
60	2.60	31.1	46.2	24.3	0.510	97.7	49.4	17.8e-8
	2.60	30.4	44.5	23.9	0.492	97.7	49.8	18.3e-8
	2.60	30.4	45.1	23.8	0.509	98.4	48.7	18.3e-8
	Average	2.60	30.6	45.3	24.0	0.504	97.9	49.3
	SD	0.0000	0.4041	0.8622	0.2646	0.0101	0.4041	0.5568
	75	1.60	28.1	40.4	22.4	0.467	98.7	50.6
Average	1.60	28.0	40.5	22.3	0.474	98.9	50.0	19.8e-8
	1.60	27.8	39.5	22.3	0.454	98.3	50.4	20.0e-8
	Average	1.60	28.0	40.1	22.3	0.465	98.6	50.3
	SD	0.0000	0.1528	0.5508	0.0577	0.0101	0.3055	0.3055
	90	1.20	26.9	38.5	21.5	0.461	99.2	51.5
	Average	1.20	27.0	37.9	21.7	0.443	98.1	51.6
Average	1.20	27.0	38.6	21.5	0.464	99.3	51.3	20.6e-8
	SD	0.0000	0.0577	0.3786	0.1155	0.0114	0.6658	0.1528
	105	0.90	26.5	37.8	21.2	0.458	98.9	48.7
	Average	0.90	26.3	37.3	21.2	0.452	98.7	49.6
	SD	0.0000	0.1155	0.3606	0.0000	6.0000e-3	0.3055	0.5859
	0.90	26.3	37.1	21.2	0.446	99.3	49.8	21.1e-8
Average	0.90	26.4	37.4	21.2	0.452	99.0	49.4	21.1e-8
	SD	0.0000	0.1155	0.3606	0.0000	6.0000e-3	0.3055	0.5859
								5.7735e-10




Figure B11 Plot of the apparent diffusion coefficient as a function of scattering vector at 30 °C for the fixed HPC concentration of 5 g/l and the fixed OTG concentration of 9.00 mM.

Table B12 Data for the HPC/OTG/water system at the fixed HPC concentration of 5 g/l and at the fixed OTG concentration of 11.04 mM.

Angle (degree)	Sample (μ s)	Mean (nm)	Width	Z_{Ave} (nm)	Poly- dispersity	In Range	Merit	D_{app} (cm ² /s)
60	2.60	31.9	49.6	24.1	0.579	97.9	46.3	17.4e-8
	2.60	32.5	50.6	24.5	0.584	98.8	47.7	17.1e-8
	2.60	32.4	50.5	24.4	0.583	98.5	47.2	17.1e-8
	Average	2.60	32.3	50.2	0.582	98.4	47.1	17.2e-8
	SD	0.0000	0.3215	0.5508	0.2082	2.6458e-3	0.4583	0.7095
75	1.80	31.3	48.9	24.0	0.568	99.9	52.5	17.5e-8
	1.80	31.6	49.0	24.0	0.572	99.2	53.1	17.5e-8
	1.80	31.9	49.7	24.1	0.583	99.1	53.9	17.4e-8
	Average	1.80	31.6	49.2	0.574	99.4	53.2	17.5e-8
	SD	0.0000	0.3000	0.4359	0.0577	7.7675e-3	0.4359	0.7024
90	1.30	29.7	44.8	22.9	0.532	98.4	50.3	18.1e-8
	1.30	29.7	45.1	22.8	0.543	98.5	50.7	18.7e-8
	1.30	30.2	46.4	23.1	0.553	98.3	51.1	18.4e-8
	Average	1.30	29.9	45.4	0.543	98.4	50.7	18.4e-8
	SD	0.0000	0.2887	0.8505	0.1528	0.0105	0.1000	0.4000
105	0.90	29.1	43.4	22.6	0.518	99.4	50.0	19.1e-8
	0.90	28.2	42.3	21.8	0.527	99.2	49.3	19.7e-8
	0.90	28.2	42.3	21.8	0.527	99.2	49.3	19.7e-8
	Average	0.90	28.5	42.7	0.524	99.3	49.5	19.5e-8
	SD	0.0000	0.5196	0.6351	0.4619	5.1962e-3	0.1155	0.4041




Figure B12 Plot of the apparent diffusion coefficient as a function of scattering vector at 30 °C for the fixed HPC concentration of 5 g/l and the fixed OTG concentration of 11.04 mM.

Table B13 Data for the HPC/OTG/water system at the fixed HPC concentration of 5 g/l and at the fixed OTG concentration of 13.20 mM.

Angle (degree)	Sample (μs)	Mean (nm)	Width	Z Ave (nm)	Poly- dispersity	In Range	Merit	D _{app} (cm ² /s)
90	1.30	29.3	44.2	22.7	0.530	97.2	50.8	18.9e-8
	1.30	29.3	44.4	22.6	0.536	97.0	51.1	18.9e-8
	1.30	28.7	42.7	22.4	0.511	97.1	51.5	19.3e-8
	Average	29.1	43.8	22.6	0.526	97.1	51.1	19.0e-8
	SD	0.0000	0.3464	0.9292	0.1528	0.1000	0.3512	2.3094e-9
	100	1.00	26.4	38.2	20.9	0.477	97.4	52.7
Average	1.00	26.5	37.8	21.2	0.460	99.5	52.2	20.9e-8
	1.00	26.5	38.0	21.1	0.468	99.3	52.5	21.0e-8
	Average	26.5	38.0	21.1	0.468	98.7	52.5	21.0e-8
	SD	0.0000	0.0577	0.2000	0.1528	8.5049e-3	1.1590	5.7735e-10
	105	0.90	26.0	37.8	20.6	0.480	98.7	51.1
	0.90	26.4	38.2	20.9	0.479	99.0	50.8	21.1e-8
Average	0.90	26.0	37.6	20.6	0.478	98.2	50.9	21.4e-8
	0.90	26.1	37.9	20.7	0.479	98.6	50.9	21.3e-8
	SD	0.0000	0.2309	0.3055	0.1732	1.0000e-3	0.4041	0.1528
	110	0.80	25.4	35.7	20.4	0.443	94.8	49.4
	0.80	25.2	36.0	20.1	0.461	97.4	50.3	22.1e-8
	Average	25.1	35.5	20.1	0.449	98.6	50.5	22.2e-8
SD	0.80	25.2	35.7	20.2	0.451	96.9	50.1	22.1e-8
	0.0000	0.1528	0.2517	0.1732	9.1652e-3	1.9425	0.5859	1.5275e-9




Figure B13 Plot of the apparent diffusion coefficient as a function of scattering vector at 30 °C for the fixed HPC concentration of 5 g/l and the fixed OTG concentration of 13.20 mM.

Table B14 Data for the HPC/OTG/water system at the fixed HPC concentration of 5 g/l and at the fixed OTG concentration of 15.00 mM.

Angle (degree)	Sample (μ s)	Mean (nm)	Width	Z_{Ave} (nm)	Poly-dispersity	In Range	Merit	D_{app} (cm^2/s)
75	1.70	29.9	41.6	24.2	0.431	95.9	49.1	18.6e-8
	1.70	30.0	42.6	24.0	0.454	95.1	47.0	18.5e-8
	1.70	29.9	42.5	24.0	0.453	94.5	49.5	18.5e-8
	Average	1.70	29.9	42.2	24.1	0.446	95.2	48.5
	SD	0.0000	0.0577	0.5508	0.1155	0.0130	0.7024	1.3429
	85	1.30	27.2	36.2	22.6	0.384	97.6	49.9
Average	1.30	27.2	36.7	22.5	0.396	97.3	50.5	20.4e-8
	1.30	27.5	37.1	22.6	0.399	97.6	50.9	20.2e-8
	Average	1.30	27.3	36.7	22.6	0.393	97.5	50.4
	SD	0.0000	0.1732	0.4509	0.0577	7.9373e-3	0.1732	0.5033
	90	1.20	26.8	35.2	22.4	0.372	98.0	49.9
	1.20	26.5	35.1	22.0	0.382	98.1	50.4	20.9e-8
Average	1.20	26.7	35.2	22.2	0.379	99.6	50.3	20.8e-8
	SD	0.0000	0.1528	0.0577	0.2000	5.1316e-3	0.8963	0.2646
	105	0.90	25.0	31.9	21.1	0.347	98.9	51.1
	0.90	25.1	31.9	21.1	0.343	97.6	50.9	22.1e-8
	0.90	25.1	31.7	21.2	0.340	98.4	50.7	22.2e-8
	Average	0.90	25.1	31.8	21.1	0.343	98.3	50.9
SD	0.0000	0.0577	0.1155	0.0577	3.5119e-3	0.6557	0.2000	5.7735e-10




Figure B14 Plot of the apparent diffusion coefficient as a function of scattering vector at 30 °C for the fixed HPC concentration of 5 g/l and the fixed OTG concentration of 15.00 mM.

Table B15 Data for the HPC/OTG/water system at the fixed HPC concentration of 5 g/l and at the fixed OTG concentration of 17.00 mM.

Angle (degree)	Sample (μ s)	Mean (nm)	Width	Z_{Ave} (nm)	Poly-dispersity	In Range	Merit	D_{app} (cm ² /s)
75	1.90	31.1	43.5	25.2	0.437	95.0	47.7	17.8e-8
	1.90	31.6	44.7	25.4	0.451	97.3	47.2	17.6e-8
	1.90	31.1	42.9	25.4	0.421	95.3	47.0	17.9e-8
	Average	31.3	43.7	25.3	0.436	95.9	47.3	17.8e-8
	SD	0.0000	0.2887	0.9165	0.0150	1.2503	0.3606	1.5275e-9
	85	1.40	28.0	36.8	0.373	98.8	50.3	19.8e-8
Average	1.40	27.9	36.4	23.4	0.367	97.3	50.4	19.9e-8
	1.40	27.7	36.3	23.3	0.372	97.8	50.0	20.1e-8
	Average	27.9	36.5	23.3	0.371	98.0	50.2	19.9e-8
	SD	0.0000	0.1528	0.2646	0.1528	3.2146e-3	0.7638	0.2082
	90	1.20	27.0	34.2	0.340	98.9	50.6	20.5e-8
	1.20	27.3	35.1	23.0	0.352	98.0	50.6	20.3e-8
Average	1.20	27.2	34.6	23.0	0.344	97.2	50.3	20.4e-8
	1.20	27.2	34.6	23.0	0.345	98.0	50.5	20.4e-8
	SD	0.0000	0.1528	0.4509	0.0577	6.1101e-3	0.8505	0.1732
	105	0.90	25.8	31.9	0.322	98.8	51.7	21.5e-8
	0.90	25.5	30.9	22.0	0.305	98.5	51.8	21.7e-8
	Average	25.9	32.1	22.1	0.324	98.5	52.0	21.4e-8
SD	0.90	25.7	31.6	22.1	0.317	98.6	51.8	21.5e-8
	0.0000	0.2082	0.6429	0.0577	0.0104	0.1732	0.1528	1.5275e-9




Figure B15 Plot of the apparent diffusion coefficient as a function of scattering vector at 30 °C for the fixed HPC concentration of 5 g/l and the fixed OTG concentration of 17.00 mM.

Table B16 Data for the HPC/OTG/water system at the fixed HPC concentration of 5 g/l and at the fixed OTG concentration of 20.00 mM.

Angle (degree)	Sample (μ s)	Mean (nm)	Width	Z _{Ave} (nm)	Poly- dispersity	In Range	Merit	D _{app} (cm ² /s)
75	1.70	27.8	34.1	23.9	0.314	95.4	47.2	20.0e-8
	1.70	27.9	33.8	24.0	0.307	97.4	46.3	19.9e-8
	1.70	27.8	33.6	24.0	0.304	95.3	47.0	20.0e-8
	Average	1.70	27.8	33.8	24.0	0.308	96.0	46.8
	SD	0.0000	0.0577	0.2517	0.0577	5.1316e-3	1.1846	0.4726
	85	1.40	27.9	34.5	23.9	0.321	98.2	49.6
Average	1.40	27.9	33.8	24.0	0.307	97.6	49.8	19.9e-8
	1.40	27.6	33.1	23.8	0.300	99.0	50.0	20.1e-8
	Average	1.40	27.8	33.8	23.9	0.309	98.3	49.8
	SD	0.0000	0.1732	0.7000	0.1000	0.0107	0.7024	0.2000
	90	1.20	27.1	32.1	23.5	0.292	98.8	49.7
	Average	1.20	26.7	31.1	23.3	0.280	98.7	49.2
Average	1.20	26.5	30.6	23.1	0.276	98.5	49.7	21.0e-8
	SD	0.0000	0.3055	0.7638	0.2000	8.3267e-3	0.1528	0.2887
	105	0.90	25.7	29.3	22.5	0.267	97.6	50.5
	Average	0.90	25.8	29.2	22.8	0.260	99.8	50.7
	SD	0.0000	0.0577	0.1000	0.1528	4.0415e-3	1.1533	0.1000
	105	0.90	25.8	29.1	22.7	0.260	99.3	50.6
Average	0.90	25.8	29.2	22.7	0.262	98.9	50.6	21.5e-8
	SD	0.0000	0.0577	0.1000	0.1528	4.0415e-3	1.1533	0.1000
Average	0.90	25.8	29.2	22.7	0.262	98.9	50.6	21.5e-8
	SD	0.0000	0.0577	0.1000	0.1528	4.0415e-3	1.1533	0.1000




Figure B16 Plot of the apparent diffusion coefficient as a function of scattering vector at 30 °C for the fixed HPC concentration of 5 g/l and the fixed OTG concentration of 20.00 mM.

Table B17 Data for the HPC/OTG/water system at the fixed HPC concentration of 5 g/l and at the fixed OTG concentration of 25.00 mM.

Angle (degree)	Sample (μ s)	Mean (nm)	Width	Z_{Ave} (nm)	Poly-dispersity	In Range	Merit	D_{app} (cm^2/s)
75	1.90	30.5	36.2	26.4	0.293	97.4	45.9	18.2
	1.90	29.9	34.6	26.2	0.275	98.8	49.3	18.6
	1.90	29.8	34.0	26.1	0.267	97.0	45.7	18.7
	Average	1.90	30.1	34.9	26.2	0.278	97.7	47.0
SD	0.0000	0.3786	1.1372	0.1528	0.0133	0.9452	2.0232	0.2646
85	1.40	27.5	28.5	24.7	0.215	99.3	48.4	20.2e-8
	1.40	27.6	29.4	24.7	0.226	99.5	48.4	20.1e-8
	1.40	27.4	29.1	24.6	0.225	99.7	47.6	20.2e-8
	Average	1.40	27.5	29.0	24.7	0.222	99.5	48.1
SD	0.0000	0.1000	0.4583	0.0577	6.0828e-3	0.2000	0.4619	5.7735e-10
90	1.30	27.6	28.7	24.9	0.216	99.4	48.1	20.1e-8
	1.30	27.8	30.0	24.8	0.234	99.4	48.0	20.0e-8
	1.30	27.8	29.6	24.8	0.228	98.4	48.1	20.0e-8
	Average	1.30	27.7	29.4	24.8	0.226	99.1	48.1
SD	0.0000	0.1155	0.6658	0.0577	9.1652e-3	0.5774	0.0577	5.7735e-10
105	1.00	27.1	28.2	24.4	0.216	98.5	49.5	20.5e-8
	1.00	26.9	28.0	24.3	0.216	98.4	49.2	20.6e-8
	1.00	27.0	28.1	24.3	0.217	98.8	49.3	20.6e-8
	Average	1.00	27.0	28.1	24.3	0.216	98.6	49.3
SD	0.0000	0.1000	0.1000	0.0577	5.7735e-4	0.2082	0.1528	5.7735e-10




Figure B17 Plot of the apparent diffusion coefficient as a function of scattering vector at 30 °C for the fixed HPC concentration of 5 g/l and the fixed OTG concentration of 25.00 mM.

Table B18 Data for the HPC/OTG/water system at the fixed HPC concentration of 5 g/l and at the fixed OTG concentration of 30.00 mM.

Angle (degree)	Sample (μ s)	Mean (nm)	Width	Z_{Ave} (nm)	Poly- dispersity	In Range	Merit	D_{app} (cm^2/s)
75	2.30	33.1	37.9	29.1	0.268	97.2	44.1	16.8e-8
	2.30	32.2	35.6	28.6	0.247	97.4	43.6	17.2e-8
	2.30	31.7	34.6	28.1	0.242	98.0	43.6	17.5e-8
	Average	2.30	32.3	36.0	0.252	97.5	43.8	17.2e-8
	SD	0.0000	0.7095	1.6921	0.5000	0.4163	0.2887	3.5119e-9
	85	1.50	29.8	29.9	0.200	98.8	45.8	18.6e-8
		1.50	29.6	30.6	0.213	99.9	45.6	18.7e-8
		1.50	29.3	28.7	0.188	98.8	45.6	18.9e-8
		Average	1.50	29.6	29.7	26.8	0.200	18.7e-8
		SD	0.0000	0.2517	0.9609	0.1528	0.0125	0.6351
		90	1.40	29.4	29.3	26.7	0.196	18.9e-8
			1.40	29.1	28.4	26.5	0.187	19.1e-8
			1.40	29.3	28.9	26.6	0.193	19.0e-8
			Average	1.40	29.3	28.9	0.192	19.0e-8
			SD	0.0000	0.1528	0.4509	0.1000	4.5826e-3
		105	1.10	28.8	28.3	26.3	0.190	19.2e-8
			1.10	28.9	28.3	26.4	0.188	19.2e-8
			1.10	28.9	28.2	26.3	0.188	19.2e-8
			Average	1.10	28.9	28.3	0.189	19.2e-8
			SD	0.0000	0.0577	0.0577	1.1547e-3	0.5508
			0.0577					




Figure B18 Plot of the apparent diffusion coefficient as a function of scattering vector at 30 °C for the fixed HPC concentration of 5 g/l and the fixed OTG concentration of 30.00 mM.

Table B19 Data of the center of mass diffusion coefficient (D_c) and the hydrodynamic radius (R_h) as a function of OTG concentration at 30 °C for the HPC/OTG/water system for the fixed HPC concentration of 5 g/l.

[OTG] (mM)	D_c (cm ² /s)	R_h (nm)
1.02	1.4535e-7	19.1
3.00	1.3757e-7	20.2
5.04	1.3737e-7	20.2
7.00	1.3515e-7	20.6
9.00	1.5855e-7	17.6
11.04	1.5428e-7	18.0
13.20	1.2143e-7	23.0
15.00	1.3796e-7	20.2
17.00	1.3096e-7	21.2
20.00	1.7294e-7	16.1
25.00	1.6284e-7	17.1
30.00	1.4966e-7	18.6




Figure B19 Plot of the polydispersity as a function of OTG concentration at 30 °C for the HPC/OTG/water system at the fixed HPC concentration of 5 g/l and at the fixed angle of 90 °.

The HPC/CTAB/Water System

Table B20 Data for the HPC/CTAB/water system at the fixed HPC concentration of 1 g/l and at the fixed CTAB concentration of 0.05 mM.

Angle (degree)	Sample (μ s)	Mean (nm)	Width	Z _{Ave} (nm)	Poly- dispersity	In Range	Merit	D _{app} (cm ² /s)
Average	60	3.00	33.7	49.2	26.6	0.489	93.8	34.6
		3.00	33.7	49.6	26.4	0.500	96.3	35.9
		3.00	33.3	48.2	26.4	0.478	95.2	36.8
		3.00	33.6	49.0	26.5	0.489	95.1	35.8
	SD	0.0000	0.2309	0.7211	0.1155	0.0110	1.2530	1.1060
								1.1547e-9
Average	75	1.70	31.7	45.9	25.1	0.477	95.8	41.0
		1.70	30.4	42.9	24.5	0.446	95.0	39.9
		1.70	30.3	41.5	24.8	0.413	92.1	39.6
		1.70	30.8	43.4	24.8	0.445	94.3	40.2
	SD	0.0000	0.7810	2.2480	0.3000	0.0320	1.9468	0.7371
								4.6188e-9
Average	90	1.30	29.6	41.8	23.8	0.448	98.2	37.4
		1.30	29.3	39.9	24.0	0.408	98.3	36.5
		1.30	29.7	40.8	24.3	0.416	97.4	36.4
		1.30	29.5	40.8	24.0	0.424	98.0	36.8
	SD	0.0000	0.2082	0.9504	0.2517	0.0212	0.4933	0.5508
								1.0000e-9
Average	105	0.80	28.1	38.4	23.0	0.411	94.2	35.6
		0.80	28.7	41.6	22.7	0.480	97.3	35.3
		0.80	28.3	39.3	23.0	0.427	96.5	34.8
		0.80	28.4	39.8	22.9	0.493	96.0	35.2
	SD	0.0000	0.3055	1.6503	0.1732	0.0361	1.6093	0.4041
								1.5275e-9




Figure B20 Plot of the apparent diffusion coefficient as a function of scattering vector at 30 °C for the fixed HPC concentration of 1 g/l and the fixed CTAB concentration of 0.05 mM.

Table B21 Data for the HPC/CTAB/water system at the fixed HPC concentration of 1 g/l and at the fixed CTAB concentration of 0.50 mM.

Angle (degree)	Sample (μs)	Mean (nm)	Width	Z _{Ave} (nm)	Poly- dispersity	In Range	Merit	D _{app} (cm ² /s)
60	3.70	47.0	73.3	35.5	0.583	96.4	40.1	11.8e-8
	3.70	47.5	74.3	35.7	0.588	96.2	41.6	11.7e-8
	3.70	47.6	74.6	35.7	0.595	94.8	42.4	11.7e-8
	Average	3.70	47.4	74.1	35.6	0.589	95.8	41.4
SD	0.0000	0.3215	0.6807	0.1155	6.0277e-3	0.8718	1.1676	5.7735e-10
75	2.40	43.6	66.2	33.5	0.542	95.6	44.6	12.7e-8
	2.40	44.9	69.1	34.2	0.562	96.3	45.7	12.4e-8
	2.40	42.6	65.1	32.6	0.552	95.0	45.7	13.0e-8
	Average	2.40	43.7	66.8	33.4	0.552	95.6	45.3
SD	0.0000	1.1533	2.0664	0.8021	0.0100	0.6506	0.6351	3.0000e-9
90	1.80	42.0	63.4	32.4	0.534	96.8	40.3	13.2e-8
	1.80	41.8	63.8	32.1	0.548	98.1	41.9	13.3e-8
	1.80	42.0	63.9	32.3	0.543	97.4	40.9	13.2e-8
	Average	1.80	41.9	63.7	32.3	0.542	97.4	41.0
SD	0.0000	0.1155	0.2646	0.1528	7.0946e-3	0.6506	0.8083	5.7735e-10
105	1.30	38.5	57.2	30.1	0.511	98.5	39.8	14.4e-8
	1.30	40.0	60.6	30.8	0.539	96.1	40.0	13.9e-8
	1.30	39.4	59.2	30.4	0.529	98.8	39.7	14.1e-8
	Average	1.30	39.3	59.0	30.4	0.526	97.8	39.8
SD	0.0000	0.7550	1.7088	0.3512	0.0142	1.4799	0.1528	2.5166e-9




Figure B21 Plot of the apparent diffusion coefficient as a function of scattering vector at 30 °C for the fixed HPC concentration of 1 g/l and the fixed CTAB concentration of 0.50 mM.

Table B22 Data for the HPC/CTAB/water system at the fixed HPC concentration of 1 g/l and at the fixed CTAB concentration of 0.80 mM.

Angle (degree)	Sample (μ s)	Mean (nm)	Width	Z _{Ave} (nm)	Poly- dispersity	In Range	Merit	D _{app} (cm ² /s)				
60	4.00	52.4	87.8	37.8	0.675	95.7	38.2	10.6e-8				
	4.00	53.7	88.6	38.4	0.690	93.9	38.5	10.3e-8				
	4.00	53.6	88.8	38.3	0.697	94.6	37.9	10.3e-8				
	Average	4.00	53.2	88.4	0.687	94.7	38.2	10.4e-8				
	SD	0.000	0.7134	0.5292	0.3215	0.0112	0.3000	1.7321e-9				
	75	2.70	49.5	80.1	36.1	0.652	96.8	40.8	11.2e-8			
		2.70	50.0	81.4	36.3	0.663	96.5	40.4	11.1e-8			
		2.70	50.7	82.8	36.7	0.669	93.5	40.8	10.9e-8			
		Average	2.70	50.1	81.4	36.4	0.661	95.6	40.7	11.1e-8		
		SD	0.0000	0.6028	1.3503	0.3055	8.6217e-3	1.8248	0.2309	1.5275e-9		
		90	1.90	48.0	78.2	34.9	0.661	95.9	39.7	11.6e-8		
			1.90	46.2	74.6	33.8	0.645	96.2	40.0	12.0e-8		
			1.90	46.8	75.8	34.2	0.651	95.2	40.4	11.9e-8		
			Average	1.90	47.0	76.2	34.3	0.652	95.8	10.0	11.8e-8	
			SD	0.0000	0.9165	1.8330	0.5568	8.0829e-3	0.5132	0.3512	2.0817e-9	
			105	1.40	42.1	66.4	31.4	0.604	97.8	39.0	13.2e-8	
				1.40	41.6	65.1	31.3	0.589	94.0	38.1	13.3e-8	
				1.40	41.2	64.5	30.9	0.591	97.9	38.1	13.5e-8	
				Average	1.40	41.6	65.3	31.2	0.595	95.6	38.4	13.3e-8
				SD	0.0000	0.4509	0.9713	0.2646	8.1445e-3	2.2234	0.5196	1.5275e-9




Figure B22 Plot of the apparent diffusion coefficient as a function of scattering vector at 30 °C for the fixed HPC concentration of 1 g/l and the fixed CTAB concentration of 0.80 mM.

Table B23 Data for the HPC/CTAB/water system at the fixed HPC concentration of 1 g/l and at the fixed CTAB concentration of 1.00 mM.

Angle (degree)	Sample (μs)	Mean (nm)	Width	Z _{Ave} (nm)	Poly- dispersity	In Range	Merit	D _{app} (cm ² /s)
60	3.50	43.3	72.3	30.0	0.718	89.7	41.3	12.8e-8
	3.50	45.5	76.9	31.8	0.743	85.9	41.1	12.2e-8
	3.50	43.2	70.0	31.4	0.635	90.0	39.2	12.9e-8
	Average	3.50	44.0	73.1	31.1	0.699	88.5	40.5
	SD	0.0000	1.3000	3.5133	0.9452	0.0565	2.2855	1.1590
	75	2.20	40.4	66.9	28.8	0.701	94.8	41.5
Average	2.20	41.4	69.0	29.4	0.711	91.8	41.9	13.4e-8
	2.20	42.2	70.5	29.8	0.717	92.3	43.3	13.1e-8
	Average	2.20	41.3	68.8	29.3	0.710	93.0	42.2
	SD	0.0000	0.9018	1.8083	0.5033	8.0829e-3	1.6073	0.9452
	90	1.50	35.2	56.4	26.0	0.630	95.6	40.5
	1.50	35.7	57.5	26.2	0.640	95.2	41.7	15.5e-8
Average	1.50	36.9	59.9	26.9	0.655	92.0	41.8	15.0e-8
	1.50	35.9	57.9	26.4	0.642	94.3	41.3	15.4e-8
	SD	0.0000	0.8737	1.7898	0.4726	0.0126	1.9732	0.7234
	105	1.10	36.0	58.1	26.4	0.644	98.7	37.7
	1.10	36.2	58.8	26.3	0.661	96.4	38.3	15.4e-8
	1.10	36.0	58.4	26.2	0.656	95.8	28.5	15.4e-8
Average	1.10	36.1	58.4	26.3	0.654	97.0	34.8	15.4e-8
	SD	0.0000	0.1155	0.6512	0.1000	8.7369e-3	1.5308	5.4930
								0.0000




Figure B23 Plot of the apparent diffusion coefficient as a function of scattering vector at 30 °C for the fixed HPC concentration of 1 g/l and the fixed CTAB concentration of 1.00 mM.

Table B24 Data for the HPC/CTAB/water system at the fixed HPC concentration of 1 g/l and at the fixed CTAB concentration of 2.00 mM.

Angle (degree)	Sample (μs)	Mean (nm)	Width	Z _{Ave} (nm)	Poly- dispersity	In Range	Merit	D _{app} (cm ² /s)
60	2.50	20.4	34.1	14.5	0.712	89.4	32.4	27.2e-8
	2.50	20.3	33.8	14.4	0.714	91.6	32.7	27.4e-8
	2.50	20.7	34.6	14.6	0.720	79.9	30.7	26.8e-8
	Average	20.5	34.2	14.5	0.715	87.0	31.9	27.1e-8
	SD	0.0000	0.2082	0.4041	0.1000	4.1633e-3	6.2180	1.0786
75	1.60	16.0	26.6	11.3	0.711	91.8	34.7	34.7e-8
	1.60	15.7	25.4	11.5	0.646	92.7	35.3	35.3e-8
	1.60	16.1	26.1	11.8	0.647	92.1	34.4	34.4e-8
	Average	15.9	26.0	11.5	0.668	92.2	34.8	34.8e-8
	SD	0.0000	0.2082	0.6028	0.2517	0.0372	0.4583	4.5826e-9
90	0.80	15.4	25.6	10.9	0.707	91.5	26.8	36.1e-8
	0.80	14.4	23.7	10.4	0.682	92.2	26.4	38.4e-8
	0.80	14.8	24.5	10.5	0.702	91.7	28.4	37.5e-8
	Average	14.9	24.6	10.6	0.697	91.8	27.2	37.3e-8
	SD	0.0000	0.5033	0.9539	0.2646	0.0132	0.3606	1.0583
105	0.70	14.2	23.0	10.3	0.656	92.1	39.1	39.1e-8
	0.70	14.5	23.7	10.5	0.672	89.9	38.3	38.3e-8
	0.70	14.1	23.1	10.2	0.669	93.7	39.3	39.3e-8
	Average	14.3	23.3	10.3	0.666	91.9	38.9	38.9e-8
	SD	0.0000	0.2082	0.3786	0.1528	8.5049e-3	1.9079	0.5292
								5.2915e-9




Figure B24 Plot of the apparent diffusion coefficient as a function of scattering vector at 30 °C for the fixed HPC concentration of 1 g/l and the fixed CTAB concentration of 2.00 mM.

Table B25 Data of the center of mass diffusion coefficient (D_c) and the hydrodynamic radius (R_h) as a function of CTAB concentration at 30 °C for the HPC/CTAB/water system for the fixed HPC concentration of 1 g/l.

[CTAB] (mM)	D_c (cm ² /s)	R_h (nm)
0.05	1.4882e-7	18.7
0.50	1.0152e-7	27.4
0.80	8.9576e-8	31.1
1.00	1.0673e-7	26.1
2.00	1.7810e-7	15.6




Figure B25 Plot of the polydispersity as a function of CTAB concentration at 30 °C for the HPC/OTG/water system at the fixed HPC concentration of 1 g/l and at the fixed angle of 90 °.

Table B26 Data for the HPC/CTAB/water system at the fixed HPC concentration of 3 g/l and at the fixed CTAB concentration of 0.05 mM.

Angle (degree)	Sample (μ s)	Mean (nm)	Width	Z _{Ave} (nm)	Poly-dispersity	In Range	Merit	D _{app} (cm ² /s)
60	3.00	31.9	45.4	25.3	0.483	93.1	43.7	17.4e-8
	3.00	31.9	46.5	25.3	0.484	90.8	43.8	17.4e-8
	3.00	31.2	44.8	24.9	0.465	94.5	43.8	17.8e-8
	Average	31.7	45.6	25.2	0.477	92.8	43.8	17.5e-8
	SD	0.0000	0.4041	0.8622	0.2309	0.01707	1.8682	0.0577
	75	1.70	28.1	38.8	22.9	0.423	94.9	46.1
Average	1.70	28.2	38.9	22.9	0.423	94.6	46.0	19.7e-8
	1.70	28.0	37.7	23.1	0.394	92.9	45.7	19.8e-8
	Average	1.70	28.1	38.5	23.0	0.413	94.1	45.9
	SD	0.0000	0.1000	0.6658	0.1155	0.0167	1.0786	0.2082
	90	1.30	27.0	35.5	22.5	0.375	96.3	44.8
	Average	1.30	27.0	35.9	22.4	0.385	98.6	45.0
Average	1.30	27.2	36.3	22.5	0.388	93.6	45.1	20.4e-8
	SD	0.0000	0.1155	0.4000	0.0577	6.8059e-3	2.5027	0.1528
	105	0.90	26.1	34.7	21.7	0.383	97.4	41.9
	Average	0.90	26.1	34.3	21.8	0.372	94.8	42.5
	SD	0.0000	0.0000	0.2000	0.0577	5.5378e-3	1.3204	0.3464
	105	0.90	26.1	34.5	21.7	0.378	95.7	42.5
Average	0.90	26.1	34.5	21.7	0.378	96.0	42.3	21.2e-8
	SD	0.0000	0.0000	0.2000	0.0577	5.5378e-3	1.3204	0.3464




Figure B26 Plot of the apparent diffusion coefficient as a function of scattering vector at 30 °C for the fixed HPC concentration of 3 g/l and the fixed CTAB concentration of 0.05 mM.

Table B27 Data for the HPC/CTAB/water system at the fixed HPC concentration of 3 g/l and at the fixed CTAB concentration of 0.50 mM.

Angle (degree)	Sample (μ s)	Mean (nm)	Width	Z_{Ave} (nm)	Poly-dispersity	In Range	Merit	D_{app} (cm^2/s)
60	5.00	48.4	75.6	36.4	0.586	94.8	45.6	11.5e-8
	5.00	48.2	75.2	36.4	0.583	93.0	46.1	11.5e-8
	5.00	48.2	74.8	36.4	0.578	94.5	47.6	11.5e-8
	Average	5.00	48.3	75.2	36.4	0.582	94.1	46.4
	SD	0.0000	0.1155	0.4000	0.0000	4.0415e-3	0.9644	1.0408
	75	3.40	43.7	66.2	33.7	0.538	99.3	49.0
Average	3.40	43.8	66.5	33.6	0.544	97.5	48.9	12.7e-8
	3.40	44.0	68.5	33.1	0.584	97.3	49.2	12.6e-8
	Average	3.40	43.8	67.1	33.5	0.555	98.0	49.0
	SD	0.0000	0.1528	1.2503	0.3215	0.0250	1.1015	0.1528
	90	1.70	41.4	63.6	31.5	0.561	99.7	46.6
	1.70	41.3	63.3	31.6	0.546	97.5	46.4	13.5e-8
Average	1.70	41.3	63.7	31.4	0.567	97.9	46.7	13.4e-8
	SD	0.0000	0.0577	0.2082	0.1000	0.0108	1.1719	0.1528
	105	1.30	39.5	60.2	30.3	0.549	97.9	47.0
	1.30	39.3	59.7	30.2	0.542	96.1	47.0	14.1e-8
	1.30	39.4	59.6	30.4	0.537	96.7	44.5	14.1e-8
	Average	1.30	39.4	59.8	30.3	0.523	96.9	46.2.
SD	0.0000	0.1000	0.3215	0.1000	6.0277e-3	0.9165	1.4434	0.0000




Figure B27 Plot of the apparent diffusion coefficient as a function of scattering vector at 30 °C for the fixed HPC concentration of 3 g/l and the fixed CTAB concentration of 0.50 mM.

Table B28 Data for the HPC/CTAB/water system at the fixed HPC concentration of 3 g/l and at the fixed CTAB concentration of 0.80 mM.

Angle (degree)	Sample (μs)	Mean (nm)	Width	Z _{Ave} (nm)	Poly- dispersity	In Range	Merit	D _{app} (cm ² /s)
60	3.40	44.3	68.4	33.7	0.568	94.1	45.3	12.5e-8
	3.40	47.4	76.1	34.9	0.634	86.3	44.4	11.7e-8
	3.40	47.2	75.3	34.9	0.622	87.3	44.5	11.8e-8
	Average	3.40	46.3	73.3	34.5	0.608	89.2	44.7
SD	0.0000	1.7349	4.2336	0.6928	0.0352	4.2442	0.4933	4.3589e-9
75	2.50	40.9	61.7	31.6	0.533	92.3	46.3	13.6e-8
	2.50	41.8	63.4	32.2	0.539	91.0	46.2	13.3e-8
	2.50	41.1	61.8	31.7	0.532	93.7	46.6	13.5e-8
	Average	2.50	41.3	62.3	31.8	0.535	92.3	46.4
SD	0.0000	0.4726	0.9539	0.3215	3.7859e-3	1.3503	0.2082	1.5275e-9
90	1.50	38.4	57.6	29.8	0.523	95.3	44.8	14.4 e-8
	1.50	38.6	58.0	29.8	0.529	95.9	44.4	14.4 e-8
	1.50	38.0	56.5	29.6	0.512	96.8	44.3	14.6e-8
	Average	1.50	38.3	57.4	29.7	0.521	96.0	44.5
SD	0.0000	0.3055	0.7767	0.1155	8.6217e-3	0.7550	0.2646	0.0000
105	1.20	36.5	52.9	28.9	0.478	94.2	43.9	15.2e-8
	1.20	36.4	53.4	28.6	0.496	98.1	44.3	15.3e-8
	1.20	36.5	53.7	28.7	0.498	95.4	43.5	15.2e-8
	Average	1.20	36.5	53.3	28.7	0.491	95.9	43.9
SD	0.0000	0.0577	0.4041	0.1528	0.0110	1.9975	0.4000	5.7735e-10




Figure B28 Plot of the apparent diffusion coefficient as a function of scattering vector at 30 °C for the fixed HPC concentration of 3 g/l and the fixed CTAB concentration of 0.80 mM.

Table B29 Data for the HPC/CTAB/water system at the fixed HPC concentration of 3 g/l and at the fixed CTAB concentration of 1.00 mM.

Angle (degree)	Sample (μs)	Mean (nm)	Width	Z _{Ave} (nm)	Poly- dispersity	In Range	Merit	D _{app} (cm ² /s)
60	4.00	46.9	76.3	34.0	0.662	93.2	44.6	11.8e-8
	4.00	47.2	77.1	34.1	0.671	93.9	44.4	11.8e-8
	4.00	46.2	75.0	33.6	0.658	94.5	44.5	12.0e-8
	Average	4.00	46.8	73.1	0.664	93.9	44.5	11.9e-8
	SD	0.0000	0.5132	1.0599	0.2646	6.6583e-3	0.6506	0.1000
	75	2.30	41.4	66.3	30.5	0.629	97.8	45.6
Average	2.30	41.8	67.0	30.8	0.632	96.6	45.6	13.3e-8
	2.30	41.5	66.4	30.6	0.629	98.6	45.3	13.4e-8
	Average	2.30	41.6	66.6	30.6	0.630	97.7	45.5
	SD	0.0000	0.2082	0.3786	0.1528	1.7321e-3	1.0066	0.1732
	90	1.60	38.9	61.6	29.0	0.609	95.4	43.3
	1.60	38.6	61.7	28.9	0.613	97.8	43.5	14.3e-8
Average	1.60	38.3	60.0	28.6	0.600	98.1	43.1	14.5e-8
	1.60	38.6	61.1	28.8	0.607	97.1	43.3	14.4e-8
	SD	0.0000	0.3000	0.9539	0.2082	6.6583e-3	1.4799	0.2000
	105	1.20	36.8	57.4	27.6	0.588	96.2	43.5
	1.20	36.6	57.1	27.5	0.586	98.0	43.4	15.2e-8
	Average	1.20	36.7	57.4	27.6	0.588	98.0	43.7
SD	1.20	36.7	57.3	27.6	0.587	97.4	43.5	15.1e-8
	0.0000	0.1000	0.1732	0.0577	1.1547e-3	1.0392	0.1528	5.7735e-10




Figure B29 Plot of the apparent diffusion coefficient as a function of scattering vector at 30 °C for the fixed HPC concentration of 3 g/l and the fixed CTAB concentration of 1.00 mM.

Table B30 Data for the HPC/CTAB/water system at the fixed HPC concentration of 3 g/l and at the fixed CTAB concentration of 2.00 mM.

Angle (degree)	Sample (μs)	Mean (nm)	Width	Z _{Ave} (nm)	Poly- dispersity	In Range	Merit	D _{app} (cm ² /s)
60	4.20	49.1	85.7	32.9	0.831	89.1	41.6	11.3e-8
	4.20	50.6	89.5	33.3	0.866	92.4	39.6	11.0e-8
	4.20	48.9	86.0	32.4	0.851	91.5	38.6	11.4e-8
	Average	4.20	49.5	87.1	32.9	0.849	91.0	39.9
	SD	0.0000	0.9292	2.1127	0.4509	0.0176	1.7059	1.5275
	75	2.40	39.8	69.2	26.9	0.815	92.9	46.1
Average	2.40	39.7	68.9	26.8	0.813	91.6	45.2	13.9e-8
	2.40	41.4	72.5	27.6	0.837	88.6	46.4	14.0e-8
	Average	2.40	40.3	70.2	27.1	0.822	91.0	45.9
	SD	0.0000	0.9539	1.9975	0.4359	0.0133	2.2053	0.6245
	90	1.70	33.8	57.4	23.5	0.753	94.0	43.9
	1.70	32.8	55.2	23.0	0.736	96.2	44.0	16.4e-8
Average	1.70	35.1	60.0	24.2	0.772	94.4	43.9	15.8e-8
	1.70	33.9	57.5	23.6	0.754	94.9	43.9	16.4e-8
	SD	0.0000	1.1533	2.4028	0.6028	0.0180	1.1719	0.0577
	105	1.10	30.4	51.9	20.9	0.774	94.2	42.1
	1.10	31.0	53.0	21.3	0.777	91.4	41.4	17.9e-8
	Average	1.10	30.2	51.5	20.8	0.769	95.8	42.2
SD	1.10	30.5	52.1	21.0	0.773	93.8	41.9	18.2e-8
	0.0000	0.4163	0.7767	0.2646	4.0415e-3	2.2271	0.4359	2.6458e-9




Figure B30 Plot of the apparent diffusion coefficient as a function of scattering vector at 30 °C for the fixed HPC concentration of 3 g/l and the fixed CTAB concentration of 2.00 mM.

Table B31 Data for the HPC/CTAB/water system at the fixed HPC concentration of 3 g/l and at the fixed CTAB concentration of 3.00 mM.

Angle (degree)	Sample (μs)	Mean (nm)	Width	Z _{Ave} (nm)	Poly- dispersity	In Range	Merit	D _{app} (cm ² /s)
60	4.10	36.5	61.4	25.6	0.734	96.4	41.4	15.2e-8
	4.10	43.5	76.0	29.1	0.832	90.6	43.5	12.8e-8
	4.10	42.2	73.5	28.4	0.832	89.7	39.1	13.1e-8
	Average	4.10	40.7	70.3	0.799	92.2	41.3	13.7e-8
	SD	0.0000	3.7233	7.8083	1.8520	0.0566	3.6364	2.2008
	75	2.60	35.1	59.8	24.3	0.761	94.3	48.4
Average	2.60	35.7	61.1	24.6	0.773	95.1	49.1	15.8e-8
	2.60	35.8	61.1	24.7	0.770	93.1	49.0	15.5e-8
	Average	2.60	35.5	60.7	24.5	0.768	94.2	48.8
	SD	0.0000	0.3786	0.7506	0.2082	6.2450e-3	1.0066	0.3786
	90	1.60	30.6	52.5	21.1	0.768	96.3	46.9
	1.60	30.8	52.7	21.2	0.772	98.1	47.1	18.0e-8
Average	1.60	29.1	49.3	20.3	0.746	95.5	46.1	19.1e-8
	1.60	30.2	51.5	20.9	0.762	96.6	46.7	18.4e-8
	SD	0.0000	0.9292	1.9079	0.4933	0.0140	1.3317	0.5292
	105	0.90	28.6	50.6	18.9	0.864	94.5	44.2
	0.90	26.6	49.5	18.6	0.852	95.1	42.6	19.8e-8
	Average	0.90	27.0	47.1	18.5	0.804	97.2	44.1
SD	0.90	27.4	49.1	18.7	0.840	95.6	43.6	19.9e-8
	0.0000	1.0583	1.7898	0.2082	0.0317	1.4177	0.8963	5.0332e-9




Figure B31 Plot of the apparent diffusion coefficient as a function of scattering vector at 30 °C for the fixed HPC concentration of 3 g/l and the fixed CTAB concentration of 3.00 mM.

Table B32 Data for the HPC/CTAB/water system at the fixed HPC concentration of 3 g/l and at the fixed CTAB concentration of 4.00 mM.

Angle (degree)	Sample (μs)	Mean (nm)	Width	Z _{Ave} (nm)	Poly- dispersity	In Range	Merit	D _{app} (cm ² /s)
60	3.30	30.9	53.2	21.1	0.804	94.6	44.6	18.0e-8
	3.30	31.8	55.1	21.6	0.824	96.8	45.1	17.4e-8
	3.30	31.2	53.9	21.3	0.797	96.1	45.3	17.8e-8
	Average	3.0	31.3	54.1	21.3	0.808	95.8	45.0
	SD	0.0000	0.4583	0.9609	0.2517	0.0140	1.1240	0.3606
	75	1.90	25.5	43.5	17.6	0.766	95.4	46.2
Average	1.90	25.5	43.4	17.6	0.766	97.6	47.0	21.8e-8
	1.90	26.2	45.0	18.0	0.780	95.4	47.5	21.2e-8
	Average	1.90	25.7	44.0	17.7	0.771	96.1	46.9
	SD	0.0000	0.4041	0.8963	0.2309	8.0829e-3	1.2702	0.6557
	90	1.30	23.7	40.5	16.4	0.766	94.4	45.4
	1.30	23.6	40.2	16.4	0.761	97.2	45.2	23.4E-8
Average	1.30	23.4	39.7	16.2	0.758	97.0	46.1	23.5E-8
	Average	1.30	23.6	40.1	16.3	0.7617	96.2	45.6
	SD	0.0000	0.1528	0.4041	0.1155	4.0415e-3	1.5620	0.4726
	105	0.90	22.0	37.6	15.1	0.772	96.7	41.6
	0.90	22.0	37.7	15.1	0.778	96.3	41.9	25.2E-8
	Average	0.90	21.8	37.2	15.0	0.769	97.4	42.4
SD	0.90	21.9	37.5	15.1	0.773	96.8	42.0	25.3e-8
	0.0000	0.1155	0.2646	0.0577	4.5826e-3	0.5568	0.4041	1.5275e-9




Figure B32 Plot of the apparent diffusion coefficient as a function of scattering vector at 30 °C for the fixed HPC concentration of 3 g/l and the fixed CTAB concentration of 4.00 mM.

Table B33 Data for the HPC/CTAB/water system at the fixed HPC concentration of 3 g/l and at the fixed CTAB concentration of 4.40 mM.

Angle (degree)	Sample (μs)	Mean (nm)	Width	Z _{Ave} (nm)	Poly- dispersity	In Range	Merit	D _{app} (cm ² /s)
60	3.30	18.3	29.2	13.5	0.626	93.1	38.7	30.3e-8
	3.30	19.5	31.5	14.3	0.645	90.7	39.6	28.4e-8
	3.30	19.0	30.5	14.0	0.635	91.9	39.3	29.2e-8
	Average	3.30	18.9	30.4	0.635	91.9	39.2	29.3e-8
	SD	0.0000	0.6028	1.1533	0.4041	0.0000	1.2000	0.4583
	75	1.10	15.7	26.5	10.9	0.747	92.3	42.6
		1.10	15.6	26.3	10.8	0.748	93.0	43.0
		1.10	15.7	26.5	10.9	0.749	91.8	43.5
		Average	1.10	15.7	26.4	10.9	0.748	92.4
90	SD	0.0000	0.0577	0.1155	0.0577	1.0000e-3	0.6028	0.4509
	90	0.80	14.7	24.6	10.4	0.718	92.8	37.7
		0.80	14.2	23.6	10.1	0.707	93.5	38.6
		0.80	14.3	23.7	10.2	0.701	93.5	38.4
	Average	0.80	14.4	24.0	10.2	0.709	93.3	38.2
	SD	0.0000	0.2646	0.5508	0.1528	9.0115e-3	0.4041	0.4726
	105	0.60	13.6	22.5	9.6	0.705	93.9	35.6
		0.60	13.7	22.9	9.7	0.715	89.2	33.7
		0.60	13.3	22.1	9.4	0.708	95.6	38.4
Average	0.60	13.5	22.5	9.6	0.709	92.9	35.9	38.6e-8
	SD	0.0000	0.2082	0.4000	0.1528	5.1316e-3	3.3151	2.3643




Figure B33 Plot of the apparent diffusion coefficient as a function of scattering vector at 30 °C for the fixed HPC concentration of 3 g/l and the fixed CTAB concentration of 4.40 mM.

Table B34 Data of the center of mass diffusion coefficient (D_c) and the hydrodynamic radius (R_h) as a function of CTAB concentration at 30 °C for the HPC/CTAB/water system for the fixed HPC concentration of 3 g/l.

[CTAB] (mM)	D_c (cm ² /s)	R_h (nm)
0.05	1.7678e-7	15.7
0.50	1.0631e-7	26.2
0.80	9.6353e-8	28.9
1.00	1.0351e-7	26.9
2.00	7.5466e-8	36.9
3.00	9.5424e-8	29.2
4.00	1.6288e-7	17.1
4.40	2.0683e-7	13.5




Figure B34 Plot of the polydispersity as a function of CTAB concentration at 30 °C for the HPC/OTG/water system at the fixed HPC concentration of 3 g/l and at the fixed angle of 90 °.

Table B35 Data for the HPC/CTAB/water system at the fixed HPC concentration of 5 g/l and at the fixed CTAB concentration of 0.05 mM.

Angle (degree)	Sample (μ s)	Mean (nm)	Width	Z_{Ave} (nm)	Poly-dispersity	In Range	Merit	D_{app} (cm^2/s)
60	2.60	29.2	40.7	23.5	0.431	97.6	50.2	19.0e-8
	2.60	29.6	42.0	23.7	0.454	95.5	50.2	18.8e-8
	2.60	30.3	43.7	24.0	0.476	95.6	50.2	18.4e-8
	Average	2.60	29.7	42.1	0.454	96.2	50.2	18.7e-8
	SD	0.0000	0.5568	1.5044	0.2517	0.0225	1.1846	0.0000
	75	1.70	28.5	39.6	23.1	0.428	97.5	51.9
Average	1.70	28.9	40.6	23.3	0.444	96.4	52.3	19.3e-8
	1.70	28.8	40.7	23.1	0.450	93.0	52.6	19.8e-8
	Average	1.70	28.7	40.3	23.2	0.441	95.6	52.3
	SD	0.0000	0.2082	0.6083	0.1155	0.0114	2.3459	0.3512
	90	1.40	28.1	38.6	23.0	0.415234	94.9	51.3
	Average	1.40	28.1	39.3	22.7	0.436	97.5	51.8
Average	1.40	28.2	39.0	23.0	0.422	97.0	52.0	19.7e-8
	SD	0.0000	0.0577	0.3512	0.1732	9.8995e-3	1.3796	0.3606
	105	0.90	26.9	37.1	21.9	0.424	98.2	52.1
	Average	0.90	27.1	35.5	22.6	0.370	98.2	51.5
	SD	0.0000	0.1000	0.8327	0.3512	0.0274	0.4619	0.3215
	105	0.90	27.0	36.7	22.2	0.405	99.0	51.6
Average	0.90	27.0	36.4	22.2	0.400	98.5	51.7	20.6e-8
	SD	0.0000	0.1000	0.8327	0.3512	0.0274	0.4619	0.3215




Figure B35 Plot of the apparent diffusion coefficient as a function of scattering vector at 30 °C for the fixed HPC concentration of 5 g/l and the fixed CTAB concentration of 0.05 mM.

Table B36 Data for the HPC/CTAB/water system at the fixed HPC concentration of 5 g/l and at the fixed CTAB concentration of 0.50 mM.

Angle (degree)	Sample (μ s)	Mean (nm)	Width	Z_{Ave} (nm)	Poly-dispersity	In Range	Merit	D_{app} (cm^2/s)
60	3.40	41.8	64.1	31.9	0.557	99.5	53.3	13.3e-8
	3.40	41.6	63.8	31.8	0.556	99.6	53.2	13.4e-8
	3.40	41.3	63.0	31.6	0.550	96.2	53.2	13.5e-8
	Average	3.40	41.6	63.6	0.554	98.4	53.2	13.4e-8
	SD	0.0000	0.2517	0.5686	0.1528	3.7859e-3	1.9348	0.0577
	75	2.20	39.2	59.3	30.2	0.536	97.4	54.2
Average	2.20	39.0	58.6	30.2	0.528	98.5	54.2	14.3e-8
	2.20	39.4	59.5	30.4	0.535	98.1	54.4	14.1e-8
	Average	2.20	39.2	59.1	30.3	0.533	98.0	54.3
	SD	0.0000	0.2000	0.4726	0.1155	4.3589e-3	0.5568	0.1155
	90	1.60	36.9	52.2	28.7	0.520	98.4	51.9
	1.60	36.9	55.0	28.7	0.515	98.4	51.6	15.1e-8
Average	1.60	36.6	54.0	28.7	0.510	97.7	52.1	15.2e-8
	Average	1.60	36.8	53.7	28.7	0.515	98.2	51.9
	SD	0.0000	0.1732	1.4189	0.0000	5.0000e-3	0.4041	0.2517
	105	1.20	27.8	51.0	27.8	0.481	99.0	52.8
	1.20	28.9	50.5	27.9	0.470	99.5	53.0	15.9e-8
	Average	1.20	27.9	52.4	27.9	0.500	99.6	53.4
SD	1.20	28.2	51.3	27.9	0.484	99.4	53.1	15.8e-8
	0.0000	0.6083	0.9849	0.0577	0.0152	0.3215	0.3055	1.1547e-9




Figure B36 Plot of the apparent diffusion coefficient as a function of scattering vector at 30 °C for the fixed HPC concentration of 5 g/l and the fixed CTAB concentration of 0.50 mM.

Table B37 Data for the HPC/CTAB/water system at the fixed HPC concentration of 5 g/l and at the fixed CTAB concentration of 0.80 mM.

Angle (degree)	Sample (μ s)	Mean (nm)	Width	Z _{Ave} (nm)	Poly- dispersity	In Range	Merit	D _{app} (cm ² /s)
60	3.80	48.9	78.5	35.9	0.636	96.5	52.0	11.4e-8
	3.80	49.7	80.5	36.3	0.650	95.2	51.3	11.2e-8
	3.80	49.7	80.2	36.4	0.644	95.7	51.6	11.2e-8
	Average	3.80	49.4	79.7	0.643	95.8	51.6	11.3e-8
	SD	0.0000	0.4619	1.0786	0.2646	7.0238e-3	0.3512	1.1547e-9
	75	2.50	45.8	71.5	34.5	0.585	98.1	53.3
		2.50	45.4	71.4	33.9	0.599	98.1	53.5
		2.50	45.7	72.3	34.0	0.608	97.4	54.2
		Average	2.50	45.6	71.7	34.1	53.7	12.2e-8
		SD	0.0000	0.2082	0.4933	0.3215	0.4726	1.0000e-9
		90	1.70	43.2	68.8	32.0	52.7	12.9e-8
			1.70	42.9	65.6	32.8	52.2	13.0e-8
			1.70	42.7	67.0	32.0	52.3	13.0e-8
			Average	42.9	67.1	32.3	52.4	13.0e-8
			SD	0.0000	0.2517	1.6042	0.2646	5.7735e-10
			105	1.40	40.5	63.2	54.6	13.8e-8
				1.40	40.6	62.1	52.7	13.7e-8
				1.40	41.1	62.8	53.2	13.5e-8
				Average	40.7	62.7	53.5	13.7e-8
				SD	0.0000	0.3215	0.9849	1.5275e-9
						0.5568	0.6000	




Figure B37 Plot of the apparent diffusion coefficient as a function of scattering vector at 30 °C for the fixed HPC concentration of 5 g/l and the fixed CTAB concentration of 0.80 mM.

Table B38 Data for the HPC/CTAB/water system at the fixed HPC concentration of 5 g/l and at the fixed CTAB concentration of 1.00 mM.

Angle (degree)	Sample (μ s)	Mean (nm)	Width	Z_{Ave} (nm)	Polydispersity	In Range	Merit	D_{app} (cm^2/s)
60	4.10	53.9	90.0	38.1	0.717	97.8	52.4	10.3e-8
	4.10	52.6	87.4	37.4	0.705	97.1	52.4	10.6e-8
	4.10	52.2	96.2	37.3	0.694	98.1	52.4	10.7e-8
	Average	52.9	91.2	37.6	0.705	97.7	52.4	10.5e-8
	SD	0.0000	0.8888	4.5211	0.4359	0.0115	0.0000	2.0817e-9
	75	2.70	48.2	78.2	35.1	0.644	98.7	53.3
Average	2.70	49.0	79.1	35.3	0.665	99.5	53.2	11.4e-8
	2.70	48.4	79.0	35.0	0.667	99.0	53.1	11.5e-8
	Average	2.70	48.5	78.8	35.1	0.659	99.1	53.2
	SD	0.0000	0.4163	0.4933	0.1528	0.0127	0.4041	5.7735e-10
	90	1.80	45.5	73.8	33.1	0.655	97.2	51.4
	Average	1.80	45.3	73.6	32.9	0.659	97.2	51.7
Average	1.80	45.1	73.0	33.0	0.648	96.9	51.4	12.3e-8
	SD	0.0000	0.2000	0.4163	0.1000	5.5678e-3	0.1732	0.1732
	105	1.40	41.7	66.1	31.0	0.612	98.2	52.9
	Average	1.40	41.2	65.2	30.7	0.610	98.7	53.4
	SD	0.0000	0.3606	0.7095	0.1732	4.1633e-3	0.8185	0.2517
	1.40	41.9	66.6	31.0	0.618	97.1	53.1	13.3e-8
Average	1.40	41.6	66.0	30.9	0.613	98.0	53.1	13.4e-8
	SD	0.0000	0.3606	0.7095	0.1732	4.1633e-3	0.8185	1.0000e-9




Figure B38 Plot of the apparent diffusion coefficient as a function of scattering vector at 30 °C for the fixed HPC concentration of 5 g/l and the fixed CTAB concentration of 1.00 mM.

Table B39 Data for the HPC/CTAB/water system at the fixed HPC concentration of 5 g/l and at the fixed CTAB concentration of 2.00 mM.

Angle (degree)	Sample (μs)	Mean (nm)	Width	Z _{Ave} (nm)	Poly- dispersity	In Range	Merit	D _{app} (cm ² /s)
60	4.80	55.8	97.5	37.3	0.832	90.2	50.8	10.0e-8
	4.80	55.3	95.0	37.2	0.833	93.6	52.2	10.1e-8
	4.80	54.6	98.3	36.8	0.818	97.3	53.1	10.2e-8
	Average	4.80	55.2	96.9	0.828	93.7	52.0	10.1e-8
	SD	0.0000	0.6028	1.7214	0.2828	8.3865e-3	3.5511	1.1590
	75	2.50	40.8	77.9	30.2	0.816	95.1	53.2
Average	2.50	43.3	75.0	29.4	0.804	96.4	53.7	12.4e-8
	2.50	44.7	77.7	30.1	0.818	97.4	53.5	12.8e-8
	Average	2.50	42.9	76.9	29.9	0.813	96.3	53.5
	SD	0.0000	1.9757	1.6197	0.4359	7.5719e-3	1.1533	0.2517
	90	1.80	41.8	71.9	28.5	0.790	93.0	51.9
	Average	1.80	40.6	69.5	27.9	0.778	97.4	51.8
Average	1.80	41.8	72.0	28.5	0.791	96.5	51.5	13.7e-8
	1.80	41.4	71.1	28.3	0.786	95.6	51.7	13.3e-8
	SD	0.0000	0.6928	1.4154	0.3464	7.2342e-3	2.3245	0.2082
	105	1.30	37.7	64.4	25.9	0.774	97.9	52.7
	Average	1.30	37.5	64.0	25.8	0.771	94.7	51.7
	SD	0.0000	0.2000	0.3512	0.1000	2.5166e-3	1.6371	0.5000




Figure B39 Plot of the apparent diffusion coefficient as a function of scattering vector at 30 °C for the fixed HPC concentration of 5 g/l and the fixed CTAB concentration of 2.00 mM.

Table B40 Data for the HPC/CTAB/water system at the fixed HPC concentration of 5 g/l and at the fixed CTAB concentration of 3.00 mM.

Angle (degree)	Sample (μ s)	Mean (nm)	Width	Z _{Ave} (nm)	Poly- dispersity	In Range	Merit	D _{app} (cm ² /s)
Average	3.80	40.6	70.5	28.4	0.840	93.6	49.7	13.1e-8
	3.80	42.6	70.7	28.9	0.856	93.4	50.2	12.7e-8
	3.80	43.7	77.0	29.2	0.858	91.9	50.0	12.6e-8
	3.80	42.3	72.7	28.8	0.851	93.0	50.0	12.8e-8
	SD	0.00	1.5716	3.6964	0.4041	9.8658e-3	0.2517	2.6458e-9
	75	2.30	37.1	65.5	24.9	0.820	96.5	52.7
Average	2.30	37.0	64.3	24.9	0.818	92.6	52.7	15.1e-8
	2.30	36.7	63.7	24.8	0.810	96.4	52.6	15.2e-8
	2.30	36.9	64.5	24.9	0.816	95.2	52.7	15.1e-8
	SD	0.0000	0.2082	0.9165	0.0577	5.2915e-3	2.2234	0.0577
	90	1.60	32.7	56.0	22.5	0.774	95.3	49.7
	1.60	32.6	55.7	22.5	0.771	96.0	49.8	17.1e-8
Average	1.60	32.6	56.0	22.5	0.773	96.8	50.3	17.0e-8
	1.60	32.6	55.9	22.5	0.773	96.0	49.9	17.0e-8
	SD	0.0000	0.0577	0.1732	0.0000	1.5275e-3	0.7506	0.3215
	105	1.30	29.7	49.8	21.0	0.723	97.7	49.9
	1.30	29.6	51.2	20.5	0.779	97.1	49.5	18.8e-8
	1.30	29.5	50.5	20.3	0.775	97.3	50.6	18.9e-8
Average	1.30	29.6	50.5	20.6	0.759	97.4	50.0	18.8e-8
	SD	0.0000	0.1000	0.7000	0.3606	0.0312	0.3055	0.5568
								1.0000e-9




Figure B40 Plot of the apparent diffusion coefficient as a function of scattering vector at 30 °C for the fixed HPC concentration of 5 g/l and the fixed CTAB concentration of 3.00 mM.

Table B41 Data for the HPC/CTAB/water system at the fixed HPC concentration of 5 g/l and at the fixed CTAB concentration of 4.00 mM.

Angle (degree)	Sample (μ s)	Mean (nm)	Width	Z_{Ave} (nm)	Poly-dispersity	In Range	Merit	D_{app} (cm^2/s)
60	3.50	29.2	49.3	20.4	0.741	95.6	45.8	19.0e-8
	3.50	31.6	54.1	21.7	0.775	94.6	45.2	17.6e-8
	3.50	32.9	54.1	23.7	0.682	95.2	45.0	16.9e-8
	Average	31.2	52.5	21.9	0.733	95.1	45.3	17.8e-8
	SD	0.0000	1.8771	2.7713	1.6623	0.0471	0.5033	0.4163
	75	1.90	26.0	44.5	17.9	0.774	92.1	48.0
Average	1.90	26.1	44.6	16.0	0.773	95.0	48.7	21.3e-8
	1.90	26.2	44.8	18.0	0.774	95.1	48.8	21.2e-8
	Average	26.1	44.6	17.3	0.774	94.1	48.5	21.3e-8
	SD	0.0000	0.1000	0.1528	1.1269	5.7735e-4	1.7039	0.4359
	90	1.20	23.0	39.4	15.8	0.775	96.0	47.6
	1.20	22.6	38.5	15.5	0.769	94.9	48.0	24.6e-8
Average	1.20	22.8	39.0	15.7	0.772	96.3	48.0	24.4e-8
	SD	0.0000	0.2000	0.4509	0.1528	3.0000e-3	0.7371	0.2309
	105	1.00	21.3	35.7	15.0	0.723	96.7	48.6
	1.00	21.5	36.0	15.1	0.726	97.6	49.0	25.8e-8
	1.00	21.5	36.1	15.1	0.728	97.3	49.2	25.8e-8
	Average	21.4	35.9	15.1	0.726	97.2	48.9	25.9e-8
SD	0.0000	0.1155	0.2082	0.0577	2.5166e-3	0.4583	0.3055	1.7321e-9




Figure B41 Plot of the apparent diffusion coefficient as a function of scattering vector at 30 °C for the fixed HPC concentration of 5 g/l and the fixed CTAB concentration of 4.00 mM.

Table B42 Data for the HPC/CTAB/water system at the fixed HPC concentration of 5 g/l and at the fixed CTAB concentration of 5.00 mM.

Angle (degree)	Sample (μ s)	Mean (nm)	Width	Z_{Ave} (nm)	Poly-dispersity	In Range	Merit	D_{app} (cm^2/s)
75	1.70	20.4	34.3	14.3	0.733	94.8	47.8	27.3e-8
	1.70	20.0	33.7	14.1	0.730	95.8	47.5	27.7e-8
	1.70	20.4	34.4	14.3	0.735	94.6	47.7	27.2e-8
	Average	1.70	20.3	34.1	14.2	0.733	95.1	47.7
SD	0.0000	0.2309	0.3786	0.1155	2.5166e-3	0.6429	0.1528	2.6458e-9
90	1.20	18.6	31.1	13.2	0.714	95.2	46.7	29.8e-8
	1.20	18.5	30.9	13.1	0.713	95.5	46.5	30.0e-8
	1.20	18.5	30.9	13.1	0.715	96.4	46.7	29.9e-8
	Average	1.20	18.5	31.0	13.1	0.714	95.7	46.6
SD	0.0000	0.0577	0.1155	0.0577	1.0000e-3	0.6245	0.1155	1.0000e-9
100	0.90	17.2	28.8	12.1	0.726	96.4	47.7	32.3e-8
	0.90	16.8	28.0	11.9	0.712	90.4	47.0	30.6e-8
	0.90	17.1	28.7	12.1	0.723	95.9	47.5	32.4e-8
	Average	0.90	17.0	28.5	12.0	0.720	94.2	47.4
SD	0.0000	0.2082	0.4359	0.1155	7.3711e-3	3.3292	0.3606	1.0116e-8
105	0.80	16.7	28.0	11.7	0.729	93.2	45.6	33.2e-8
	0.80	16.8	28.3	11.8	0.729	97.5	46.4	33.0e-8
	0.80	16.5	27.7	11.6	0.725	95.2	46.0	33.6e-8
	Average	0.80	16.7	28.0	11.7	0.728	95.3	46.0
SD	0.0000	0.1528	0.3000	0.1000	2.3094e-3	2.1517	0.4000	3.0551e-9




Figure B42 Plot of the apparent diffusion coefficient as a function of scattering vector at 30 °C for the fixed HPC concentration of 5 g/l and the fixed CTAB concentration of 5.00 mM.

Table B43 Data of the center of mass diffusion coefficient (D_c) and the hydrodynamic radius (R_h) as a function of CTAB concentration at 30 °C for the HPC/CTAB/water system for the fixed HPC concentration of 5 g/l.

[CTAB] (mM)	D_c (cm ² /s)	R_h (nm)
0.05	1.7519e-7	15.9
0.50	1.1801e-7	23.6
0.80	9.7793e-8	28.4
1.00	8.6926e-8	32.0
2.00	7.5264e-8	37.0
3.00	9.0627e-8	30.0
4.00	1.2942e-7	21.5
5.00	1.9097e-7	14.6




Figure B43 Plot of the polydispersity as a function of CTAB concentration at 30 °C for the HPC/OTG/water system at the fixed HPC concentration of 5 g/l and at the fixed angle of 90 °.

C. Surface Tension Measurement

The OTG/Water System

Table C1 Surface tension as a function of the total OTG solution at 30 °C
for the OTG/water system (Figure 3.5)

[OTG] mM	Surface tension (mN/m)		Average	SD
	1	2		
2.00	40.3	39.7	40.00	0.4243
4.00	33.8	33.2	33.50	0.4243
6.00	29.3	29.6	29.45	0.2121
8.00	27.6	28.0	27.80	0.2828
8.50	27.9	27.3	27.60	0.4243
9.00	27.8	27.3	27.55	0.3536
9.50	27.6	27.6	27.60	0.0000
10.00	27.6	27.7	27.65	0.0707
11.00	27.7	27.6	27.65	0.0707
12.00	27.6	27.6	27.60	0.0000
13.00	27.6	27.6	27.60	0.0000
14.00	27.6	27.6	27.60	0.0000
15.00	27.6	27.6	27.60	0.0000

The CTAB/Water System

Table C2 Surface tension as a function of the total CTAB solution at 30 °C
for the CTAB/water system (Figure 3.7)

[CTAB] mM	Surface tension (mN/m)		Average	SD
	1	2		
0.05	56.4	56.3	56.35	0.0707
0.10	53.7	53.6	53.65	0.0707
0.50	43.0	42.9	42.95	0.0707
0.70	40.4	40.5	40.45	0.0707
0.80	38.9	38.9	38.90	0.0000
0.85	38.4	38.5	38.45	0.0707
1.00	37.4	37.6	37.50	0.1414
1.50	37.4	37.5	37.45	0.0707
2.00	37.8	37.9	37.85	0.0707
2.50	37.8	38.0	37.90	0.1414
3.00	37.8	38.0	37.90	0.1414
3.50	37.0	37.0	37.00	0.0000
4.00	37.0	37.0	37.00	0.0000
5.00	37.0	37.2	37.10	0.1414
6.00	37.0	37.2	37.10	0.1414
7.00	37.5	37.7	37.60	0.1414
8.00	37.0	37.1	37.05	0.0707
9.00	37.5	37.7	37.60	0.1414
10.00	37.0	37.2	37.10	0.1414

The HPC/OTG/Water System

Table C3 Surface tension as a function of the total OTG concentration at 30 °C for the HPC/OTG/water system and for the fixed HPC concentration of 5 g/l (Figure 3.10)

[OTG] (mM)	Surface tension (mN/m)		Average	SD
	1	2		
0.00	41.2	41.2	41.20	0.0000
0.08	41.2	41.2	41.20	0.0000
0.20	40.5	40.5	40.50	0.0000
0.42	40.5	40.4	40.45	0.0707
1.02	40.1	40.0	40.05	0.0707
5.04	33.9	33.9	33.90	0.0000
8.04	29.8	29.8	29.80	0.0000
10.20	29.8	29.8	29.80	0.0000
16.20	29.8	29.7	29.75	0.0707
20.04	29.8	29.9	29.85	0.0707

The HPC/CTAB/Water System

Table C4 Surface tension as a function of the total CTAB solution at 30 °C for the HPC/CTAB/water system and for the fixed HPC concentration of 1 g/l (Figure 3.15 (a))

[CTAB] (mM)	Surface tension (mN/m)		Average	SD
	1	2		
0.05	41.9	41.8	41.85	0.0707
0.10	40.9	40.9	40.90	0.0000
0.50	39.7	39.7	39.70	0.0000
0.70	39.1	39.1	39.10	0.0000
0.80	39.0	39.0	39.00	0.0000
0.85	39.2	39.2	39.20	0.0000
0.90	39.2	39.2	39.20	0.0000
1.00	39.0	39.0	39.00	0.0000
1.50	38.9	38.9	38.90	0.0000
2.00	38.6	38.7	38.65	0.0707
2.50	38.5	38.6	38.65	0.0707
3.00	38.4	38.4	38.40	0.0000
3.50	37.7	37.7	37.70	0.0000
4.00	37.6	37.7	37.65	0.0707
5.00	37.6	37.7	37.65	0.0707
6.00	37.6	37.5	37.55	0.0707
7.00	37.4	37.5	37.45	0.0707
8.00	37.2	37.3	37.25	0.0707
9.00	37.1	37.2	37.15	0.0707
10.00	37.1	37.1	37.05	0.0707

Table C5 Surface tension as a function of the total CTAB solution at 30 °C for the HPC/CTAB/water system and for the fixed HPC concentration of 5 g/l (Figure 3.15 (b))

[CTAB] (mM)	Surface tension (mN/m)		Average	SD
	1	2		
0.05	41.0	41.2	41.10	0.1414
0.10	40.4	40.6	40.50	0.1414
0.50	39.7	39.9	39.80	0.1414
0.70	38.7	38.7	38.70	0.0000
0.80	38.7	38.8	38.75	0.0707
0.85	38.8	38.8	38.80	0.0000
0.90	38.9	39.0	38.95	0.0707
1.00	39.0	39.1	39.05	0.0707
1.50	38.8	38.9	38.90	0.1414
2.00	38.6	38.7	38.65	0.0707
2.50	38.4	38.5	38.45	0.0707
3.00	38.4	38.2	38.30	0.1414
3.50	38.1	38.2	38.15	0.0707
4.00	37.7	37.7	37.70	0.0000
5.00	37.6	37.7	37.65	0.0707
6.00	37.8	37.8	37.80	0.0000
7.00	37.4	37.5	37.45	0.0707
8.00	37.5	37.5	37.50	0.0000
9.00	37.4	37.3	37.35	0.0707
10.00	37.2	37.3	37.25	0.0707

D. dn/dc Measurement

Table D1 Refractive index of HPC as a function of HPC concentration
(Figure 2.10)

[HPC] (g/l)	dn				Average	SD
	1	2	3	4		
0.10	1.81e-5	1.85e-5	1.89e-5	1.93e-5	1.8700e-5	5.1640e-7
0.20	3.49e-5	3.52e-5	3.56e-5	3.60e-5	3.5425e-5	4.7871e-7
0.30	5.25e-5	5.28e-5	5.32e-5	5.35e-5	5.3000e-5	4.3970e-7
0.40	6.82e-5	6.86e-5	6.89e-5	6.93e-5	6.8750e-5	4.6547e-7
0.50	8.26e-5	8.29e-5	8.32e-5	8.36e-5	8.3075e-5	4.2720e-7
0.60	9.86e-5	9.89e-5	9.92e-5	9.96e-5	9.9075e-5	4.2720e-7

E. Conductivity Measurement

The CTAB/Water System

Table E1 Conductivity as a function of CTAB concentration at 30 °C for the CTAB/water system (Figure 3.8)

[CTAB] (mM)	Conductivity (μs/cm)
0.05	8.5
0.10	12.4
0.50	48.7
0.70	67.0
0.80	76.9
0.85	79.5
0.90	85.0
1.00	90.6
1.50	104.5
2.00	118.5
2.50	131.8
3.00	142.1
3.50	154.4
4.00	165.7
5.00	180.4
6.00	208.0
7.00	231.0
8.00	260.0
9.00	276.0
10.00	300.0

Table E2 Conductivity as a function of the total CTAB concentration at 30 °C for the HPC/CTAB/water system and for the fixed HPC concentration of 1 g/l (Figure 3.16)

[CTAB] (mM)	Conductivity (μs/cm)
0.05	9.5
0.10	15.0
0.50	49.2
0.70	64.6
0.80	92.7
0.85	74.6
0.90	84.1
1.00	90.6
1.50	108.2
2.00	130.0
2.50	140.6
3.00	150.6
3.50	163.2
4.00	175.5
5.00	194.0
6.00	210.0
7.00	241.0
8.00	261.0
9.00	281.0
10.00	305.0

Table E3 Conductivity as a function of the total CTAB concentration at 30 °C for the HPC/CTAB/water system and for the fixed HPC concentration of 5 g/l (Figure 3.16)

[CTAB] (mM)	Conductivity (μs/cm)
0.10	23.0
0.50	52.5
0.70	67.1
0.80	73.1
0.85	76.9
0.90	85.1
1.00	84.4
1.50	107.9
2.00	130.4
2.50	145.8
3.00	162.7
3.50	182.1
4.00	196.2
5.00	227.0
6.00	253.0
7.00	263.0
8.00	298.0
9.00	328.0
10.00	335.0

CURRICULUM VITAE

Name : Ms. Pimpa Hormmirun

Birth Date : April 1, 1974

Nationality : Thai

University Education :

1992-1995 Bachelor's Degree of Science in Chemistry
Kasetsart University