

การสังเคราะห์อะตอมที่ตัดแปลงด้วยวิธีการแบบรวดเร็ว



นาย ไกร เมฆาสวรรณดำรง

วิทยานิพนธ์นี้เป็นส่วนหนึ่งของการศึกษาตามหลักสูตรปริญญาวิศวกรรมศาสตรมหาบัณฑิต

สาขาวิชาวิศวกรรมเคมี ภาควิชาวิศวกรรมเคมี

คณะวิศวกรรมศาสตร์ จุฬาลงกรณ์มหาวิทยาลัย

ปีการศึกษา 2542

ISBN 974-334-214-1

ลิขสิทธิ์ของจุฬาลงกรณ์มหาวิทยาลัย

12 พ.ย. 2546

119262929

# ONE POT SYNTHESIS OF SILICA MODIFIED ALUMINA



Mr. Okorn Mekasuvandamrong

สถาบันวิทยบริการ  
จุฬาลงกรณ์มหาวิทยาลัย

A Thesis Submitted in Partial Fulfillment of the Requirements  
for the Degree of Master of Engineering in Chemical Engineering

Department of Chemical Engineering

Faculty of Engineering

Chulalongkorn University


Academic Year 1999

ISBN 974-334-214-1


Thesis Title                      One pot synthesis of silica-modified alumina  
By                                      Mr. Okorn Mekasuvandamrong  
Department                      Chemical Engineering  
Thesis Advisor                      Professor Piyasan Praserthdam, Dr.Ing.  
Thesis Co-advisor                      Miss Waraporn Tanakulrungsank, Dr.Eng.

---


Accept by the Faculty of Engineering, Chulalongkorn University in Partial  
Fulfillment of the Requirements for the Master's Degree


..... Dean of Faculty of Engineering  
( Professor Somsak Panyakeow, Dr.Eng.)

Thesis Committee

.....Chairman  
(Associate Professor Kroekchai Sukanjanajtee, Ph.D.)

.....Thesis Advisor  
(Professor Piyasan Praserthdam, Dr.Ing.)

.....Thesis Co-advisor  
(Waraporn Tanakulrungsank, Dr.Eng.)

.....Member  
(Suphot Phatanasri, Dr.Eng.)

นายโอกร เมฆาสุวรรณดำรง : การสังเคราะห์อะลูมินาที่ดัดแปลงด้วยซิลิกาแบบรวดเดียว  
(ONE POT SYNTHESIS OF SILICA MODIFIED ALUMINA) อ. ที่ปรึกษา :  
ศ. ดร. ปิยะสาร ประเสริฐธรรม, อ. ที่ปรึกษาร่วม : อ.ดร. วราภรณ์ ชนะกุลรังสรรค์,  
80 หน้า. ISBN 974-334-214-1

ในการศึกษานี้ได้ทำการเตรียมอะลูมินาที่ดัดแปลงด้วยซิลิกา โดยใช้อะลูมินาไอโซโพรพอกไซด์ (Alumina isopropoxide) และ เทตระเอทิลออร์โทซิลิเกต (Tetraethyl orthosilicate) มาทำปฏิกิริยากับตัวทำละลายที่ต้องการศึกษา 1. ใส์โทลูอินในบีกเกอร์และในช่องว่างระหว่างบีกเกอร์ กับหม้ออัดความดัน 2. ใส์ 1-บิวทานอลแทนโทลูอิน 3. ใส์โทลูอินในบีกเกอร์ และใส์น้ำลงในช่องว่างระหว่างบีกเกอร์ กับหม้ออัดความดัน เมื่อปฏิกิริยาเกิดขึ้นอย่างสมบูรณ์แล้ว ทำการแยกสารที่ไม่ต้องการออกที่อุณหภูมิเหนือกว่าจุดวิกฤตของตัวทำละลาย ผลิตภัณฑ์ที่ได้นำมาให้ความร้อนในอากาศโดยใช้เตาเผา จะได้อะลูมินาที่ดัดแปลงด้วยซิลิกาที่มีความเสถียรทางความร้อนที่สูงและมีพื้นที่ผิวขนาดใหญ่ ตัวอย่างเช่นผลิตภัณฑ์ที่เตรียมจากอะลูมินาไอโซโพรพอกไซด์ (Alumina isopropoxide) และ เทตระเอทิล ออโรซิลิเกต (Tetraethyl orthosilicate) ละลายใน 1-บิวทานอล ที่อัตราส่วนโดยมวลเท่ากับ 8 มีพื้นที่ผิว  $169 \text{ m}^2/\text{g}$  หลังจากให้ความร้อนในอากาศที่อุณหภูมิ  $1150 \text{ }^\circ\text{C}$  เป็นเวลา 1 ชั่วโมง ซึ่งความเสถียรทางความร้อนและขนาดของพื้นที่ผิวจะขึ้นอยู่กับปฏิกิริยาที่เกิดขึ้นในแต่ละตัวทำละลายที่ใช้ในการสังเคราะห์

ภาควิชา.....วิศวกรรมเคมี.....  
สาขาวิชา.....วิศวกรรมเคมี.....  
ปีการศึกษา.....2542.....

ลายมือชื่อนิติ.....  
ลายมือชื่ออาจารย์ที่ปรึกษา.....  
ลายมือชื่ออาจารย์ที่ปรึกษาร่วม.....

# #4170663821: MAJOR CHEMICAL ENGINEERING

KEY WORD: SILICA-MODIFIED ALUMINA / SOLVOTHERMAL / CRITICAL / HIGH THERMAL STABILITY

OKORN MEKASUVANDUMRONG : ONE POT SYNTHESIS OF SILICA MODIFIED ALUMINA

THESIS ADVISOR: PROF. PIYASAN PRASERTHDAM, Dr.Ing.

THESIS CO-ADVISOR : . WARAPORN TANAKULRUNGSANK, Dr.Eng.

80 pp. ISBN 974-334-214-1

Mixtures of alumina isopropoxide (AIP) and tetraethyl orthosilicate (TEOS) in various organic solvents were set in an autoclave and heated at 300 °C for 2 h. The methods using in the preparation had three types. At the first preparation, toluene was used as the solvent in the beaker and in the gap between the autoclave wall and the beaker. In the second preparation, 1-butanol was used as the solvent instead of toluene. In the third preparation, toluene was used in the beaker and the water was added in the gap between the autoclave wall and the beaker. The fluid phase was removed at the supercritical temperature. The products were calcined in air to yield silica-modified aluminas. These silica-modified aluminas had high thermal stability and maintained large surface area at high temperature. For example, the product prepared from mixture of AIP and TEOS with Al/Si = 8 in 1-butanol had a surface area of 169 m<sup>2</sup>/g even after the calcination at 1150 °C. The surface area and thermal stability of products depended on the reaction mechanism operated in each solvent.

ภาควิชา.....วิศวกรรมเคมี.....

สาขาวิชา.....วิศวกรรมเคมี.....

ปีการศึกษา.....2542.....

ลายมือชื่อนิสิต.....*Toor*.....

ลายมือชื่ออาจารย์ที่ปรึกษา.....*el y*.....

ลายมือชื่ออาจารย์ที่ปรึกษาร่วม.....*Waraporn Tanakulrungsank*.....

# CONTENTS

	<b>PAGE</b>
ABSTRACT (IN THAI).....	iv
ABSTRACT (IN ENGLISH).....	v
ACKNOWLEDGEMENTS.....	vi
LIST OF TABLES.....	ix
LIST OF FIGURES.....	x
CHAPTER	
I INTRODUCTION.....	1
II LITERATURE REVIEWS.....	4
III THEORY.....	10
3.1 Alumina.....	10
3.2 Growth of single crystal.....	15
IV EXPERIMENTAL.....	26
4.1 Chemicals.....	26
4.2 Equipment.....	27
4.3 Synthesis of silica modified alumina.....	28
4.4 Characterization.....	30
V RESULTS AND DISCUSSION.....	34
5.1 RESULTS.....	34
5.1.1 Catalyst characterization.....	34
5.2.2 Testing the mechanism of one-pot synthesis.....	59
5.2 DISCUSSION.....	65
VI CONCLUSION AND RECOMMENDATIONS.....	70
6.1 Conclusions.....	70
6.2 Recommendations for future studies.....	71
REFERENCES.....	72

	<b>PAGE</b>
<b>APPENDICES</b>	75
Appendix A. CALCULATION OF CATALYST PREPARATION.....	76
Appendix B. CALCULATION OF CATALYST PROPERTIES.....	77
VITA.....	80



สถาบันวิทยบริการ  
จุฬาลงกรณ์มหาวิทยาลัย

## LIST OF TABLES

TABLE	PAGE
3.1 Packing order of different hydroxide	11
3.2 Decomposition sequence of aluminum hydroxides	15
3.3 Comparison of crystal growth methods	20
3.4 High pressure polymorphism of some simple solids	25
4.1 Operation conditions of gas chromatograph (GOW-MAC)	31
5.1 Elemental analysis of the products	35
5.2 The BET surface areas of silica-modified alumina at various silicon content and various calcination temperature	50



สถาบันวิทยบริการ  
จุฬาลงกรณ์มหาวิทยาลัย



## LIST OF FIGURES

FIGURE	PAGE
3.1 Structure of gibbsite $\text{Al}(\text{OH})_3$ .....	12
3.2 Schematic representation of boehmite ; (a) Al-O-OH chain ; (b) Profile of one chain ; (c) Profile of two antiparallel chains; (d) Schematic representation of c .....	13
3.3 Structure of boehmite $\text{AlO}(\text{OH})$ .....	13
3.4 Decomposition sequence of aluminum hydroxides.....	14
3.5 Czochralski method for crystal growth.....	16
3.6 (a) Stockbarger method: $T_m$ = crystal melting point. (b) Bridgman method: times $t_1, t_2$ and $t_3$ are shown. (c) Zone melting method. (d) verneuil method.....	18
3.7 Pressure-temperature relations for water at constant volume. Dashed curves represent present pressures developed inside a closed vessel; numbers represent the percentage degree of filling of the vessel by water at ordinary P, T. (After Kennedy, 1950)	22
3.8 The P, T phase diagram for carbon. (After Bundy, 1963).....	24
4.1 BET instrument.....	33
5.1a XRD patterns of precursor gels obtained by the reaction of AIP and TEOS in toluene.....	39
5.1b XRD patterns of precursor gels obtained by the reaction of AIP and TEOS in 1-butanol.....	40
5.2a XRD patterns of the silica-modified alumina precursor obtained by calcination at 600 °C of the precursor gels prepared in toluene.....	41
5.2b XRD patterns of the silica-modified alumina precursor obtained by calcination at 600 °C of the precursor gels prepared in 1-butanol.....	42

5.3a XRD patterns of the silica-modified alumina precursor obtained by calcination at 1000 °C of the precursor gels prepared in toluene.....	43
5.3b XRD patterns of the silica-modified alumina precursor obtained by calcination at 1000 °C of the precursor gels prepared in 1-butanol.....	44
5.4a XRD patterns of the silica-modified alumina precursor obtained by calcination at 1150 °C of the precursor gels prepared in toluen.....	45
5.4b XRD patterns of the silica-modified alumina precursor obtained by calcination at 1150 °C of the precursor gels prepared in 1-butanol.....	46
5.5a IR spectra of precursor gels for silica-modified aluminas obtained by the reaction of AIP and TEOS in toluene with various TEOS contents.....	48
5.5b IR spectra of precursor gels for silica-modified aluminas obtained by the reaction of AIP and TEOS in 1-butanol with various TEOS contents.....	49
5.6a The BET surface areas of silica-modified aluminas prepared in toluene at every calcination temperature.....	52
5.6b The BET surface areas of silica-modified aluminas prepared in 1-butanol at every calcination temperature.....	52
5.7a TEM image of TAS8(600).....	54
5.7b TEM image of TAS $\infty$ (600).....	54
5.7c TEM image of TAS8(1150).....	55
5.7d TEM image of TAS $\infty$ (1150).....	55
5.8a TEM image of BAS1(600).....	56
5.8b TEM image of BAS8(600).....	56
5.8c TEM image of BAS $\infty$ (600).....	57
5.8d TEM image of BAS1(1150).....	57
5.8e TEM image of BAS8(1150).....	58
5.8f TEM image of BAS $\infty$ (1150).....	58

5.9a XRD patterns of precursor gels obtained in 1-butanol and toluene, which the addition of water in the gap .....	60
5.9b XRD patterns of precursor gels obtained in 1-butanol and toluene, which the addition of water in the gap at calcination temperature of 1000 °C.....	61
5.9c XRD patterns of precursor gels obtained in 1-butanol and toluene, which the addition of water in the gap at calcination temperature of 1150 °C.....	62
5.10 IR spectra of the products obtained in toluene with the addition of water in the gap, between the beaker and autoclave wall.....	63
5.11a TEM image of H3AS8(600).....	64
5.11b TEM image of H3AS8(1150).....	64