

การสังเคราะห์และตรวจพิสูจน์เอกสารลักษณ์ของชิ้นก้าวไปต่อเมื่อเบรน
สำหรับการแยกใช้ลืนผสม

นายสมบูรณ์ศักดิ์ สุทธิอรุณรัตน์



วิทยานิพนธ์นี้เป็นส่วนหนึ่งของการศึกษาตามหลักสูตรปริญญาวิทยาศาสตร์มหาบัณฑิต^๑
สาขาวิชา ปีตรเคมีและวิทยาศาสตร์พลิเมอร์
หลักสูตร ปีตรเคมีและวิทยาศาสตร์พลิเมอร์
คณะวิทยาศาสตร์ จุฬาลงกรณ์มหาวิทยาลัย
ปีการศึกษา 2542

ISBN 974-334-102-2

ลิขสิทธิ์ของจุฬาลงกรณ์มหาวิทยาลัย


**SYNTHESIS AND CHARACTERIZATION OF SILICALITE MEMBRANE
FOR SEPARATION OF MIXED XYLENES**

Mr. Somboonsak Suttiarunrat


**A Thesis Submitted in Partial Fulfillment of the Requirements
for the Degree of Master of Science in Petrochemistry and Polymer Science
Program of Petrochemistry and Polymer Science
Faculty of Science
Chulalongkorn University
Academic Year 1999
ISBN 974-334-102-2**

Thesis Title Synthesis and characterization of silicalite membrane for separation of mixed xylenes
By Mr. Somboonsak Suttiarunrat
Department Petrochemistry and Polymer Science
Thesis Advisor Orawon Chailapakul , Ph.D.
Thesis Coadvisor Assistant Professor Tawan Sooknoi , Ph.D.

Accepted by the Faculty of Science, Chulalongkorn University in Partial Fulfillment of the Requirements for the Master's Degree


 Dean of Faculty of Science
(Associate Professor Wanchai Phothiphichitr , Ph.D.)


Thesis Committee

 Chairman
(Associate Professor Supawan Tantayanon , Ph.D.)

 Thesis Advisor
(Orawon Chailapakul , Ph.D.)

 Thesis Coadvisor
(Assistant Professor Tawan Sooknoi , Ph.D.)

 Member
(Associate Professor Wimonrat Trakarnpruk , Ph.D.)

 Member
(Assistant Professor Anchaleeporn W. Lothongkum , D.Eng.)

สมบูรณ์ศักดิ์ สุทธิอรุณรัตน์ : การสังเคราะห์และตรวจพิสูจน์เอกลักษณ์ของชิลิกาไอล์ต์เมมเบรนสำหรับการแยกไชลีนผสม (SYNTHESIS AND CHARACTERIZATION OF SILICALITE MEMBRANE FOR SEPARATION OF MIXED XYLENES)

อ. ที่ปรึกษา : อ. ดร. อรุวรรณ ชัยลภากุล, อ. ที่ปรึกษาร่วม : พศ. ดร. ตะวัน สุขน้อย ;
86 หน้า. ISBN 974-334-102-2

งานวิจัยนี้สังเคราะห์ชิลิกาไอล์ต์เมมเบรน เพื่อใช้ในการแยกไชลีนผสม ชิลิกาไอล์ต์เมมเบรนที่ใช้เตรียมขึ้นจากสูตรเดลที่มีองค์ประกอบเป็น $0.1\text{TPABr}-0.05\text{Na}_2\text{O}-\text{SiO}_2-80\text{H}_2\text{O}$ ตัวรองรับที่ใช้ในการทดลอง คือ แผ่นโนโบรซิลิเกตและเส้นไชลิกา จากการทดลองพบว่าแผ่นโนโบรซิลิเกตเป็นตัวรองรับที่ดีกว่าเส้นไชลิกา เพราะเกิดผลลัพธ์ชิลิกาไอล์ต์คุณภาพดีที่สุด ผิวน้ำของตัวรองรับทึ่งตา ชิลิกาไอล์ต์เมมเบรนที่เตรียมได้จะถูกนำไปเผาที่อุณหภูมิ 500 องศาเซลเซียส เป็นเวลา 6 ชั่วโมง เพื่อกำจัดเอนไซม์ที่อยู่ในโครงของผลลัพธ์ชิลิกาไอล์ต์ การวิเคราะห์เมมเบรนจะใช้เทคนิค SEM และ XRD ผลของ SEM แสดงให้เห็นว่าการปรับสภาพพื้นผิwtัวรองรับมีความสำคัญต่อการเกิดชิลิกาไอล์ต์เมมเบรนบนตัวรองรับ และพบว่าขนาดของตัวรองรับมีผลต่อขนาดของผลลัพธ์ และความหนาของเมมเบรน นั่นคือ ตัวรองรับที่มีโครงขนาดใหญ่จะเกิดผลลัพธ์ชิลิกาไอล์ต์ที่มีขนาดใหญ่และมีความหนาของเมมเบรนมากกว่าตัวรองรับที่มีขนาดโครงเล็ก ผลของ XRD ของสารที่สังเคราะห์ได้มีลักษณะตรงกันกับ XRD ของชิลิกาไอล์ต์มาตรฐาน ชิลิกาไอล์ต์เมมเบรนถูกเชื่อมเข้ากับแก้ว 3 ทาง โดยวิธีการเชื่อมด้วยแก๊สหือกการใช้เรซินอีพอกซี่ ผลการเชื่อมที่ดี คือ การใช้เรซินอีพอกซี่ การแยกไชลีนผสมด้วยชิลิกาไอล์ต์เมมเบรน จะศึกษาโดยการใช้เทคนิคแก๊สโครมาโทกราฟี ที่อุณหภูมิ 140 องศาเซลเซียส ความดันของแก๊สตัวพาประมาณ 1 บาร์ ผลที่ได้พบว่าพาราไชลีนและเมตาไชลีนในไชลีนผสมจะแยกออกจากกันโดยไชลีน ค่า separation factor ของพาราไชลีนและเมตาไชลีนต่อไชลีนผสม เท่ากับ 1.47 และของอิโซไชลีนต่อไชลีนพสม เท่ากับ 0.04

ภาควิชา ลายมือชื่อนิติศ
สาขาวิชา... มีโครงการและวิทยาศาสตร์พอลิเมอร์ ลายมือชื่ออาจารย์ที่ปรึกษา
ปีการศึกษา..... 2542 ลายมือชื่ออาจารย์ที่ปรึกษาร่วม

4073419523 : MAJOR PETROCHEMISTRY AND POLYMER SCIENCE

KEYWORDS : SILICALITE / MEMBRANE / SYNTHESIS

SOMBOONSAK SUTTIARUNRAT : SYNTHESIS AND
CHARACTERIZATION OF SILICALITE MEMBRANE FOR
SEPARATION OF MIXED XYLEMES. THESIS ADVISOR :
ORAWON CHAILAPAKUL, Ph.D. THESIS COADVISOR : ASSIST.
PROF. TAWAN SOOKNOI, Ph.D. 86 PP. ISBN 974-334-102-2.

This research is to synthesize the silicalite membrane for the separation of mixed xylenes. The silicalite membrane was prepared by the hydrogel formula. The composition of the gel was $0.1\text{TPABr}-0.05\text{Na}_2\text{O}-\text{SiO}_2-80\text{H}_2\text{O}$. Supports used in this research were borosilicate discs and silica fiber. It was found that the surface area of the borosilicate disc facilitated the crystal growth of silicalite more than that of the silica fiber. The silicalite membrane was calcined at $500\text{ }^{\circ}\text{C}$ for 6 hours to remove organic templates inside the pores of silicalite crystals. SEM and XRD were used to characterize the membranes. The SEM results showed that the treatment of the support affected the coating of the silicalite membrane onto the support. It was also found that the pore size of the support had an effect on the size of the crystal and the thickness of membrane. Silicalite membrane formed on the support with larger pore size had bigger crystal size and more thickness than the one with small pore size. The XRD patterns corresponded to that of the standard silicalite. The silicalite membrane was sealed with 3-way Pyrex glass by gas welding or epoxy resin. The better results were obtained when epoxy resin was used as a binder. The separation of mixed xylenes using this membrane was investigated by gas chromatographic technique. The experiments were carried out at $140\text{ }^{\circ}\text{C}$ with carrier gas pressure of 0.5 bar. The chromatograms showed that p-xylene and m-xylene in mixed xylenes could be separated from o-xylene by using this synthesized silicalite membrane. The separation factor of p-xylene and m-xylene to mixed xylenes was 1.47 and that of o-xylene to mixed xylenes was 0.04.

ภาควิชา

สาขาวิชา ปัตต์เคมีและวิทยาศาสตร์พอลิเมอร์

ปีการศึกษา..... 2542

ลายมือชื่อนิสิต

ลายมือชื่ออาจารย์ที่ปรึกษา.....

ลายมือชื่ออาจารย์ที่ปรึกษาร่วม.....



ACKNOWLEDGEMENTS

The author would like to express his sincere thanks to his advisor, Dr. Orawon Chailapakul and his coadvisor, Assistant Professor Dr. Tawan Sooknoi, for their supervisions, helpful suggestions and encourgments throughout this research. He is also grateful to Associate Professor Dr. Supawan Tantayanon, Associate Professor Dr. Wimonrat Trakarnpruk and Assistant Professor Dr. Anchaleeporn W. Lothongkum, for serving as the chairperson and the committee, and valuable comments.

He would like to thank the Asahi Glass Foundation for the financial support. He is appreciated the supports from the Department of Chemistry, Faculty of Science, King Mongkut's Institute of Technology Ladkrabang for the equipment, chemicals and facilities.

The last but not least, he deeply appreciates and thanks his parents and his family for their consistent supports and encouragements.

CONTENTS

	PAGE
ABSTRACT (IN THAI).....	iv
ABSTRACT (IN ENGLISH).....	v
ACKNOWLEDGEMENTS.....	vi
CONTENTS.....	vii
LIST OF TABLES.....	x
LIST OF FIGURES.....	xi
CHAPTER	
I INTRODUCTION	
Introduction.....	1
Objective and scope of the research.....	4
II THEORY	
2.1 Molecular sieves.....	7
2.2 Zeolites.....	7
2.2.1 Zeolite structure.....	8
2.2.2 Pore size and dimension.....	8
2.2.3 Zeolite properties.....	12
2.2.4 Applications of zeolites.....	16
2.3 Membrane separation.....	22
2.3.1 Membrane materials.....	24
2.3.2 Transport in membrane.....	26
2.3.3 Gas permeation.....	27
2.4 silicalite.....	28

CONTENTS (continued)

	PAGE
III EXPERIMENTAL	
3.1 Membrane preparation.....	32
3.1.1 Chemicals.....	32
3.1.2 Equipment.....	33
3.1.3 Procedures.....	33
3.1.3.1 Support treatment.....	33
3.1.3.2 Membrane synthesis.....	34
3.2 Membrane characterization.....	34
3.2.1 Thermogravimetric Analysis.....	34
3.2.2 Scanning Electron Microscopy.....	35
3.2.3 X-ray Diffraction.....	35
3.3 Separation process.....	35
IV RESULTS AND DISCUSSIONS	
4.1 Silicalite synthesis and characterization.....	37
4.2 The silicalite membrane on different supports.....	37
4.3 Silicalite membrane synthesis and characterization.....	46
4.3.1 The effect of support treatment.....	46
4.3.2 Calcination.....	50
4.3.3 The pore size effect of the borosilicate disc support.....	50
4.4 Gas separation process.....	55
4.4.1 Sealing procedure.....	55
4.4.2 GC packed column.....	57
4.4.3 The separation with silicalite membrane.....	63
4.5 Crack of membrane.....	71

CONTENTS (continued)

	PAGE
V CONCLUSIONS AND FURTHER WORKS	
Conclusions.....	75
Suggestions and further works.....	76
REFERENCES.....	77
APPENDICES.....	80
VITA.....	86

LIST OF TABLES

TABLE	PAGE
2.1 Cations that may form molecular sieve framework structures and the metal oxide charge possible.....	7
2.2 Known zeolite structures listed by pore opening, as defined as the number of T units that shape the channel.....	10
2.3 Pore structure of zeolite.....	10
2.4 Some dimensional parameters of common zeolites.....	11
2.5 Parameters of physical adsorption and chemisorption.....	14
2.6 Common adsorbents.....	15
2.7 Commercial molecular sieve products.....	17
2.8 UOP Sorbex processes for liquid-phase separations.....	19
2.9 Physical properties for C ₈ -aromatic compounds.....	20
2.10 Industrial applications of membrane separation processes.....	23
2.11 Common polymers used in membranes.....	25
2.12 XRD pattern of silicalite, calcined in air at 600 °C for 1 hour.....	30
3.1 Source of chemicals.....	32
3.2 Main equipment.....	33
4.1 The crystal size of silicalites and the thicknesses of silicalite membrane on each support.....	50
4.2 The comparison of retention times of each isomer.....	60
4.3 The separation factors and the permeate distributions of p-, m- and o-xylenes.....	68
4.4 The kinetic diameters of xylenes.....	70

LIST OF FIGURES

FIGURE	PAGE
1.1 Amoco p-xylene crystallization process.....	1
1.2 UOP Parex simulated moving bed for adsorptive separation.....	2
2.1 Classification of molecular sieve material.....	6
2.2 Examples of the three types of pore openings in the zeolite molecular sieves.....	9
2.3 Projections of ZSM-5, -11, -12, -23 and -44 structures.....	12
2.4 Molecular dimension and zeolite pore size.....	13
2.5 Classification of adsorptive separations.....	18
2.6 Chevron p-xylene crystallization process.....	21
2.7 Amoco p-xylene crystallization process.....	21
2.8 Separation of p-xylene by adsorption, UOP Parex process.....	22
2.9 General membrane process.....	24
2.10 Mechanisms of transport in membranes.....	27
2.11 Gas permeation.....	28
2.12 Framework structure and idealized channel system in ZSM-5 (silicalite).....	29
3.1 The support was placed in the middle of the autoclave by hanging on the stand.....	34
3.2 The cell for gas separation process.....	35
3.3 Schematic of gas separation process.....	36
4.1 XRD pattern of the silicalite from Ludox before calcination.....	38
4.2 XRD pattern of the silicalite from silica fumed before calcination.....	39
4.3 Standard XRD pattern of the silicalite before calcination.....	40
4.4 TGA thermogram of the silicalite from Ludox.....	41
4.5 TGA thermogram of the silicalite from silica fumed.....	42
4.6 XRD pattern of silicalite membrane on silica fiber support.....	43
4.7 XRD pattern of silicalite membrane on borosilicate disc support.....	44
4.8 SEM image of silicalite membrane on silica fiber support.....	45
4.9 SEM image of silicalite membrane on borosilicate disc support.....	45

LIST OF FIGURES (continued)

FIGURE	PAGE
4.10 SEM image of silicalite membrane on treated borosilicate disc support.....	47
4.11 SEM image of silicalite membrane on untreated borosilicate disc support....	47
4.12 XRD pattern of silicalite membrane on treated borosilicate disc support.....	48
4.13 XRD pattern of silicalite membrane on untreated borosilicate disc support... 4.14 XRD patterns of silicalite membrane; before and after calcination.....	49 51
4.15 XRD standard pattern of silicalite after calcination.....	52
4.16 SEM image of cross section of silicalite membrane on the borosilicate disc support, 4-5.5 μm	53
4.17 SEM image of cross section of silicalite membrane on the borosilicate disc support, 10-16 μm	53
4.18 SEM image of cross section of silicalite membrane on the borosilicate disc support, 16-40 μm	53
4.19 SEM images of cross section of silicalite membrane at high magnification.....	54
4.20 The gas chromatograms of xylene isomers and mixed xylenes diffusing through silicalite membrane at a temperature of 140 °C. The flow rate of carrier gas was 5 ml/min	56
4.21 The gas chromatograms of mixed xylenes diffusing through silicalite membrane at a temperature of 140 °C, carrier gas pressure of 1 bar.....	58
4.22 The gas chromatograms of mixed xylenes injected at the injection port.....	59
4.23 The gas chromatogram of mixed xylenes injected at the injection port (p-xylene : m-xylene :o-xylene =1:1:1).....	60
4.24 The gas chromatogram of mixed xylenes injected through the loop of gas sampling valve (p-xylene : m-xylene :o-xylene =1:1:1).....	61
4.25 The chromatograms; before and after the installation of the cell.....	62
4.26 The chromatogram of water injected at injection port.....	63
4.27 The gas chromatogram of mixed xylenes (1:1:1) diffusing through the silicalite membrane.....	64

LIST OF FIGURES (continued)

FIGURE	PAGE
4.28 The gas chromatogram of mixed xylenes (1:2:1) diffusing through the silicalite membrane.....	65
4.29 The gas chromatogram of mixed xylenes (1:1:1) diffusing through the silicalite membrane.....	66
4.30 The relation between the permeation time and the separation factor.....	69
4.31 Effect of pore size on molecular diffusivity in porous solid.....	70
4.32 The gas chromatogram of mixed xylenes (1:1:2) diffusing through the silicalite membrane which crack occurred.....	71
4.33 The gas chromatogram of mixed xylenes (1:1:1) diffusing through the silicalite membrane which crack occurred.....	72
4.34 SEM images of crack of silicalite membrane.....	73
4.35 The chromatogram intensity of water was changed upon the curing time of resin.....	74